



SLOVENSKI STANDARD
oSIST prEN ISO 12571:2020
01-december-2020

Higrotermalno obnašanje gradbenih materialov in proizvodov - Ugotavljanje higroskopnosti (ISO/DIS 12571:2020)

Hygrothermal performance of building materials and products - Determination of hygroscopic sorption properties (ISO/DIS 12571:2020)

Wärme- und feuchtetechnisches Verhalten von Baustoffen und Bauprodukten - Bestimmung der hygroskopischen Sorptionseigenschaften (ISO/DIS 12571:2020)

Performance hygrothermique des matériaux et produits pour le bâtiment - Détermination des propriétés de sorption hygroscopique (ISO/DIS 12571:2020)

<https://standards.iteh.ai/catalog/standards/sist/047861f3-db23-49fb-aaa1-395d054385a/osist-pr-en-iso-12571-2020>

Ta slovenski standard je istoveten z: prEN ISO 12571

ICS:

91.100.01	Gradbeni materiali na splošno	Construction materials in general
91.120.30	Zaščita pred vlago	Waterproofing

oSIST prEN ISO 12571:2020

en,fr,de

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[oSIST prEN ISO 12571:2021](#)

<https://standards.iteh.ai/catalog/standards/sist/047861f3-db23-49fb-aaa1-385f9054385a/osist-pren-iso-12571-2021>

DRAFT INTERNATIONAL STANDARD

ISO/DIS 12571

ISO/TC 163/SC 1

Secretariat: DIN

Voting begins on:
2020-10-15Voting terminates on:
2021-01-07

Hygrothermal performance of building materials and products — Determination of hygroscopic sorption properties

Projection thermique — Revêtements appliqués par projection thermique — Représentation symbolique sur les dessins

ICS: 91.100.01

iTeh STANDARD PREVIEW (standards.iteh.ai)

[oSIST prEN ISO 12571:2021](https://standards.iteh.ai/catalog/standards/sist/047861f3-db23-49fb-aaa1-385f9054385a/osist-pren-iso-12571-2021)<https://standards.iteh.ai/catalog/standards/sist/047861f3-db23-49fb-aaa1-385f9054385a/osist-pren-iso-12571-2021>

THIS DOCUMENT IS A DRAFT CIRCULATED FOR COMMENT AND APPROVAL. IT IS THEREFORE SUBJECT TO CHANGE AND MAY NOT BE REFERRED TO AS AN INTERNATIONAL STANDARD UNTIL PUBLISHED AS SUCH.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

This document is circulated as received from the committee secretariat.

ISO/CEN PARALLEL PROCESSING



Reference number
ISO/DIS 12571:2020(E)

© ISO 2020

iTeh STANDARD PREVIEW (standards.iteh.ai)

[oSIST prEN ISO 12571:2021](https://standards.iteh.ai/catalog/standards/sist/047861f3-db23-49fb-aaa1-385f9054385a/osist-pren-iso-12571-2021)
<https://standards.iteh.ai/catalog/standards/sist/047861f3-db23-49fb-aaa1-385f9054385a/osist-pren-iso-12571-2021>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2020

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions, symbols and units	1
3.1 Terms and definitions.....	1
3.2 Symbols and units.....	2
4 Principle	2
4.1 Sorption curve.....	2
4.2 Desorption curve.....	2
5 Apparatus	3
5.1 Desiccator method.....	3
5.2 Climatic chamber method.....	3
6 Test specimens	3
6.1 Specification of the test specimens.....	3
6.2 Number of test specimens.....	3
7 Procedure	3
7.1 Test conditions.....	3
7.2 Desiccator method.....	4
7.2.1 General.....	4
7.2.2 Sorption curve.....	4
7.2.3 Desorption curve.....	4
7.3 Climatic chamber method.....	5
7.3.1 Sorption curve.....	5
7.3.2 Desorption curve.....	6
8 Calculation and expression of results	6
8.1 Hygroscopic sorption.....	6
8.2 Equilibrium moisture content curves.....	6
9 Accuracy of measurement	7
9.1 Error in moisture content.....	7
9.2 Control of environmental conditions.....	7
9.2.1 Desiccator method.....	7
9.2.2 Climatic chamber method.....	7
10 Test report	8
Annex A (informative) Air relative humidities above saturated solutions in equilibrium	9
Annex B (informative) Preparation of saturated solutions	12
Annex C (informative) Example of the procedure for determining a point on a sorption curve	15
Annex D (informative) Method using a glass jar	16
Bibliography	18

ISO/DIS 12571:2020(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 163, *Thermal performance and energy use in the built environment* Subcommittee SC 1, *Test and measurement methods*.

This third edition cancels and replaces the second edition (ISO 12571:2013), which has been technically revised.

The main changes compared to the previous edition are as follows:

- Revision of [Table A.1](#)

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

The International Organization for Standardization (ISO) draw attention to the fact that it is claimed that compliance with this document may involve the use of a patent.

ISO take no position concerning the evidence, validity and scope of this patent right.

The holder of this patent right has assured ISO that he/she is willing to negotiate licences under reasonable and non-discriminatory terms and conditions with applicants throughout the world. In this respect, the statement of the holder of this patent right is registered with ISO. Information may be obtained from the patent database available at www.iso.org/patents.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights other than those in the patent database. ISO shall not be held responsible for identifying any or all such patent rights.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[oSIST prEN ISO 12571:2021](https://standards.iteh.ai/catalog/standards/sist/047861f3-db23-49fb-aaa1-385f9054385a/osist-pren-iso-12571-2021)

<https://standards.iteh.ai/catalog/standards/sist/047861f3-db23-49fb-aaa1-385f9054385a/osist-pren-iso-12571-2021>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[oSIST prEN ISO 12571:2021](#)

<https://standards.iteh.ai/catalog/standards/sist/047861f3-db23-49fb-aaa1-385f9054385a/osist-pren-iso-12571-2021>

Hygrothermal performance of building materials and products — Determination of hygroscopic sorption properties

1 Scope

This International Standard specifies two alternative methods for determining hygroscopic sorption properties of porous building materials and products:

- a) using desiccators and weighing cups (desiccator method);
- b) using a climatic chamber (climatic chamber method).

The desiccator method is the reference method.

This International Standard does not specify the method for sampling.

The methods specified in this International Standard can be used to determine the moisture content of a sample in equilibrium with air at a specific temperature and humidity.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 9346, *Hygrothermal performance of buildings and building materials — Physical quantities for mass transfer — Vocabulary*

ISO 12570, *Hygrothermal performance of building materials and products — Determination of moisture content by drying at elevated temperature*

3 Terms and definitions, symbols and units

3.1 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 9346 and the following apply.

3.1.1

equilibrium moisture content

moisture content of a porous material in equilibrium with the environment and the relative humidity of the ambient air, at a specified temperature

3.1.2

moisture content mass by mass

mass of evaporable water divided by mass of dry material

3.1.3

moisture content volume by volume

volume of evaporable water divided by volume of dry material

ISO/DIS 12571:2020(E)

3.1.4

moisture content mass by volume

mass of evaporable water divided by volume of dry material

Note 1 to entry: The mass of water is determined by weighing the specimen before and after drying at the appropriate drying temperature until constant mass is reached.

3.1.5

sorption curve

curve established at a series of increasing equilibrium relative humidities at a given temperature

3.1.6

desorption curve

curve established at a series of decreasing equilibrium relative humidities at a given temperature

3.2 Symbols and units

Symbol	Quantity	Unit
m	mass of test specimen	kg
m_0	mass of dried test specimen	kg
u	moisture content mass by mass	kg/kg
ψ	moisture content volume by volume	m^3/m^3
w	moisture content mass by volume	kg/m^3

iTeh STANDARD PREVIEW
(standards.iteh.ai)

4 Principle

4.1 Sorption curve

oSIST prEN ISO 12571:2021

The specimen is dried to constant mass. While maintaining a constant temperature, the specimen is placed consecutively in a series of test environments, with relative humidity increasing in stages. The moisture content is determined when equilibrium with each environment is reached. Equilibrium with the environment is established by weighing the specimen until constant mass is reached. A minimum of four test atmospheres shall be selected in the humidity range under consideration.

After establishing the moisture content at each relative humidity the sorption curve can be drawn.

4.2 Desorption curve

The starting point for desorption is a relative humidity of at least 95 %. This might be the last point of the sorption curve or might be reached by sorption from a dried test specimen. While maintaining a constant temperature, the specimen is placed consecutively in a series of test environments, with relative humidity decreasing in stages. The moisture content is determined when equilibrium with each environment is reached. Equilibrium with the environment is established by weighing the specimen until constant mass is reached. A minimum of four test atmospheres shall be selected in the humidity range under consideration. Finally, the specimen is dried to constant mass.

After establishing the moisture content at each relative humidity the desorption curve can be drawn.

NOTE A defined starting point for desorption has been chosen for better reproducibility.

5 Apparatus

5.1 Desiccator method

The test apparatus shall include:

- a) **weighing cups** which do not absorb water and with tight-fitting lids;
- b) **balance**, capable of weighing to an accuracy of $\pm 0,01$ % of the mass of the test specimen;

NOTE If larger weighing cups are used, the weighing accuracy can be determined with respect to the total mass and the required accuracy of the test results.
- c) **drying oven**, in accordance with ISO 12570;
- d) **desiccator**, capable of maintaining the relative humidity within ± 2 % relative humidity;
- e) **constant-temperature chamber**, capable of maintaining the specified test temperature to an accuracy of $\pm 0,5$ K.

5.2 Climatic chamber method

The test apparatus shall include:

- a) **weighing cups** which do not absorb water;
- b) **balance**, capable of weighing to an accuracy of $\pm 0,01$ % of the mass of the test specimen;

NOTE If larger weighing cups are used, the weighing accuracy can be determined with respect to the total mass and the required accuracy of the test results.
- c) **drying oven**, in accordance with ISO 12570;
- d) **climatic chamber**, capable of maintaining the relative humidity within ± 5 % relative humidity and the temperature within ± 2 K over the whole test area.

6 Test specimens

6.1 Specification of the test specimens

A test specimen shall be representative of the product and have a mass of at least 10 g. Specimens of materials with a dry density less than 300 kg/m^3 shall have an area of at least $100 \text{ mm} \times 100 \text{ mm}$. If it can be demonstrated from other references that the result will not be affected, a test specimen can be cut or crushed into smaller pieces to reduce the time to reach equilibrium with the environment.

6.2 Number of test specimens

A minimum of three specimens shall be tested. The procedure in [Clause 7](#) shall be applied to each specimen.

7 Procedure

7.1 Test conditions

Reference sorption curves shall be established at a temperature of $(23 \pm 0,5) ^\circ\text{C}$ or $(27 \pm 0,5) ^\circ\text{C}$ in tropical countries. If agreed between the parties, sorption curves can be established at other temperatures for specific applications.