



SLOVENSKI STANDARD
oSIST prEN 12165:2022
01-oktober-2022

Baker in bakrove zlitine - Palice (lite in iztiskane) za izkovke

Copper and copper alloys - Wrought and unwrought forging stock

Kupfer und Kupferlegierungen - Vormaterial für Schmiedestücke

Cuivre et alliages de cuivre - Barres corroyées et brutes pour matriçage

Ta slovenski standard je istoveten z: prEN 12165

<https://standards.iteh.ai/catalog/standards/sist/04697729-8b6d-4ef3-9e4d-fcfd4337f329/osist-pren-12165-2022>

ICS:

77.150.30 Bakreni izdelki Copper products

oSIST prEN 12165:2022

en,fr,de

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

DRAFT
prEN 12165

August 2022

ICS 77.150.30

Will supersede EN 12165:2016

English Version

Copper and copper alloys - Wrought and unwrought forging stock

Cuivre et alliages de cuivre - Barres corroyées et brutes
pour matriçage

Kupfer und Kupferlegierungen - Vormaterial für
Schmiedestücke

This draft European Standard is submitted to CEN members for enquiry. It has been drawn up by the Technical Committee CEN/TC 133.

If this draft becomes a European Standard, CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

This draft European Standard was established by CEN in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.

Recipients of this draft are invited to submit, with their comments, notification of any relevant patent rights of which they are aware and to provide supporting documentation.

Warning : This document is not a European Standard. It is distributed for review and comments. It is subject to change without notice and shall not be referred to as a European Standard.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

Contents	Page
European foreword.....	3
Introduction	5
1 Scope.....	6
2 Normative references.....	6
3 Terms and definitions	6
4 Designations.....	7
4.1 Material.....	7
4.1.1 General.....	7
4.1.2 Symbol.....	7
4.1.3 Number	7
4.2 Material condition	7
4.3 Product.....	7
5 Ordering information	9
6 Requirements.....	10
6.1 Composition	10
6.2 Mechanical properties.....	10
6.3 Resistance to dezincification	10
6.4 Dimensions and tolerances	10
6.4.1 Diameter.....	10
6.4.2 Deviation from circular form.....	11
6.4.3 Length.....	11
6.4.4 Straightness.....	11
6.5 Surface quality.....	11
6.6 Internal inclusion.....	12
7 Sampling.....	12
7.1 General.....	12
7.2 Analysis.....	12
7.3 Hardness and dezincification resistance tests	12
8 Test methods	12
8.1 Analysis.....	12
8.2 Hardness test.....	12
8.2.1 General.....	12
8.2.2 Preparation of samples.....	13
8.2.3 Procedure for testing.....	13
8.3 Dezincification resistance test	13
8.4 Retests for analysis, hardness and dezincification resistance	13
8.5 Rounding of results	13
9 Declaration of conformity and inspection documentation.....	14
9.1 Declaration of conformity.....	14
9.2 Inspection documentation.....	14
10 Marking, packaging, labelling.....	14
Bibliography.....	27

European foreword

This document (prEN 12165:2022) has been prepared by Technical Committee CEN/TC 133 “Copper and copper alloys”, the secretariat of which is held by DIN.

This document is currently submitted to the CEN Enquiry.

This document will supersede EN 12165:2016

In comparison with EN 12165:2016, the following significant technical changes were made:

- a) Introduction in the § 6.5 of eddy current test parameters;
- b) Introduction of the § 6.6 Internal inclusion;
- c) Modified the definition of diameter at § 6.4.1;
- d) Added a new Figure for straightness at § 6.4.4 and modified values in Table 11;
- e) Introduction in the chemical composition Tables of a footnote to explain the meaning of elements for which no upper and lower limits are defined;
- f) CuZn4Si4MnP (CW245E) and CuZn9Si4MnP (CW246E) added in the new Table 3
- g) Chemical composition of CuZn39Pb3 (CW614N), CuZn40Pb2 (CW617N), CuZn35Pb1,5AlAs (CW625N) and CuZn33Pb1,5AlAs (CW626N) modified in Table 8;
- h) Added a new alloy CuZn40Pb1 (CW627N) in Table 8;
- i) Chemical composition of CuZn33Pb1AlSiAs (CW725R) modified in Table 9;
- j) Added a new alloy CuZn36Si1P (CW726R) in Table 9;
- k) Removed Tables of Mechanical properties (old Table 9, Table 10, Table 11, Table 12, Table 13, Table 14, Table 15 and Table 16);
- l) Renamed Table 17 in Table 10, Table 18 in Table 11, Table 19 in Table 12;
- m) Added new Table 13.

This document is one of a series of European Standards for the copper and copper alloy products rod, wire, profile and forgings. Other products are specified as follows:

- EN 12163, *Copper and copper alloys — Rod for general purposes*;
- EN 12164, *Copper and copper alloys — Rod for free machining purposes*;
- EN 12166, *Copper and copper alloys — Wire for general purposes*;
- EN 12167, *Copper and copper alloys — Profiles and bars for general purposes*;
- EN 12168, *Copper and copper alloys — Hollow rod for free machining purposes*;
- EN 12420, *Copper and copper alloys — Forgings*;

prEN 12165:2022 (E)

- EN 13601, *Copper and copper alloys — Copper rod, bar and wire for general electrical purposes*;
- EN 13602, *Copper and copper alloys — Drawn round copper wire for the manufacture of electrical conductors*;
- EN 13605, *Copper and copper alloys — Copper profiles and profiled wires for electrical purposes*.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[oSIST prEN 12165:2022](https://standards.iteh.ai/catalog/standards/sist/04697729-8b6d-4ef3-9e4d-fcf4337f329/osist-pren-12165-2022)

<https://standards.iteh.ai/catalog/standards/sist/04697729-8b6d-4ef3-9e4d-fcf4337f329/osist-pren-12165-2022>

Introduction

The European Committee for Standardization (CEN) draws attention to the fact that it is claimed that compliance with this document may involve the use of a patent concerning the alloys CuZn4Si4MnP (CW245E), CuZn9Si4MnP (CW246E), CuZn33Pb1AlSiAs (CW725R), and CuZn36Si1P (CW726R) given in 6.1.

CEN takes no position concerning the evidence, validity and scope of this patent right.

The holder of this patent right has ensured the CEN that he is willing to negotiate licenses either free of charge or under reasonable and non-discriminatory terms and conditions with applicants throughout the world. In this respect, the statement of the holder of this patent right is registered with CEN.

— For CuZn4Si4MnP (CW245E) and CuZn9Si4MnP (CW246E) information may be obtained from:

Viega Technology GmbH & Co. KG
Viega Platz 1
57439 Attendorn
GERMANY

— For CuZn33Pb1AlSiAs (CW725R) information may be obtained from:

Diehl Brass Solutions Stiftung & Co. KG
Heinrich-Diehl-Straße 9
D-90552 Röthenbach/Pegnitz
GERMANY

— For CuZn36Si1P (CW726R) information may be obtained from:

Luvata Oy
Kuparitie 5
28330 Pori
FINLAND

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights other than those identified above. CEN shall not be held responsible for identifying any or all such patent rights.

CEN and CENELEC maintain online lists of patents relevant to their standards. Users are encouraged to consult the lists for the most up to date information concerning patents (<ftp://ftp.cencenelec.eu/EN/IPR/Patents/IPRdeclaration.pdf>).

Due to developing legislation, the composition of a material may be restricted to the composition specified in this European Standard with respect to individual uses (e.g. for the use in contact with drinking water in some Member States of the European Union). These individual restrictions are not part of this European Standard. Nevertheless, for materials for which traditional and major uses are affected, these restrictions are indicated. The absence of an indication, however, does not imply that the material can be used in any application without any legal restriction.

1 Scope

This document specifies the composition, property requirements and dimensional tolerances for forging stock of copper and copper alloys.

The sampling procedures and the methods of test for verification of conformity to the requirements of this document are also specified.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 1173, *Copper and copper alloys - Material condition designation*

EN 1412, *Copper and copper alloys - European numbering system*

EN 1976, *Copper and copper alloys - Cast unwrought copper products*

EN 10204, *Metallic products - Types of inspection documents*

EN 17263, *Copper and copper alloys - Eddy current testing on the outer surface of rods, bars, hollow rods and wires for the detection of defects by encircling test coil*

EN ISO 6506-1, *Metallic materials - Brinell hardness test - Part 1: Test method (ISO 6506-1)*

EN ISO 6509-1, *Corrosion of metals and alloys - Determination of dezincification resistance of copper alloys with zinc - Part 1: Test method (ISO 6509-1)*

ISO 1190-1, *Copper and copper alloys — Code of designation — Part 1: Designation of materials*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

3.1
forging
three-dimensional shaped product produced by a plastic forming process such as hammering or pressing between open or closed dies, including hammering between flat surfaces, normally when hot

Note 1 to entry Forging processes include, drop forging, hot stamping and hot pressing.

3.2
forging stock
extruded, rolled or drawn product such as rod, hollow rod, bar or profile or cast product, intended for the production of forgings

3.3

deviation from circular form

difference between the maximum and the minimum diameters measured at any one cross-section of a round product

4 Designations

4.1 Material

4.1.1 General

The material is designated either by symbol or by number (see Tables 1 to 9).

4.1.2 Symbol

The material symbol designation is based on the designation system given in ISO 1190-1.

NOTE Although material symbol designations used in this standard might be the same as those in other standards using the designation system given in ISO 1190-1, the detailed composition requirements are not necessarily the same.

4.1.3 Number

The material number designation is in accordance with the system given in EN 1412.

4.2 Material condition

For the purposes of this standard, the following designations, which are in accordance with the system given in EN 1173, apply for the material condition:

M material condition for the product as manufactured without specified mechanical properties;

4.3 Product

The product designation provides a standardized pattern of designation from which a rapid and unequivocal description of a product can be conveyed in communication. It provides mutual comprehension at the international level with regard to products which meet the requirements of the relevant European Standard.

The product designation is no substitute for the full content of the standard.

The product designation for products to this standard shall consist of:

- denomination (Forging stock);
- number of this European Standard (EN 12165);
- material designation, either symbol or number (see Tables 1 to 9);
- DW for compliance in the chemical composition according to the 4 MS Common Composition List. This information is mandatory in the case in which the product is used for drinking water applications according to the 4 MS Common Composition List and not to be given in other cases;
- cross-sectional shape (the following designations shall be used as appropriate: RND for round, SQR for square, HEX for hexagonal, OCT for octagonal, RCT for rectangular (bar), PFL for profile);
- for rod with round or regular polygonal cross-section, hollow rod or bar, the nominal cross-sectional dimension(s) (diameter, width across-flats, external dimension × internal dimension, width × thickness, as appropriate);

prEN 12165:2022 (E)

- for profiles, the number of the profile, or a fully dimensioned and toleranced drawing;
- for round rod, the tolerance class (see Table 10).


The derivation of a product designation is shown in the following examples.

EXAMPLE 1 Forging stock conforming to this standard, in material designated either CuZn40Pb2 or CW617N, for standard applications, in material condition M, round, nominal diameter 15 mm, tolerance class A, will be designated as follows:

Forging stock — EN 12165 — CuZn40Pb2 — M — RND15A

or

Forging stock — EN 12165 — CW617N — M — RND15A




EXAMPLE 2 Forging stock conforming to this standard, in material designated either CuZn40Pb2 or CW617N, for drinking water applications according to the 4 MS Common Composition List, in material condition M, round, nominal diameter 15 mm, tolerance class A, will be designated as follows:

Forging stock — EN 12165 — CuZn40Pb2 — DW — M — RND15A

<https://standards.iteh.ai/catalog/standards/sist/04697729-8b6d-4ef3-9e4d-fcfd4337f329/osist-pren-12165-2022>

Forging stock — EN 12165 — CW617N — DW — M — RND15A



5 Ordering information

In order to facilitate the enquiry, order and confirmation of order procedures between the purchaser and the supplier, the purchaser shall state on his enquiry and order the following information:

- a) mass of product required;
- b) denomination (Forging stock);
- c) number of this European Standard (EN 12165);
- d) material designation (see Tables 1 to 9);
- e) DW for compliance in the chemical composition according to the 4 MS Common Composition List. This information is mandatory in the case in which the product is used for drinking water applications according to the 4 MS Common Composition List and not to be given in other cases;
- f) cross-sectional shape;
- g) size required:
 - 1) for round rod, diameter and whether class A or class B tolerance is required, unless the tolerance class shall be left to the discretion of the supplier (see Table 10);
 - 2) for rod with regular polygonal cross-section or hollow rod or bar, nominal dimension(s) and tolerance(s) required unless they shall be left to the discretion of the supplier;
 - 3) for profiles, a fully dimensioned and toleranced drawing;
- h) the length of product required, if not left to the discretion of the supplier;

It is recommended that the product designation, as described in 4.3, is used for items b) to h.

In addition, the purchaser shall also state on the enquiry and order any the following, if required:

- i) whether special surface quality is required (see 6.5);
- j) whether surface quality test is required (see 6.5) and the class;
- k) whether a declaration of conformity is required (see 9.1);
- l) whether an inspection document is required, and if so, which type (see 9.2);
- m) whether there are any special requirements for marking, packaging or labelling (see Clause 10).