
Kemikalije, ki se uporabljajo za pripravo pitne vode – Tetrakalijev pirofosfat

Chemicals used for treatment of water intended for human consumption -
Tetrapotassium pyrophosphate

Produkte zur Aufbereitung von Wasser für den menschlichen Gebrauch -
Tetrakaliumdiphosphat

Produits chimiques utilisés pour le traitement de l'eau destinée à la consommation
humaine - Pyrophosphate tétrapotassique

iTeh STANDARD PREVIEW

(standards.itih.ai)

[SIST EN 1207:1999](https://standards.itih.ai/catalog/standards/sist/62af199-c2c9-4b60-a93c-a55b-408e484f/sist-en-1207-1999)

Ta slovenski standard je istoveten z: EN 1207:1997

<https://standards.itih.ai/catalog/standards/sist/62af199-c2c9-4b60-a93c-a55b-408e484f/sist-en-1207-1999>

ICS:

13.060.20	Pitna voda	Drinking water
71.100.80	Kemikalije za čiščenje vode	Chemicals for purification of water

SIST EN 1207:1999**en**

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 1207:1999

<https://standards.iteh.ai/catalog/standards/sist/6f2af199-c2c9-4b60-a93c-a55b468e484f/sist-en-1207-1999>

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN 1207

September 1997

ICS 71.100.80

Descriptors: potable water, water treatment, chemical compounds, pyrophosphates, potassium pyrophosphates, description, physical properties, chemical properties, impurities, toxic substances, tests, labelling, storage, information

English version

Chemicals used for treatment of water intended for human
consumption - Tetrapotassium pyrophosphate

Produits chimiques utilisés pour le traitement de l'eau
destinée à la consommation humaine - Pyrophosphate
tétrapotassique

Produkte zur Aufbereitung von Wasser für den
menschlichen Gebrauch - Tetrakaliumdiphosphat

This European Standard was approved by CEN on 26 September 1997.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

SIST EN 1207:1999

CEN members are the national standards bodies of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Central Secretariat: rue de Stassart, 36 B-1050 Brussels

Contents

	Page
Foreword.....	3
Introduction	4
1 Scope	4
2 Normative references	4
3 Description	5
3.1 Identification	5
3.2 Commercial form	6
3.3 Physical properties	6
3.4 Chemical properties	7
4 Purity criteria	8
4.1 Composition of commercial product	8
4.2 Impurities and main by-products	8
4.3 Toxic substances	8
5 Test methods	9
5.1 Sampling	9
5.2 Analyses	10
6 Labelling - Transportation - Storage	14
6.1 Means of delivery	14
6.2 Risk and safety labelling according to the EU Directives	14
6.3 Transportation regulations and labelling	14
6.4 Marking	14
6.5 Storage	14
Annex A (informative) General information on tetrapotassium pyrophosphate	15
Annex B (informative) Bibliography	17



Foreword

This European Standard has been prepared by Technical Committee CEN/TC 164 "Water supply", the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by March 1998, and conflicting national standards shall be withdrawn at the latest by March 1998.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and the United Kingdom.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 1207:1999

<https://standards.iteh.ai/catalog/standards/sist/6f2af199-c2c9-4b60-a93c-a55b468e484f/sist-en-1207-1999>

Introduction

In respect of potential adverse effects on the quality of water intended for human consumption, caused by the product covered by this Standard :

- 1) This Standard provides no information as to whether the product may be used without restriction in any of the Member States of the EU or EFTA ;
- 2) It should be noted that, while awaiting the adoption of verifiable European criteria, existing national regulations concerning the use and/or the characteristics of this product remain in force.

1 Scope

This European Standard describes the characteristics and specifies the requirements and the corresponding test methods for tetrapotassium pyrophosphate used for treatment of water intended for human consumption. It gives information on its use in water treatment.

2 Normative reference

This European standard incorporates by dated or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies.

EN 26595	Water quality - Determination of total arsenic - Silver diethyldithiocarbamate spectrophotometric method (ISO 6595:1982)
EN ISO 3696	Water for analytical laboratory use - Specification and test methods (ISO 3696 : 1987)
ISO 2997	Phosphoric acid for industrial use - Determination of sulphate content - Method by reduction and titrimetry.
ISO 3165	Sampling of chemical products for industrial use - Safety in sampling
ISO 3357	Sodium tripolyphosphate and sodium pyrophosphate for industrial use. Determination of total phosphorus (V) oxide content - Quinoline phosphomolybdate gravimetric method.
ISO 3360	Phosphoric acid and sodium phosphates for industrial use (including foodstuffs) - Determination of fluorine content - Alizarin complexone and lanthanum nitrate photometric method.
ISO 5666-1	Water quality - Determination of total mercury by flameless atomic absorption spectrometry - Part 1 : method after digestion with permanganate - peroxodisulfate.

ISO 5961	Water quality - Determination of cadmium by atomic absorption spectrometry.
ISO 6206	Chemical products for industrial use - Sampling - Vocabulary.
ISO 6703-1	Water quality - Determination of cyanide - Part_1 : determination of total cyanide.
ISO 8213	Chemical products for industrial use - Sampling techniques - Solid chemical products in the form of particles varying from powders to coarse lumps.
ISO 8288	Water quality - Determination of heavy metals - Atomic absorption spectrometric method.
ISO 9174	Water quality - Determination of total chromium - Atomic absorption spectrometric methods.
ISO 9965	Water quality - Determination of selenium - Atomic absorption spectrometric method (hydride technique).
ISO 11885	Water quality - Determination of 33 elements by inductively coupled plasma atomic emission spectroscopy

ITeH STANDARD PREVIEW
(standards.iteh.ai)

3 Description

3.1 Identification

[SIST EN 1207:1999
https://standards.iteh.ai/catalog/standards/sist/6f2af199-c2c9-4b60-a93c-a55b468e484f/sist-en-1207-1999](https://standards.iteh.ai/catalog/standards/sist/6f2af199-c2c9-4b60-a93c-a55b468e484f/sist-en-1207-1999)

3.1.1 Chemical name

Tetrapotassium pyrophosphate.

3.1.2 Synonym or common names

Diphosphoric acid tetrapotassium salt : TKPP.

3.1.3 Relative molecular mass

330,0.

3.1.4 Empirical formula

$K_4P_2O_7$

3.1.5 Chemical formula

$K_4P_2O_7$

3.1.6 CAS Registry Number ¹⁾

7320-34-5.

3.1.7 EINECS reference²⁾

230-785-7.

3.2 Commercial form

Tetrapotassium pyrophosphate is available in a number of different forms (see 3.3.1).

Different commercial forms, solids or dissolved in water are possible. All concentrations mentioned refer to the active matter and shall be calculated accordingly.

NOTE : Tetrapotassium pyrophosphate can be a component of mixtures sold for water treatment purposes.

3.3 Physical properties

3.3.1 Appearance

Solid : white powder.

Liquid : clear solution.

ITeH STANDARD PREVIEW
(standards.iteh.ai)
<https://standards.iteh.ai/catalog/standards/sist/6f2af199-c2c9-4b60-a93c-a55b468e484f/sist-en-1207-1999>

3.3.2 Density

Solid : bulk density 400 g/dm³.

Liquid : 1,046 g/ml for a product concentration of 50 g/l at 20°C.

3.3.3 Solubility in water :

Approximately 1 300 g/l at 25 °C.

3.3.4 Vapour pressure

Not applicable.

3.3.5 Boiling point at 100 kPa³⁾

Not applicable.

¹⁾ Chemical Abstracts Service Registry Number

²⁾ European Inventory of Existing Commercial Chemical Substances

³⁾ 100 kPa = 1 bar

3.3.6 Melting point

1 100 °C.

3.3.7 Specific heat

Not known.

3.3.8 Viscosity (dynamic)

Solid : not applicable.

Liquid : 5 mPa.s for a product concentration of 50 g/l.

3.3.9 Critical temperature

Not applicable.

3.3.10 Critical pressure

Not applicable.

3.3.11 Physical hardness

Not applicable. <https://standards.iteh.ai/catalog/standards/sist/6f2af199-c2c9-4b60-a93c-a55b468e484f/sist-en-1207-1999>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

3.4 Chemical properties

Solutions of tetrapotassium pyrophosphate have alkaline reactions.

The pH value of a solution containing 1 % (m/m) is approximately 10.

4 Purity criteria

Limits have been given for impurities and toxic substances where these are likely to be present in significant quantities from the current production process and raw materials. If a change in the production process or raw materials leads to significant quantities of other impurities or by-products being present, this shall be notified to the user.

4.1 Composition of commercial product

The product shall conform to the following requirements on a dry mass basis :

- phosphate content expressed as P_2O_5 : $(43 \pm 1,0)$ percent by mass (% (m/m)) ;
- potassium content expressed as K_2O : $(57 \pm 1,0)$ percent by mass (% (m/m)).