
Plastic containers for intravenous injections

Récipients en plastique pour injections intraveineuses

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

ISO 15747:2018

<https://standards.iteh.ai/catalog/standards/iso/6e5ec4ae-bc92-4db5-881e-56c89bba5506/iso-15747-2018>



iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

ISO 15747:2018

<https://standards.iteh.ai/catalog/standards/iso/6e5ec4ae-bc92-4db5-881e-56c89bba5506/iso-15747-2018>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2018

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Requirements	2
4.1 Physical requirements	2
4.1.1 Manufacturing process compatibility	3
4.1.2 Resistance to temperature, pressure and leakage	3
4.1.3 Resistance to dropping	3
4.1.4 Transparency	3
4.1.5 Water vapour permeability	3
4.1.6 Particulate contamination	3
4.1.7 Cover	3
4.1.8 Access port — Penetration ability of the insertion point	3
4.1.9 Access port — Adhesion strength of the infusion device and impermeability of the insertion point	3
4.1.10 Access port — Tightness of the injection point	4
4.1.11 Hanger	4
4.1.12 Identification	4
4.2 Chemical requirements	4
4.2.1 Requirements for the raw container or the sheeting	4
4.2.2 Requirements for the test fluid	4
4.3 Biological requirements	5
4.3.1 Impermeability for microorganisms	5
4.3.2 Migration	5
5 Application of tests	5
Annex A (normative) Physical tests	6
Annex B (normative) Chemical tests	9
Annex C (normative) Biological tests	12
Annex D (normative) Reference spike	14
Bibliography	16

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 76, *Transfusion, infusion and injection, and blood processing equipment for medical and pharmaceutical use*.

This third edition cancels and replaces the second edition (ISO 15747:2010), which has been technically revised. The main changes compared to the previous edition are as follows:

- the text of the Introduction has been moved as NOTE to the end of the Scope;
- a metallic reference spike has been defined, in [Annex D](#), to harmonise measurement of insertion point functional properties, for orientation and comparison purpose between different containers;
- the test for tightness of the injection point after piercing with a cannula has been revised to better define acceptance criteria;
- the wording of the titles of requirements and related tests procedures has been harmonised for better clarity.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Plastic containers for intravenous injections

1 Scope

This document specifies requirements to the safe handling and the physical, chemical and biological testing of plastic containers for parenterals.

This document is applicable to plastic containers for parenterals having one or more chambers and having a total nominal capacity in the range of 50 ml to 5 000 ml such as film bags or blow-moulded plastic bottles for direct administration of infusion (injection) solutions.

NOTE In some countries, national or regional pharmacopoeias or other government regulations are legally binding and these requirements take precedence over this document.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 2768-1, *General tolerances — Part 1: Tolerances for linear and angular dimensions without individual tolerance indications*

ISO 2768-2, *General tolerances — Part 2: Geometrical tolerances for features without individual tolerance indications*

ISO 8536-4, *Infusion equipment for medical use — Part 4: Infusion sets for single use, gravity feed*

ISO 10993-1, *Biological evaluation of medical devices — Part 1: Evaluation and testing within a risk management process*

ISO 10993-5, *Biological evaluation of medical devices — Part 5: Tests for in vitro cytotoxicity*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

3.1

access port

area of the *infusion container* (3.7) consisting of the *insertion point* (3.9) and the *injection point* (3.8), if applicable

3.2

cover

part that protects the *access port* (3.1) during storage and also provides evidence that the infusion container has been tampered with

Note 1 to entry: The cover can also envelop the entire container (e.g. outer bag).

3.3

empty container

raw container (3.11) with *identification* (3.6), which is suitable for the acceptance, storage and administration of the injection solution

3.4

gauge pressure

pressure zero-referenced against local atmospheric pressure

Note 1 to entry: Container internal gauge pressure is:

- positive when the container is pressurized above the surrounding atmospheric pressure, and is
- negative when the container is subjected to suction.

3.5

hanger

part of the container that is used to hang it up

3.6

identification

paper label, foil label, printing or embossing used to identify the product

3.7

infusion container

container filled to its *nominal capacity* (3.10) with parenteral injection product and with *identification* (3.6) for the storage and administration of the parenteral injection product

3.8

injection point

point where pharmaceuticals are injected

Note 1 to entry: The injection point and the insertion point can be identical.

Note 2 to entry: Some containers intentionally do not have an injection point.

3.9 <https://standards.iteh.ai/catalog/standards/iso/6e5ec4ae-bc92-4db5-881e-56c89bba5506/iso-15747-2018>

insertion point

point which accepts the insertion part of the infusion device

3.10

nominal capacity

intended or declared fluid volume of a container

3.11

raw container

empty container (3.3) that has not yet been sterilized and has no *identification* (3.6)

3.12

sheeting

plastic material intended for the production of *empty containers* (3.11)

4 Requirements

4.1 Physical requirements

For physical tests see [Annex A](#).

4.1.1 Manufacturing process compatibility

The infusion container shall be in accordance with the requirements given in [4.1.2](#) to [4.1.5](#) and [4.1.7](#) to [4.1.12](#) after the manufacturing process (such as sterilization).

4.1.2 Resistance to temperature, pressure and leakage

The infusion container shall withstand alternating thermal stress, shall be resistant to pressure and shall be leak-free when tested as specified in [A.3](#).

4.1.3 Resistance to dropping

The infusion container shall sustain no damage after being dropped when tested as specified in [A.4](#).

4.1.4 Transparency

The infusion container shall be sufficiently transparent so that suspended particles, turbidity and discoloration can be recognised when tested as specified in [A.5](#). Alternative procedures may be used.

Blocking of UV radiation should be considered depending on the content of the container.

4.1.5 Water vapour permeability

Unless otherwise defined for specific applications or uses, the packed infusion solution shall not lose more than 5 % of its mass during the period of usability, when tested as specified in [A.6](#).

Permeability of other gases (e.g. oxygen) should be taken into account depending on the content of the container.

4.1.6 Particulate contamination

Infusion containers shall be manufactured so that contamination with particles is avoided.

When empty infusion containers are tested as specified in [A.7](#), no more than 25 particles with a diameter $\geq 10 \mu\text{m}$ and no more than 3 particles with a diameter $\geq 25 \mu\text{m}$ shall be found per millilitre of nominal capacity. Finished parenteral solutions in the infusion containers shall be in accordance with relevant pharmacopoeial requirements for particulate matter in finished products.

4.1.7 Cover

The access port shall be protected by a cover. Its intactness is determined by visual inspection. It shall be possible to remove the cover without using mechanical aids.

4.1.8 Access port — Penetration ability of the insertion point

It shall be possible to pierce the insertion point with the insertion part of an infusion device as specified in ISO 8536-4 or of a reference spike as described in [Annex D](#). The force shall not exceed 200 N at an insertion rate of $500 \text{ mm} \cdot \text{min}^{-1}$, when tested as specified in [A.8](#).

4.1.9 Access port — Adhesion strength of the infusion device and impermeability of the insertion point

The material and design of the access port shall be suitable for accepting the insertion part of an infusion device in accordance with ISO 8536-4 or of a reference spike as described in [Annex D](#), for sealing off the insertion point and for holding the insertion part firmly when subject to tensile load. When tested as specified in [A.9](#), no leakage shall occur and the insertion part shall not slide out from the insertion point. The removal force shall be greater than 15 N.

Packed solution and used spike can affect the results of the test and should be considered during the testing.

4.1.10 Access port — Tightness of the injection point

If the container has an injection point, this shall not leak after puncturing and removal of the cannula when tested as specified in [A.10](#).

Diameter of needles used in the field to add pharmaceuticals in a liquid form into an IV container can differ from that specified in [A.10](#), for instance to make transfer of viscous drugs easier and faster. Results obtained when applying the specified procedure provide benchmark to evaluate injection point performance. However, they do not necessarily reflect the product performance in the intended use.

4.1.11 Hanger

It shall be possible to hang the infusion container up when it is in use. The hanger shall withstand a tensile load when tested as specified in [A.11](#).

4.1.12 Identification

The identification characters shall be clearly legible, and affixed labels shall not become detached when tested as specified in [A.12](#).

4.2 Chemical requirements

For chemical tests see [Annex B](#).

4.2.1 Requirements for the raw container or the sheeting

The sheeting shall fulfil the requirements given in [Table 1](#). Alternatively, it may be tested as described in the relevant pharmacopoeias.

Table 1 — Requirements for the raw container or the sheeting

Requirements	Maximum permissible value	Test as specified in
Residue on ignition:		
polyolefin	5 mg/g	B.2
polyvinyl chloride, containing plasticizers	1 mg/g	
Metals: Ba, Cd, Cr, Cu, Pb, Sn	for each metal, 3 mg/kg	B.3

4.2.2 Requirements for the test fluid

The test fluid shall be prepared as specified in [B.4](#). No coloration, but weak opalescence of the test fluid, is permissible. It shall fulfil the requirements specified in [Table 2](#).

Table 2 — Requirements for the test fluid

Requirements	Maximum permissible value	Test as specified in
Acidity or alkalinity	0,4 ml sodium hydroxide solution [$c(\text{NaOH}) = 0,01 \text{ mol/l}$] 0,8 ml hydrochloric acid [$c(\text{HCl}) = 0,01 \text{ mol/l}$]	B.6
UV absorbance	in the range of 230 nm to 360 nm: $\leq 0,25$ for infusion containers with a nominal capacity $\leq 100 \text{ ml}$ $\leq 0,2$ for infusion containers with a nominal capacity $> 100 \text{ ml}$	B.7
Evaporation residue	5 mg	B.8
Oxidizable constituents	1,5 ml	B.9
Ammonia	0,8 mg/l	B.10
Metals: Ba, Cr, Cu, Pb Sn, Cd Al	for each metal, 1 mg/l for each metal, 0,1 mg/l 0,05 mg/l	B.11
Heavy metals	2 mg/l	B.12

4.3 Biological requirements

The biological tests shall be carried out according to [Annex C](#).

4.3.1 Impermeability for microorganisms

The infusion container shall be impermeable to microorganisms when tested as specified in [C.2](#).

4.3.2 Migration

The materials used for the manufacture of infusion containers (e.g. films, wrappings, adhesives, adhesion promoters, printing inks) shall not release any substances into the infusion solution in such quantities that they have a pyrogenic or toxic effect when tested as specified in [C.3](#), [C.4](#) and ISO 10993-1.

5 Application of tests

A distinction is made between type testing and batch testing. All tests specified in [Annexes A](#) to [C](#) are type testing. They shall be repeated if one or more of the following conditions is changed significantly so that the requirements as specified in [Clause 4](#) might be affected:

- the design;
- the plastic composition;
- the process of manufacturing the infusion container;
- the sterilization process.

Annex A (normative)

Physical tests

A.1 General

Physical testing shall be performed using an infusion container filled up to the nominal capacity with infusion solution or with water.

A.2 Sampling

Take samples required for the tests specified in [A.3](#) to [A.12](#) in accordance with the requirements of statistical quality control for sampling for the type test.

NOTE Guidance for sampling is provided, for instance, in ISO 2859-1 for inspection by attributes or in ISO 3951-1 for inspection by variables.

A.3 Resistance to temperature, pressure and leakage

Store infusion containers for 24 h at $(-25 \pm 5) ^\circ\text{C}$ and subsequently for 24 h at $(50 \pm 5) ^\circ\text{C}$, and then subject them to an internal gauge pressure of 50 kPa between two plane parallel plates at $(20 \text{ to } 30) ^\circ\text{C}$. Maintain this pressure for 15 min. An equivalent test method may be used in which an external pressure, such as a pressure cuff, is applied to the bag in order to generate an equivalent internal pressure.

The test is passed if no leakage can be determined on visual inspection. The test does not apply to the internal seals separating chambers within a container.

For infusion containers labelled “protect from freezing”, omit storage at $-25 ^\circ\text{C}$.

A.4 Resistance to dropping

Drop the infusion containers on a hard, rigid, smooth surface at a temperature of $(20 \text{ to } 30) ^\circ\text{C}$. Determine the height of drop in accordance with [Table A.1](#), depending upon the nominal capacity of the infusion container.

The test is passed if no infusion container is broken and no leakage can be determined on visual inspection.

Table A.1 — Height of drop depending upon nominal capacity

Nominal capacity ml	Height of drop m
50 to 749	1,00
750 to 1 499	0,75
1 500 to 2 499	0,50
2 500 and above	0,25