



Designation: C846 – 94(Reapproved 2009)

Standard Practice for Application of Cellulosic Fiber Insulating Board for Wall Sheathing¹

This standard is issued under the fixed designation C846; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This practice covers the requirements for storing, handling, and application of cellulosic fiber insulating board products.

1.2 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*²

C208 Specification for Cellulosic Fiber Insulating Board
D1554 Terminology Relating to Wood-Base Fiber and Particle Panel Materials

2.2 *Voluntary Product Standard:*

ANSI/AHA A194.1 Cellulosic Fiberboard³

2.3 *Federal Specifications:*

FF-N-105-B with Interim Amendment 4 Nails, Brads, Staples and Spikes: Wire Cut and Wrought⁴
UU-B-790-A Building Paper, Vegetable Fiber: (Kraft, Waterproofed, Water Repellent and Fire Resistant)⁴

3. Terminology

3.1 *Definitions of Terms Specific to This Standard:*

¹ This practice is under the jurisdiction of ASTM Committee C16 on Thermal Insulation and is the direct responsibility of Subcommittee C16.40 on Insulation Systems.

Current edition approved April 1, 2009. Published August 2009. Originally approved in 1976. Last previous edition approved in 2003 as C846 – 94 (2003). DOI: 10.1520/C0846-94R09.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Available from American Hardboard Assoc., 1210 W. Northwest Highway, Palatine, IL.

⁴ Available from Standardization Documents Order Desk, DODSSP, Bldg. 4, Section D, 700 Robbins Ave., Philadelphia, PA 19111-5098, http://www.dodssp.daps.mil.

3.1.1 *exterior finish*—the shingle, lap, or panel siding material, masonry veneer, or stucco applied over the sheathing as a protective, decorative exterior finish of the building.

3.1.2 *fasteners*—nails, staples, or screws used for application of the sheathing.

3.1.3 *framing members*—those portions of the studs, headers, bracing, and blocking which serve to receive the sheathing. Framing members can be wood or metal.

3.1.4 *regular wall sheathing*—described in Definitions D1554 and Specification C208. It is 4 ft (1.22 m) wide with square-cut edges on all sides and 1/2 in. (12.7 mm) in thickness.

3.1.5 *structural wall sheathing*—described in Definitions D1554 and Specification C208. When installed in accordance with Section 7, it is considered a structural sheathing providing adequate racking resistance. It is 4 ft (1.22 m) wide and 1/2 in. (12.7 mm) or 25/32 in. (19.8 mm) in thickness with square-cut edges on all sides.

3.1.6 *vertical application*—sheathing applied with the long edges parallel to the studs.

4. Significance and Use

4.1 This standard provides recommendations for the installation in a safe and effective manner. Actual conditions may vary greatly, and additional care should be taken to ensure a safe and effective installation.

4.2 This standard presents requirements that are general in nature and considered practical. They are not intended as specific recommendations. The user should consult the manufacturer for recommended application methods and procedures.

4.3 This standard does not address the applicability of regulatory limitations. This is the responsibility of the user.

5. Materials

5.1 *Sheathing* shall conform to ANSI/AHA A194.1 and Specification C208.

5.2 *Nails* for application of sheathing to wood framing shall conform to Federal Specification FF-N-105-B, including Interim Amendment 4, and shall be in accordance with Table 1.

5.3 *Staples* for application of 1/2-in. and 25/32-in. sheathing to wood framing shall meet the following requirements:



TABLE 1 Nail Dimensions

Sheathing Thickness, in. (mm)		Galvanized Steel Roofing Nails	Common Nails
1/2 (12.7)	Gage	11	11 1/2 (6d)
	Length, min. in. (mm)	1 1/2 (38.1)	2 (50.8)
	Head diameter, min. in. (mm)	7/16 (11.1)	17/64 (6.75)
	Wire diameter, min. in. (mm)	0.120 (3.06) ^A	0.1130 (2.87)
25/32 (19.8)	Gage	11	10 1/4 (8d)
	Length, min. in. (mm)	1 3/4 (44.5)	2 1/2 (63.5)
	Head diameter, min. in. (mm)	7/16 (11.1)	9/32 (7.14)
	Wire diameter, min. in. (mm)	0.120 (3.06) ^A	0.131 (3.33)

^A Prior to galvanizing.

Gage	16
Thickness, min. in. (mm)	0.057 (1.45)
Width, min. in. (mm)	0.063 (1.59)
Length, min. in. (mm)	1 1/2 (38.1)
Crown, min. in. (mm)	7/16 (11.1)
Points	chisel point divergent point divergent chisel point

5.4 Screws for application of 1/2-in. and 25/32-in. sheathing on 14-gage (0.075-in.) (1.90-mm) to 20-gage (0.036-in.) (0.91mm) steel studs shall meet the following requirements:

Head type	bugle head
Head diameter, min. in. (mm)	5/16 (7.94)
Length, min. in. (mm)	1 1/4 (31.8)
Major diameter, in. (mm)	9/64 (3.57)
Minor diameter, in. (mm)	7/64 (2.78)
Point	drill point

5.5 Framing Members shall be of such size and quality as to be structurally adequate for the type of building being constructed.

5.5.1 Stud spacing shall be 16 in. (0.41 m) or 24 in. (0.61 m) on center depending on code requirements.

6. Storage

6.1 Sheathing shall be stored flat, and supported and protected from direct contact with the ground. Sheathing shall not be stored in a heated warehouse and shall be allowed to come to equilibrium at job site conditions prior to application. Sheathing should be protected from rain prior to installation.

7. Application (see Table 2)

7.1 Vertical Application (see Fig. 1)—Apply 4-ft (1.22-m) wide by 1/2-in. (12.7-mm) or by 25/32-in. (19.8-mm) sheathing vertically with long edges parallel to the vertical studs. Center all joints over the framing members with a 1/8-in. (3.18-mm) gap between edges. Leave a 1/8-in. gap at doors, windows, and horizontal joints. Sheathing should extend from sill to plate. If not, headers for adequate nailing should be provided at all horizontal joints. Apply fasteners for 1/2-in. or 25/32-in. material using roofing nails, common nails (5.2) or staples (5.3) for wood framing and screws (5.4) for metal framing. Apply fasteners to intermediate framing members first. For wood framing, space fasteners 6 in. (152 mm) (Note 1) on center. Apply perimeter fasteners 3 in. (76 mm) (Note 1) on center and a minimum of 3/8 in. (9.5 mm) from the edge. Apply staples (5.3) vertically with the crown parallel to the framing member. Drive fasteners flush with the sheathing surface, but do not countersink. For metal framing, space the fasteners 5 in. (127 mm) around the perimeter of the sheets and 10 in. (254 mm) into intermediate framing.

NOTE 1—When bracing strength is provided separately, intermediate fasteners may be 8 in. (203 mm) on center and perimeter fasteners 4 in. (102 mm) on center.

8. General Recommendations for Installing Exterior Finishes Over Sheathing

8.1 Regular and Structural Wall Sheathing—Fasten furring strips, stucco bases, etc., through the sheathing to the framing.

8.1.1 Horizontal Lap Siding—Apply directly over the sheathing and fasten to each stud. Nails must be long enough

TABLE 2 Fastener Spacing

Sheathing	Framing	Fastener Spacing, in. (mm) on Center	
		Intermediate Framing	Perimeter Framing
1/2 or 25/32 in. by 4 ft by 8 ft or 9 ft (12.7 or 19.8 mm by 1.22 m by 2.44 m or 2.74 m)	wood	6 (152)	3 (76)
1/2 or 25/32 in. by 4 ft by 8 ft or 9 ft (19.8 or 12.7 mm by 1.22 m by 2.44 m or 2.74 m)	metal	10 (254)	5 (127)
With separate bracing: 1/2 in. by 4 ft by 8 ft or 9 ft (12.7 mm by 1.22 m by 2.44 m or 2.74 m)	wood	8 (203)	4 (102)
25/32 in. by 4 ft by 8 ft or 9 ft (19.8 mm by 1.22 m by 2.44 m or 2.74 m)			