



SLOVENSKI STANDARD
oSIST prEN 4650:2020

01-oktober-2020

Aeronavtika - Postopek označevanja žic in kablov z UV-laserjem

Aerospace series - Wire and cable marking process, UV Laser

Luft- und Raumfahrt - Leitungs- und Kabelkennzeichnungsverfahren durch UV-Laser

Série aérospatiale - Procédé de marquage des fils et câbles par laser UV

Ta slovenski standard je istoveten z: prEN 4650

<https://standards.iteh.ai/catalog/standards/sist/74f55d37-5f47-4fa2-a594-cf58ffed5562/osist-pren-4650-2020>

ICS:

49.060	Letalska in vesoljska električna oprema in sistemi	Aerospace electric equipment and systems
--------	---	---

oSIST prEN 4650:2020

en,fr,de

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[oSIST prEN 4650:2020](https://standards.iteh.ai/catalog/standards/sist/74f55d37-5f47-4fa2-a594-cf58ffed5562/osist-pren-4650-2020)

<https://standards.iteh.ai/catalog/standards/sist/74f55d37-5f47-4fa2-a594-cf58ffed5562/osist-pren-4650-2020>

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

DRAFT
prEN 4650

August 2020

ICS

Will supersede EN 4650:2010

English Version

Aerospace series - Wire and cable marking process, UV Laser

Série aérospatiale - Procédé de marquage des fils et câbles par laser UV

Luft- und Raumfahrt - Leitungs- und Kabelkennzeichnungsverfahren durch UV-Laser

This draft European Standard is submitted to CEN members for enquiry. It has been drawn up by the Technical Committee ASD-STAN.

If this draft becomes a European Standard, CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

This draft European Standard was established by CEN in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.

[https://standards.iteh.ai/catalog/standards/sist/74f55d37-5f47-4fa2-a594-](https://standards.iteh.ai/catalog/standards/sist/74f55d37-5f47-4fa2-a594-cf58fa15562/osist-pr-en-4650-2020)

Recipients of this draft are invited to submit, with their comments, notification of any relevant patent rights of which they are aware and to provide supporting documentation.

Warning : This document is not a European Standard. It is distributed for review and comments. It is subject to change without notice and shall not be referred to as a European Standard.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

Contents	Page
European foreword	4
Introduction	5
1 Scope.....	6
2 Normative references.....	6
3 Terms, definitions, symbols and abbreviations.....	6
3.1 Terms and definitions	6
3.2 Symbols and abbreviations	11
4 Requirements.....	11
4.1 UV laser wire marking requirements.....	11
4.2 Design construction file.....	11
4.3 Process requirements	11
4.3.1 Laser wavelength	11
4.3.2 Mask based laser marking systems (see Clause 8).....	11
4.3.3 Scanner laser marking systems (see Clause 8).....	12
4.3.4 IR radiation	13
4.4 System requirements	13
4.4.1 Laser type.....	13
4.4.2 Laser output control	13
4.5 Quality requirements – General.....	14
4.5.1 Insulation Damage.....	14
4.5.2 Legibility and permanence.....	14
4.5.3 Mark contrast.....	14
5 Quality assurance provisions	14
5.1 Responsibility for inspection.....	14
5.1.1 General.....	14
5.1.2 Test equipment and inspection facilities	14
5.2 Quality conformance inspection.....	14
5.2.1 General.....	14
5.2.2 Inspection conditions	14
5.3 Verification inspection	15
5.4 Quality conformance inspection.....	15
6 Test methods	15
6.1 Design construction file.....	15
6.2 Laser wavelength (see Clause 8)	15
6.3 Laser pulse length (see Clause 8)	15
6.4 Applied laser fluence	16
6.4.1 Mask Based Marking System.....	16
6.4.2 Scanning Laser Marking System.....	16
6.5 Laser dot overlap in Scanning Laser Marking Systems.....	17
6.6 IR radiation	17
6.7 Laser type.....	18
6.8 Laser output control	18

6.9	Insulation damage	18
6.10	Legibility and permanence.....	18
6.11	Mark contrast measurements.....	18
7	Packaging.....	18
8	Notes.....	18
8.1	Principle of the marking process	18
8.1.1	General	18
8.1.2	Mask-based laser marking systems	18
8.1.3	Scanning laser marking systems.....	18
8.2	Markability of wire constructions	19
8.3	Properties of UV laser-marked insulation materials.....	19
8.3.1	General	19
8.3.2	Mark depth.....	20
8.3.3	Mark permanence.....	20
8.3.4	Mark colour.....	20
8.3.5	Polymer insulation background colour	20
8.3.6	Fungus.....	21
8.4	Laser wavelength.....	21
8.5	Pulse length.....	21
8.6	Pulse repetition rate.....	21
8.7	Laser type	22

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[oSIST prEN 4650:2020](https://standards.iteh.ai/catalog/standards/sist/74f55d37-5f47-4fa2-a594-cf58ffed5562/osist-pren-4650-2020)

<https://standards.iteh.ai/catalog/standards/sist/74f55d37-5f47-4fa2-a594-cf58ffed5562/osist-pren-4650-2020>

prEN 4650:2020 (E)

European foreword

This document (prEN 4650:2020) has been prepared by the Aerospace and Defence Industries Association of Europe — Standardization (ASD-STAN).

After enquiries and votes carried out in accordance with the rules of this Association, this Standard has received the approval of the National Associations and the Official Services of the member countries of ASD-STAN, prior to its presentation to CEN.

This document is currently submitted to the CEN Enquiry.

This document will supersede EN 4650:2010.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[oSIST prEN 4650:2020](#)

<https://standards.iteh.ai/catalog/standards/sist/74f55d37-5f47-4fa2-a594-cf58ffed5562/osist-pren-4650-2020>

Introduction

Ultraviolet (UV) laser wire marking was developed in 1987 to provide a safe, permanent means of marking thin wall insulations; it is now the aerospace industry standard method for marking wire identification codes on to the surface of electrical wires and cables. It provides a simple, convenient, environmentally friendly, cost effective means of marking and identifying wires and jacketed cables. While a few larger airframe manufacturers have developed process standards and specifications for their own use during the introduction of this technology, there has been variability in the issues covered within these specifications and there has been no comprehensive standard process document developed for general use. The intended use of this document is to serve directly as a process standard for use by laser wire marking concerns. It can also serve as a model set of comprehensive requirements for use by organizations who intend to develop in-house laser marking process specifications or serve as a means for evaluating the adequacy and completeness of such specifications by procuring activities.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[oSIST prEN 4650:2020](https://standards.iteh.ai/catalog/standards/sist/74f55d37-5f47-4fa2-a594-cf58ffed5562/osist-pren-4650-2020)

<https://standards.iteh.ai/catalog/standards/sist/74f55d37-5f47-4fa2-a594-cf58ffed5562/osist-pren-4650-2020>

prEN 4650:2020 (E)**1 Scope**

This document is applicable to the marking of aerospace vehicle electrical wires and cables using ultraviolet (UV) lasers.

This document specifies the process requirements for the implementation of UV laser marking of aerospace electrical wire and cable and fibre optic cable to achieve an acceptable quality mark using equipment designed for UV laser wire marking of identification codes on aircraft wire and cable subject to EN 3475-100, *Aerospace series — Cables, electrical, aircraft use — Test methods — Part 100: General*. Wiring specified as UV laser markable and which has been marked in accordance with this document will conform to the requirements of EN 3838.

This document is applicable to the marking of airframe electrical wires and cables using ultraviolet (UV) lasers. The laser process practices defined in this standard are mandatory.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 3475-100, *Aerospace series - Cables, electrical, aircraft use - Test methods - Part 100: General*

EN 3475-705, *Aerospace series - Cables, electrical, aircraft use - Test methods - Part 705: Contrast measurement*

EN 3475-706, *Aerospace series - Cables, electrical, aircraft use - Test methods - Part 706: Laser markability*

EN 3838, *Aerospace series - Requirements and tests on user-applied markings on aircraft electrical cable*¹⁾

EN ISO 10012, *Measurement management systems - Requirements for measurement processes and measuring equipment (ISO 10012)*

3 Terms, definitions, symbols and abbreviations**3.1 Terms and definitions**

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <http://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

3.1.1 cable

electrical cable, unless noted as a fibre optic cable. 2 (two) or more insulated conductors, solid or stranded, contained in a common covering, or 2 (two) or more insulated conductors twisted or molded together without common covering, or one insulated conductor with a metallic covering shield or outer conductor

¹⁾ Published as ASD-STAN Standard at the date of publication of this document by AeroSpace and Defence industries Association of Europe — Standardization (ASD-STAN), <http://www.asd-stan.org/>

3.1.2**component**

for the purposes of this document this shall be an electrical wire or multi-conductor cable or fibre optic cable

3.1.3**contrast**

measurement relating to the difference in luminance of the mark and its associated background according to a precise formula

3.1.4**damage**

for the purpose of this document, with reference to wire and cable, damage is defined as an unacceptable reduction in the mechanical or electrical properties of the insulation (i.e., specifically a measurable reduction in the performance of the wire or cable that is outside of its defined specification or is otherwise unacceptable)

3.1.5**dot overlap**

dot overlap for scanning laser systems is defined in relation to the diameter, D, of the laser beam at the surface of the wire at the $1/e^2$ point, and the distance, d, between the centres of the adjacent dots

Note 1 to entry: The percentage overlap = $(1-(d/D)) \times 100 \%$

3.1.6**excimer**

gas laser deriving its name from the term "excited dimer"

Note 1 to entry: The laser is energized by means of an electrical discharge in a specialized mixture of rare gases and halogens. Excimer lasers are available operating at a number of discrete wavelengths throughout the UV, the most common of which are 193 nm, 248 nm, 308 nm and 351 nm. The wavelength is dependant only on the gas mix used; 308 nm is commonly used for UV laser wire marking.

3.1.7**fibre optic cable**

cable that is designed to transmit light waves between a light transmission source and a receiver

Note 1 to entry: In signal applications, the transmitter and receiver include devices that are used to convert between optical and electronic pulses. Typical cables include a glass or plastic core, a layer of cladding having a lower refractive index to refract or totally reflect light inward at the core/cladding boundary, a buffer, strength members and jacketing to protect the inner cable from environmental damage.

3.1.8**fluence**

energy density, measured in joules per square centimetre (J/cm^2), of a single pulse of the laser beam, which is at the surface of the wire insulation or cable jacket

3.1.9**font**

defining shape and style of a character set for printing or marking

3.1.10**gauge**

wire size specified for a wire in a wire harness assembly by the wire harness assembly drawing

prEN 4650:2020 (E)**3.1.11****harmonic generation**

use of non-linear optical processes to change the wavelength of a laser, enabling the output of an infrared laser to be converted to shorter wavelengths

Note 1 to entry: In the case of Neodymium (Nd) lasers this results in a frequency doubled output at 532 nm in the green and a frequency tripled output at 355 nm in the UV, which is used for wire marking.

3.1.12**harness**

assembly of any number of wires, electrical/optical cables and/or groups and their terminations which is designed and fabricated so as to allow for installation and removal as a unit

Note 1 to entry: A harness may be an open harness or a protected harness.

3.1.13**infrared**

IR electromagnetic radiation in the wavelength range from approximately 700 nm to in excess of 10 000 nm

3.1.14**insulation**

outer polymer covering of an electrical wire or multi-conductor cable or fibre optic cable

3.1.15**IR laser**

laser that produces a beam of radiation in the IR range

3.1.16**jacket**

outer protective covering for a cable

3.1.17**laser**

laser is an acronym for Light Amplification by the Stimulated Emission of Radiation. Lasers are a source of intense monochromatic light in the ultraviolet, visible or infrared region of the spectrum. The “active” or lasing medium may be a solid, liquid or gas. The laser beam is generated by energizing the active medium using an external power source, which is most commonly electrical or optical

3.1.18**laser average power**

optical power, measured in Watts (W), delivered by the laser source

3.1.19**laser pulse energy**

optical energy, measured in Joules (J) contained in each laser pulse

3.1.20**laser pulse length**

time interval between the laser energy crossing half the maximum energy on the rising and the falling edges of the pulse; referred to as FWHM – full width half maximum

Note 1 to entry: Pulse lengths are measured in nanoseconds (ns). 1 ns = 10⁻⁹ s.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[oSIST prEN 4650:2020](https://standards.iteh.ai/catalog/standards/sist/74f55d37-5f47-4fa2-a594-cf58ffed5562/osist-pren-4650-2020)

<https://standards.iteh.ai/catalog/standards/sist/74f55d37-5f47-4fa2-a594-cf58ffed5562/osist-pren-4650-2020>

3.1.21**laser pulse rate**

number of laser pulses delivered per second, measured in Hertz (Hz). Also referred to as the laser pulse frequency or repetition rate

3.1.22**legibility**

properties of a mark that enable it to be easily and correctly read

3.1.23**luminance**

quantitative measurement of the visible light reflected from a surface, in this case the wire or cable insulation

3.1.24**mark**

meaningful alphanumeric or machine readable mark applied to the surface of a wire or cable jacket

3.1.25**markability**

markability of a wire construction to be marked to provide legible identification marks of a specified contrast when marked in accordance with this document

3.1.26**neodymium Nd**

elemental metal that forms the active laser material in the most common type of solid-state laser

Note 1 to entry: The neodymium is held in an optically transparent solid “host” material, and is energized by optical input, either from a flash lamp or from the optical output from a diode laser. The host material does not play a direct role but can slightly influence the laser wavelength. Typical host materials are specialized crystal materials, such as Yttrium Aluminium Garnet (YAG), Yttrium Lithium Fluoride (YLF) and Yttrium Vanadate (YVO4). These lasers are commonly referred to as Nd:YAG, Nd:YLF and Nd:YVO4 respectively. The primary wavelength of Nd solid state lasers is in the infrared (IR) at a wavelength of approximately 1 064 nm. The IR output of such lasers can be conveniently reduced to lower wavelengths suitable for wire marking by use of harmonic generation.

3.1.27**purchaser**

activity that can issue a purchase order or contract

3.1.28**q-switched laser**

laser that retains and circulates the laser energy internally within the laser until a signal is sent to open the “Q-switch”, usually an electro-optic component. The Q-switch acts like a gate that when opened allows the trapped laser beam to exit on a nanosecond timescale. This technique is routinely used on long pulse solid state lasers to create short laser pulses such as those required for UV laser wire marking

3.1.29**quality conformance**

tests performed on production samples at a specified frequency to ensure that the requirements of this document are met

iTeh STANDARD PREVIEW
(standards.iteh.ai)