



SLOVENSKI STANDARD
SIST EN 3838:2022

01-julij-2022

Nadomešča:
SIST EN 3838:2010

Aeronavtika - Zahteve in preskusi pri označevanju električnih kablov v zračnih plovilih za uporabnike

Aerospace series - Requirements and tests on user-applied markings on aircraft electrical cables

Luft- und Raumfahrt - Anforderungen und Prüfungen der Anwenderkennzeichnung auf elektrischen Luftfahrzeugleitungen

Série aérospatiale - Exigences et essais sur les marquages utilisateurs de câbles électriques aéronautiques

Ta slovenski standard je istoveten z: EN 3838:2022

ICS:

29.060.20	Kabli	Cables
49.060	Letalska in vesoljska električna oprema in sistemi	Aerospace electric equipment and systems

SIST EN 3838:2022

en,fr,de

EUROPEAN STANDARD

EN 3838

NORME EUROPÉENNE

EUROPÄISCHE NORM

May 2022

ICS 49.060

Supersedes EN 3838:2010

English Version

Aerospace series - Requirements and tests on user-applied markings on aircraft electrical cables

Série aérospatiale - Exigences et essais sur les marquages utilisateurs de câbles électriques aéronautiques

Luft- und Raumfahrt - Anforderungen und Prüfungen der Anwenderkennzeichnung auf elektrischen Luftfahrzeugleitungen

This European Standard was approved by CEN on 13 March 2022.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.

<https://standards.iteh.ai/catalog/standards/sist/b19669a0-4ee1-4487-b4e2-f58506f09704/sist-en-3838-2022>



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

Contents	Page
European foreword	4
Introduction	5
1 Scope.....	6
2 Normative references.....	6
3 Terms and definitions.....	7
4 Qualification tests.....	7
4.1 Tests.....	7
4.2 Test sequence.....	7
5 Acceptance tests.....	9
6 Test methods.....	9
6.1 Visual examination of markings.....	9
6.1.1 Object	9
6.1.2 Apparatus	9
6.1.3 Test specimen	9
6.1.4 Procedure	9
6.1.5 Requirements.....	9
6.2 Permanence of markings.....	9
6.2.1 Object	9
6.2.2 Apparatus	10
6.2.3 Test specimen	10
6.2.4 Procedure	10
6.2.5 Requirements.....	10
6.3 Resistance to fluids	10
6.3.1 Object	10
6.3.2 Apparatus	10
6.3.3 Specimen.....	10
6.3.4 Procedure	10
6.3.5 Requirements.....	10
6.4 Heat ageing.....	10
6.4.1 Object	10
6.4.2 Apparatus	10
6.4.3 Specimen.....	10
6.4.4 Procedure	11
6.4.5 Requirements.....	11
6.5 Exposure to light	11
6.5.1 Object	11
6.5.2 Apparatus	11
6.5.3 Specimen.....	11
6.5.4 Procedure	11
6.5.5 Requirements.....	11
6.6 Marking contrast.....	12
6.6.1 Object	12
6.6.2 Apparatus	12
6.6.3 Test specimen	12

6.6.4	Procedure	12
6.6.5	Requirements.....	12
6.7	Bending at ambient temperature	12
6.7.1	Object.....	12
6.7.2	Apparatus.....	12
6.7.3	Test specimen	12
6.7.4	Procedure.....	12
6.7.5	Requirements.....	12
6.8	Voltage test.....	13
6.8.1	Object.....	13
6.8.2	Apparatus	13
6.8.3	Test specimen	13
6.8.4	Procedure.....	13
6.8.5	Requirements.....	13
	Bibliography	14

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN 3838:2022](https://standards.iteh.ai/catalog/standards/sist/b19669a0-4ee1-4487-b4e2-f58506f09704/sist-en-3838-2022)

<https://standards.iteh.ai/catalog/standards/sist/b19669a0-4ee1-4487-b4e2-f58506f09704/sist-en-3838-2022>

EN 3838:2022 (E)

European foreword

This document (EN 3838:2022) has been prepared by the Aerospace and Defence Industries Association of Europe — Standardization (ASD-STAN).

After enquiries and votes carried out in accordance with the rules of this Association, this document has received the approval of the National Associations and the Official Services of the member countries of ASD-STAN, prior to its presentation to CEN.

This document shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by November 2022, and conflicting national standards shall be withdrawn at the latest by November 2022.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 3838:2010.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this document: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

(standards.iteh.ai)

SIST EN 3838:2022

<https://standards.iteh.ai/catalog/standards/sist/b19669a0-4ee1-4487-b4e2-f58506f09704/sist-en-3838-2022>

Introduction

Durability of function-related marking of aircraft electrical cables is of great importance throughout the life of an aircraft, during initial assembly, operation and maintenance operations in service.

Markings should, therefore, be made to a sufficiently high standard to satisfy requirements initially and for the remainder of the expected life marked cable or equipment containing it.

Markings are applied by the user to the cable insulation, jacket or sheath and should not degrade the performance of the cable. They should be applied in accordance with design requirements using a process approved by the Design Authority.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN 3838:2022](https://standards.iteh.ai/catalog/standards/sist/b19669a0-4ee1-4487-b4e2-f58506f09704/sist-en-3838-2022)

<https://standards.iteh.ai/catalog/standards/sist/b19669a0-4ee1-4487-b4e2-f58506f09704/sist-en-3838-2022>

EN 3838:2022 (E)**1 Scope**

This document specifies tests that are to be performed on markings applied by the user to ensure that their durability is satisfactory and that, after application of markings directly to the cable insulation, jacket or sheath, the cable will meet the performance requirements laid down.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 3475-201, *Aerospace series — Cables, electrical, aircraft use — Test methods — Part 201: Visual examination*

EN 3475-302:2006, *Aerospace series — Cable, electrical, aircraft use — Test methods — Part 302: Voltage proof test*

EN 3475-401:2002, *Aerospace series — Cables, electrical, aircraft use — Test Methods — Part 401: Accelerated ageing*

EN 3475-405:2002, *Aerospace series — Cables, electrical, aircraft use — Test methods — Part 405: Bending at ambient temperature*

EN 3475-411, *Aerospace series — Cables, electrical, aircraft use — Test methods — Part 411: Resistance to fluids*

EN 3475-703:2002, *Aerospace series — Cables, electrical, aircraft use — Test methods — Part 703: Permanence of manufacturer's marking*

EN 3475-705, *Aerospace series — Cables, electrical, aircraft use — Test methods — Part 705: Contrast measurement*

EN ISO 4892-3, *Plastics — Methods of exposure to laboratory light sources — Part 3: Fluorescent UV lamps (ISO 4892-3)*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

3.1

marking

identification mark applied directly to the cable insulation, jacket or sheath by any process that meets the requirements of this document

3.2

aggressive marking system

marking which can deform or damage the insulating layer of a cable

Note 1 to entry: hot-stamp is defined as such a method. Other methods of marking may be defined as aggressive by the end users.

4 Qualification tests

4.1 Tests

The tests in Table 1 shall be performed at the introduction of the marking process, at every change in technology or processing technique affecting the cable insulation, jacket or sheath or as required by the end users.

Tests shall be performed on the sizes for qualification defined in the cable specification for each colour, material and construction of cable, jacket and sheath which will be directly marked.

Before the tests defined in Table 1 are performed on specimens of user marked cable, ensure that the specimens have been subjected to any post marking curing which is normal for the defined marking process.

Table 1

Title	Subclause
Visual examination of markings	6.1
Permanence of markings	6.2
Resistance to fluids	6.3
Heat ageing	6.4
Exposure to light	6.5
Marking contrast	6.6
Bending at ambient temperature	6.7

4.2 Test sequence

The number of specimens for each test and the sequence of testing shall be as laid down in Table 2.

Each specimen shall be taken sequentially from a continuous length of cable.

Table 2 — All marking techniques except UV laser marking

Group	Number of specimens	Tests	
		Title	Subclause
1	5	Visual examination of markings	6.1
		Marking contrast	6.6
		Permanence of markings	6.2
2	1 per fluid	Visual examination of markings	6.1
		Resistance to fluids	6.3
		Marking contrast	6.6
3	3	Visual examination of markings	6.1
		Heat ageing	6.4
		Marking contrast	6.6
4	3	Visual examination of markings	6.1
		Exposure to light	6.5
		Visual examination of markings	6.1
5 ^a	3	Visual examination of markings	6.1
		Bending at ambient temperature	6.7
		Voltage proof test	6.8

^a Group 5 tests only performed on markings made by aggressive marking systems.

Table 3 — UV laser marking

Group	Number of specimens	Tests	
		Title	Subclause
1	3	Visual examination of markings	6.1
		Heat ageing	6.4
		Marking contrast	6.6
2	3	Visual examination of markings	6.1
		Exposure to light	6.5
		Visual examination of markings	6.1
3	3	Visual examination of markings	6.1
		Voltage proof test	6.8
		Visual examination of markings	6.1