
Vsadki (implantati) za kirurgijo - Kovinski materiali - 6. del: Kobalt-nikelj-krom-molibdenova kovana zlitina (ISO/DIS 5832-6:2021)

Implants for surgery - Metallic materials - Part 6: Wrought cobalt-nickel-chromium-molybdenum alloy (ISO/DIS 5832-6:2021)

Chirurgische Implantate - Metallische Werkstoffe - Teil 6: Kobalt-Nickel-Chrom-Molybdän-Schmiedelegerung (ISO/DIS 5832-6:2021)

Implants chirurgicaux - Produits à base de métaux - Partie 6: Alliage corroyé à base de cobalt, de nickel, de chrome et de molybdène (ISO/DIS 5832-6:2021)

<https://standards.iteh.ai/catalog/standards/sist/e4339523-2596-444b-818b-39d508122c8a/osist-pr-en-iso-5832-6-2021>

Ta slovenski standard je istoveten z: prEN ISO 5832-6

ICS:

| | | |
|-----------|---|---|
| 11.040.40 | Implantanti za kirurgijo, protetiko in ortetiko | Implants for surgery, prosthetics and orthotics |
|-----------|---|---|

oSIST prEN ISO 5832-6:2021

en,fr,de

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[oSIST prEN ISO 5832-6:2021](#)

<https://standards.iteh.ai/catalog/standards/sist/e4339523-2596-444b-818b-38d508122c8a/osist-pren-iso-5832-6-2021>

DRAFT INTERNATIONAL STANDARD

ISO/DIS 5832-6

ISO/TC 150/SC 1

Secretariat: DIN

Voting begins on:
2021-02-11Voting terminates on:
2021-05-06

Implants for surgery — Metallic materials —

Part 6: Wrought cobalt-nickel-chromium-molybdenum alloy

*Implants chirurgicaux — Produits à base de métaux —**Partie 6: Alliage corroyé à base de cobalt, de nickel, de chrome et de molybdène*

ICS: 11.040.40

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[oSIST prEN ISO 5832-6:2021](https://standards.iteh.ai/catalog/standards/sist/e4339523-2596-444b-818b-38d508122c8a/osist-pren-iso-5832-6-2021)<https://standards.iteh.ai/catalog/standards/sist/e4339523-2596-444b-818b-38d508122c8a/osist-pren-iso-5832-6-2021>

THIS DOCUMENT IS A DRAFT CIRCULATED FOR COMMENT AND APPROVAL. IT IS THEREFORE SUBJECT TO CHANGE AND MAY NOT BE REFERRED TO AS AN INTERNATIONAL STANDARD UNTIL PUBLISHED AS SUCH.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

This document is circulated as received from the committee secretariat.

ISO/CEN PARALLEL PROCESSING



Reference number
ISO/DIS 5832-6:2021(E)

© ISO 2021

iTeh STANDARD PREVIEW (standards.iteh.ai)

[oSIST prEN ISO 5832-6:2021](https://standards.iteh.ai/catalog/standards/sist/e4339523-2596-444b-818b-38d508122c8a/osist-pren-iso-5832-6-2021)

<https://standards.iteh.ai/catalog/standards/sist/e4339523-2596-444b-818b-38d508122c8a/osist-pren-iso-5832-6-2021>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2021

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

| | Page |
|-------------------------------------|----------|
| Foreword..... | iv |
| Introduction..... | v |
| 1 Scope..... | 1 |
| 2 Normative references..... | 1 |
| 3 Terms and definitions..... | 1 |
| 4 Chemical composition..... | 1 |
| 5 Microstructure..... | 2 |
| 5.1 General..... | 2 |
| 5.2 Grain size index..... | 2 |
| 6 Mechanical properties..... | 2 |
| 7 Test methods..... | 3 |

iTeh STANDARD PREVIEW (standards.iteh.ai)

[oSIST prEN ISO 5832-6:2021](https://standards.iteh.ai/catalog/standards/sist/e4339523-2596-444b-818b-38d508122c8a/osist-pren-iso-5832-6-2021)

<https://standards.iteh.ai/catalog/standards/sist/e4339523-2596-444b-818b-38d508122c8a/osist-pren-iso-5832-6-2021>

ISO/DIS 5832-6:2021(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 150, *Implants for surgery*, Subcommittee SC 1 *Materials*.

This third edition cancels and replaces the second edition (ISO 5832-6:1997) which has been technically revised.

The main changes compared to the previous edition are as follows:

- introduction updated;
- requirements for boron in [table 1](#) added;
- information on grain size in [5.2](#) added;
- requirements for mechanical properties in [table 2](#) updated and harmonised to ISO 5832-series.

A list of all parts in the ISO 5832 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

While no known surgical implant material has ever been shown to cause absolutely no adverse reactions in the human body, long-term clinical experience with the material referred to in this document has shown that an acceptable level of biological response can be expected when the material is used in appropriate applications. However, this standard covers the raw material and not finished medical devices, where the design and fabrication of the device can impact biological response.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[oSIST prEN ISO 5832-6:2021](https://standards.iteh.ai/catalog/standards/sist/e4339523-2596-444b-818b-38d508122c8a/osist-pren-iso-5832-6-2021)

<https://standards.iteh.ai/catalog/standards/sist/e4339523-2596-444b-818b-38d508122c8a/osist-pren-iso-5832-6-2021>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[oSIST prEN ISO 5832-6:2021](https://standards.iteh.ai/catalog/standards/sist/e4339523-2596-444b-818b-38d508122c8a/osist-pren-iso-5832-6-2021)

<https://standards.iteh.ai/catalog/standards/sist/e4339523-2596-444b-818b-38d508122c8a/osist-pren-iso-5832-6-2021>

Implants for surgery — Metallic materials —

Part 6:

Wrought cobalt-nickel-chromium-molybdenum alloy

1 Scope

This document specifies the characteristics of, and corresponding test methods for, wrought cobalt-nickel chromium- molybdenum alloy for use in the manufacture of surgical implants.

NOTE The mechanical properties of a sample obtained from a finished product made of this alloy can differ from those specified in this document.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 643, *Steels — Micrographic determination of the apparent grain size*

ISO 6892-1, *Metallic materials — Tensile testing — Part 1: Method of test at room temperature*

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

4 Chemical composition

The heat analysis of the alloy, when determined as specified in [Clause 7](#), shall conform to the relevant chemical composition specified in [Table 1](#).

Table 1 — Chemical composition

| Element | Mass fraction % (m/m) |
|------------|--------------------------|
| Nickel | 33,0 to 37,0 |
| Chromium | 19,0 to 21,0 |
| Molybdenum | 9,0 to 10,5 |
| Iron | 1,0 max. |
| Titanium | 1,0 max. |
| Manganese | 0,15 max. |
| Silicon | 0,15 max. |
| Carbon | 0,025 max. |

Table 1 (continued)

| Element | Mass fraction % (m/m) |
|------------|--------------------------|
| Phosphorus | 0,015 max. |
| Sulfur | 0,010 max. |
| Boron | 0,015 max. |
| Cobalt | Balance |

5 Microstructure

5.1 General

The microstructure of the alloy shall be uniform.

5.2 Grain size index

The grain size in the annealed condition, as determined in accordance with [clause 7](#), shall not be coarser than grain size No. 4. The grain size in other conditions may be determined as agreed upon between the manufacturer and the user.

6 Mechanical properties

The tensile properties of the alloy, when tested in accordance with [clause 7](#), shall be in accordance with the values specified in [Table 2](#).

NOTE 1 The mechanical properties of this material can be altered by cold-working and cold-working plus ageing processes.

If any of the test pieces fail within the gauge limits and do not meet specified requirements, two retest pieces shall be tested in the same manner, for each failed test piece. The alloy shall be deemed to conform only if both additional test pieces meet the specified requirements.

If a test piece fails outside the gauge limits, the test is acceptable if the percentage elongation after fracture meets the requirements. If the percentage elongation after fracture does not meet requirements the test shall be discarded and a retest shall be performed.

If any of the retests fails to meet the appropriate requirements, the product represented shall be deemed not to conform to this document. However, the manufacturer may, if desired, subject the material to heat treatment again and resubmit it for testing in accordance with this document.

Table 2 — Mechanical properties

| Condition | Tensile strength | Yield Strength or proof strength | Elongation after fracture ^a |
|-------------|-------------------------------|----------------------------------|--|
| | R _m min. MPa | R _{p0,2} min. MPa | A min. % |
| Annealed | 793 | 241 | 50 |
| Medium Hard | 1000 | 655 | 20 |
| Hard | 1207 | 1000 | 10 |

^a Gauge length = $5.65\sqrt{S_0}$ or 50 mm, where S_0 is the original cross-sectional area, in square millimeters.