

---

---

**Vitreous and porcelain enamels —  
Release from enamelled articles in  
contact with food — Methods of test  
and limits**

*Émaux vitrifiés — Libération depuis les articles émaillés en contact  
avec les aliments — Méthode d'essai et limites*

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

ISO 4531:2018

<https://standards.iteh.ai/catalog/standards/sist/a8f0391e-5335-47d2-abaf-4401e72b9d3f/iso-4531-2018>



**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

ISO 4531:2018

<https://standards.iteh.ai/catalog/standards/sist/a8f0391e-5335-47d2-abaf-4401e72b9d3f/iso-4531-2018>



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2018

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
CP 401 • Ch. de Blandonnet 8  
CH-1214 Vernier, Geneva  
Phone: +41 22 749 01 11  
Fax: +41 22 749 09 47  
Email: [copyright@iso.org](mailto:copyright@iso.org)  
Website: [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

Page

<b>Foreword</b> .....	<b>iv</b>
<b>Introduction</b> .....	<b>v</b>
<b>1 Scope</b> .....	<b>1</b>
<b>2 Normative references</b> .....	<b>1</b>
<b>3 Terms and definitions</b> .....	<b>1</b>
<b>4 Principle</b> .....	<b>1</b>
<b>5 Reagents</b> .....	<b>2</b>
<b>6 Apparatus</b> .....	<b>2</b>
<b>7 Samples</b> .....	<b>3</b>
<b>8 Preparation of samples</b> .....	<b>3</b>
<b>9 Test conditions</b> .....	<b>3</b>
<b>10 Procedure</b> .....	<b>4</b>
10.1 Release test.....	4
10.1.1 Release test lab apparatus.....	4
10.1.2 Release from enamelled articles.....	5
10.2 Sampling the release test solution for analysis (sample measuring solution).....	5
<b>11 Expression of results</b> .....	<b>5</b>
11.1 Reporting.....	5
11.2 Test report.....	6
<b>Annex A (informative) Explanatory information on release limits</b> .....	<b>7</b>
<b>Bibliography</b> .....	<b>9</b>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

This document was prepared by the European Committee for Standardization (CEN) Technical Committee CEN/TC 262, *Metallic and other inorganic coatings, including for corrosion protection and corrosion testing of metals and alloys*, in collaboration with ISO Technical Committee ISO/TC 107, *Metallic and other inorganic coatings*, in accordance with the agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This first edition cancels and replaces ISO 4531-1:1998 and ISO 4531-2:1998, which have been combined and technically revised.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at [www.iso.org/members.html](http://www.iso.org/members.html).

## Introduction

The release of metal-ions from enamelled articles requires effective means of control to ensure protection against possible hazards arising from the use of improperly formulated, applied and fired enamels and/or inorganic decorations on the food contact surfaces of enamelled articles used for the preparation, cooking, serving and storage of foodstuffs.

As a secondary consideration, different requirements from country to country for the control of the release of ions from the surfaces of enamelled articles present non-tariff barriers to international trade in these commodities. Accordingly, there is a need to establish internationally accepted methods of testing enamelled articles for the release of metal-ions.

## iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 4531:2018

<https://standards.iteh.ai/catalog/standards/sist/a8f0391e-5335-47d2-abaf-4401e72b9d3f/iso-4531-2018>

## **iTeh STANDARD PREVIEW (standards.iteh.ai)**

ISO 4531:2018

<https://standards.iteh.ai/catalog/standards/sist/a8f0391e-5335-47d2-abaf-4401e72b9d3f/iso-4531-2018>

# Vitreous and porcelain enamels — Release from enamelled articles in contact with food — Methods of test and limits

## 1 Scope

This document specifies a simulating method of test for determination of the release of metal-ions from enamelled articles, which are intended to come into contact with food.

It also specifies limits for the release of metal-ions from enamelled articles, which are intended to come into contact with food.

It is applicable to enamelled articles, including tanks and vessels, which are intended to be used for the preparation, cooking, serving and storage of food.

## 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 648, *Laboratory glassware — Single-volume pipettes*

ISO 1042, *Laboratory glassware — One-mark volumetric flasks*

ISO 3585, *Borosilicate glass 3.3 — Properties*

ISO 3696, *Water for analytical laboratory use — Specification and test methods*

ISO 4788, *Laboratory glassware — Graduated measuring cylinders*

ISO 28764, *Vitreous and porcelain enamels — Production of specimens for testing enamels on sheet steel, sheet aluminium and cast iron*

## 3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

## 4 Principle

For the release of metal-ions, if present, from the surfaces of articles or test specimen a mass fraction of 3 % (w/v) acetic acid solution shall be used. Three consecutive release tests shall be performed using the same sample and a fresh test solution per test. The first two release test solutions (M1, M2) are discarded. Only the third release test solution (M3) shall be used for analysis. A blank test (B1, B2, B3) is required for each release test, of which only the third release test solution (B3) shall be used for analysis.

## 5 Reagents

During the determination, use only reagents of recognized analytical grade and only distilled water, or water of equivalent purity (grade 3 water conforming to the requirements of ISO 3696).

It is permissible to prepare proportionately greater quantities of test solution and analytical solutions than specified in 5.2.

**5.1 Acetic acid**, ( $\text{CH}_3\text{COOH}$ ), concentrated, density  $\rho = 1,05$  g/ml.

**5.2 Test solution**, acetic acid, a 3 % (w/v) solution.

By means of a graduated measuring cylinder (6.4) add, to 500 ml of water,  $(30 \pm 1)$  g (28,6 ml) of concentrated acetic acid (5.1) and make up to 1 l. Prepare the test solution freshly prior to use and in sufficient quantity to enable the whole of any group of tests and analysis to be completed.

**5.3 Analytical stock solutions**, the standard stock solutions, or multi-element solutions, used for ICP-analysis shall be used.

**5.4 Dishwashing agent**, commercially available, non-acidic manual dishwashing detergent in common dilution.

## 6 Apparatus

Use only laboratory glassware, conforming to the requirements of appropriate International Standards, where they exist, and made of borosilicate glass as specified in ISO 3585.

**6.1 ICP spectrometer**, with a limit of detection at least six times lower than the release limits in Table 1. Other analysis equipment that achieves the equivalent performance may also be used (e.g. AAS/GF).

**6.2 One-mark volumetric flasks**, capacities 100 ml and 1 000 ml, conforming to the requirements specified for class B or better one-mark volumetric flasks in ISO 1042. Other sizes of one-mark volumetric flasks may also be required.

**6.3 One-mark pipettes**, capacities 10 ml and 100 ml, conforming to the requirements specified for class B or better one-mark pipettes in ISO 648. Other sizes of one-mark pipettes may also be required.

**6.4 Graduated measuring cylinders**, capacities 50 ml and 500 ml, conforming to the requirements specified in ISO 4788. Other sizes of graduated measuring cylinders may also be required.

**6.5 Vessels, containers, stoppers and connectors** shall consist of a material, such as glass or polytetrafluoroethylene (PTFE).

**6.6 Vessels made of borosilicate glass**, in accordance with ISO 3585, internal diameter 80 mm, external diameter 90 mm, height 36 mm, 10 mm diameter of the filling hole.

The calculation of the surface/volume (S/V) ratio is reported below.

Each chamber has an internal diameter of 80 mm. Therefore, the tested area  $a$  of one test plate is  $5\,025\text{ mm}^2$  ( $a = \pi r^2$ ).

The volume of the chamber  $V$  with a height  $h$  of 36 mm and a gasket thickness  $t$  of 2 mm is calculated from Formula (1):

$$V = (h + 2 \cdot t) \cdot a \quad (1)$$



$$V = (36 \text{ mm} + 2 \cdot 2 \text{ mm}) \cdot 5\,025 \text{ mm}^2 = 201\,000 \text{ mm}^3$$

The S/V ratio can be calculated from [Formula \(2\)](#):

$$\frac{S}{V} = \frac{5\,025 \text{ mm}^2}{201\,000 \text{ mm}^3} = 0,025 \text{ mm}^{-1} \quad (2)$$

The S/V ratio for two plates that shall be used, therefore, is equal to 0,05 mm<sup>-1</sup>.

**6.7 Silicone gaskets**, internal diameter 80 mm, external diameter of minimum 90 mm, thickness 2mm.

**6.8 Silicon stoppers**, diameter 10 mm, 20 mm length.

**6.9 PTFE-thermo insulating plate**, dimension of minimum 105 mm × 105 mm, 2 mm thickness.

**6.10 Blank samples plate made of borosilicate glass**, in accordance with ISO 3585 and dimensions of minimum 105 mm × 105 mm, 2 mm thickness.

**6.11 Flange frame**, of corrosion resistant steel.

**6.12 Heating apparatus**, able to support the release test temperature, e.g. (95 ± 2) °C.

**6.13 Beaker**, to preheat the test solution made of borosilicate glass, of minimum 600 ml volume. The beaker is also used as a blank sample container when testing articles.

**6.14 Borosilicate glass lid**, in accordance with ISO 3585.

**6.15 Release test lab apparatus**, see <https://standards.iteh.ai/catalog/standards/sist/a8f0391e-5335-47d2-abaf-10711d3f/iso-4531-2018>

## 7 Samples

The laboratory sample shall consist of four single test plates or two articles, identical in material, shape, dimensions and decoration. The sample may be specifically produced test plates or actual industrially produced articles.

For testing vitreous and porcelain enamelled tanks and vessels, test specimens prepared in accordance with ISO 28764 shall be used. These test specimens shall be tested as flat ware.

If a different enamel product is used for the rim of a tableware article it shall also be tested.

## 8 Preparation of samples

Wash the samples briefly in an aqueous solution at (40 ± 5) °C containing 1 ml/l of dishwashing agent ([5.4](#)). Rinse the samples thoroughly with tap water, then with distilled water and allow to drain. Wipe dry with clean filter paper. Do not use any sample that shows residual staining.

Do not handle the surface to be tested after it has been cleaned or prepared.

For articles, an alternative cleaning procedure shall be used if specified in the article's product manual.

## 9 Test conditions

For enamelled surfaces that are used at room temperature only, the test conditions shall be 24 h at (40 ± 2) °C.