



SLOVENSKI STANDARD

SIST EN ISO 5817:2023

01-maj-2023

Nadomešča:

SIST EN ISO 5817:2014

Varjenje - Talilno zvarjeni spoji na jeklu, niklju, titanu in njihovih zlitinah (izključeno varjenje s snopom) - Stopnje sprejemljivosti nepravilnosti (ISO 5817:2023)

Welding - Fusion-welded joints in steel, nickel, titanium and their alloys (beam welding excluded) - Quality levels for imperfections (ISO 5817:2023)

Schweißen - Schmelzschweißverbindungen an Stahl, Nickel, Titan und deren Legierungen (ohne Strahlschweißen) - Bewertungsgruppen von Unregelmäßigkeiten (ISO 5817:2023)

<https://standards.iteh.ai/catalog/standards/sist/5d57fd43-0d84-4749-b8bf-583e0731d53d/sist-en-iso-5817-2023>

Soudage - Assemblages en acier, nickel, titane et leurs alliages soudés par fusion (soudage par faisceau exclu) - Niveaux de qualité par rapport aux défauts (ISO 5817:2023)

Ta slovenski standard je istoveten z: EN ISO 5817:2023

ICS:

25.160.40 Varjeni spoji in vari Welded joints and welds

SIST EN ISO 5817:2023

en,fr,de

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN ISO 5817

March 2023

ICS 25.160.40

Supersedes EN ISO 5817:2014

English Version

**Welding - Fusion-welded joints in steel, nickel, titanium
and their alloys (beam welding excluded) - Quality levels
for imperfections (ISO 5817:2023)**

Soudage - Assemblages en acier, nickel, titane et leurs
alliages soudés par fusion (soudage par faisceau exclu)
- Niveaux de qualité par rapport aux défauts (ISO
5817:2023)

Schweißen - Schmelzschweißverbindungen an Stahl,
Nickel, Titan und deren Legierungen (ohne
Strahlschweißen) - Bewertungsgruppen von
Unregelmäßigkeiten (ISO 5817:2023)

This European Standard was approved by CEN on 10 February 2023.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

Contents	Page
European foreword.....	3

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN ISO 5817:2023

<https://standards.iteh.ai/catalog/standards/sist/5d57fd43-0d84-4749-b8bf-583c0731d53d/sist-en-iso-5817-2023>

European foreword

This document (EN ISO 5817:2023) has been prepared by Technical Committee ISO/TC 44 "Welding and allied processes" in collaboration with Technical Committee CEN/TC 121 "Welding and allied processes" the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by September 2023, and conflicting national standards shall be withdrawn at the latest by September 2023.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 5817:2014.

Any feedback and questions on this document should be directed to the users' national standards body/national committee. A complete listing of these bodies can be found on the CEN website.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and the United Kingdom.

Endorsement notice

The text of ISO 5817:2023 has been approved by CEN as EN ISO 5817:2023 without any modification.

INTERNATIONAL STANDARD

**ISO
5817**

Fourth edition
2023-02

Welding — Fusion-welded joints in steel, nickel, titanium and their alloys (beam welding excluded) — Quality levels for imperfections

*Soudage — Assemblages en acier, nickel, titane et leurs alliages
soudés par fusion (soudage par faisceau exclu) — Niveaux de qualité
par rapport aux défauts*

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN ISO 5817:2023

<https://standards.iteh.ai/catalog/standards/sist/5d57fd43-0d84-4749-b8bf-583c0731d53d/sist-en-iso-5817-2023>



Reference number
ISO 5817:2023(E)

© ISO 2023

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN ISO 5817:2023

<https://standards.iteh.ai/catalog/standards/sist/5d57fd43-0d84-4749-b8bf-583c0731d53d/sist-en-iso-5817-2023>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2023

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword.....	iv
Introduction.....	v
1 Scope.....	1
2 Normative references.....	1
3 Terms and definitions.....	2
4 Symbols.....	3
5 Assessment of imperfections.....	4
Annex A (informative) Examples of determination of percentage (%) porosity.....	21
Annex B (informative) Additional criteria for welds in steel subject to fatigue.....	23
Bibliography.....	26

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN ISO 5817:2023

<https://standards.iteh.ai/catalog/standards/sist/5d57fd43-0d84-4749-b8bf-583c0731d53d/sist-en-iso-5817-2023>

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 44, *Welding and allied processes*, Subcommittee SC 10, *Quality management in the field of welding*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 121, *Welding and allied processes*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This fourth edition cancels and replaces the third edition (ISO 5817:2014), which has been technically revised.

The main changes are as follows:

- editorial updates;
- actual throat thickness a_A , used in [Table 1](#), nos 1.3, 1.4, 1.16 and 3.2;
- figures for [Table 1](#), nos 1.4, 1.5, 1.6, 1.11, 1.14, 1.16, 1.19, 2.12, 2.13 and 4.1 changed or added;
- [Table 1](#), no. 4.1: exclusion of several imperfections and change of acceptance criteria;
- Former Annex B deleted.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html. Official interpretations of ISO/TC 44 documents, where they exist, are available from this page: <https://committee.iso.org/sites/tc44/home/interpretation.html>.

Introduction

This document is intended to be used as a reference in the drafting of application codes and/or other application standards. It contains a simplified selection of fusion weld imperfections based on the designations given in ISO 6520-1.

Some of the imperfections described in ISO 6520-1 have been used directly and some have been grouped together. The basic numerical referencing system from ISO 6520-1 has been used.

The purpose of this document is to specify dimensions of typical imperfections which might be expected in normal fabrication. It may be used within a quality system for the production of welded joints. It provides three sets of dimensional values from which a selection can be made for a particular application. The quality level necessary in each case should be specified by the application standard or the responsible designer in conjunction with the manufacturer, user and/or other parties concerned. The quality level shall be prescribed before the start of production, preferably at the enquiry or order stage. For special purposes, additional details may be prescribed. If the welds will be subsequently coated with a protective coating, lining or paint, the welds might require more thorough post weld treatment or surface finishing to achieve the requirements in ISO 8501-3.

The quality levels given in this document provide basic reference data and are not specifically related to any particular application. They refer to types of welded joint in fabrication and not to the complete product or component itself. It is possible, therefore, that different quality levels are applied to individual welded joints in the same product or component.

The main part of the document takes no account of fitness or design for purpose. [Annex B](#) gives a possibility to address design for purpose for fatigue applications.

It would normally be expected that for a particular welded joint the dimensional limits for imperfections can all be covered by specifying one quality level. In some cases, it can be necessary to specify different quality levels for different imperfections in the same welded joint. The choice of quality level for any application should take account of design considerations, subsequent processing (e.g. surfacing), mode of stressing (e.g. static, dynamic), service conditions (e.g. temperature, environment) and consequences of failure. Economic factors are also important and should include not only the cost of welding but also of inspection, testing and repair.

Although this document includes types of imperfection relevant to the fusion welding processes listed in [Clause 1](#), only those which are applicable to the process and application in question need to be considered.

Imperfections are quoted in terms of their actual dimensions, and their detection and evaluation can require the use of one or more methods of non-destructive testing. The detection and sizing of imperfections is dependent on the testing methods and the extent of testing specified in the application standard or contract.

This document does not address the methods used for the detection of imperfections. However, ISO 17635 contains a correlation between the quality level and acceptance level for different NDT methods.

This document is directly applicable to visual testing of welds and does not include details of recommended methods of detection or sizing by non-destructive means. It should be considered that there are difficulties in using these limits to establish appropriate criteria applicable to non-destructive testing methods, such as ultrasonic testing (UT), radiographic testing (RT), eddy current testing (ET), penetrant testing (PT) and magnetic particle testing (MT) and that these will possibly need to be supplemented by requirements for inspection, examining and testing.

The values given for imperfections are for welds produced using normal welding practice. Requirements for smaller (more stringent) values as stated in quality level B may include additional manufacturing processes, e.g. grinding, TIG dressing.

[Annex B](#) gives additional requirements for welds subject to fatigue.

