



Standard Specification for Coextruded Composite Pipe¹

This standard is issued under the fixed designation F 1488; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers coextruded composite pipe, produced by a coextrusion die system, in which the concentric layers are formed and combined before exiting the die.

1.1.1 Materials listed in the material section are permitted to be used in any layer of the coextruded composite pipe. When coextruded composite pipe is produced with three layers, the middle layer is permitted to be solid or thermally foamed.

1.1.2 The function of this specification is to provide standardization of product, to produce technical data, and to serve as a purchasing guide.

1.2 Compounds that do not meet the requirements of the material section are excluded.

1.3 The coextruded composite pipe is permitted to be perforated in accordance with any specified standard or by agreement between the purchaser and the supplier.

1.4 The coextruded composite pipe is permitted to be belled for joining by solvent cementing or belled for joining by an elastomeric seal (gaskets), in accordance with any specified standard or by agreement between the purchaser and the supplier.

1.5 Recommendations for storage, joining, installation, and rationale are listed in Appendixes X1, X2, X3, and X4, respectively.

~~1.6 The values stated in inch-pound units are to be regarded as the standard. A companion standard written in SI units is under development.~~

1.6 The values stated in inch-pound units are to be regarded as standard. No other units of measurement are included in this standard. A companion standard written in SI units is under development.

1.7 The text of this specification references notes, footnotes, and appendixes which provide explanatory material. These notes and footnotes (excluding those in tables and figures) shall not be considered as requirements of this specification.

1.8 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

NOTE 1—Related specifications are as follows: D2661, D2665, D2729, D2750, D2751, D2949, D3034, F512, F628, F758, F789, and F891. 1—Related specifications are as follows: D 2661, D 2665, D 2729, D 2750, D 2751, D 2949, D 3034, F 512, F 628, F 758, F 789, and F 891.

2. Referenced Documents

2.1 The following standards contain provisions which, though referenced in this specification, constitute provisions of this specification. All standards are subject to revision and parties using this specification shall reference the most recent edition of the standards listed as follows.

2.2 *ASTM Standards:*²

D 618 Practice for Conditioning Plastics for Testing

D 696 Test Method for Coefficient of Linear Thermal Expansion of Plastics Between -30°C and 30°C with a Vitreous Silica Dilatometer

D 883 Terminology Relating to Plastics

D 1600 Terminology for Abbreviated Terms Relating to Plastics

D 1898 Standard Practice for Sampling of Plastics³

D 1972 Practice for Generic Marking of Plastic Products

D 2122 Test Method for Determining Dimensions of Thermoplastic Pipe and Fittings

D 2235 Specification for Solvent Cement for Acrylonitrile-Butadiene-Styrene (ABS) Plastic Pipe and Fittings

D 2321 Practice for Underground Installation of Thermoplastic Pipe for Sewers and Other Gravity-Flow Applications

¹ This specification is under the jurisdiction of ASTM Committee F17 on Plastic Piping Systems and is the direct responsibility of Subcommittee F17.11 on Composite. Current edition approved Aug. 10, 2003. Published September 2003. Originally approved in 1994. Last previous edition approved in 2000 as F 1488-00 ^{ϵ 1}. Current edition approved Aug. 1, 2009. Published August 2009. Originally approved in 1994. Last previous edition approved in 2003 as F1488-03.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

- D 2412 Test Method for Determination of External Loading Characteristics of Plastic Pipe by Parallel-Plate Loading
- D 2444 Test Method for Determination of the Impact Resistance of Thermoplastic Pipe and Fittings by Means of a Tup (Falling Weight)
- D 2564 Specification for Solvent Cements for Poly(Vinyl Chloride) (PVC) Plastic Piping Systems
- D 2661 Specification for Acrylonitrile-Butadiene-Styrene (ABS) Schedule 40 Plastic Drain, Waste, and Vent Pipe and Fittings
- D 2665 Specification for Poly(Vinyl Chloride) (PVC) Plastic Drain, Waste, and Vent Pipe and Fittings
- D 2729 Specification for Poly(Vinyl Chloride) (PVC) Sewer Pipe and Fittings
- D2750 ~~Specification for Acrylonitrile-Butadiene-Styrene (ABS) Plastic Utilities Conduit and Fittings~~ Specification for Acrylonitrile- Butadiene-Sytrene (ABS) Plastics Utilities Conduit and Fittings³
- D 2751 Specification for Acrylonitrile-Butadiene-Styrene (ABS) Sewer Pipe and Fittings
- D 2855 Practice for Making Solvent-Cemented Joints with Poly(Vinyl Chloride) (PVC) Pipe and Fittings
- D 2949 Specification for 3.25-in. Outside Diameter Poly(Vinyl Chloride) (PVC) Plastic Drain, Waste, and Vent Pipe and Fittings
- D 3034 Specification for Type PSM Poly(Vinyl Chloride) (PVC) Sewer Pipe and Fittings⁴
- ~~D3139 Specification for Joints for Plastic Pressure Pipes Using Flexible Elastomeric Seals⁴~~ Specification for Type PSM Poly(Vinyl Chloride) (PVC) Sewer Pipe and Fittings
- D 3212 Specification for Joints for Drain and Sewer Plastic Pipes Using Flexible Elastomeric Seals
- ~~D3965 Specification for Rigid Acrylonitrile-Butadiene-Styrene (ABS) Compounds for Pipe and Fittings~~
- ~~D4000 Classification System for Specifying Plastic Materials³~~ 4000 Classification System for Specifying Plastic Materials
- D 4396 Specification for Rigid Poly(Vinyl Chloride) (PVC) and Chlorinated Poly(Vinyl Chloride) (CPVC) Compounds for Plastic Pipe and Fittings Used in Nonpressure Applications
- D 5033 Guide for the Development of ASTM Standards Relating to Recycling and Use of Recycled Plastics
- F 402 Practice for Safe Handling of Solvent Cements, Primers, and Cleaners Used for Joining Thermoplastic Pipe and Fittings
- F 412 Terminology Relating to Plastic Piping Systems
- F 477 Specification for Elastomeric Seals (Gaskets) for Joining Plastic Pipe
- F 493 Specification for Solvent Cements for Chlorinated Poly(Vinyl Chloride) (CPVC) Plastic Pipe and Fittings
- F 512 Specification for Smooth-Wall Poly(Vinyl Chloride) (PVC) Conduit and Fittings for Underground Installation
- F 545 Specification for PVC and ABS Injected Solvent Cemented Plastic Pipe Joints
- F 628 Specification for Acrylonitrile-Butadiene-Styrene (ABS) Schedule 40 Plastic Drain, Waste, and Vent Pipe With a Cellular Core
- F 656 Specification for Primers for Use in Solvent Cement Joints of Poly(Vinyl Chloride) (PVC) Plastic Pipe and Fittings
- F 758 Specification for Smooth-Wall Poly(Vinyl Chloride) (PVC) Plastic Underdrain Systems for Highway, Airport, and Similar Drainage
- F 789 Specification for Type PS-46 and Type PS-115 Poly(Vinyl Chloride) (PVC) Plastic Gravity Flow Sewer Pipe and Fittings
- F 891 Specification for Coextruded Poly(Vinyl Chloride) (PVC) Plastic Pipe with ~~With~~ a Cellular Core astm-f1488-09
- F 913 Specification for Thermoplastic Elastomeric Seals (Gaskets) for Joining Plastic Pipe

2.3 ANSI Standards:

- ANSI Z 34.1 American National Standard for Certification-Third-Party Certification Program³
- ANSI Z 34.2 American National Standard for Certification-Self-Certification by Producer or Supplier³

2.4 Federal Standard:

- Fed. Std. No. 123 Marking for Shipments (Civil Agencies)⁴

2.5 Military Standard:

- MIL-STD-129 Marking for Shipment and Storage⁴

2.6 Uniform Classification Committee Standard:

~~Uniform Freight Classification~~

Uniform Freight Classification ⁵

2.7 National Motor Freight Traffic Association Standard:

~~National Motor Freight Classification~~

National Motor Freight Classification ⁶

³ Discontinued. See 1997 Annual Book of ASTM Standards, Vol 08.01.

³ Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, <http://www.ansi.org>.

⁴ Annual Book of ASTM Standards, Vol 08.04.

⁴ Available from Standardization Documents Order Desk, DODSSP, Bldg. 4, Section D, 700 Robbins Ave., Philadelphia, PA 19111-5098, <http://www.dodssp.daps.mil>.

⁵ Discontinued. See 1997 Annual Book of ASTM Standards, Vol 08.04.

⁵ Available from the Uniform Classification Committee, Suite 1106, 222 South Riverside Plaza, Chicago, IL 60606.

⁶ Annual Book of ASTM Standards, Vol 08.02.

⁶ Available from National Motor Freight Traffic Association (NMFTA), 1001 N. Fairfax St., Alexandria, VA 22314, <http://www.nmfta.org>.

3. Terminology

3.1 *Definitions*—Definitions are in accordance with Terminologies D 883 and F 412 and F 412. Abbreviations are in accordance with Terminology D 1600. Plastic materials are classified in accordance with Classification System D 4000. Generic marking is in accordance with Practice D 1972.

3.1.1 *coextrusion*—a process whereby two or more heated or unheated plastic material streams forced through one or more shaping orifice(s) become one continuously formed piece.

3.1.2 *compound*—a mixture of a polymer with other ingredients, such as fillers, stabilizers, catalysts, processing aids, lubricants, modifiers, pigments, or curing agents.

3.1.3 *dimension ratio*—the average specified diameter of a pipe divided by the minimum specified wall thickness.

3.1.4 *out-of-roundness*—the allowed difference between the maximum measured diameter and the minimum measured diameter (stated as an absolute deviation).

3.1.5 *thermally foamed plastic*—a cellular plastic produced by applying heat to effect gaseous decomposition or volatilization of a constituent. (1985)

3.1.6 *virgin plastic, adj*—material in the form of pellets, granules, powder, floc, or liquid that has not been subjected to use or processing other than that required for its initial manufacture. (1985, D 883)

3.2 *Definitions of Terms Specific to This Standard:*

3.2.1 *coextruded composite pipe*—pipe consisting of two or more concentric layers of the same or different material bonded together in processing by any combination of temperature, pressure, grafting, crosslinking, or adhesion with a specific purpose to serve as pipe.

3.2.2 *IPS-DR-PS Series*—coextruded pipe produced to an iron pipe outside diameter (OD) with a dimension ratio (DR) and pipe stiffness (PS).

3.2.3 *IPS Schedule 40 Series*—coextruded composite pipe produced to an iron pipe outside diameter (OD) with a Schedule 40 wall thickness.

3.2.4 *lot*—all pipe produced of one size and from one extrusion line, during one designated 24-h period.

3.2.5 *qualification test*—an evaluation, generally nonrepetitive, conducted on an existing, altered, or new product to determine acceptability.

3.2.6 *rework composite pipe material*—a blend of the different materials used in the different layers of the coextruded composite pipe.

3.2.7 *Sewer and Drain DR-PS Series*—coextruded composite pipe produced to a sewer and drain outside diameter (OD) with a dimension ratio (DR) and pipe stiffness (PS).

4. Classification

4.1 Coextruded composite pipe produced in compliance with this specification in different dimension ratios (DR) and pipe stiffness (PS) is used for different applications.

4.1.1 *IPS Schedule 40 Series*—Coextruded composite pipe is used for above or below ground installation for communication conduit, electrical conduit, drain, waste, and vent pipe, and plastic underdrain systems for highway, airport, and similar drainage, where a Schedule 40 IPS is required.

4.1.2 *IPS-DR-PS Series*—Coextruded composite pipe is used for above or below ground installation for communication conduit, electrical conduit, and drain, waste, and vent pipe.

4.1.3 *Sewer and Drain DR-PS Series*—Coextruded composite pipe is used for gravity flow sewer and drain pipe, and plastic underdrain systems for highway, airport, and similar drainage.

4.2 Before installing coextruded composite pipe in an industrial waste disposal system, the approval of the cognizant building code authority is required. Some coextruded composite pipe is designed for temperature use in excess of 180°F (82°C). Consult the manufacturer for recommendations on use.

5. Ordering Information

5.1 Orders for coextruded composite pipe produced in compliance with this specification shall include the following:

5.2 ASTM designation (F 1488) and year of issue,

5.3 Series size,

5.4 Footage of each size, and

5.5 Materials.

6. Material

6.1 *Basic Materials*—The outer layer shall be made of virgin material that contains pigments or screening agents to provide protection against UV radiation. The material shall conform to the requirements prescribed in the material specification.

6.2 *ABS Material Specification*—The ABS shall be virgin plastic ABS material conforming to the requirements of Specification D 3965 and shall meet all of the requirements for Cell Class 4-2-2-2-2.

6.2.1 The color and form of the material shall be by agreement between the purchaser and the supplier.

6.3 *PVC Material Specification*—The PVC shall be virgin plastic material conforming to the requirements of Specification

D 4396 and shall meet all of the requirements for Cell Class 1-1-4-3-2.

6.3.1 The color and form of the material shall be by agreement between the purchaser and the supplier in accordance with Specification D 4396.

6.3.2 Individual cell class values are permitted to be greater than those listed.

6.4 *CPVC Material Specification*—The CPVC shall be virgin plastic material conforming to the requirements of Specification D 4396 and shall meet all of the requirements for Cell Class 2-2-4-2-4.

6.4.1 The color and form of the material shall be by agreement between the purchaser and the supplier in accordance with Specification D 4396.

6.4.2 Individual cell class values are permitted to be greater than those listed.

6.5 *Rework Material*—A blend of clean rework material generated from the manufacturer’s own pipe production may be used by the same manufacturer, provided the pipe produced meets all of the requirements of this specification.

6.5.1 Rework material is excluded from standard definitions of recycled materials in accordance with Guide D 5033.

6.5.2 Rework material generated from composite pipe shall not be used in the outer layer.

6.5.3 Rework material generated from composite pipe with a thermally foamed layer shall not be used in the inner or outer layer.

7. Performance Requirements

7.1 *Pipe Stiffness*—The minimum pipe stiffness at 5 % deflection when measured in accordance with Test Method D 2412, shall equal or exceed the value in Table 1, Table 2, Table 3 or Table 4, as applicable. The rate of crosshead motion shall be 0.20 to 0.25 in./min. (5.1 to 6.3 mm/min). Three specimens shall be tested. If all three meet this requirement, the sample meets this requirement. If one or two fail, additional testing shall be conducted in accordance with 7.1.1. If all three fail, the sample does not meet the requirement.

7.1.1 *Pipe Stiffness and Lower Confidence Limit*—In the event that one or two of the specimens tested in 7.1 fail to meet the minimum requirement, the average pipe stiffness of eleven specimens shall meet or exceed the minimum requirement given in Table 1, Table 2, Table 3, or Table 4 as applicable. The 99 % lower confidence limit (LCL) shall be within 15 % of the average value. The LCL shall be calculated using the Student’s “t” distribution, with $N-1$ degrees of freedom, where N is the number of specimens (11). The critical t value shall be used to at least three significant digits. Alternatively, if the LCL exceeds the minimum PS requirement in Table 1, Table 2, Table 3 or Table 4 as applicable, but is not within 15 % of the average, the sample meets the requirements of the Pipe Stiffness testing. The eleven specimens include the three tested under 7.1, and an additional eight with rotation by 35°, as specified in D 2412, continuing throughout the remaining specimens.

The LCL based on testing eleven specimens is calculated as follows:

$$\text{LCL} = (\text{Avg. PS}) - \{ 2.76(\text{Std. Dev}) / \sqrt{N} \} \quad (1)$$

where:

$$(\text{Avg. PS}) = \{ \sum(\text{PS}) \} / (11)$$

$$(\text{Std. Dev}) = \left[\frac{\sum \text{PS}^2 - (\sum \text{PS})^2 / N}{N - 1} \right]^{1/2}$$

$$N = 11$$

The 15 % requirement is calculated as:

$$(\text{Avg} - \text{LCL}) / (\text{Avg}) \times 100 \% \leq 15 \% \quad (2)$$

7.1.2 The strength and load-carrying capabilities of plastic pipe is measured and reported as pipe stiffness and determined in accordance with Test Method D 2412. The term “crushing strength” is not applicable to plastic piping.

NOTE 2—The 5 % deflection criteria is arbitrarily selected for testing convenience. It is not to be considered as a limitation with respect to in-use

TABLE 1 Minimum Wall Thickness Required for Pipe Stiffness and Impact Strength for IPS Schedule 40 Series^A

Nominal Pipe Size, in.	Minimum Wall Thickness, in.	Minimum Pipe Stiffness, lbf/in./in. at 5 % Deflection	Minimum Impact Strength at 32°F (0°C), ft-lbf
1¼	0.140	140	25
1½	0.145	140	25
2	0.154	140	25
2½	0.203	140	25
3	0.216	140	25
3½	0.226	140	25
4	0.237	140	40
5	0.258	140	40
6	0.280	140	40
8	0.322	90	60
10	0.365	90	60
12	0.460	90	60

^A The maximum wall thickness shall not be greater than 1.12 times the minimum.

TABLE 2 Minimum Wall Thickness Required for Pipe Stiffness and Impact Strength for IPS-DR-PS DWV^A

Nominal Pipe Size, in.	Dimension Ratio		Minimum Impact Strength at 32°F (0°C), ft-lbf
	DR 24	DR 22	
	Pipe Stiffness		
	PS140	PS200	
1¼	0.067	0.075	25
1½	0.077	0.086	25
2	0.099	0.108	25
2½	0.120	0.130	25
3 ^B	0.135	0.148	25
3	0.142	0.159	25
3½	0.162	0.182	25
4	0.183	0.204	25
5	0.226	0.252	25
6	0.269	0.301	25
8	0.350	0.392	25
10	0.437	0.488	25
12	0.518	0.579	25

^A The maximum wall thickness shall not be greater than 1.12 times the minimum.

^B Special outside diameter of 3.25.

TABLE 3 Minimum Wall Thickness Required for Pipe Stiffness and Impact Strength for IPS-DR-PS Communication Conduit or Underground Electrical Conduit^A

Nominal Pipe Size, in.	Dimension Ratio					Minimum Impact Strength at 32°F (0°C) ft-lbf
	DR 42	DR 38	DR 34	DR 27	DR 25.5	
	Pipe Stiffness					
	PS25	PS35	PS50	PS100	PS120	
1¼	0.060	0.060	0.060	0.060	---	25
1½	0.060	0.060	0.060	0.060	---	25
2	0.060	0.060	0.068	0.086	---	25
2½	0.068	0.076	0.085	0.106	0.093	25
3	0.080	0.090	0.102	0.127	0.113	25
3½	0.093	0.103	0.116	0.145	---	25
4	0.104	0.118	0.132	0.164	---	25
5	0.129	0.146	0.164	0.203	0.177	25
6	0.154	0.174	0.195	0.241	0.219	25
8	0.201	0.227	0.254	0.314	0.260	25
10	0.250	0.283	0.316	0.372	---	25
12	0.297	0.335	0.375	0.465	---	25

^A The maximum wall thickness shall not be greater than 1.12 times the minimum.

deflection. The engineer is responsible for establishing the acceptable deflection limit.

7.2 Impact Resistance—The minimum impact resistance, when tested at the time of manufacture, shall comply with the requirements of Table 1, Table 2, Table 3, or Table 4. Test in accordance with Test Method D 2444, using Tup B and Holder B. Use a 6-lb (2.5-kg) tup for all sizes.

7.2.1 Test 10 specimens. When 9 or 10 specimens pass, accept the lot. When 2 or more specimens fail, test 10 additional specimens. When 17 of 20 specimens tested pass, accept the lot. When 4 or more of 20 specimens fail, test 20 additional specimens. When 32 of 40 specimens pass, accept the lot. When 9 or more of 40 specimens fail, the lot does not meet the requirements of this specification.

TABLE 4 Minimum Wall Thickness Required for Pipe Stiffness and Impact Strength for Sewer and Drain-DR-PS^A

Nominal Pipe Size, in.	Dimension Ratio					Minimum Impact Strength at 32°F (0°C), ft-lbf
	DR38	DR34	DR27	DR24	DR22	
	Pipe Stiffness					
	PS35	PS50	PS100	PS140	PS200	
2	0.060	0.066	0.083	0.089	0.102	25
3	0.085	0.095	0.120	0.135	0.148	25
4	0.110	0.124	0.156	0.175	0.191	25
6	0.165	0.184	0.232	0.261	0.285	25
8	0.221	0.247	0.311	0.350	0.381	25
9	0.248	0.277	0.350	0.393	0.429	25
10	0.276	0.308	0.389	0.437	0.477	25
12	0.328	0.367	0.463	0.520	0.568	25

^A The maximum wall thickness shall not be greater than 1.12 times the minimum.

7.2.2 Failure of the test specimen shall be shattering or any crack or break extending entirely through the pipe wall and visible to the unaided eye.

7.3 *Bond*—The bond between layers shall be strong and uniform. It shall not be possible to separate any two layers with a probe or point of a knife blade so that the layers separate cleanly or the probe or knife blade moves freely between the layers; nor shall separation of the layers occur during other tests in this specification. Refer to 10.1. (See 7.3.1.)

7.3.1 The bond test is conducted at the time of manufacture.

8. Other Requirements

8.1 *Dimensions and Tolerances:*

8.1.1 *Outside Diameter*—The outside diameter and tolerance shall meet the requirements of Table 5 when measured in accordance with Test Method D 2122. The tolerance for out-of-roundness shall apply to the pipe at the time of manufacturer.

TABLE 5 Outside Diameter and Tolerance

Nominal Pipe Size, in.	IPS Schedule 40 Series and IPS-DR-PS Series	Sewer and Drain-DR-PS Series	Tolerance on Average Outside Diameter, in.	Out of Roundness Maximum Diameter Minus Minimum Diameter, in.
1¼	1.660	...	+0.008 -0.002	0.060
1½	1.900	...	+0.010 -0.002	0.060
2	2.375	2.25	+0.010 -0.002	0.060
2½	2.875	...	+0.010 -0.002	0.060
3 ^A	3.250	...	+0.012 -0.004	0.060
3	3.500	3.25	+0.012 -0.004	0.060
3½	4.000	...	+0.012 -0.004	0.100
4	4.500	4.215	+0.014 -0.004	0.100
5	5.563	...	+0.015 -0.005	0.100
6	6.625	6.275	+0.016 -0.006	0.100
8	8.625	8.400	+0.024 -0.006	0.150
9	...	9.440	+0.020 -0.005	0.150
10	10.750	10.500	+0.024 -0.006	0.150
12	12.750	12.500	+0.024 -0.006	0.150

^A Special outside diameter of 3.25.