



**SLOVENSKI STANDARD**  
**oSIST prEN ISO 4629-3:2020**  
**01-april-2020**

---

**Veziva za barve in lake - Določevanje hidroksilnega števila - 3. del: Hitri preskus (ISO 4629-3:2018)**

Binders for paints and varnishes - Determination of hydroxyl value - Part 3: Rapid test (ISO 4629-3:2018)

Bindemittel für Beschichtungsstoffe - Bestimmung der Hydroxylzahl - Teil 3: Schnellverfahren (ISO 4629-3:2018)

Liants pour peintures et vernis - Détermination de l'indice d'hydroxyle - Partie 3: Méthode rapide (ISO 4629-3:2018)

**Ta slovenski standard je istoveten z: prEN ISO 4629-3**

---

**ICS:**

87.060.20      Veziva      Binders

**oSIST prEN ISO 4629-3:2020      en,fr,de**



INTERNATIONAL  
STANDARD

ISO  
4629-3

First edition  
2018-10

---

---

**Binders for paints and varnishes —  
Determination of hydroxyl value —**

**Part 3:  
Rapid test**

*Liants pour peintures et vernis — Détermination de l'indice  
d'hydroxyle —*

*Partie 3: Méthode rapide*

iTeh STANDARD PREVIEW  
(standards.iteh.ai)

SIST EN ISO 4629-3:2020

<https://standards.iteh.ai/catalog/standards/sist/6d55283a-6580-445e-b6e3-a9cb8407fe3c/sist-en-iso-4629-3-2020>



Reference number  
ISO 4629-3:2018(E)

© ISO 2018

iTeh STANDARD PREVIEW  
(standards.iteh.ai)

SIST EN ISO 4629-3:2020

<https://standards.iteh.ai/catalog/standards/sist/6d55283a-6580-445e-b6e3-a9cb8407fe3c/sist-en-iso-4629-3-2020>



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2018

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
CP 401 • Ch. de Blandonnet 8  
CH-1214 Vernier, Geneva  
Phone: +41 22 749 01 11  
Fax: +41 22 749 09 47  
Email: [copyright@iso.org](mailto:copyright@iso.org)  
Website: [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

	Page
Foreword.....	iv
Introduction.....	v
<b>1 Scope.....</b>	<b>1</b>
<b>2 Normative references.....</b>	<b>1</b>
<b>3 Terms and definitions.....</b>	<b>1</b>
<b>4 Principle.....</b>	<b>1</b>
<b>5 Reagents.....</b>	<b>2</b>
<b>6 Apparatus.....</b>	<b>2</b>
<b>7 Sampling.....</b>	<b>2</b>
<b>8 Procedure.....</b>	<b>2</b>
<b>9 Expression of results.....</b>	<b>3</b>
<b>10 Precision.....</b>	<b>3</b>
<b>11 Test report.....</b>	<b>3</b>
<b>Bibliography.....</b>	<b>4</b>

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

SIST EN ISO 4629-3:2020

<https://standards.iteh.ai/catalog/standards/sist/6d55283a-6580-445e-b6e3-a9cb8407fe3c/sist-en-iso-4629-3-2020>

## ISO 4629-3:2018(E)

### Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).


This document was prepared by Technical Committee ISO/TC 35, *Paints and varnishes*.

A list of all parts in the ISO 4629 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at [www.iso.org/members.html](http://www.iso.org/members.html).

## Introduction


The most frequently described method for determining the hydroxyl number is conversion with acetic anhydride in pyridine with subsequent titration of the released acetic acid.



However, this method suffers from the following disadvantages:

- the sample is boiled under reflux for 1 h;
- the method cannot be automated;
- small hydroxyl numbers cannot be determined exactly;
- unpleasant and toxic pyridine is used.

For these reasons, a far simpler method was selected for automation. The (primary and secondary) hydroxyl groups are converted to acidic carbamate groups using toluene-4-sulfonyl-isocyanate.



The carbamate can then be titrated with the strong base tetrabutylammonium hydroxide (TBAOH) under non-aqueous conditions, i.e. in an organic solvent.

**ITeH STANDARD PREVIEW**  
**(standards.iteh.ai)**

[SIST EN ISO 4629-3:2020](https://standards.iteh.ai/catalog/standards/sist/6d55283a-6580-445e-b6e3-a9cb8407fe3c/sist-en-iso-4629-3-2020)

<https://standards.iteh.ai/catalog/standards/sist/6d55283a-6580-445e-b6e3-a9cb8407fe3c/sist-en-iso-4629-3-2020>





# Binders for paints and varnishes — Determination of hydroxyl value —

## Part 3: Rapid test

### 1 Scope

This document specifies a titrimetric method for determining the hydroxyl groups in resins and binders for paints and varnishes.

This method is primarily suitable for neutral media. Acidic products provide higher values; neutral products provide, through neutralization of the acidic carbamates, lower values. For these products, preliminary tests are performed to ensure the applicability of the method.

### 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 4618, *Paints and varnishes — Terms and definitions*

ISO 3696, *Water for analytical laboratory use — Specification and test methods*

ISO 15528, *Paints, varnishes and raw materials for paints and varnishes — Sampling*

### 3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 4618 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

#### 3.1

##### hydroxyl value

number of milligrams of potassium hydroxide (KOH) corresponding to hydroxyl groups that have been acetylated under specified test conditions in 1 g of the product tested

[SOURCE: ISO 4629-1:2016, 3.1]

### 4 Principle

The primary and secondary hydroxyl groups of the sample are converted to acidic carbamate groups using toluene-4-sulfonyl-isocyanate. The carbamate can then be titrated with the strong base tetrabutylammonium hydroxide (TBAOH) under non-aqueous conditions, i.e. in an organic solvent.

## ISO 4629-3:2018(E)

### 5 Reagents

During the analysis, use only reagents of recognized analytical grade and only water of at least grade 3 purity as specified in ISO 3696.

**5.1 Solution of tetrabutylammonium hydroxide (TBAOH) in isopropanol/methanol,**  $c(\text{TBAOH}) = 1,0 \text{ mol/l}$ .

**5.2 Reaction solution.**

Place approximately 250 ml acetonitrile in a 500 ml volumetric flask and titrate with 20 ml toluene-4-sulfonyl-isocyanate. Make up the solution to the mark with acetonitrile and mix thoroughly. The reaction solution has a shelf life of approximately 1 month.

**5.3 Acetonitrile,** HPLC-Grade.

**5.4 Toluene,** analytical grade.

### 6 Apparatus

Ordinary laboratory equipment and glassware, together with the following.

**6.1 Conical flask,** capacity about 250 ml.

**6.2 Watch glass.**

**6.3 Burette.**

**6.4 Potentiometric titration apparatus.**

### 7 Sampling

Take a representative sample of the product to be tested, as specified in ISO 15528.

### 8 Procedure

Depending on the expected hydroxyl number, weigh out 1 g to 15 g<sup>1)</sup> of the product under test in the conical flask (6.1), dissolve with 3 ml toluene and 7 ml acetonitrile and heat to 30 °C to 35 °C.

Add 10 ml reaction solution (5.2) and cover the flask with the watch glass (6.2). Allow the reaction to proceed for 5 min under gentle stirring. Then add 1,5 ml distilled water (to hydrolyse the excess reaction solution) and stir for an additional 3 min.

Add 30 ml acetonitrile (5.3) and titrate the mixture with the tetrabutylammonium hydroxide solution (5.1) until after the second point of change.

The electrode should be immersed in the solution immediately before the measurement. The electrode and burette shall be rinsed with acetone before each use.

After each titration rinse the electrode and burette tip with acetone followed by distilled water. Then place the electrode in distilled water for 1 min.

---

1) The optimum sample mass, in grams, can be calculated as follows:  $40/\text{expected hydroxyl number}$  (numerical value equation).