



Designation: D2126 – 09

Standard Test Method for Response of Rigid Cellular Plastics to Thermal and Humid Aging¹

This standard is issued under the fixed designation D2126; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope*

1.1 This test method covers procedures for the thermal and humid exposure of rigid cellular plastics. Conditions used shall be agreed upon between the purchaser and the supplier.

NOTE 1—A list of commonly used exposure conditions is found in Table 1.

1.2 The values stated in SI units are to be regarded as the standard. The values in parentheses are for information only.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

NOTE 2—This test method is equivalent to ISO 2796 in the sampling and calculation sections. It is not equivalent to ISO 2796 in the procedure section.

2. Referenced Documents

2.1 *ASTM Standards:*²

D883 Terminology Relating to Plastics

D1037 Test Methods for Evaluating Properties of Wood-Base Fiber and Particle Panel Materials

2.2 *ISO Standard:*

ISO 2796 Cellular Plastics Rigid—Test for Dimensional Stability³

3. Terminology

3.1 The terms given in Terminology D883 are applicable to this test method.

¹ This test method is under the jurisdiction of ASTM Committee D20 on Plastics and is the direct responsibility of Subcommittee D20.22 on Cellular Materials - Plastics and Elastomers.

Current edition approved Sept. 1, 2009. Published September 2009. Originally approved in 1962. Last previous edition approved in 2004 as D2126 - 04. DOI: 10.1520/D2126-09.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For Annual Book of ASTM Standards volume information, refer to the standard's Document Summary page on the ASTM website.

³ Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, http://www.ansi.org.

4. Significance and Use

4.1 Because of the wide variety of potential uses of rigid cellular plastics, artificial exposure to estimate the effective behavior of these materials must be based, to a great extent, on the intended application. Toward this end, this test method is intended to recommend a variety of conditions from which one or more of the desired exposure conditions can be selected. (Note 3)

4.2 The conditions recommended in this test method have been widely used in artificially exposing rigid cellular plastics and in determining the effects of various temperatures and humidities on these materials. Final test measurements are determined after the specimens return to room temperature. Where specified, the specimens will be tested at the exposure condition, but must be reported as such.

4.3 Dimensional changes measured by this test method can be used to compare the performance of materials in a particular environment, to assess the relative stability of two or more cellular plastics, or to specify an acceptance criterion for a particular material. The results of this test method are not suitable for predicting end-use product performance or characteristics, nor are they adequate for engineering or design calculations.

NOTE 3—Where thermal shock is known or suspected to occur due to rapid heating to (or cooling from) a particular temperature, guidance on the permissible heating or cooling rates, or both, shall be obtained from the manufacturer of the material concerned.

NOTE 4—The dimensional change of a specimen can vary depending upon the age of the sample or the length of time between specimen preparation and the beginning of the test, or both.

4.4 Before proceeding with this test method, reference shall be made to the specification of the material being tested. Any test specimen preparation, conditioning, dimensions, or testing parameters covered in the materials specification, or combination thereof, shall take precedence over those mentioned in this test method. If there are no specifications, then the default conditions apply.

5. Apparatus

5.1 *Balance*, capable of weighing, to 0.05 %, a test specimen having a mass of 100 g or less.

*A Summary of Changes section appears at the end of this standard