



SLOVENSKI STANDARD

SIST EN 12596:2023

01-november-2023

Nadomešča:
SIST EN 12596:2014

Bitumen in bitumenska veziva - Določanje dinamične viskoznosti z metodo kapilare z vakuumom

Bitumen and bituminous binders - Determination of dynamic viscosity by vacuum capillary

Bitumen und bitumenhaltige Bindemittel - Bestimmung der dynamischen Viskosität mit Vakuum-Kapillaren

Bitumes et liants bitumineux - Détermination de la viscosité dynamique par viscosimètre capillaire sous vide

Ta slovenski standard je istoveten z: **EN 12596:2023**

<https://standards.iteh.ai/catalog/standards/sist/827f61aa-92a2-4b70-a6e2-d40b8e105ff1/sist-en-12596-2023>

ICS:

75.140	Voski, bitumni in drugi naftni proizvodi	Waxes, bituminous materials and other petroleum products
91.100.50	Veziva. Tesnilni materiali	Binders. Sealing materials

SIST EN 12596:2023

en,fr,de

EUROPEAN STANDARD

EN 12596

NORME EUROPÉENNE

EUROPÄISCHE NORM

July 2023

ICS 75.140; 91.100.50

Supersedes EN 12596:2014

English Version

Bitumen and bituminous binders - Determination of dynamic viscosity by vacuum capillary

Bitumes et liants bitumineux - Détermination de la viscosité dynamique par viscosimètre capillaire sous vide

Bitumen und bitumenhaltige Bindemittel - Bestimmung der dynamischen Viskosität mit Vakuum-Kapillaren

This European Standard was approved by CEN on 28 May 2023.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and United Kingdom.

Document Preview

[SIST EN 12596:2023](https://standards.iteh.ai/catalog/standards/sist/827f61aa-92a2-4b70-a6c2-d40b8e105ff1/sist-en-12596-2023)

<https://standards.iteh.ai/catalog/standards/sist/827f61aa-92a2-4b70-a6c2-d40b8e105ff1/sist-en-12596-2023>



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

Contents	Page
European foreword	3
1 Scope.....	5
2 Normative references.....	5
3 Terms and definitions.....	5
4 Principle.....	6
5 Apparatus	6
6 Preparation of test samples	8
7 Procedure	8
8 Calculation.....	9
9 Expression of results	10
10 Precision	10
10.1 Repeatability	10
10.2 Reproducibility.....	10
11 Test report.....	10
Annex A (normative) Specifications of viscometers.....	11
Annex B (informative) Calibration of viscometers	17
Annex C (informative) Example for calculation of results	19
Bibliography	20

SIST EN 12596:2023

<https://standards.iteh.ai/catalog/standards/sist/827f61aa-92a2-4b70-a6e2-d40b8e105ff1/sist-en-12596-2023>

European foreword

This document (EN 12596:2023) has been prepared by Technical Committee CEN/TC 336 “Bituminous binders”, the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by January 2024, and conflicting national standards shall be withdrawn at the latest by January 2024.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 12596:2014.

In comparison with the previous edition, the main technical changes are:

- amended scope (clarification of applicability of test methods); deletion of notes from scope;
- “accuracy” is changed to “maximum permissible error” in several clauses (5.2, 5.4, 5.5 and 5.6);
- reference to mercury thermometer deleted (5.2);
- reference to total immersion thermometer deleted (5.2);
- maximum permissible error for temperature of bath changed from 0,5 °C to 0,3 °C (5.3);
- the required precision of the oven reduced to (135 ± 5) °C in (5.7, 7.2, 7.4 and 7.5);
- time to reach thermal equilibrium prolonged to 1 hour;
- “bulb” changed into “tube section” in 5.1.2, 5.1.3, Figures A.2 and A.3, and added “tube section” to Clause 9 (consistency of wording);
- new subclause 5.8 added on Calibration/Verification;
- information on validity of individual test data to calculate mean value added in Clause 8; including a new NOTE 2 and renumbering existing notes respectively;
- appropriate range of flow time readings added in Clause 9;
- Table B.1 updated with informative values for viscosity standards;
- all time measurements with a maximum permissible error of 0,1 s in B.3.1;
- Annex C deleted;
- new Annex C introduced with examples on calculation;
- ASTM E77-98 deleted from the Bibliography;
- reference to ASTM D2171-01 in Bibliography updated and reference (footnote) to Institute of Petroleum deleted.

EN 12596:2023 (E)

Any feedback and questions on this document should be directed to the users' national standards body. A complete listing of these bodies can be found on the CEN website.

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and the United Kingdom.

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

[SIST EN 12596:2023](https://standards.iteh.ai/catalog/standards/sist/827f61aa-92a2-4b70-a6c2-d40b8e105ff1/sist-en-12596-2023)

<https://standards.iteh.ai/catalog/standards/sist/827f61aa-92a2-4b70-a6c2-d40b8e105ff1/sist-en-12596-2023>

1 Scope

This document specifies a method for the determination of the dynamic viscosity of bituminous binders by means of a vacuum capillary viscometer at 60 °C in a range between 0,003 6 Pa·s and 580 000 Pa·s. Other temperatures are possible if calibration constants are known. Bituminous emulsions and non-newtonian binders (e.g. some polymer modified bitumen) are not within the scope of this method.

WARNING — The use of this document can involve hazardous materials, operations and equipment. This document does not purport to address all of the safety problems associated with its use. It is the responsibility of the user of this document to identify the hazards and assess the risks involved in performing this test method and to implement sufficient control measures to protect individual operators (and the environment). This includes appropriate safety and health practices and determination of the applicability of regulatory limitations prior to use.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 58, *Bitumen and bituminous binders - Sampling bituminous binders*

EN 12594, *Bitumen and bituminous binders - Preparation of test samples*

EN ISO 3696:1995, *Water for analytical laboratory use - Specification and test methods (ISO 3696:1987)*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

— ISO Online browsing platform: available at <https://www.iso.org/obp>

— IEC Electropedia: available at <https://www.electropedia.org/>

<https://standards.iteh.ai/catalog/standards/sist/827f61aa-92a2-4b70-a6e2-d40b8e105ff1/sist-en-12596-2023>

3.1

dynamic viscosity

ratio between the applied shear stress and the velocity gradient

Note 1 to entry: Dynamic viscosity is a measure of the resistance to the flow of a liquid and is commonly called the viscosity of the liquid. For the purposes of this document, the word viscosity means the dynamic viscosity of a liquid.

Note 2 to entry: The SI unit of dynamic viscosity is Pa·s.

3.2

newtonian liquid

liquid with a viscosity that is independent of the rate of shear

Note 1 to entry: The constant ratio of the shear stress to the velocity gradient is the dynamic viscosity of the liquid. If this ratio is not constant, the liquid is non-Newtonian.

EN 12596:2023 (E)**3.3****density**

mass of a liquid divided by its volume

Note 1 to entry: When reporting density, the unit of density used, together with the temperature, is stated explicitly, for example kg/m³.

Note 2 to entry: The SI unit of density is kg/m³.

3.4**kinematic viscosity**

ratio between the dynamic viscosity and the density of a liquid at the temperature of viscosity measured

Note 1 to entry: Kinematic viscosity is a measure of the resistance to flow of a liquid under gravity.

Note 2 to entry: The SI unit of kinematic viscosity is m²/s; for practical use, a sub-multiple (mm²/s) is more convenient.

4 Principle

To determine the time for a fixed volume of the liquid to be drawn up through a capillary tube by means of a vacuum, under closely controlled conditions of vacuum and temperature. The viscosity is calculated by multiplying the flow time in seconds by the viscometer calibration factor.

5 Apparatus

5.1 Viscometer, capillary-type and made of borosilicate glass as described in 5.1.1 to 5.1.3.

Calibrated viscometers are available from commercial suppliers. Details regarding the calibration of viscometers are given in Annex B.

5.1.1 Cannon-Manning vacuum capillary viscometer (CMVV).

The CMVV is available in eleven sizes (see Table A.1), covering a range between 0,003 6 Pa·s to 8 000 Pa·s.

Details of the design and construction of CMVV are shown in Figure A.1. The size numbers, approximate calibration factors *K*, and viscosity ranges for the series of CMVV are given in Table A.1.

For all viscometer sizes, the volume of measuring bulb C is approximately three times that of bulb B. Bulb B, bulb C and bulb D are defined by timing marks F, G and H.

5.1.2 Asphalt Institute vacuum capillary viscometer (AIVV).

The AIVV is available in seven sizes (see Table A.2) from a range between 4,2 Pa·s to 580 000 Pa·s. Sizes 50 to 200 are best suited to viscosity measurements of bituminous binders at 60 °C.

Details of design and construction of the AIVV are shown in Figure A.2. The size numbers, approximate capillary radii, approximate calibration factors *K*, and viscosity range for the series of AIVV are given in Table A.2.

This viscometer has measuring tube section B, tube section C and tube section D, located on the viscometer arm M, which is a precision bore glass capillary. The measuring bulbs/test sections are 20 mm long capillary segments defined by timing marks F, G, H and I.

5.1.3 Modified Koppers vacuum capillary viscometer (MKVV).

The MKVV is available in five sizes (see Table A.3) covering a range between 4,2 Pa·s to 20 000 Pa·s. Sizes 50 to 200 are best suited to viscosity measurements of bituminous binders at 60 °C.

Details of design and construction of the MKVV are shown in Figure A.3. The size numbers, approximate capillary radii, approximate calibration factors K , and viscosity ranges for the series of MKVV are given in Table A.3.

This viscometer consists of a separate filling tube A, and precision-bore glass capillary vacuum tube M. These two parts are joined by a borosilicate ground glass joint N, with a 24/40 standard taper. Measuring tube section B, tube section C and tube section D, on the glass capillary are 20 mm long capillary segments, defined by timing marks F, G, H and I.

5.1.4 Holder, made by drilling two holes, 22 mm and 8 mm internal diameter, through a No. 11 rubber stopper. The centre-to-centre distance between holes shall be 25 mm. Slit the rubber stopper between the holes and between the 8 mm hole and edge of the stopper. When placed in a 51 mm diameter hole in the bath cover, the stopper shall hold the viscometer in place. For the MKVV the viscometer holder can be made by drilling a 28 mm hole through the centre of a No. 11 rubber stopper and slitting the stopper between the hole and the edge.

Such holders are commercially available.

5.2 Temperature measuring device.

A temperature measuring device (combining sensor and reading unit) shall

- have a range from at least 55 °C to 65 °C;
- be readable to 0,05 °C or less;
- have a maximum permissible error of 0,2 °C.

Sensors based on platinum resistance thermometers have been found suitable but other principles are also allowed. The temperature measuring device shall be calibrated regularly.

When measuring and controlling nominally constant temperatures, as in this test method, the thermal response time can be rather high (e.g. slow response to a change in temperature). Care shall be taken to consider this aspect since low thermal response time of the sensor can indicate greater cyclic variations than the bituminous material in practise experiences.

5.3 Bath, suitable for immersion of the viscometer so that the liquid reservoir or the top of the capillary whichever is uppermost, is at least 20 mm below the top of the bath level, and with provisions for visibility of the viscometer and the thermometer. Firm supports for the viscometer shall be provided, or the viscometer shall be an integral part of the bath. The efficiency of the stirring and the balance between heat losses and heat input shall be such that the temperature of the bath medium does not vary by more than 0,3 °C over the length of the viscometer, or from viscometer to viscometer in the various bath positions.

5.4 Vacuum system, capable of maintaining a vacuum with a maximum permissible error of 100 Pa of the desired level up to and including 40 000 Pa. A vacuum or aspirator pump is suitable for the vacuum source.

5.5 Timer, or stop watch (spring or battery driven) graduated in divisions of 0,1 s or less and a maximum permissible error of 0,5 s over 1 000 s when tested over intervals of not less than 15 min. Verify the maximum permissible error frequently.

5.6 Electrical timing devices, used only on electrical circuits the frequencies of which are controlled with a maximum permissible error of 0,5 s over 1 000 s. Verify the maximum permissible error frequently.

EN 12596:2023 (E)

NOTE Alternating currents, the frequencies of which are intermittently and not continuously controlled, as provided by some public power systems, can cause large errors, particularly over short timing intervals, when used to actuate electrical timing devices.

5.7 Oven, capable of maintaining (135 ± 5) °C.

5.8 Calibration/Verification, all equipment shall be calibrated/verified at least once per year.

6 Preparation of test samples

The laboratory sample shall be taken in accordance with EN 58. Prepare the test sample in accordance with EN 12594.

Heat the sample with care to prevent local overheating until it has become sufficiently fluid to pour, if possible, stir the sample occasionally to aid heat transfer and to ensure uniformity.

If the sample contains air bubbles, transfer a minimum of 20 ml into a suitable container and heat to (135 ± 5) °C, stirring occasionally to prevent local overheating and taking care to avoid the entrapment of air.

7 Procedure

7.1 Maintain the bath (5.3) at $(60,0 \pm 0,3)$ °C. Apply the necessary corrections, if any, to all thermometer readings.

7.2 Select a clean, dry viscometer that will give a flow time greater than 60 s and below 1 000 s, and preheat to 60 °C. If the sample contains air bubbles, preheat the viscometer to (135 ± 5) °C.

7.3 Charge the viscometer by pouring the prepared sample to within ± 2 mm of fill line E (Figure A.1, Figure A.2 and Figure A.3).

Carry out the test within 4 h of pouring.

7.4 If the sample contains air bubbles, place the charged viscometer in an oven or bath maintained at (135 ± 5) °C for a period of 10 min, to allow large air bubbles to escape.

7.5 Remove the viscometer from the oven or bath at (135 ± 5) °C and within 5 min, insert the viscometer into the holder (5.1.4) and position the viscometer vertically in the bath (5.3) so that the upper most timing mark is at least 20 mm below the surface of the bath liquid.

7.6 Establish a $(40\ 000 \pm 100)$ Pa vacuum below atmospheric pressure in the vacuum system and connect the vacuum system to the viscometer with the toggle valve or stopcock closed in the line leading to the viscometer.

7.7 After the viscometer has been in the bath for at least 1 h to ensure that the sample reaches thermal equilibrium, start the flow of binder in the viscometer by opening the toggle valve or stopcock in the line leading to the vacuum system.

7.8 Read to within 0,1 s, the time required for the leading edge of the meniscus to pass between all successive pairs of timing marks. Report flow times between 60 s and 1 000 s, noting the identification of the pair of timing marks.

7.9 Upon completing the test, clean the viscometer thoroughly by rinsing several times with an appropriate solvent completely miscible with the sample, followed by a completely volatile solvent. Dry the tube by passing a slow stream of filtered dry air through the capillary for 2 min, or until the last trace