
Papir, karton, lepenka in vlaknine - Standardna atmosfera za kondicioniranje in preskušanje ter postopek za nadzor atmosfere in kondicioniranje vzorcev (ISO/DIS 187:2022)

Paper, board and pulps - Standard atmosphere for conditioning and testing and procedure for monitoring the atmosphere and conditioning of samples (ISO/DIS 187:2022)

Papier, Pappe und Zellstoff– Normalklima für die Vorbehandlung und Prüfung und Verfahren zur Überwachung des Klimas und der Probenvorbehandlung (ISO/DIS 187:2022)

Papier, carton et pâtes - Atmosphère normale de conditionnement et d'essai et méthode de surveillance de l'atmosphère et de conditionnement des échantillons (ISO/DIS 187:2022)

<https://standards.iteh.ai/catalog/standards/sist/fe4bba31-872b-4a7e-88a8-6744ceca167c/osist-pren-iso-187-2022>

Ta slovenski standard je istoveten z: prEN ISO 187

ICS:

85.040	Vlaknine	Pulps
85.060	Papir, karton in lepenka	Paper and board

oSIST prEN ISO 187:2022

en,fr,de

**iTeh STANDARD
PREVIEW
(standards.iteh.ai)**

[oSIST prEN ISO 187:2022](https://standards.iteh.ai/catalog/standards/sist/fe4bba31-872b-4a7e-88a8-6744ceca167c/osist-pren-iso-187-2022)

<https://standards.iteh.ai/catalog/standards/sist/fe4bba31-872b-4a7e-88a8-6744ceca167c/osist-pren-iso-187-2022>

DRAFT INTERNATIONAL STANDARD

ISO/DIS 187

ISO/TC 6/SC 2

Secretariat: SIS

Voting begins on:
2022-01-14Voting terminates on:
2022-04-08

Paper, board and pulps — Standard atmosphere for conditioning and testing and procedure for monitoring the atmosphere and conditioning of samples

Papier, carton et pâtes — Atmosphère normale de conditionnement et d'essai et méthode de surveillance de l'atmosphère et de conditionnement des échantillons

ICS: 85.060; 85.040

iTeh STANDARD PREVIEW (standards.iteh.ai)

[oSIST prEN ISO 187:2022](https://standards.iteh.ai/catalog/standards/sist/fe4bba31-872b-4a7e-88a8-6744ceca167c/osist-pren-iso-187-2022)<https://standards.iteh.ai/catalog/standards/sist/fe4bba31-872b-4a7e-88a8-6744ceca167c/osist-pren-iso-187-2022>

This document is circulated as received from the committee secretariat.

THIS DOCUMENT IS A DRAFT CIRCULATED FOR COMMENT AND APPROVAL. IT IS THEREFORE SUBJECT TO CHANGE AND MAY NOT BE REFERRED TO AS AN INTERNATIONAL STANDARD UNTIL PUBLISHED AS SUCH.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

ISO/CEN PARALLEL PROCESSING



Reference number
ISO/DIS 187:2022(E)

© ISO 2022

**iTeh STANDARD
PREVIEW
(standards.iteh.ai)**

[oSIST prEN ISO 187:2022](https://standards.iteh.ai/catalog/standards/sist/fe4bba31-872b-4a7e-88a8-6744ceca167c/osist-pren-iso-187-2022)

<https://standards.iteh.ai/catalog/standards/sist/fe4bba31-872b-4a7e-88a8-6744ceca167c/osist-pren-iso-187-2022>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2022

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

Page

Foreword.....	iv
Introduction.....	v
1 Scope.....	1
2 Normative references.....	1
3 Terms and definitions.....	1
4 Principle.....	1
5 Standard atmosphere.....	1
6 Conditioning procedure.....	2
6.1 Pre-conditioning of the sample.....	2
6.2 Conditioning.....	2
6.3 Testing.....	2
7 Test report.....	2
Annex A (normative) Measurement of temperature and relative humidity.....	4
Annex B (informative) Interdependence of temperature and relative humidity.....	5
Bibliography.....	8

**iTeh STANDARD
PREVIEW
(standards.iteh.ai)**

[oSIST prEN ISO 187:2022](https://standards.iteh.ai/catalog/standards/sist/fe4bba31-872b-4a7e-88a8-6744ceca167c/osist-pren-iso-187-2022)

<https://standards.iteh.ai/catalog/standards/sist/fe4bba31-872b-4a7e-88a8-6744ceca167c/osist-pren-iso-187-2022>

ISO/DIS 187:2022(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see the following URL: [Foreword - Supplementary information](#)

ISO 187 was prepared by Technical Committee ISO/TC 6, *Paper, board and pulps*, Subcommittee SC 2, *Test methods and quality specifications for paper and board*.

This third edition cancels and replaces the second edition (ISO 187:1990), which has been technically revised with the following main changes: [oSIST prEN ISO 187:2022](#)

- Revised Introduction <https://standards.iteh.ai/catalog/standards/sist/fe4bba31-872b-4a7e-88a8-6744ceca167c/osist-pren-iso-187-2022>
- Normative references have been removed;
- Content added to [clause 5](#) and [6](#);
- [Annex A](#) has been simplified.

Introduction

The physical properties of paper are affected by its moisture content which, in turn, is dependent on the relative humidity of the surrounding atmosphere and its history. In order that tests may be made on paper in a defined physical state, it is brought into equilibrium in an atmosphere of standardized temperature and relative humidity, and tested in that atmosphere.

The moisture content of a given paper in equilibrium with a given atmosphere varies according to whether the equilibrium is reached by sorption or by desorption of moisture and how far the moisture content is from its equilibrium value. This hysteresis influences those physical properties that change with moisture content. Preconditioning paper from low relative humidity and then bringing it into the standard atmosphere will avoid most of the hysteresis effect and typically result in the moisture content of a given sample being within 0.15% when the sample is later conditioned to 50% r.h. and 23°C. Unless otherwise specified, the equilibrium condition should be attained from a low relative humidity.

For a number of years three standard test atmospheres had been in common use:

20 °C/65 % r.h.;

23 °C/50 % r.h. and

27 °C/65 % r.h.

Since 1993 the atmosphere of 23°C /50% r.h. has been considered the ISO standard test atmosphere for testing of pulp, paper, and board. However, this atmosphere may be difficult to attain in some countries located in tropical zones, and in such countries the 27°C /65% r.h. atmosphere is permitted.

(standards.iteh.ai)

[oSIST prEN ISO 187:2022](https://standards.iteh.ai/catalog/standards/sist/fe4bba31-872b-4a7e-88a8-6744ceca167c/osist-pren-iso-187-2022)

<https://standards.iteh.ai/catalog/standards/sist/fe4bba31-872b-4a7e-88a8-6744ceca167c/osist-pren-iso-187-2022>

**iTeh STANDARD
PREVIEW
(standards.iteh.ai)**

[oSIST prEN ISO 187:2022](https://standards.iteh.ai/catalog/standards/sist/fe4bba31-872b-4a7e-88a8-6744ceca167c/osist-pren-iso-187-2022)

<https://standards.iteh.ai/catalog/standards/sist/fe4bba31-872b-4a7e-88a8-6744ceca167c/osist-pren-iso-187-2022>

Paper, board and pulps — Standard atmosphere for conditioning and testing and procedure for monitoring the atmosphere and conditioning of samples

1 Scope

This International Standard specifies the standard atmospheres for conditioning and testing pulp, paper and board, the conditioning procedure and the procedures for measuring the temperature and relative humidity.

For the conditioning of laboratory sheets in accordance with ISO 5269-1 or 5269-3 using the conventional sheet former, the standard atmosphere is that defined in this document but the sheets are not preconditioned.

2 Normative references

There are no normative references in this document.

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/fe4bba31-872b-4a7e-88a8-6744ceca167c/osist-pren-iso-187-2022>

3.1

relative humidity (r.h.)

ratio, expressed as a percentage, of the actual water vapour content of the air to the water vapour content of air saturated with water vapour at the same temperature and pressure.

3.2

conditioning

process of establishing a reproducible moisture content equilibrium of a sample in an atmosphere of specified temperature and relative humidity.

Note 1 to entry: This equilibrium is considered to be attained when the results of two consecutive weighings of the sample, carried out at an interval of time of not less than 1 h, do not differ by more than 0.25 %.

4 Principle

Exposure of a sample to a specific conditioning atmosphere in such a manner that a reproducible state of moisture content equilibrium is reached.

5 Standard atmosphere

The standard atmosphere for testing pulp, paper and paperboard shall be $(23 \pm 1)^\circ\text{C}$ and $(50 \pm 2) \% \text{ r.h.}$. In tropical countries an atmosphere of $(27 \pm 1)^\circ\text{C}$ and $(65 \pm 2) \% \text{ r.h.}$ may be used.

ISO/DIS 187:2022(E)

A test atmosphere shall be deemed to be within the requirements of this International Standard if all the test results determined as described in [annex A](#) are within the prescribed limits.

Even short-term excursions of temperature or humidity beyond these limits, to the extent that the equilibrium moisture content of the sample will be affected, are not permitted. Whenever the test atmosphere is known to have been outside the limits and if there is any chance that the moisture content of samples has been changed by such excursions, all samples shall be reconditioned (repeating [clause 6](#)) before any further testing is done. If the samples have been subjected to a relative humidity exceeding 75% they shall be discarded as dried-in strain in the sample may have been released, causing a permanent change in properties.

For laboratory sheets prepared according to ISO 5269-1, or to 5269-3 using the conventional sheet former, if it is known or suspected that the relative humidity has fallen below the lower limit, to the extent that the moisture content may have decreased, the sheets shall be discarded and new samples prepared. If this is not possible and the samples are tested, the circumstance must be reported.

6 Conditioning procedure

6.1 Pre-conditioning of the sample

For tests in which the hysteresis of the equilibrium moisture content may lead to important errors, the sample shall be pre-conditioned for 24 h in air of relative humidity between 10 % and 35 % and a temperature not above 40 °C before conditioning. Laboratory sheets prepared in the conventional sheet former (ISO 5269-1 and 5269-3) shall not be pre-conditioned. Ensure that the water content of the air in the pre-conditioning atmosphere is lower than in the conditioning atmosphere.

6.2 Conditioning

The specimens of the sample shall be held such that the conditioning air has free access to all their surfaces so that their moisture contents attain a state of equilibrium with the water vapour in the atmosphere. This equilibrium is considered to be attained when the difference of two consecutive weighings (M_n and M_{n+1}) of the specimens of the sample at least 1 h apart is lower or equal to 0,25 % of the mass M_n . The interval between weighings needs to be longer for higher grammage papers and the degree of agreement expected between successive weighings should take account of the known cycling characteristics of the test room.

Handle preconditioned and conditioned sheets or specimens as little as possible; especially avoid touching or breathing on test areas.

NOTE With good air circulation a conditioning period of 4 h is usually sufficient for paper. A minimum time of 5 h to 8 h will be required for higher grammage papers. Boards of higher grammage and specially treated materials may require a conditioning period of 48 h or longer.

6.3 Testing

Unless allowed by the individual ISO Standard, test specimens in the standard testing atmosphere.

7 Test report

The test report of any testing which is required to be done in this standard atmosphere shall include the following information:

- a) reference to this document, i.e. ISO 187;
- b) the nominal conditioning atmosphere used;
- c) the time for which the sample was conditioned;