



SLOVENSKI STANDARD
kSIST FprEN ISO/TS 21596:2021
01-september-2021

Trdna biogoriva - Določanje stopnje mletja - Metoda trdega grozda za toplotno obdelana goriva iz biomase (ISO/PRF TS 21596:2021)

Solid biofuels - Determination of grindability - Hardgrove type method for thermally treated biomass fuels (ISO/PRF TS 21596:2021)

Biogene Festbrennstoffe - Bestimmung der Mahlbarkeit - Hardgrove-Verfahren für thermisch behandelte Brennstoffe aus Biomasse (ISO/PRF TS 21596:2021)

Biocombustibles solides - Détermination de la broyabilité - Méthode de type Hardgrove pour les combustibles de biomasses traitées thermiquement (ISO/PRF TS 21596:2021)

<https://standards.iteh.ai/catalog/standards/sist/2838faae-dd74-478c-8a03-0ac191f28aab/ksist-fpr-en-iso-ts-21596-2021>

Ta slovenski standard je istoveten z: FprCEN ISO/TS 21596

ICS:

75.160.40 Biogoriva Biofuels

kSIST FprEN ISO/TS 21596:2021 en

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[kSIST FprEN ISO/TS 21596:2021](https://standards.iteh.ai/catalog/standards/sist/2838faae-dd74-478c-8a03-9acd8df28aab/ksist-fpren-iso-ts-21596-2021)

<https://standards.iteh.ai/catalog/standards/sist/2838faae-dd74-478c-8a03-9acd8df28aab/ksist-fpren-iso-ts-21596-2021>

TECHNICAL
SPECIFICATION

ISO/TS
21596

First edition

**Solid biofuels — Determination
of grindability — Hardgrove type
method for thermally treated biomass
fuels**

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[kSIST FprEN ISO/TS 21596:2021](https://standards.iteh.ai/catalog/standards/sist/2838faae-dd74-478c-8a03-9acd8df28aab/ksist-fpren-iso-ts-21596-2021)

<https://standards.iteh.ai/catalog/standards/sist/2838faae-dd74-478c-8a03-9acd8df28aab/ksist-fpren-iso-ts-21596-2021>

PROOF / ÉPREUVE



Reference number
ISO/TS 21596:2021(E)

© ISO 2021

iTeh STANDARD PREVIEW (standards.iteh.ai)

[kSIST FprEN ISO/TS 21596:2021](https://standards.iteh.ai/catalog/standards/sist/2838faae-dd74-478c-8a03-9acd8df28aab/ksist-fpren-iso-ts-21596-2021)

<https://standards.iteh.ai/catalog/standards/sist/2838faae-dd74-478c-8a03-9acd8df28aab/ksist-fpren-iso-ts-21596-2021>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2021

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents	Page
Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	2
5 Apparatus	2
5.1 Standard HGI mill.....	2
5.2 Sieves.....	2
5.3 Glass measuring cylinder.....	2
5.4 Sieving machine.....	3
5.5 Balance.....	3
5.6 Cutting mill.....	3
6 Sampling and sample preparation	3
6.1 General.....	3
6.2 Moisture conditions.....	3
6.3 Pre-grinding and sieving.....	3
6.4 Sample size.....	3
7 Procedure	3
8 Calculation	4
9 Reproducibility	5
10 Test report	5
Annex A (normative) Calibration curve and Thermally Treated Biomass Grindability Index (TTBGI) values for the reference materials	6
Bibliography	9

ISO/TS 21596:2021(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 238 *Solid biofuels*.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

Grindability characteristics are of fundamental importance during solid biofuel preparation for energy conversion processes, requiring a predictable particle size distribution. Particles that are too large or too wide in their distribution may result in feeding problems as well as un-burnt fuel passing through the conversion process. Also, in case of processing of biomass for pre-treatment, consistency in particle size determines the yield of such pre-treatment as well as the quality of the final solid biofuel.

The effectiveness of combustion in a pulverized fuel furnace depends strongly on the reactivity and particle size distribution of the pulverized fuel among other factors. For coal, the Hardgrove Grindability Index (HGI) test was developed to characterize the relative grindability of a particular quality of coal relative to a pre-determined standard quality of coal (ASTM D 409). The HGI test is an empirical batch method that simulates the continuous grinding and crushing operation of a ball, table or tube type of industrial coal pulverizer, herein also called coal mill. The HGI value is an indication of the degree of grinding required to reach a particular particle size necessary for effective combustion.

Manufacturers of coal pulverizers for preparation of pulverized coal for combustion in coal burning plants provide curves that show the relationships between the HGI for coal, coal mill capacity in terms of tonne/h and coal mill power in kW. This is done as part of the boiler contract and guarantees. It also serves as a first indication as to how to operate a mill when pulverizing different coals with predetermined standard properties. A HGI of 50, which is standard industry convention, implies that 100 % capacity in tonnes per hour (as indicated) can be reached for the coal at a fineness of 70 % less than 75 microns and 99,5 % less than 300 microns. So, if a coal has a HGI of less than 50 it implies some level of pulverizer capacity loss while on the other hand, a HGI higher than 50 indicates some level of pulverizer capacity gain. The HGI method is internationally accepted and quoted as part of the specification of coal for international trade.

Grindability may also be applied to thermally pre-treated compressed biomass materials, such as pellets, for pulverization in coal mills. Pre-treatment methods for biomass fuels such as torrefaction, steam treatment or hydro-thermal carbonization (HTC) upgrade the properties of biomass making it more effective as a fuel. With increasing interest in the use of such pre-treated biomass fuels for direct co-firing applications in conventional pulverized coal boilers, this method herein describes a laboratory procedure for determination of the grindability of pre-treated biofuels for powder fuel preparation.

The HGI determination is subject to many limitations, including the fact that measurements can be insensitive to the heterogeneous properties of coal that arise from different mineral contents, maceral constituents and levels of maturity. Three relevant adaptations are applied to the standard HGI method in order to extend its applicability to thermally pre-treated biomass fuels. The adaptations and their justification are as follows:

- Amount of sample used for the test determination.
- Particle size used as basis for defining grindability.
- Reference materials for establishing the calibration curve.

0.1 Amount of the sample used for test determination

Coal pulverizers are volumetric devices but with the densities of coals being fairly similar, the capacity of these devices is expressed in mass units per hour. In contrast different biomass materials have different densities. Therefore, the sample amount was changed to the volume $(75 \pm 0,5) \text{ cm}^3$ of input material, which approximates the bulk volume of the standard reference coal samples with a particle size between 1,18 mm and 600 μm .

0.2 Particle size used as basis for defining grindability

The standard HGI test for coal uses the mass of particles passing a sieve with an aperture size of 75 μm as criteria for determining the grindability and the resulting HGI value. The furnace volume is designed from the knowledge of coals to be utilized so as to provide an adequate residence time for complete combustion. Combustion efficiency depends in part on fuel particle size especially for pulverized coal

ISO/TS 21596:2021(E)

furnaces. As the combustion efficiency also depends on the reactivity, which is linked to volatile matter content of fuels, the particle size for high-volatile fuels, such as thermally treated biomass, would not necessarily need to meet the strict fineness requirements for coal powders. Therefore, a sieve with an aperture size of 500 µm is used for determination of grindability of thermally treated biomass. This adaptation also has positive implications on the repeatability of the determination.

0.3 Reference materials for establishing the calibration curve

In the standard HGI test for coal, four references coals are needed for calibrating a HGI mill. This enables reproducibility of the results across different labs. For the thermally treated biomass grindability index determination, this is the very first step. The thermally treated biomass grindability index is an index for materials originating from biomass. The sieving behavior of biomass materials differs fundamentally from that of coals due to the difference in the sphericity of the coal particles. Biomass materials, including thermally treated biomass, are more fibrous and have lengthy dust particles compared to coals. Thermal treatment processes, such as torrefaction, modifies the property of biomass by making biomass more like charcoal. Woody charcoal is a product of slow pyrolysis, which degrades the fibrous nature of the biomass. This consequently improves its grindability as well as the sphericity of the pulverized fuel.

The adapted grindability method uses wood pellets (ISO 17225-2:2021 A1 class pellets) and wood based charcoal (ISO 17225-1:2021 Table 14) as calibration reference materials. These biomass reference materials will be given assigned Thermally Treated Biomass Grindability Index (TTBGI) values as a result of the procedures described in the [Annex A](#). The materials are available commercially for the determination.

iTeh STANDARD PREVIEW **(standards.iteh.ai)**

[kSIST FprEN ISO/TS 21596:2021](#)

<https://standards.iteh.ai/catalog/standards/sist/2838faae-dd74-478c-8a03-9acd8df28aab/ksist-fpren-iso-ts-21596-2021>

Solid biofuels — Determination of grindability — Hardgrove type method for thermally treated biomass fuels

1 Scope

This document describes a method for determination of grindability of graded thermally treated and densified biomass fuels such as classified in ISO/TS 17225-8, for the purpose of preparing fuels with a defined particle size distribution for effective combustion in pulverized fuel boilers. The grindability characteristics determined by the test method provide guidance as to the pulverizing mill performance when utilizing such fuels.

Apart from pelletized materials as described in ISO/TS 17225-8, the method can also be applied to non-compressed or non-densified thermally treated biomass as specified in ISO 17225-1:2021 Table 14 and Table 15.

The results created with this method are not relevant for large wood chips, since limitations apply for large pulverizing coal mills, which are typically not used for grinding materials such as chips.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 16559, *Solid biofuels – Terminology, definitions and descriptions*

ISO 18135, *Solid Biofuels — Sampling*

ISO 14780, *Solid biofuels — Sample preparation*

ISO 18134-1, *Solid biofuels — Determination of moisture content — Oven dry method — Part 1: Total moisture — Reference method*

ISO 18134-2, *Solid biofuels — Determination of moisture content — Oven dry method — Part 2: Total moisture — Simplified method*

ISO 17827-2, *Solid biofuels — Determination of particle size distribution for uncompressed fuels — Part 2: Vibrating screen method using sieves with aperture of 3,15 mm and below*

ISO 21945, *Solid biofuels — Simplified sampling method for small scale applications*

ISO 3310-1, *Test sieves — Technical requirements and testing — Part 1: Test sieves of metal wire cloth*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 16559 apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

ISO/TS 21596:2021(E)

3.1 coal mill
industrial pulverizer used for the purpose of size reduction (and including drying) of hard coal with the purpose of creating fine coal powder for combustion in a pulverized fuel fired unit

3.2 HGI mill
stationary grinding device used in the laboratory for the purpose of determining the grindability of coals for industrial coal mill application

3.3 TTBTGI
thermally treated biomass grindability index
measure for the tendency of a fixed volume of thermally treated biomass material to produce fine particles after grinding under defined settings and conditions

3.4 reference material
materials used to calibrate instruments and validate a measurement method

4 Principle

The TTBTGI for a particular biomass is derived by measuring the tendency of a fixed volume ($75 \pm 0,5$) cm³ of biomass fuel materials to produce particles below 500 µm sieve aperture size when grinded and crushed in a standard HGI mill under standard conditions (vertical force on balls = 284 N ± 2 N). The TTBTGI for biofuels has been developed by three adaptations to the existing Hardgrove Grindability Index (HGI) for standard coals (see ASTM D 409) as follows:

- Amount of test sample ($75 \pm 0,5$) cm³;
- Sieve aperture size (500 µm); and
- Reference materials selected for calibration of the grindability method in this standard are wood based charcoal (ISO 17225-1 Table 14) and wood pellets (ISO 17225-2 A1) in addition to standard coals as specified in ASTM D 409.

5 Apparatus

The following apparatus are required for the determination:

5.1 Standard HGI mill

Standard HGI mill, as per ASTM D 409 specification, verified on a periodic basis.

5.2 Sieves

Sieves, with a circular or rectangle sieve area and an effective sieve area of minimum 250 cm². The sieves shall have an aperture geometry in accordance with ISO 3310-1 (metal wire cloth). The frame of the sieves shall have a height that enables the sieves to contain the samples and allows a free movement of the sample during the sieving process. Sieves, having aperture sizes of 1,18 mm, 600 µm and 500 µm are required. For the purpose of calibration also a sieve having an aperture size of 75 µm is required.

5.3 Glass measuring cylinder

Glass measuring cylinder, class A, having a filling volume of ($75 \pm 0,5$) cm³.