



SLOVENSKI STANDARD

oSIST prEN ISO 1402:2020

01-junij-2020

Gumene in polimerne cevi ter cevni priključki - Hidrostatično preskušanje (ISO/DIS 1402:2020)

Rubber and plastics hoses and hose assemblies - Hydrostatic testing (ISO/DIS 1402:2020)

Gummi- und Kunststoffschläuche und Schlauchleitungen - Hydrostatische Prüfung (ISO/DIS 1402:2020)

Tuyaux et flexibles en caoutchouc et en plastique - Essais hydrostatiques (ISO/DIS 1402:2020)

iTeh STANDARD PREVIEW
(standards.iteh.ai)
oSIST prEN ISO 1402:2020
<https://standards.iteh.ai/catalog/standards/sist/82e4bb3e-c139-4ed6-bc24-b82f00012ed/osist-pr-en-iso-1402-2020>

Ta slovenski standard je istoveten z: prEN ISO 1402

ICS:

23.040.70	Gumene cevi in armature	Hoses and hose assemblies
-----------	-------------------------	---------------------------

oSIST prEN ISO 1402:2020

en,fr,de

iTeh STANDARD PREVIEW **(standards.iteh.ai)**

[oSIST prEN ISO 1402:2020](https://standards.iteh.ai/catalog/standards/sist/82e4bb3e-c139-4ed6-bc24-bff2f00012ed/osist-pren-iso-1402-2020)

<https://standards.iteh.ai/catalog/standards/sist/82e4bb3e-c139-4ed6-bc24-bff2f00012ed/osist-pren-iso-1402-2020>

DRAFT INTERNATIONAL STANDARD

ISO/DIS 1402

ISO/TC 45/SC 1

Secretariat: DIN

Voting begins on:
2020-03-26Voting terminates on:
2020-06-18

Rubber and plastics hoses and hose assemblies — Hydrostatic testing

Tuyaux et flexibles en caoutchouc et en plastique — Essais hydrostatiques

ICS: 23.040.70

iTeh STANDARD PREVIEW (standards.iteh.ai)

[oSIST prEN ISO 1402:2020](https://standards.iteh.ai/catalog/standards/sist/82e4bb3e-c139-4ed6-bc24-bff2f00012ed/osist-pren-iso-1402-2020)<https://standards.iteh.ai/catalog/standards/sist/82e4bb3e-c139-4ed6-bc24-bff2f00012ed/osist-pren-iso-1402-2020>

THIS DOCUMENT IS A DRAFT CIRCULATED FOR COMMENT AND APPROVAL. IT IS THEREFORE SUBJECT TO CHANGE AND MAY NOT BE REFERRED TO AS AN INTERNATIONAL STANDARD UNTIL PUBLISHED AS SUCH.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

This document is circulated as received from the committee secretariat.

ISO/CEN PARALLEL PROCESSING



Reference number
ISO/DIS 1402:2020(E)

© ISO 2020

iTeh STANDARD PREVIEW (standards.iteh.ai)

[oSIST prEN ISO 1402:2020](https://standards.iteh.ai/catalog/standards/sist/82e4bb3e-c139-4ed6-bc24-bff2f00012ed/osist-pren-iso-1402-2020)

<https://standards.iteh.ai/catalog/standards/sist/82e4bb3e-c139-4ed6-bc24-bff2f00012ed/osist-pren-iso-1402-2020>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2020

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 General	1
5 Apparatus	1
6 Test pieces	2
6.1 Hose assemblies.....	2
6.2 Hoses.....	2
6.3 Number of test pieces.....	2
7 Application of hydrostatic pressure	2
7.1 General.....	2
7.2 Procedure.....	2
8 Hydrostatic pressure tests	2
8.1 Proof pressure hold test.....	2
8.2 Measurement of deformation under pressure.....	3
8.2.1 General procedure.....	3
8.2.2 Change in length at the specified test pressure.....	3
8.2.3 Change in external diameter at the specified test pressure, measured at the approximate middle of the hose assembly.....	4
8.2.4 Twisting at the specified test pressure.....	5
8.2.5 Warping at the specified test pressure.....	5
8.3 Burst pressure test.....	5
8.4 Leakage test.....	5
8.4.1 Test pieces.....	5
8.4.2 Procedure.....	6
8.4.3 Criteria for failure.....	6
9 Test report	6

ISO/DIS 1402:2020(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 45, *Rubber and rubber products*, Subcommittee SC 1, *Rubber and plastics hoses and hose assemblies*.

This fifth edition cancels and replaces the fourth edition (ISO 1402:2009), which has been technically revised.

The main changes compared to the previous edition are as follows:

- The tolerances of the pressure given in the [figure 3](#) and relative [clause 7.2.2](#), [8.1](#) and [8.2](#).
- A description of the failure mode in the [clause 8.3](#).

A list of all parts in the ISO 1402 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Rubber and plastics hoses and hose assemblies — Hydrostatic testing

1 Scope

This International Standard specifies methods for the hydrostatic testing of rubber and plastics hoses and hose assemblies, including methods for the determination of dimensional stability.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 4671, *Rubber and plastics hoses and hose assemblies — Methods of measurement of the dimensions of hoses and the lengths of hose assemblies*

ISO 7751, *Rubber and plastics hoses and hose assemblies — Ratios of proof and burst pressure to maximum working pressure*

ISO 8330, *Rubber and plastics hoses and hose assemblies — Vocabulary*

ISO 23529, *Rubber — General procedures for preparing and conditioning test pieces for physical test methods*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 8330 apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

4 General

Unless otherwise specified, all tests shall be carried out at standard temperature (see ISO 23529).

5 Apparatus

5.1 Pressure source, capable of applying pressure at the rate specified in 7.2.2, up to the required test pressure.

5.2 Calibrated pressure gauge or pressure transducer with digital readout, chosen for each test so that the test pressure is between 15 % and 85 % of the full-scale reading.

In the interest of accuracy, calibrated pressure gauges or pressure transducers with digital readouts shall be checked at frequent intervals and the fitting of restrictors is recommended to minimize shock damage.

5.3 Dimensional equipment, sliding vernier callipers or micrometer, length measuring tape, circumferential measuring tape (π tape).

ISO/DIS 1402:2020(E)

6 Test pieces

6.1 Hose assemblies

When hose assemblies are to be tested, the manufactured assembly length shall be used for the test.

6.2 Hoses

The hydrostatic pressure and burst tests shall be carried out on a hose test piece with a minimum free length, excluding end fittings and end reinforcements, of 600 mm when deformation is to be measured and 300 mm when it is not. When a longer test length is required for a particular hose type or size, it must be specified in the individual hose product specification.

6.3 Number of test pieces

At least two test pieces shall be tested.

7 Application of hydrostatic pressure

7.1 General

Water or another liquid suitable for the hose under test shall be used as the test medium.

WARNING — Hoses and hose assemblies pressurized by liquids can fail in a potentially dangerous manner. For this reason, the test shall be performed in a suitable enclosure. Also, the use of air and other gases as test media shall be avoided because of the risk to operators. In special cases, where such media are required for the tests, strict safety measures are imperative. Furthermore, it is stressed that, even when a liquid is used as the test medium, it is essential that all air is expelled from the test piece because of the risk of injury to the operator due to the sudden expansion of trapped air released when the hose bursts.

7.2 Procedure

7.2.1 Fill the test piece with test liquid, expelling all air, and connect to the test equipment. Close the valve and apply the hydrostatic pressure at a uniform rate of increase. Measure the pressure using a calibrated pressure gauge or pressure transducer with digital readout ([5.2](#)).

IMPORTANT — It is important to allow unrestricted movement of the free or plugged end of the test piece during the test.

7.2.2 The rate of pressure increase shall be constant and chosen to reach the final pressure after a period of between 30 s and 60 s for hoses with nominal inside diameters up to 50 mm. For hoses with nominal inside diameters greater than 50 mm and less than or equal to 250 mm, the time needed to reach the final pressure shall be between 60 s and 240 s. For hoses with nominal inside diameters greater than 250 mm, and/or when the test hose is longer than the minimum free length specified in [clause 6.2](#), the time needed to reach the final pressure shall be decided between the manufacturer and the user.

8 Hydrostatic pressure tests

8.1 Proof pressure hold test

When proof pressure tests are used to determine leakage of hoses or hose assemblies, apply the specified proof pressure in accordance with [7.2.2](#) and hold it neither for less than 30 s nor for more than 60 s, unless otherwise specified in the product standard, examining the test pieces during this period

for evidence of leakage, cracking, abrupt distortions indicating irregularity in material or manufacture, or other signs of failure. The tolerance of the pressure is +10% of the specified pressure.

Unless otherwise specified for the hose, the proof pressure shall be related to the maximum working pressure by the ratio given in ISO 7751.

NOTE 1 This text uses the term “maximum working pressure” instead of the deprecated term “design working pressure”.

NOTE 2 The test is not applicable to curved hose.

8.2 Measurement of deformation under pressure

8.2.1 General procedure

8.2.1.1 Setting up the test piece

When tests for determining change in length, change in outside diameter and twisting and/or warping are required, straighten the hose or hose assembly, lay it out horizontally for inspection and apply a hydrostatic pressure of 0,07 MPa (0,7 bar) approximately 5 min after completion of the proof pressure test. It is not necessary to apply 0,07 MPa (0,7 bar) when it is stable in keeping straightness without pressure. The supporting surface upon which the hose/hose assembly rests shall be flat and smooth enough to allow the hose/hose assembly to expand or contract without restriction. Alternatively, the hose/hose assembly may be supported on rollers, or suspended vertically. When a section of hose is used as a test piece, it may also be placed in a test rig in a vertical position.

8.2.1.2 Reference marks (standards.iteh.ai)

For long hoses or hose test pieces (see 6.2), while maintaining the pressure, make three reference marks (A, B and C) on the outer surface, the middle mark (B) being made approximately midway along the length of the hose, and the outer marks (A and C) 250 mm (minimum) from B. Each mark shall consist of an arc on the circumference of the hose through which is drawn a straight line perpendicular to the arc, the three lines being co-linear (see Figure 1).

For hose assemblies, measure the distance between the contact faces of the end fittings, or place the reference marks on the hose surface near the end of the inserted part of the fitting.

8.2.1.3 Measurement of initial dimensions

At the initial state (no pressure or maintain pressure of 0,07 MPa (0,7 bar) maintain for approximately 5 min) make the appropriate measurements (see 8.2.2, 8.2.3 and 8.2.4) at the reference marks A and C with an accuracy of ± 1 mm using the measuring tape (see 5.3) and record these. Also measure the external diameter or circumference accurately.

8.2.2 Change in length at the specified test pressure

NOTE The test pressure will be specified in the appropriate hose product specification and could be the maximum working pressure (see Note 1 to 8.1), the proof pressure or any other pressure below the proof pressure at which the hose deformation characteristics are to be measured.

Raise the pressure to the test pressure specified in the hose product standard at the rate specified in 7.2.2 and maintain it for 5 min (or longer when specified in the hose product standard). At the end of this period, measure the length between the reference marks A and C or, in the case of hose assemblies, between the contact faces of the end fittings, with an accuracy of ± 1 mm, using the measuring tape (see 5.3) and record these values. The tolerance of the pressure is +10% of the specified pressure.