



Designation: C484 – 99(Reapproved 2009)

Standard Test Method for Thermal Shock Resistance of Glazed Ceramic Tile¹

This standard is issued under the fixed designation C484; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers the determination of the resistance to thermal shock of glazed ceramic tiles under normal conditions of use.

1.2 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*²

C242 Terminology of Ceramic Whitewares and Related Products

C373 Test Method for Water Absorption, Bulk Density, Apparent Porosity, and Apparent Specific Gravity of Fired Whiteware Products

3. Terminology

3.1 *Definitions*—For the definitions of terms used on this test method, refer to Terminology C242.

4. Summary of Test Method

4.1 This test method consists of determining the thermal shock resistance of ceramic tiles by cycling a sample ten times between the temperatures of $15 \pm 5^\circ\text{C}$ ($59 \pm 9^\circ\text{F}$) and $145 \pm 5^\circ\text{C}$ ($293 \pm 9^\circ\text{F}$). This test method includes two procedures, with and without immersion, for tiles with a water absorption less than or equal to 10 % and tiles with a water absorption

greater than 10 %, respectively. After completing ten cycles, the tiles are inspected for any damage as a result of the cycling.

5. Significance and Use

5.1 This test method is intended for testing glazed ceramic tile that are to be used in areas in which they may be subjected to rapid or severe temperature changes.

6. Apparatus

6.1 *Water Bath*, for testing with immersion, through which $15 \pm 5^\circ\text{C}$ ($59 \pm 9^\circ\text{F}$) water flows at a rate of 1 gal/min. The bath shall hold at least 5 gal (19 L) of water and shall be of dimensions such that five whole tiles are immersed completely when placed in the bath vertically.

6.2 *Covered Water Bath*, for testing without immersion, consisting of the Water Bath in 6.1 covered with an aluminum sheet and layer of aluminum grains. The aluminum sheet shall be 5.18–mm (0.204–in.) thick—No. 4 B&S—gage and of dimensions such that five whole tiles can be placed glazed face down on it. The aluminum sheet shall cover the mouth of the bath with the flow of water directed such that it is in contact with bottom surface of the aluminum sheet. The entire top surface of the aluminum sheet shall be covered with a 3–mm (0.197–in.) thick layer of aluminum grains. The diameters of the aluminum grains shall be in the range of 0.3 mm (0.012 in.) to 0.6 mm (0.024 in.).

6.3 *Oven*, capable of maintaining a constant temperature of $145 \pm 5^\circ\text{C}$ ($293 \pm 9^\circ\text{F}$).

7. Sampling

7.1 The test sample shall consist of five whole tiles or trim units, selected at random from the lot to be tested.

8. Procedure

8.1 Before testing for resistance to thermal shock, inspect the tiles for visible defects. To assist in detecting defects, a suitable stain, such as waterproof black India ink or a 1 % aqueous solution of methylene blue, may be used. Apply the ink or dye solution to the face of the tiles and wipe off with a damp cloth after 1 min. All tiles should be free from defects before testing.

8.2 *Testing With Immersion*—For tiles with a water absorption less than or equal to 10 %, the low temperature condition

¹ This test method is under the jurisdiction of ASTM Committee C21 on Ceramic Whitewares and Related Products and is the direct responsibility of Subcommittee C21.06 on Ceramic Tile.

Current edition approved May 1, 2009. Published September 2009. Originally approved in 1961. Last previous edition approved in 2003 as C484 – 99 (2003). DOI: 10.1520/C0484-99R09.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For Annual Book of ASTM Standards volume information, refer to the standard's Document Summary page on the ASTM website.