
**Textiles — Test method for accelerated
hydrolysis of textile materials and
biodegradation under controlled
composting conditions of the resulting
hydrolysate**

*Textiles — Méthode d'essai pour hydrolyse accélérée des matières
textiles et la biodégradation dans des conditions de compostage
contrôlées de l'hydrolysates résultant*

(<https://standards.iteh.ai>)
Document Preview

ISO 21701:2019

<https://standards.iteh.ai/catalog/standards/iso/3448944f-3c37-4af8-96ae-a690bec6c58e/iso-21701-2019>



iTeh Standards
(<https://standards.itih.ai>)
Document Preview

ISO 21701:2019

<https://standards.itih.ai/catalog/standards/iso/3448944f-3c37-4af8-96ae-a690bec6c58e/iso-21701-2019>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2019

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	2
5 Reference material	3
6 Apparatus	3
7 Test procedure	4
7.1 Preparation of test material	4
7.2 Preparation of the inoculum	4
7.3 Accelerated hydrolysis test (abiotic test)	4
7.4 Biodegradation test (biotic test) of hydrolysate	4
7.5 Gas chromatographic analysis	5
8 Calculation and expression of results	5
8.1 Amount of carbon dioxide in grams	5
8.2 Percentage of biodegradation	7
8.3 Validity of results	7
9 Test report	7
Annex A (informative) Example of apparatus	8
Annex B (informative) Example of accelerated hydrolysis test results	9
Bibliography	10

ISO 21701:2019

<https://standards.iteh.ai/catalog/standards/iso/3448944f-3c37-4af8-96ae-a690bec6c58e/iso-21701-2019>

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 38, *Textiles*.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

ISO 21701:2019

<https://standards.iteh.ai/catalog/standards/iso/3448944f-3c37-4af8-96ae-a690bec6c58e/iso-21701-2019>

Introduction

Textile fibres can be classified into natural fibres and man-made fibres according to ISO/TR 11827. Some of man-made fibres manufactured from organic materials are biodegradable and can be divided into three major categories in relation to their origin, i.e. natural material base, biology base and petroleum base. The representative bio-based, man-made biodegradable fibre is polylactide and petroleum-based, man-made biodegradable fibres are manufactured from polyethylene terephthalate succinate, polycaprolactone, polypropylene carbonate, polybutylene succinate or copolymer using them.

The biodegradation of petroleum-based fibres is relatively slow compared to biology-based or natural fibres due to the chemical structure. In addition, the rate of biodegradation of textile materials such as fibres and yarns can also be affected negatively by high molecular weight, degree of crystallinity and orientation occurred during the spinning. Although some standards refer to the instrument analysis, such as gas chromatograph or infrared analysis, the process and calculation method are not standardized. Therefore, it is difficult to determine the biodegradation of petroleum-based textile materials using the existing standards available for natural fibres, biology-based fibres or plastic materials used for packaging.

To overcome these difficulties, the new test method is proposed by a combination of accelerated hydrolysis and biodegradation using instrument analysis for analysis of evolved carbon dioxide.

Under the composting of textile materials both mechanisms, abiotic and biotic processes, operate together and the microorganisms eventually remove the hydrolysate in a synergistic process. It is difficult and time consuming to reproduce this in the laboratory. For convenience, the accelerated hydrolysis, which is an abiotic process, should be carried out followed by biodegradation subsequently. The rate and extent of molecular weight loss is measured as indicative of losses in physical properties from accelerated hydrolysis and then the biodegradability of hydrolysate is estimated by direct measurement of evolved carbon dioxide with a gas chromatograph.

Document Preview

ISO 21701:2019

<https://standards.iteh.ai/catalog/standards/iso/3448944f-3c37-4af8-96ae-a690bec6c58e/iso-21701-2019>

