



Standard Specification for Polyvinylidene Fluoride (PVDF) Corrosive Waste Drainage Systems¹

This standard is issued under the fixed designation F 1673; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers requirements for polyvinylidene drainage systems for corrosive applications. Requirements for material, pipe and fittings are included. Polyvinylidene fluoride includes emulsion/suspension polymerization and copolymers of vinylidene fluoride/hexafluoropropylene produced by either method.

1.2 These requirements apply to Schedule 40 and 80 IPS and SDR 21 pipe sizes. Pipe and fittings are to be joined by heat fusion or mechanical methods using the equipment supplied by the manufacturers.

1.3 This specification is not intended to provide for interchangeability between plastic pipe and fittings from different manufacturers, but it does allow for transition fittings for joining one manufacturer's product to another's product, provided the joining technique used is other than heat fusion.

1.4 This specification is not for polyvinylidene pressure systems.

~~1.5 The values stated in inch-pound units are to be regarded as the standard. The values in parentheses are for information only.~~

1.5 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.6 Notes and appendixes are not a mandatory part of this specification.

1.7 The following safety hazard caveat pertains only to the test method portion, Section 8, of this specification: *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*²

D 543 [Practices for Evaluating the Resistance of Plastics to Chemical Reagents](#)

D 570 [Test Method for Water Absorption of Plastics](#)

D 618 ~~[Practice for Conditioning Plastics and Electrical Insulating Materials for Testing](#)~~² [Practice for Conditioning Plastics for Testing](#)

D 883 [Terminology Relating to Plastics](#)

D 1599 [Test Method for Resistance to Short-Time Hydraulic Pressure of Plastic Pipe, Tubing, and Fittings](#)

D 1600 [Terminology for Abbreviated Terms Relating to Plastics](#)

D 2122 [Test Method for Determining Dimensions of Thermoplastic Pipe and Fittings](#)

D 2321 [Practice for Underground Installation of Thermoplastic Pipe for Sewers and Other Gravity-Flow Applications](#)

D 2412 [Test Method for Determination of External Loading Characteristics of Plastic Pipe by Parallel-Plate Loading](#)

D 2444 [Test Method for Determination of the Impact Resistance of Thermoplastic Pipe and Fittings by Means of a Tup \(Falling Weight\)](#)

D 2657 [Practice for Heat Fusion Joining of Polyolefin Pipe and Fittings](#)

D 3222 [Specification for Unmodified Poly\(Vinylidene Fluoride\) \(PVDF\) ~~Molding, Extrusion, Molding Extrusion~~ and Coating Materials](#)

D 3311 [Specification for Drain, Waste, and Vent \(DWV\) Plastic Fittings Patterns](#)

D 5575 ~~[Specification-Classification System for Copolymers of Vinylidene Fluoride \(VDF\) with Other Fluorinated Monomers](#)~~

F 412 [Terminology Relating to Plastic Piping Systems](#)

F 1290 [Practice for Electrofusion Joining Polyolefin Pipe and Fittings](#)

¹ This specification is under the jurisdiction of ASTM Committee F17 on Plastic Piping Systems and is the direct responsibility of Subcommittee F17.63 on DWV. Current edition approved Apr. 10, 2002. Published June 2002. Originally published as F1673-95. Last previous edition F1673-95.

Current edition approved Aug. 1, 2009. Published September 2009. Originally approved in 1995. Last previous edition approved in 2004 as F 1673 - 04.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

F 1498 [Specification for Taper Pipe Threads \(60°\) and 60 for Thermoplastic Pipe and Fittings](#)

2.2 *Federal Standard:*

Fed. Std. No. 123 Marking for Shipment³

2.3 *Military Standard:*

~~MIL-STD 129 Marking for Shipment and Storage⁶~~

MIL-STD 129 Marking for Shipment and Storage³

iTeh Standards (<https://standards.iteh.ai>) Document Preview

[ASTM F1673-04\(2009\)](#)

<https://standards.iteh.ai/catalog/standards/sist/2477f854-d2e6-43cc-bf8e-c26933c76113/astm-f1673-042009>

² Annual Book of ASTM Standards, Vol 08.04.

³ Available from Standardization Documents Order Desk, DODSSP, Bldg. 4, Section D, 700 Robbins Ave., Philadelphia, PA 19111-5098, <http://www.dodssp.daps.mil>.

2.4 *Other Standard:*
Uniform Plumbing Code ⁴

3. Terminology

3.1 Definitions:

3.1.1 Definitions used in this specification are in accordance with the definitions given in Terminologies D 833 and F 412 and abbreviations are in accordance with Terminology D 1600, unless otherwise indicated.

3.1.2 The plumbing terminology used in this specification is in accordance with the definitions given in the *Uniform Plumbing Code*, unless otherwise indicated.

4. Classification

4.1 *General*—This specification covers PVDF pipe and fittings made from PVDF or VF/HFP copolymers in Schedule 40 and 80 IPS sizes and in SDR 21.

4.2 This specification also includes molded fittings and the larger sizes (8, 10, 12 in.) of fabricated fittings.

4.3 This specification covers PVDF pipe (SDR 21) made from PVDF defined by a hydrostatic design stress of 2300 psi (15.85 MPa).

5. Materials and Manufacture

5.1 Polyvinylidene fluoride (PVDF) material for pipe or fittings shall conform to the requirements of Type I or Type II PVDF as defined in Specification D 3222 or copolymers as defined in Specification D 5575.

5.2 The PVDF material may contain pigment and fillers not detrimental to the pipe and fittings, provided the pipe and fittings produced meet the requirements of this specification.

5.3 *Rework Material*—Clean rework material, generated from the manufacturer’s pipe and fittings products may be used by the same manufacturer, provided that the pipe or fittings produced meet the requirements of this specification.

6. Requirements Requirements

6.1 Dimensions and Tolerances—Pipe and Fittings:

6.1.1 Pipe:

6.1.1.1 Dimensions and tolerances for pipe shown in Table 1 and Table 2 shall be measured in accordance with Method D 2122. The tolerance for out-of-roundness shall apply only to pipe prior to shipment.

6.1.1.2 *Toe-In*—The outside diameter, when measured in accordance with Method D 2122, shall meet the requirements of Table 1 and Table 2 at any point within 1.5 pipe diameters or 11.8 in. (300 mm), whichever is less, to the cut end of the pipe length.

6.1.2 Fittings:

6.1.2.1 The minimum wall thickness of the body all fittings shall not be less than the corresponding Schedule 40 pipe size and shall be measured in accordance with Method D 2122.

6.1.2.2 Spigot ends of fittings shall conform to the diameter and out-of-roundness requirements for pipe.

6.1.2.3 Socket ends of fittings shall conform to the dimensional requirements for size and tolerances as provided by the manufacturer.

6.1.2.4 The average minimum diameters of waterways of fittings, excluding adapters, shall be as specified in Table 3.

6.1.2.5 Taper pipe threads in any fittings shall be as specified in Specification F 1498. The tolerance shall be 1½ large or small turns from the basic thread dimension and gaged in accordance with 8.7.

⁴ Annual Book of ASTM Standards, Vol 08.02.

⁴ Available from International Association of Plumbing and Mechanical Officials, 5001 E. Philadelphia St., Ontario, CA 91761, <http://www.iapmo.org>.

TABLE 1 Outside Diameters and Tolerances for PVDF Pipe Schedules 40 and 80 and SDR 21, in. (mm)

Nominal Pipe Size	Average Outside Diameter	Tolerance	Out-of-Roundness (Maximum Diameter Minus Minimum Diameter)
1¼	1.660 (42.16)	±0.005 (±0.13)	0.050 (1.28)
1½	1.900 (48.26)	±0.006 (±0.15)	0.060 (1.52)
2	2.375 (60.32)	±0.006 (±0.15)	0.070 (1.78)
3	3.500 (88.90)	±0.008 (±0.20)	0.080 (2.04)
4	4.500 (114.30)	±0.009 (±0.23)	0.100 (2.54)
6	6.625 (168.28)	±0.011 (±0.28)	0.100 (2.54)
8	8.625 (219.08)	±0.015 (±0.38)	0.150 (3.80)
10	10.750 (273.05)	±0.015 (±0.38)	0.150 (3.80)
12	12.750 (323.85)	±0.015 (±0.38)	0.150 (3.80)

TABLE 2 Wall Thicknesses and Tolerances for PVDF Pipe Schedules 40 and 80 and SDR 21, in. (mm)

NOTE 1— For fittings, the wall thickness is a minimum value, except that a 10 % variation resulting from core shift is allowable. In such a case, the average of the two opposite wall thickness' shall equal or exceed the value shown in the Schedule 40 table.

Nominal Pipe Sizes	Schedule 40		Schedule 80		SDR 21, 230 psi		SDR 32.5, 150 psi	
	Minimum	Tolerance	Minimum	Tolerance	Minimum	Tolerance	Minimum	Tolerance
1¼	0.140 (3.56)	+0.020 (+0.51)	0.191 (4.85)	+0.023 (+0.58)	0.062 (1.57)	+0.020 (+0.51)	0.062 (1.57)	+0.020 (0.51)
1½	0.140 (3.56)	+0.020 (+0.51)	0.191 (4.85)	+0.023 (+0.58)	0.079 (2.01)	+0.020 (+0.51)	0.062 (1.57)	+0.020 (0.51)
2	0.145 (3.68)	+0.020 (+0.51)	0.200 (5.08)	+0.024 (+0.61)	0.062 (1.57)	+0.020 (+0.51)	0.062 (1.57)	+0.020 (0.51)
2½	0.145 (3.68)	+0.020 (+0.51)	0.200 (5.08)	+0.024 (+0.61)	0.090 (2.28)	+0.020 (+0.51)	0.062 (1.57)	+0.020 (0.51)
3	0.154 (3.91)	+0.020 (+0.51)	0.218 (5.54)	+0.026 (+0.66)	0.077 (1.96)	+0.020 (+0.51)	0.073 (1.85)	+0.020 (0.51)
4	0.154 (3.91)	+0.020 (+0.51)	0.218 (5.54)	+0.026 (+0.66)	0.113 (2.87)	+0.020 (+0.51)	0.073 (1.85)	+0.020 (0.51)
5	0.216 (5.49)	+0.026 (+0.66)	0.300 (7.62)	+0.036 (+0.91)	0.114 (2.90)	+0.026 (+0.665)	0.108 (2.74)	+0.020 (0.51)
6	0.216 (5.49)	+0.026 (+0.66)	0.300 (7.62)	+0.036 (+0.91)	0.167 (4.22)	+0.020 (+0.51)	0.108 (2.74)	+0.020 (0.51)
8	0.237 (6.02)	+0.028 (+0.71)	0.337 (8.56)	+0.040 (+1.02)	0.147 (3.73)	+0.026 (+0.66)	0.138 (3.51)	+0.020 (0.51)
10	0.237 (6.02)	+0.028 (+0.71)	0.337 (8.56)	+0.040 (+1.02)	0.214 (5.44)	+0.026 (+0.66)	0.138 (3.51)	+0.020 (0.51)
12	0.280 (7.11)	+0.034 (+0.86)	0.432 (10.97)	+0.052 (+1.32)	0.216 (5.49)	+0.034 (+0.97)	0.204 (5.18)	+0.0241 (0.61)
16	0.280 (7.11)	+0.034 (+0.86)	0.432 (10.97)	+0.052 (+1.32)	0.315 (8.00)	+0.038 (+0.97)	0.204 (5.18)	+0.0241 (0.61)
20	0.322 (8.18)	+0.039 (+0.99)	0.500 (12.70)	+0.060 (+1.52)	0.281 (7.14)	+0.039 (+1.24)	0.99265 (6.73)	+0.032 (0.81)
24	0.322 (8.18)	+0.039 (+0.99)	0.500 (12.70)	+0.060 (+1.52)	0.411 (10.44)	+0.049 (+1.24)	0.265 (6.73)	+0.032 (0.81)
30	0.365 (9.27)	+0.044 (+1.12)	0.593 (15.06)	+0.071 (+1.80)	0.350 (8.90)	+0.044 (+1.55)	0.331 (8.41)	+0.040 (1.02)
36	0.365 (9.27)	+0.044 (+1.12)	0.593 (15.06)	+0.071 (+1.80)	0.512 (13.00)	+0.061 (+1.55)	0.331 (8.41)	+0.040 (1.02)
42	0.406 (10.31)	+0.049 (+1.24)	0.687 (17.45)	+0.082 (+2.08)	0.415 (10.54)	+0.049 (+1.85)	0.392 (9.96)	+0.04
48	0.406 (10.31)	+0.049 (+1.24)	0.687 (17.45)	+0.082 (+2.08)	0.607 (15.42)	+0.073 (+1.85)	0.392 (9.96)	+0.047 (+1.19)

TABLE 3 Average Waterway Diameter, in. (mm)

Nominal Pipe Size	Unthreaded Fittings		Under Half Thread of Male Adapters	
	Minimum	Maximum	Minimum	Maximum
1¼	1.227 (31.17)	1.280 (32.51)	1.220 (30.99)	1.280 (32.51)
1½	1.446 (36.73)	1.501 (38.13)	1.458 (37.03)	1.501 (38.13)
2	1.881 (47.78)	1.946 (49.43)	1.915 (48.64)	1.946 (49.43)
3	2.820 (71.63)	2.983 (75.77)	2.849 (72.36)	2.983 (75.77)
4	3.737 (94.92)	3.972 (100.89)	3.806 (96.67)	3.972 (100.89)
6	5.646 (143.41)	6.008 (152.53)	5.851 (148.62)	6.008 (152.53)
8	7.490 (190.25)
10	9.407 (238.94)
12	11.197 (284.40)

ASTM F1673-04(2009)

6.1.2.6 The patterns, dimensions, and laying lengths of molded fittings, including adaptors, shall meet the requirements of Specification D 3311, or shall be of a proven design and allow a smooth transition of fluid flow from one direction to another.

6.1.2.7 Cleanouts, cleanout plugs, and caps as commonly used in the manufacturer's laboratory drainage system, shall have a thread size and depth sufficient to ensure that the minimum waterway sizes are maintained.

6.1.2.8 Traps—All traps shall have a minimum water seal of 2 in.

6.2 Chemical Resistance—Pipe and fittings material shall be evaluated in accordance with Practice D 543, Procedures I and II, using the chemicals listed in 8.3. The weight change shall not exceed 2 %, nor shall the apparent tensile strength change by more than 10 %. In cases where there is a change in the apparent tensile strength greater than 10 %, a further evaluation shall be made after removal from the chemical and conditioning for 72 h. If there is a minimum of 50 % recovery of tensile strength after 72 h, and that figure is within ±10 % of the original tensile strength, the specimen shall be considered acceptable.

6.3 Water Absorption—Pipe and fitting materials shall not change in weight more than 0.50 % when tested in accordance with 8.4.

6.4 System Integrity:

6.4.1 Fused joints and associated pipe shall withstand a pressure of 50 psi (345 kPa) without leaking when tested in accordance with 8.5.1.

6.4.2 Mechanical joints shall withstand a pressure of 14.5 psi (100 kPa) without leaking when tested in accordance with 8.5.2.

NOTE 1—Mechanical joints include transition, compression, threaded, and other type mechanical joints.

6.4.3 Mechanical joints shall incorporate a positive mechanical system for axial restraint in addition to any restraint provided by friction.

6.4.4 Mechanical joints shall show no evidence of separation at the joint under Force *P* when tested in accordance with 8.6.1, nor shall they leak or show any other damage when tested in accordance with 8.6.2. Two fittings shall be tested and both shall pass.

6.5 All stainless steel parts shall be made of corrosion-resistant steel, containing not less than 16 % chromium and not less than 6 % nickel by weight.

6.6 Sealing Rings—Sealing rings shall be made from a material with a chemical resistance similar to PVDF.