



Designation: D3597–02 Designation: D 3597 – 02 (Reapproved 2008)

Standard Performance Specification for Woven Upholstery Fabrics—Plain, Tufted, or Flocked¹

This standard is issued under the fixed designation D 3597; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This performance specification covers the performance requirements for plain, tufted, or flocked woven upholstery fabrics as used in the manufacture of new indoor furniture. These requirements apply to both the warp and filling directions for those factors where each fabric direction is pertinent.

1.2 This performance specification is not applicable to fabrics used in porch, deck, or lawn furniture; nor for knitted fabrics, bonded or laminated fabrics, or surface-coated fabrics (such as vinyls and urethanes).

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:²

D 123 Terminology Relating to Textiles

D 434 Test Method for Resistance to Slippage of Yarns in Woven Fabrics Using a Standard Seam

D 1175 Test Method for Abrasion Resistance of Textile Fabrics (Oscillatory Cylinder and Uniform Abrasion)³

D 1424 Test Method for Tearing Strength of Fabrics by Falling-Pendulum Type (Elmendorf)(Elmendorf-Type) Apparatus

D 2262 Test Method for Tearing Strength of Woven Fabrics by the Tongue (Single Rip) Method (Constant-Rate-of-Transverse Tensile Testing Machine)

~~D 2905 Practice for Statements on Number of Specimens for Textiles~~

~~D 4157 Test Method for Abrasion Resistance of Textile Fabrics (Oscillatory Cylinder Method)~~ Test Method for Tearing Strength of Woven Fabrics by the Tongue (Single Rip) Method (Constant-Rate-of-Transverse Tensile Testing Machine)⁰

D 5034 Test Method for Breaking Strength and Elongation of Textile Fabrics (Grab Test)

2.2 AATCC Test Methods:⁴

8 AATCC Colorfastness to Crocking:

Crockmeter Method

16 Colorfastness to Light

23 Colorfastness to Burnt Gas Fumes

107 Colorfastness to Water

116 Colorfastness to Crocking:

Rotary Vertical Crockmeter Method⁴

129 Colorfastness to Ozone in the Atmosphere Under High Humidities

Gray Scale for Color Change, Evaluation Procedure 1

Chromatic Transference Scale, AATCC Evaluation Procedure 8 AATCC 9–Step Chromatic Transference Scale

Specifications Standards Test Procedures for Upholstered Furniture Fabrics⁵

¹ This performance specification is under the jurisdiction of ASTM Committee D13 on Textiles and is the direct responsibility of Subcommittee D13.63 on Home Furnishings.

Current edition approved April 10, 2002. Published July 2002. Originally published as D3597–77. Last previous edition D3597–95 (2001).

Current edition approved Aug. 1, 2008. Published October 2008. Originally approved in 1977. Last previous edition approved in 2002 as D 3597 – 02.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For Annual Book of ASTM Standards volume information, refer to the standard's Document Summary page on the ASTM website.

³ Withdrawn. The last approved version of this historical standard is referenced on www.astm.org.

⁴ Issued in 1969 by the National Association of Furniture Manufacturers and the National Retail Furniture Association. Available from Home Furniture Manufacturers Assn., P. O. Box HP-7, High Point, NC 27261.

⁴ AATCC Technical Manual, available from the American Association of Textile Chemists and Colorists, P. O. Box 12215, Research Triangle Park, NC 27709.

⁵ Available from the Bureau of Consumer Protection, Federal Trade Commission, Washington, DC 20580.

Guides for the Household Furniture Industry ⁶

2.3 *Federal Standard:*

16CFR, Chapter II-Consumer Product Safety Commission, Subchapter D-Flammable Fabrics Act Regulation⁷

2.4 *Military Standard:*

ASQ/ANSI Z1.4 Sampling Procedures and Tables for Inspection by Attributes⁸

NOTE 1—Reference to test methods in this standard give only the permanent part of the designation of ASTM, AATCC, or other test methods. The current editions of each test method cited shall prevail.

3. Terminology

3.1 For definitions of textile terms used in this performance specification, refer to Terminology D 123. Definitions found in a dictionary of common terms are suitable for terms used in this performance specification.

4. Significance and Use

4.1 Fabrics intended for this end-use should meet all of the requirements listed in Table 1.

4.2 It should be recognized that fabrics can be produced utilizing an almost infinite number of combinations of construction variables (e.g., type of fibers, percentage of fibers, yarn twist, yarn number, warp and pick count, chemical and mechanical finished). Additionally, fashion or aesthetics dictate that the ultimate consumer may find acceptable articles made from fabrics that do not conform to all of the requirements in Table 1.

4.2.1 Hence, no single performance specification can possibly apply to all the various fabrics that could be utilized for this end-use.

4.3 The uses and significance of particular properties and test methods are discussed in the appropriate section of the specified test methods.

5. Specification Requirements

5.1 The properties of woven upholstery fabrics (plain, tufted, or flocked) shall conform to the specification requirements in Table 1.

⁵ Issued in 1969 by the National Association of Furniture Manufacturers and the National Retail Furniture Association. Available from Home Furniture Manufacturers Assn., P. O. Box HP-7, High Point, NC 27261.

⁶ Available from Superintendent of Documents, U.S. Government Printing Office, Washington, DC 20402.

⁶ Available from the Bureau of Consumer Protection, Federal Trade Commission, Washington, DC 20580.

⁷ Available from Standardization Documents Order Desk, Bldg. 4 Section D, 700 Robbins Ave., Philadelphia, PA 19111-5094, Attn: NPODS.

⁷ Available from Superintendent of Documents, U.S. Government Printing Office, Washington, DC 20402.

⁸ Singer No. 23 needle, or its equivalent has been found satisfactory for this method.

⁸ Available from Standardization Documents Order Desk, Bldg. 4 Section D, 700 Robbins Ave., Philadelphia, PA 19111-5094, Attn: NPODS.

TABLE 1 Specification Requirements

Characteristics	Requirements	Section
Breaking strength (load)	222 N (50 lbf), min	6.1
Tongue tear strength	27 N (6 lbf), min	6.2
Resistance to yarn slippage	111 N (25 lbf), min	6.3
Surface abrasion ^A		
Light-duty	3000 cycles (double rubs), min	6.4
Medium-duty	9000 cycles (double rubs), min	6.4
Heavy-duty	15,000 cycles (double rubs), min	6.4
Dimensional change:		
Warp or filling	5.0% shrinkage, max to 2.0% gain, max	6.5
Colorfastness to: ^B		
Water, ^C Color Change	grade 4, ^D min	6.6
Solvent, ^C Color Change	grade 4, ^D min	6.7
Burnt gas fumes-2 cycles	grade 4, ^D min	6.8
Crocking:		
Dry	grade 4, ^E min	6.9
Wet	grade 3, ^E min	6.9
Light-40 AATCC Fading Units	grade 4, ^D min	6.10
Ozone 1 cycle	grade 4, ^D min	6.11
Retention of hand, character, and appearance	no significant change	6.12
Durability of back coating	no significant change	6.13
Flammability	pass	6.14
FTC Requirements	pass	6.15

^A For guideline purposes see 6.4.1.

^B Class in the colorfastness requirements is based on a numerical scale of 5 for negligible for no colorchange or color transfer to 1 for very severe color change or color transfer.

^C For guidelines purposes—See Section 6.6.2.

^D AATCC Gray Scale for Color Change.

^E AATCC Chromatic Transference Scale.