



**SLOVENSKI STANDARD**  
**oSIST prEN ISO/ASTM 52936-1:2021**  
**01-september-2021**

---

**[Not translated]**

Additive manufacturing of polymers - Powder bed fusion - Part 1: General principles and preparation of test specimens for PBF-LB (ISO/ASTM DIS 52936-1:2021)

Additive Fertigung - Qualifizierungsgrundsätze - Laserbasiertes pulverbettbasiertes Schmelzen von Polymeren - Teil 1: Allgemeines und Herstellung von Prüfkörpern (ISO/ASTM DIS 52936-1:2021)

Fabrication additive de polymères - Fusion sur lit de poudre - Partie 1: Principes généraux et préparation des éprouvettes pour PBF-LB (ISO/ASTM DIS 52936-1:2021)

<https://standards.iteh.ai/catalog/standards/sist/c574c747-7566-4356-a960-a5bdhc2746de/osist-pr-en-iso-astm-52936-1-2021>

**Ta slovenski standard je istoveten z: prEN ISO/ASTM 52936-1**

---

**ICS:**

25.030	3D-tiskanje	Additive manufacturing
83.080.01	Polimerni materiali na splošno	Plastics in general

**oSIST prEN ISO/ASTM 52936-1:2021**      **en,fr,de**

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[oSIST prEN ISO/ASTM 52936-1:2021](https://standards.iteh.ai/catalog/standards/sist/c574c747-7566-4356-a960-a5bdb2746de/osist-pren-iso-astm-52936-1-2021)

<https://standards.iteh.ai/catalog/standards/sist/c574c747-7566-4356-a960-a5bdb2746de/osist-pren-iso-astm-52936-1-2021>

# DRAFT INTERNATIONAL STANDARD

## ISO/ASTM DIS 52936-1

ISO/TC 261

Secretariat: DIN

Voting begins on:  
2021-08-13Voting terminates on:  
2021-11-05

### Additive manufacturing of polymers — Powder bed fusion —

Part 1:

### General principles and preparation of test specimens for PBF-LB

*Fabrication additive de polymères - Fusion sur lit de poudre —**Partie 1: Principes généraux et préparation des éprouvettes pour le PBF laser*

ICS: 25.030

**iTeh STANDARD PREVIEW**  
(standards.iteh.ai)

oSIST prEN ISO/ASTM 52936-1:2021

<https://standards.iteh.ai/catalog/standards/sist/c574c747-7566-4356-a960-a5bdbc2746de/osist-pren-iso-astm-52936-1-2021>

Member bodies are requested to consult relevant national interests in ISO/TC 61, ISO/TC 61/SC 9 before casting their ballot to the e-Balloting application.

THIS DOCUMENT IS A DRAFT CIRCULATED FOR COMMENT AND APPROVAL. IT IS THEREFORE SUBJECT TO CHANGE AND MAY NOT BE REFERRED TO AS AN INTERNATIONAL STANDARD UNTIL PUBLISHED AS SUCH.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

This document is circulated as received from the committee secretariat.

### ISO/CEN PARALLEL PROCESSING



Reference number  
ISO/ASTM DIS 52936-1:2021(E)

© ISO 2021

## iTeh STANDARD PREVIEW (standards.iteh.ai)

<https://standards.iteh.ai/catalog/standards/sist/c574c747-7566-4356-a960-a5bdbc2746de/osist-pren-iso-astm-52936-1-2021>



### **COPYRIGHT PROTECTED DOCUMENT**

© ISO/ASTM International 2021

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester. In the United States, such requests should be sent to ASTM International.

ISO copyright office  
CP 401 • Ch. de Blandonnet 8  
CH-1214 Vernier, Geneva  
Phone: +41 22 749 01 11

Email: [copyright@iso.org](mailto:copyright@iso.org)  
Website: [www.iso.org](http://www.iso.org)

Published in Switzerland

ASTM International  
100 Barr Harbor Drive, PO Box C700  
West Conshohocken, PA 19428-2959, USA  
Phone: +610 832 9634  
Fax: +610 832 9635  
Email: [khooper@astm.org](mailto:khooper@astm.org)  
Website: [www.astm.org](http://www.astm.org)

<b>Contents</b>		Page
<b>Foreword</b> .....		<b>iv</b>
<b>Introduction</b> .....		<b>v</b>
<b>1</b>	<b>Scope</b> .....	<b>1</b>
<b>2</b>	<b>Normative references</b> .....	<b>1</b>
<b>3</b>	<b>Terms and definitions</b> .....	<b>1</b>
<b>4</b>	<b>Preparation of test specimen</b> .....	<b>3</b>
4.1	General.....	3
4.2	Dimensions of test specimen.....	3
4.3	Conditioning and preparation of the material.....	3
4.4	Test specimens manufacturing.....	3
4.4.1	Test specimens processing.....	4
4.5	Rinsing, handling and storage of test specimens.....	4
<b>5</b>	<b>Report on test-specimen preparation</b> .....	<b>4</b>
<b>Bibliography</b> .....		<b>6</b>

## iTeh STANDARD PREVIEW (standards.iteh.ai)

[oSIST prEN ISO/ASTM 52936-1:2021](https://standards.iteh.ai/catalog/standards/sist/c574c747-7566-4356-a960-a5bdbc2746de/osist-pren-iso-astm-52936-1-2021)

<https://standards.iteh.ai/catalog/standards/sist/c574c747-7566-4356-a960-a5bdbc2746de/osist-pren-iso-astm-52936-1-2021>

## ISO/ASTM DIS 52936-1:2021(E)

### Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

The committee responsible for this document is ISO/TC 261, Additive manufacturing, in cooperation with ASTM Committee F42, Additive Manufacturing Technologies, on the basis of a partnership agreement between ISO and ASTM International with the aim to create a common set of ISO/ASTM standards on Additive Manufacturing.

This first edition of ISO/ASTM 52936-1 cancels and replaces ISO 27547-1, which has been technically revised.

The main changes compared to ISO 27547-1 are as follows:

- New standard number and title to make clear its status as additive manufacturing standard;
- Requirements for conditions revised to allow use of state of the art machines;
- Informative Annex B deleted because this procedure is not state of the art anymore.

## Introduction

Many factors in an additive manufacturing test specimen-preparation process can influence the properties of the test specimens prepared and hence the measured values obtained when the test specimens are used in a test method. The mechanical properties of such test specimens are in fact strongly dependent on the conditions of the process used to prepare the test specimens. Exact definition of each of the main parameters of the process is a basic requirement for reproducible operating conditions.

It is important in defining test specimen-preparation conditions to consider any influence the conditions could have on the properties to be determined. Test specimens prepared by additive manufacturing techniques can show differences in molecular morphology (as with crystalline and semicrystalline polymers), differences in powder morphology (after undergoing a sintering process, for instance), differences in thermal history and differences in thickness of the layers, test specimen orientation or test specimen location, used to prepare the specimen. Only if each of these is controlled can differences in the values of the properties measured be avoided.

This international Standard has been developed by ISO/TC 261, ISO/TC 61/SC 9 and ASTM F42 in close cooperation on the basis of a partnership between ISO and ASTM international with the aim to create a common set of ISO/ASTM standards on Additive Manufacturing.

## iTeh STANDARD PREVIEW (standards.iteh.ai)

[oSIST prEN ISO/ASTM 52936-1:2021](https://standards.iteh.ai/catalog/standards/sist/c574c747-7566-4356-a960-a5bdbc2746de/osist-pren-iso-astm-52936-1-2021)

<https://standards.iteh.ai/catalog/standards/sist/c574c747-7566-4356-a960-a5bdbc2746de/osist-pren-iso-astm-52936-1-2021>

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[oSIST prEN ISO/ASTM 52936-1:2021](https://standards.iteh.ai/catalog/standards/sist/c574c747-7566-4356-a960-a5bdbc2746de/osist-pren-iso-astm-52936-1-2021)

<https://standards.iteh.ai/catalog/standards/sist/c574c747-7566-4356-a960-a5bdbc2746de/osist-pren-iso-astm-52936-1-2021>



# Additive manufacturing of polymers — Powder bed fusion —

## Part 1: General principles and preparation of test specimens for PBF-LB

### 1 Scope

This document specifies the general principles to be followed when test specimens of thermoplastic materials are prepared by laser-based powder bed fusion (PBF-LB/P), which is commonly known as laser sintering. The (PBF-LB/P) process is used to prepare test specimens layer upon layer in which thermal energy selectively fuses regions of a powder bed. This document provides a basis for establishing reproducible and reportable sintering conditions. Its purpose is to promote uniformity in describing the main process parameters, build orientation of the sintering process and also to establish uniform practice in reporting sintering conditions.

This document does not specify the test procedure itself.

### 2 Normative references (standards.iteh.ai)

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO/ASTM 52921, *Standard terminology for additive manufacturing- Coordinate systems and test methodologies*

ISO 3167, *Plastics — Multipurpose test specimens*

ISO 20753, *Plastics — Test specimens*

### 3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO/ASTM 52900 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

#### 3.1

##### laser wavelength

wavelength at the peak intensity of the laser

Note 1 to entry: Laser wavelength expressed in nanometres.

**ISO/ASTM DIS 52936-1:2021(E)****3.2****laser power**

power of the laser beam at each defined process operation

Note 1 to entry: Laser power expressed in watts.

Note 2 to entry: The laser power can be different when producing the contour (outline) of the test specimen and when hatching the part.

**3.3****laser mode**

parameter indicating which of the various electromagnetic standing waves that can be produced in the laser cavity is actually being used in a particular application

**3.4****beam radius**

radius of the laser beam

Note 1 to entry: It is expressed in millimetres.

**3.5****scan speed**

speed of travel of the laser beam across the surface of the test specimen being prepared

Note 1 to entry: It is expressed in millimetres per second.

Note 2 to entry: a synonymous term is beam speed.

Note 3 to entry: The scan speed can be different when producing the contour (outline) of the test specimen and when hatching the part.

**3.6****preheating temperature**

temperature to which the build chamber is heated before the build cycle starts

Note 1 to entry: Preheating temperature expressed in degrees Celsius.

**3.7****preheating time**

length of time required for the powder bed to reach the preheating temperature

Note 1 to entry: Preheating teemperature expressed in minutes.

Note 2 to entry: Since it is necessary to have a steady-state temperature throughout the whole build chamber, the preheating time can be rather long, often around 30 minutes."

**3.8****contour**

track followed by the laser beam when producing the outline of each layer

**3.9****hatching**

closely spaced parallel laser paths used to fuse the bulk material in each layer

**3.10****cool-down temperature**

temperature of the powder bed when the parts are removed from the powder bed

Note 1 to entry: The cool-down temperature is measured at the center of the surface of the powder bed.