



Designation: C1695 – 09

Standard Specification for Fabrication of Flexible Removable and Reusable Blanket Insulation for Hot Service¹

This standard is issued under the fixed designation C1695; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers the minimum requirements for materials and fabrication of flexible removable and reusable blanket insulation for hot service, from above ambient temperatures to 1000°F (538°C).

1.2 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:²

- C168 Terminology Relating to Thermal Insulation
- C553 Specification for Mineral Fiber Blanket Thermal Insulation for Commercial and Industrial Applications
- C680 Practice for Estimate of the Heat Gain or Loss and the Surface Temperatures of Insulated Flat, Cylindrical, and Spherical Systems by Use of Computer Programs
- C892 Specification for High-Temperature Fiber Blanket Thermal Insulation
- C1086 Specification for Glass Fiber Mechanically Bonded Felt Thermal Insulation
- C1129 Practice for Estimation of Heat Savings by Adding Thermal Insulation to Bare Valves and Flanges
- C1136 Specification for Flexible, Low Permeance Vapor Retarders for Thermal Insulation
- C1263 Test Method for Thermal Integrity of Flexible Water Vapor Retarders

¹ This specification is under the jurisdiction of ASTM Committee C16 on Thermal Insulation and is the direct responsibility of Subcommittee C16.40 on Insulation Systems.

Current edition approved Sept. 1, 2009. Published September 2009. DOI: 10.1520/C1695-09.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

- D3389 Test Method for Coated Fabrics Abrasion Resistance (Rotary Platform Abrader)
- D3776 Test Methods for Mass Per Unit Area (Weight) of Fabric
- D3786 Test Method for Bursting Strength of Textile Fabrics—Diaphragm Bursting Strength Tester Method
- D5034 Test Method for Breaking Strength and Elongation of Textile Fabrics (Grab Test)
- D5035 Test Method for Breaking Force and Elongation of Textile Fabrics (Strip Method)
- D5587 Test Method for Tearing Strength of Fabrics by Trapezoid Procedure
- D6413 Test Method for Flame Resistance of Textiles (Vertical Test)

2.2 Other Standards:

- 3E Plus^R Insulation Thickness Computer Program North American Insulation Manufacturers Association (NAIMA)³
- MIL-C-20079H Military Specification Cloth, Glass; Tape, Textile Glass and Thread, Glass and Wire Reinforced Glass⁴

3. Terminology

3.1 *General*—Definitions included in Terminology C168 shall apply to the terms used in this specification.

3.2 Definitions of Terms Specific to This Standard:

3.3 *removable and reusable blanket insulation, n*—An insulation blanket, encased in woven fabric and / or woven wire mesh, that has attachment mechanisms designed to allow the assembly to be installed, then later removed and reinstalled, without using any new insulation or fabric materials.

3.4 *coated fabric, n*—A woven fabric coated with a rubber or plastic compound such that the woven fabric material itself is not exposed to the environment.

3.5 *lacing hook, n*—a metal hook that is located on the outside surface of an insulation blanket and that is secured

³ Available from North American Insulation Manufacturers Association (NAIMA), 44 Canal Center Plaza, Suite 310 Alexandria, VA 22314, http://www.naima.org

⁴ Available from Standardization Documents Order Desk, DODSSP, Bldg. 4, Section D, 700 Robbins Ave., Philadelphia, PA 19111-5098, http://www.dodssp.daps.mil.

through the blanket; tie wire is wrapped around it so as to secure an insulation blanket around a pipe component or piece of equipment.

3.6 *lacing anchor, n*—a metal disk, located on the outside of an insulation blanket, that is secured to a pin that passes through the blanket; the assembly is used to wrap tire wire around so as to secure an insulation blanket around a pipe component or piece of equipment.

3.7 *D-ring, n*—a section of heavy wire which forms a complete loop in either a rectangular shape or the shape of the capital letter “D”, that is used in removable insulation blankets for attaching a fabric strap that secures the blanket around a pipe component or piece of equipment.

4. Materials

4.1 Insulation shall be of a flexible fibrous material acceptable for the maximum temperature of the application. Acceptable materials must be one of the following:

High Temperature Fiber Blanket per Specification **C892**, any Type or Grade

Needled Glass Fiber Mechanically Bonded Felt per Specification **C1086**

Mineral Fiber Blanket, per Specification **C553**, of the Type suitable for the application.

4.2 Material for the outer jacket liner and straps, where used, shall be woven glass fiber cloth that has been treated with a water resistant compound, such as silicone or fluorocarbon, that is suitable for both interior and exterior use, and having the properties as shown in **Table 1**.

4.3 Material for the inner jacket shall be the same as for the outer jacket for surface temperatures less than 500°F (260°C).

4.3.1 For surfaces from 501°F (261°C) to 1000°F (538°C) where leaks of process fluids are not expected, the inner layer and gussets shall be one of the following:

4.3.1.1 a plain, heat cleaned, glass fiber fabric,

4.3.1.2 a Type 304 stainless steel wire knitted mesh made from 0.008 inch (0.20 mm) diameter wire with nominal 6 to 8 openings per in.

4.3.2 For surfaces from 501°F (261°C) to 1000°F (538°C) where leaks of process fluids are expected, such as flange pairs and valves, the inner layer and gussets shall be as specified in **4.3.1** and **4.3.1.1** above but also with Type 304 stainless steel foil that has a minimum thickness of 0.001 in. (0.025 mm). This foil shall be placed between the insulation material and the outer fabric or wire mesh.

4.4 Tie-Down Straps shall be constructed of one of the following three types of material: (1) the same material as the outer jacket, (2) a woven glass fiber fabric, or (3) a tape of suitable thickness with the same coating as the outer jacket material. If the same material as the outer jacket is used, then a double thickness is required with an edge trim sewn in place along both edges. Edge trim shall be applied to prevent exposed fabric edges. Ends of the straps shall be turned under ¼ (6.35mm) to ½ (13mm) inch and double-stitched to prevent unraveling.

4.5 Drawstrings shall be made from 100% textured glass fiber sleeving with plain weave, ⅜ in. inside diameter and 0.03 in. wall thickness. Drawstrings shall be suitable for 1000°F (538°C) services.

4.6 PTFE-coated glass fiber thread shall be used for service temperatures to 500°F (260°C). Glass fiber thread shall be 0.021 inch (0.53 mm) diameter, minimum 20 lbs (9 kg). breaking strength.

4.7 Stainless steel thread shall be used for service temperatures above 500°F (260°C). Thread shall be minimum 0.015 in. (0.38 mm) diameter and minimum 18 lbs (8.16 kg). breaking strength.

4.8 All hardware such as D-rings, buckles, tags, etc., shall be Type 304 stainless steel.

TABLE 1 Physical and Performance Requirements for Fabrics

	Plain, heat cleaned glass fiber fabric ^A	Glass fiber fabric coated with Silicone Glass	Fiber fabric coated with Fluorocarbon
Weight (minimum) oz/sq. yd (g/m ²) per ASTM D3776	17.7 (602)	16.5 (561)	15 (510)
Breaking Strength lbs/inch (kg/cm) per Test Methods D5034 or D5035	Warp 200 (35.7) Fill 100 (17.9)	Warp 225 (40.19) Fill 175 (31.26)	Warp 225 (40.19) Fill 175 (31.26)
Tear Strength lbs (kg) per Test Method D5587	See ^A	Warp 40 (18.14) Fill 25 (11.33)	Warp 40 (18.14) Fill 25 (11.33)
Burst Strength psi (kg/cm ²) per Test Method D3786	Not Applicable	200 (14)	200 (14)
Abrasion Resistance per Test Method D3389	See ^A	CS-10 Wheel, 500g loads 500 revs, 15% weight loss max	CS-10 Wheel, 500g loads 500 revs, 15% weight loss max
Color	beige	Gray	Gray
Temperature Resistance °F (°C) per Test Method C1263	1000° F (538° C)	500° F (260° C)	600° F (315° C)
Flame Resistance Test Method D6413	See ^A	Char Length 1 inch max. (25.4cm) Afterglow 3 seconds max. Flame out 1 second max.	Char Length 1 inch max. (25.4cm) Afterglow 3 seconds max. Flame out 1 second max.

^AMeets **MIL-C-20079H**, Type 1, Class 9