
**Prevailing torque type steel hexagon
nuts — Mechanical and performance
properties**

Écrous hexagonaux autofreinés en acier — Caractéristiques mécaniques et performances

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 2320:1997

<https://standards.iteh.ai/catalog/standards/sist/78f1c59f-7edc-4c71-8538-9619516d9f74/iso-2320-1997>



Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

International Standard ISO 2320 was prepared by Technical Committee ISO/TC 2, *Fasteners*, Subcommittee SC 1, *Mechanical properties of fasteners*.

This third edition cancels and replaces the second edition (ISO 2320:1983), which has been technically revised.

Annexes A and B form an integral part of this International Standard. Annex C is for information only.

© ISO 1997

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Organization for Standardization
Case postale 56 • CH-1211 Genève 20 • Switzerland
Internet central@iso.ch
X.400 c=ch; a=400net; p=iso; o=isocs; s=central

Printed in Switzerland

Prevailing torque type steel hexagon nuts – Mechanical and performance properties

1 Scope

This International Standard specifies the mechanical and performance properties for prevailing torque type steel hexagon nuts (including those with flange) when tested over an ambient temperature range of 10 °C to 35 °C. Properties will vary at higher and lower temperature.

It applies to prevailing torque type nuts

- with nominal thread diameters up to and including 39 mm;
- of triangular ISO thread according to ISO 68;
- with diameter/pitch combinations according to ISO 261;
- with thread tolerances 6H according to ISO 965-2;
- with specific mechanical requirements;
- with dimensions as specified in product standards provided they make reference to this International Standard;
- within the temperature range –50 °C to +300 °C for all metal type nuts;
- within the temperature range –50 °C to +120 °C for non-metallic insert type nuts¹⁾.

It does not apply to nuts requiring special properties which may require special materials or coatings to improve

- weldability;
- corrosion resistance; <https://standards.iteh.ai/catalog/standards/sist/78f1c59f-7edc-4c71-8538-9619516d9f74/iso-2320-1997>
- performance outside the above specified temperature ranges.

Prevailing torque performance decreases with increasing re-use. The nut user should consider the implications of decreased performance prior to re-use.

NOTE — Information on torque/clamping force performance requirements and testing are given in the annex C. These functional requirements and the accompanying test procedure are still under discussion and cannot be specified mandatorily for the time being.

2 Normative references

The following standards contain provisions which, through reference in this text, constitute provisions of this International Standard. At the time of publication, the editions indicated were valid. All standards are subject to revision, and parties to agreements based on this International Standard are encouraged to investigate the possibility of applying the most recent editions of the standards indicated below. Members of IEC and ISO maintain registers of currently valid International Standards.

ISO 68-1 : –²⁾, *ISO general purpose screw threads – Basic profile – Part 1: Metric screw threads.*

ISO 261 : –³⁾, *ISO general purpose metric threads – General plan.*

1) By careful choice of non-metallic materials higher service temperature properties can be attained by agreement between user and manufacturer.

2) To be published. (Revision of ISO 68:1973)

3) To be published. (Revision of ISO 261:1973)

ISO 898-1:–⁴⁾, *Mechanical properties of fasteners made of carbon steel and alloy steel – Part 1: Bolts, screws and studs.*

ISO 898-2:1992, *Mechanical properties of fasteners – Part 2: Nuts with specified proof load values – Coarse thread.*

ISO 898-6:1994, *Mechanical properties of fasteners – Part 6: Nuts with specified proof load values – Fine pitch thread.*

ISO 965-2:–⁵⁾, *ISO general purpose metric screw threads – Tolerances – Part 2: Limits of sizes for general purpose bolt and nut threads – Medium quality.*

ISO 4042:–⁶⁾, *Fasteners – Electroplated castings.*

ISO 4753:–⁷⁾, *Fasteners – End of parts with external metric ISO thread.*

ISO 6506:1981, *Metallic materials – Hardness test – Brinell test.*

ISO 6507-1:–⁸⁾, *Metallic materials – Vickers hardness test – Part 1: Test method.*

ISO 6508:1986, *Metallic materials – Hardness test – Rockwell test (scales A – B – C – D – E – F – G – H – K).*

3 Definitions

For the purposes of this International Standard the following definitions apply.

3.1 prevailing torque type nut: Nut which is not free-running on a mating thread by virtue of a self-contained prevailing torque feature, and which provides a degree of resistance to rotation independent of clamping or compression forces.

3.2 prevailing torque developed by a nut: Torque necessary to rotate the nut on its mating, externally threaded component and with no axial load in the mating component.

4 Designation system

The property classes specified for prevailing torque type nuts are the same as specified in ISO 898-2 and ISO 898-6 for hexagon nuts, namely

– nuts with nominal heights $\geq 0,8 d$ (effective lengths of thread $\geq 0,6 d$) are designated by a number to indicate the maximum appropriate property class of bolts with which they may be mated, see table 1;

– nuts with nominal heights $\geq 0,5 d$ and $< 0,8 d$ (effective height of thread $\geq 0,4 d$ and $< 0,6 d$) are designated by a combination of two numbers: the second indicates the nominal stress under proof load on a hardened test mandrel, while the first indicates that the loadability of a bolt-nut assembly is reduced in comparison with the loadability on a hardened test mandrel and also in comparison with a bolt-nut assembly described in table 1. Table 2 gives the designation system and the stresses under proof load of these nuts.

4) To be published. (Revision of ISO 898-1:1988)

5) To be published. (Revision of ISO 965-2:1980)

6) To be published. (Revision of ISO 4042:1989)

7) To be published. (Revision of ISO 4753:1983)

8) To be published. (Revision of ISO 6507-1:1982; ISO 6507-2:1983; ISO 6507-3:1989; ISO 409-1:1982; ISO 409-2:1983 and ISO/DIS 409-3)

Table 1 — Designation system for nuts with nominal heights $\geq 0,8 d$

| Property class of the nut | Coarse thread | 5 | 6 | 8 | 9 | 10 | 12 |
|--|-------------------|------------|------------|------------|-------------------|--------------------|---------------------|
| | Fine pitch thread | — | 6 | 8 | — | 10 | 12 |
| Property class of the mating bolt or screw | | ≤ 5.8 | ≤ 6.8 | ≤ 8.8 | 9.8 ≤ 8.8 | 10.9 9.8 8.8 | 12.9 10.9 8.8 |

NOTE — In general, nuts of a higher property class can replace nuts of lower property class. However it is not recommended that a heat-treated all-metal nut be combined with a bolt of lower property class.

Table 2 — Designation system and stresses under proof load for nuts with nominal heights $\geq 0,5 d$ and $< 0,8 d$

| Property class of nut | Nominal stress under proof load | Actual stress under proof load |
|-----------------------|---------------------------------|--------------------------------|
| | N/mm ² | N/mm ² |
| 04 | 400 | 380 |
| 05 | 500 | 500 |

iTeh STANDARD PREVIEW (standards.iteh.ai)

5 Materials and processes

5.1 Materials

ISO 2320:1997

Nuts shall be made of steel conforming to the chemical composition limits specified in table 3. The prevailing torque element of insert-type nuts may be made of a material other than steel. It is recommended that users and manufacturers consider the maximum limits for sulphur, manganese, boron and other intentionally added elements which may result in component failure, when in excessive amounts.

Table 3 — Limits of chemical composition

| Property class | | Chemical composition limit (check analysis), % | | | |
|-------------------------------------|-------------------|---|------------|-----------|-----------|
| Coarse thread | Fine pitch thread | C max. | Mn min. | P max. | S min. |
| 5 ¹⁾ ; 6 ¹⁾ | 6 | 0,50 | — | 0,060 | 0,150 |
| 8; 9; 04 ¹⁾ | 8 | 0,58 | 0,25 | 0,060 | 0,150 |
| 10 ²⁾ ; 05 ²⁾ | 10 ²⁾ | 0,58 | 0,30 | 0,048 | 0,058 |
| 12 ²⁾ | 12 ²⁾ | 0,58 | 0,45 | 0,048 | 0,058 |

1) Nuts may be manufactured from free cutting steel, unless otherwise agreed between the user and the manufacturer. In such cases the following maximum sulfur, phosphorus and lead contents are permissible:
S 0,34 %, P 0,11 % and Pb 0,35 %.

2) Alloying elements may be added if necessary to develop the mechanical properties of the nuts.

5.2 Heat treatment

5.2.1 Nuts with coarse thread

Nuts of property classes 05, 8 (style 1, > M16), 10 and 12 shall be quenched and tempered. Case hardening is not allowed for any property class.

5.2.2 Nuts with fine pitch thread

Nuts of property classes 05, 8 (style 1), 10 and 12 shall be quenched and tempered. Case hardening is not allowed for any property class.

5.3 Thread

The thread of the prevailing torque type nuts must conform to ISO 965-2 except for the prevailing torque element.

In the case of prevailing torque type nuts with non-metallic insert, the go gauge must be capable of being screwed in freely by hand as far as the insert.

In the case of all-metal nuts the go gauge must be capable of being screwed in freely by hand for at least one thread.

5.4 Finish

iTeh STANDARD PREVIEW
(standards.iteh.ai)

All-metal nuts shall be lubricated and nuts with non-metallic insert may be lubricated to meet the stated performance requirements. The lubricant shall not constitute a health hazard to the user, nor emit an unpleasant odour during assembly and shall be suitable for automatic or robotic assembly.

<https://standards.iteh.ai/catalog/standards/sist/78f1c59f-7edc-4c71-8538->

Lubricant, when used, must be suitable for assembly speeds from 10 to 500 r/min.

The performance of nuts which are supplied with a protective coating and/or lubricant shall not deteriorate when the nuts are stored indoors for a period of six months. The storage temperature shall be within the range $-5\text{ }^{\circ}\text{C}$ to $+40\text{ }^{\circ}\text{C}$.

NOTE — In the case where nuts are given a protective coating or cleaning following delivery to the user, the nut manufacturer shall not be held responsible for failure of the nut to meet dimensional, mechanical or performance properties traceable to the plating or coating.

5.5 Hydrogen embrittlement

For hydrogen embrittlement see ISO 4042.

6 Mechanical properties

When tested by methods described in 8.1 and 8.2, the nuts shall have the mechanical properties set out in tables 4 and 5.

Nuts shall withstand the proof load values specified in tables 6 and 7 for the applicable property class when tested as specified in 8.1.

Table 4 — Mechanical properties, coarse thread

| Thread mm | | Property class | | | | | | | | | | |
|--------------|-----|---|------------------------|---|-------------------------------|------------------------|---|--------------|------------------------|---|-----------------------|-------|
| | | 04 | | | | | 05 | | | | | |
| over | to | Stress under proof load σ_p N/mm ² | Vickers hardness HV | Stress under proof load σ_p N/mm ² | Nut state | Vickers hardness HV | Stress under proof load σ_p N/mm ² | Nut state | Vickers hardness HV | Stress under proof load σ_p N/mm ² | Nut state | style |
| | M4 | | | | | | | | | | | |
| | M7 | | | | neither quenched nor tempered | | | | | | quenched and tempered | |
| | M10 | 380 | 188 | 500 | thin | 272 | 500 | 353 | 200 | 890 | 302 | thin |
| | M16 | | | | | | | | | | | |
| | M39 | | | | | | | | | | | |

| Thread mm | | Property class | | | | | | | | | | | | |
|--------------|-----|---|------------------------|---|-------------------------------|------------------------|---|-----------------------|------------------------|---|--------------|-------------------------------|--|--|
| | | 5 ^H | | | | | 6 | | | | | 8 | | |
| over | to | Stress under proof load σ_p N/mm ² | Vickers hardness HV | Stress under proof load σ_p N/mm ² | Nut state | Vickers hardness HV | Stress under proof load σ_p N/mm ² | Nut state | Vickers hardness HV | Stress under proof load σ_p N/mm ² | Nut state | style | | |
| | M4 | 520 | | 600 | | | 800 | | 180 | | | | | |
| | M7 | 580 | | 670 | | | 855 | | 200 | | | | | |
| | M10 | 590 | | 680 | | | 870 | | 302 | | | | | |
| | M16 | 610 | 130 | 700 | neither quenched nor tempered | 150 | 880 | 1 | 233 | 890 | 353 | 1 | | |
| | M39 | 630 | 146 | 720 | 720 | 170 | 920 | quenched and tempered | 302 | 890 | 302 | neither quenched nor tempered | | |

Table 4 (concluded)

| Thread mm | 9 ¹⁾ | | | | 10 | | | | 12 | | | |
|--------------|------------------------------------|---------------------|-------------------------------|------------------------------------|---------------------|-----------------------|------------------------------------|---------------------|-----------------------|------------------------------------|---------------------|-----------------------|
| | Stress under proof load σ_p | Vickers hardness HV | Nut | Stress under proof load σ_p | Vickers hardness HV | Nut | Stress under proof load σ_p | Vickers hardness HV | Nut | Stress under proof load σ_p | Vickers hardness HV | Nut |
| over to | N/mm ² | min. max. | state | N/mm ² | min. max. | state | N/mm ² | min. max. | state | N/mm ² | min. max. | state |
| M4 | 900 | 170 | neither quenched nor tempered | 1 040 | | quenched and tempered | 1 140 | | quenched and tempered | 1 150 | | quenched and tempered |
| M7 | 915 | | | 1 040 | | | 1 140 | | | 1 150 | | |
| M10 | 940 | | 2 | 1 040 | 272 | | 1 140 | 295 | 1 | 1 160 | 272 | 1 |
| M16 | 950 | 188 | | 1 050 | 353 | | 1 170 | 353 | | 1 190 | 353 | |
| M39 | 920 | | | 1 060 | | | | | | 1 200 | | |

NOTE — Minimum hardness is mandatory only for heat-treated nuts and nuts too large to be proof-load tested. For all other nuts, minimum hardness is not mandatory but is provided for guidance only. For nuts which are not quenched and tempered, and which satisfy the proof load test, minimum hardness shall not be cause for rejection.

1) The maximum bolt hardness of property classes 5.6 and 5.8 will be changed to be 220 HV in the next revision of ISO 898-1 as this is the maximum bolt hardness in the thread engagement area whereas only the thread end or the head may have a maximum hardness of 250 HV. Therefore the values of stress under proof load are based on a maximum bolt hardness of 220 HV.

Table 5 — Mechanical properties, fine pitch thread

| Nominal thread diameter d mm | Property class 04 | | | | Property class 05 | | | | |
|-----------------------------------|--|---------------------------------------|---|--|---------------------------------------|---------------------------------------|--|---------------------------------------|----------------------|
| | Stress under proof load S_p N/mm ² | Vickers hardness HV min. max. | Nut state neither quenched nor tempered | Stress under proof load S_p N/mm ² | Vickers hardness HV min. max. | Nut state quenched and tempered | Stress under proof load S_p N/mm ² | Vickers hardness HV min. max. | Nut state thin |
| $8 \leq d \leq 39$ | 380 | 188 302 | | 500 | 272 353 | quenched and tempered | | | |

| Nominal thread diameter d mm | Property class 6 | | | | Property class 8 | | | | |
|-----------------------------------|--|---------------------------------------|---|--|---------------------------------------|---------------------------------------|--|---------------------------------------|---|
| | Stress under proof load S_p N/mm ² | Vickers hardness HV min. max. | Nut state neither quenched nor tempered ¹⁾ | Stress under proof load S_p N/mm ² | Vickers hardness HV min. max. | Nut state quenched and tempered | Stress under proof load S_p N/mm ² | Vickers hardness HV min. max. | Nut state neither quenched nor tempered |
| $8 \leq d \leq 10$ | 770 | 188 | | 955 | 250 353 | quenched and tempered | 890 | 195 302 | neither quenched nor tempered |
| $10 < d \leq 16$ | 780 | 233 | 1 | 1 030 | 295 | tempered | — | — | — |
| $16 < d \leq 33$ | 870 | | | 1 090 | | | | | |
| $33 < d \leq 39$ | 930 | | | | | | | | |

| Nominal thread diameter d mm | Property class 10 | | | | Property class 12 | | | | |
|-----------------------------------|--|---------------------------------------|---------------------------------------|--|---------------------------------------|---------------------------------------|--|---------------------------------------|---------------------------------------|
| | Stress under proof load S_p N/mm ² | Vickers hardness HV min. max. | Nut state quenched and tempered | Stress under proof load S_p N/mm ² | Vickers hardness HV min. max. | Nut state quenched and tempered | Stress under proof load S_p N/mm ² | Vickers hardness HV min. max. | Nut state quenched and tempered |
| $8 \leq d \leq 10$ | 1 100 | 295 353 | quenched and tempered | 1 055 | 250 353 | quenched and tempered | 1 200 | 295 353 | quenched and tempered |
| $10 < d \leq 16$ | 1 100 | | | 1 080 | 260 | tempered | — | — | — |
| $16 < d \leq 39$ | — | | | | | | | | |

NOTE — Minimum hardness is mandatory for heat-treated nuts and for nuts too large to be proof-load tested. For all other nuts, minimum hardness is not mandatory but is provided for guidance only. For nuts which are not quenched and tempered, and which satisfy the proof-load test, minimum hardness shall not be cause for rejection.

1) For thread diameters above 16 mm, nuts may be quenched and tempered at the discretion of the manufacturer.

Table 6 — Proof load values – Coarse thread
(see also ISO 898-2)

| Thread | Pitch of the thread mm | Nominal stress area of the mandrel A_s mm ² | Property class | | | | | | | | | |
|--------|---------------------------|--|--------------------------------------|---------|---------|---------|---------|---------|---------|-----------|---------|-----------|
| | | | 04 | 05 | 5 | 6 | 8 | | 9 | 10 | 12 | |
| | | | Proof load ($A_s \times S_p$) N | | | | | | | | | |
| | | thin | thin | style 1 | style 1 | style 1 | style 2 | style 2 | style 1 | style 1 | style 2 | |
| M3 | 0,5 | 5,03 | 1 910 | 2 500 | 2 600 | 3 000 | 4 000 | – | 4 500 | 5 200 | 5 700 | 5 800 |
| M4 | 0,7 | 8,78 | 3 340 | 4 400 | 4 550 | 5 250 | 7 000 | – | 7 900 | 9 150 | 10 000 | 10 100 |
| M5 | 0,8 | 14,2 | 5 400 | 7 100 | 8 250 | 9 500 | 12 140 | – | 13 000 | 14 800 | 16 200 | 16 300 |
| M6 | 1 | 20,1 | 7 640 | 10 000 | 11 700 | 13 500 | 17 200 | – | 18 400 | 20 900 | 22 900 | 23 100 |
| M7 | 1 | 28,9 | 11 000 | 14 500 | 16 800 | 19 400 | 24 700 | – | 26 400 | 30 100 | 32 900 | 33 200 |
| M8 | 1,25 | 36,6 | 13 900 | 18 300 | 21 600 | 24 900 | 31 800 | – | 34 400 | 38 100 | 41 700 | 42 500 |
| M10 | 1,5 | 58,0 | 22 000 | 29 000 | 34 200 | 39 400 | 50 500 | – | 54 500 | 60 300 | 66 100 | 67 300 |
| M12 | 1,75 | 84,3 | 32 000 | 42 200 | 51 400 | 59 000 | 74 200 | – | 80 100 | 88 500 | 98 600 | 100 300 |
| M14 | 2 | 115 | 43 700 | 57 500 | 70 200 | 80 500 | 101 200 | – | 109 300 | 120 800 | 134 600 | 136 900 |
| M16 | 2 | 157 | 59 700 | 78 500 | 95 800 | 109 900 | 138 200 | – | 149 200 | 164 900 | 183 700 | 186 800 |
| M18 | 2,5 | 192 | 73 000 | 96 000 | 121 000 | 138 200 | 176 600 | 170 900 | 176 000 | 203 500 | – | 230 400 |
| M20 | 2,5 | 245 | 93 100 | 122 500 | 154 400 | 176 400 | 225 400 | 218 100 | 225 400 | 259 700 | – | 294 000 |
| M22 | 2,5 | 303 | 115 100 | 151 500 | 190 900 | 218 200 | 278 800 | 269 700 | 278 800 | 321 200 | – | 363 600 |
| M24 | 3 | 353 | 134 100 | 176 500 | 222 400 | 254 200 | 324 800 | 314 200 | 324 800 | 374 200 | – | 423 600 |
| M27 | 3 | 459 | 174 400 | 229 500 | 289 200 | 330 500 | 422 300 | 408 500 | 422 300 | 486 500 | – | 550 800 |
| M30 | 3,5 | 561 | 213 200 | 280 500 | 353 400 | 403 900 | 516 100 | 499 300 | 516 100 | 594 700 | – | 673 200 |
| M33 | 3,5 | 694 | 263 700 | 347 000 | 437 200 | 499 700 | 638 500 | 617 700 | 638 500 | 735 600 | – | 832 800 |
| M36 | 4 | 817 | 310 500 | 408 500 | 514 700 | 588 200 | 751 600 | 727 100 | 751 600 | 866 000 | – | 980 400 |
| M39 | 4 | 976 | 370 900 | 488 000 | 614 900 | 702 700 | 897 900 | 868 600 | 897 900 | 1 035 000 | – | 1 171 000 |

(standards.iteh.ai)
Table 7 — Proof load values – Fine pitch thread
(see also ISO 898-6)
ISO 2320:1997

| Thread $d \times P^{(1)}$ | Nominal stress area of the mandrel A_s mm ² | Property class | | | | | | | | | |
|------------------------------|--|--------------------------------------|---------|---------|-----------|---------|---------|-----------|---------|--|--|
| | | 04 | 05 | 6 | 8 | | 10 | | 12 | | |
| | | Proof load ($A_s \times S_p$) N | | | | | | | | | |
| | | thin | thin | style 1 | style 1 | style 2 | style 1 | style 2 | style 2 | | |
| M8 × 1 | 39,2 | 14 900 | 19 600 | 30 200 | 37 400 | 34 900 | 43 100 | 41 300 | 47 000 | | |
| M10 × 1 | 64,5 | 24 500 | 32 200 | 49 600 | 61 600 | 57 400 | 71 000 | 68 000 | 77 400 | | |
| M10 × 1,25 | 61,2 | 23 300 | 30 600 | 47 100 | 58 400 | 54 500 | 67 300 | 64 600 | 73 400 | | |
| M12 × 1,25 | 92,1 | 35 000 | 46 000 | 71 800 | 88 000 | 82 000 | 102 200 | 97 200 | 110 500 | | |
| M12 × 1,5 | 88,1 | 33 500 | 44 000 | 68 700 | 84 100 | 78 400 | 97 800 | 92 900 | 105 700 | | |
| M14 × 1,5 | 125 | 47 500 | 62 500 | 97 500 | 119 400 | 111 200 | 138 700 | 131 900 | 150 000 | | |
| M16 × 1,5 | 167 | 63 500 | 83 500 | 130 300 | 159 500 | 148 600 | 185 400 | 176 200 | 200 400 | | |
| M18 × 1,5 | 215 | 81 700 | 107 500 | 187 000 | 221 500 | – | – | 232 200 | – | | |
| M18 × 2 | 204 | 77 500 | 102 000 | 177 500 | 210 100 | – | – | 220 300 | – | | |
| M20 × 1,5 | 272 | 103 400 | 136 000 | 236 600 | 280 200 | – | – | 293 800 | – | | |
| M20 × 2 | 258 | 98 000 | 129 000 | 224 500 | 265 700 | – | – | 278 600 | – | | |
| M22 × 1,5 | 333 | 126 500 | 166 500 | 289 700 | 343 000 | – | – | 359 700 | – | | |
| M22 × 2 | 318 | 120 800 | 159 000 | 276 700 | 327 500 | – | – | 343 400 | – | | |
| M24 × 2 | 384 | 145 900 | 192 000 | 334 100 | 395 500 | – | – | 414 700 | – | | |
| M27 × 2 | 496 | 188 500 | 248 000 | 431 500 | 510 900 | – | – | 535 700 | – | | |
| M30 × 2 | 621 | 236 000 | 310 500 | 540 300 | 639 600 | – | – | 670 600 | – | | |
| M33 × 2 | 761 | 289 200 | 380 500 | 662 100 | 783 800 | – | – | 821 900 | – | | |
| M36 × 3 | 865 | 328 700 | 432 500 | 804 400 | 942 800 | – | – | 934 200 | – | | |
| M39 × 3 | 1 030 | 391 400 | 515 000 | 957 900 | 1 123 000 | – | – | 1 112 000 | – | | |

P is the pitch of thread

Table 8 — Clamping forces and prevailing torques for hexagon nuts and hexagon nuts with flange with coarse thread

| Thread (d) | Clamping force, kN | | | | | | | | | | | | Prevailing torque, N.m | | | | | | | | | |
|---------------|--------------------|------|------|------|------|------|------|------|--------------------------------------|-----------------------|-----------------------|--------------------------------------|------------------------------------|-----------------------|--|--|--|--------------------------------|--|--|--|--|
| | Property class | | | | | | | | | | | | Property classes 04, 5, 6, 8 and 9 | | | | | Property classes 05, 10 and 12 | | | | |
| | 04 | 05 | 5 | 6 | 8 | 9 | 10 | 12 | First assembly ¹⁾ max. | First removal min. | Fifth removal min. | First assembly ²⁾ max. | First removal min. | Fifth removal min. | | | | | | | | |
| M3 | 1,4 | 1,9 | 1,4 | 1,7 | 2,2 | 2,5 | 3,1 | 3,7 | 0,43 | 0,12 | 0,08 | 0,6 | 0,15 | 0,1 | | | | | | | | |
| M4 | 2,5 | 3,3 | 2,5 | 2,9 | 3,8 | 4,3 | 5,5 | 6,4 | 0,9 | 0,18 | 0,12 | 1,2 | 0,22 | 0,15 | | | | | | | | |
| M5 | 4 | 5,2 | 4 | 4,7 | 6,2 | 6,9 | 8,9 | 10,4 | 1,6 | 0,29 | 0,2 | 2,1 | 0,35 | 0,24 | | | | | | | | |
| M6 | 5,7 | 7,4 | 5,7 | 6,6 | 8,7 | 9,8 | 12,5 | 14,6 | 3 | 0,45 | 0,3 | 4 | 0,55 | 0,4 | | | | | | | | |
| M7 | 8,2 | 10,7 | 8,3 | 9,5 | 12,6 | 14,1 | 18,0 | 21,0 | 4,5 | 0,65 | 0,45 | 6 | 0,85 | 0,6 | | | | | | | | |
| M8 | 10,3 | 13,5 | 10,4 | 12,1 | 15,9 | 17,8 | 22,8 | 26,6 | 6 | 0,85 | 0,6 | 8 | 1,15 | 0,8 | | | | | | | | |
| M10 | 16,4 | 21,5 | 16,5 | 19,1 | 25,3 | 28,3 | 36,1 | 42,4 | 10,5 | 1,5 | 1 | 14 | 2 | 1,4 | | | | | | | | |
| M12 | 23,8 | 31,2 | 24 | 27,8 | 36,7 | 41,1 | 52,5 | 61,4 | 15,5 | 2,3 | 1,6 | 21 | 3,1 | 2,1 | | | | | | | | |
| M14 | 32,5 | 42,5 | 32,8 | 38 | 50 | 56,1 | 71,6 | 84 | 24 | 3,3 | 2,3 | 31 | 4,4 | 3 | | | | | | | | |
| M16 | 44,4 | 58 | 45 | 51,8 | 68,2 | 76,5 | 97,5 | 114 | 32 | 4,5 | 3 | 42 | 6 | 4,2 | | | | | | | | |
| M18 | 56,1 | 73 | 55 | 63,4 | 86,2 | — | 119 | 140 | 42 | 6 | 4,2 | 56 | 8 | 5,5 | | | | | | | | |
| M20 | 71,7 | 94 | 70 | 81 | 110 | — | 152 | 178 | 54 | 7,5 | 5,3 | 72 | 10,5 | 7 | | | | | | | | |
| M22 | 88,7 | 116 | 86 | 100 | 136 | — | 189 | 220 | 68 | 9,5 | 6,5 | 90 | 13 | 9 | | | | | | | | |
| M24 | 103 | 135 | 101 | 116 | 159 | — | 220 | 256 | 80 | 11,5 | 8 | 106 | 15 | 10,5 | | | | | | | | |
| M27 | 134 | 175 | 107 | 152 | 206 | — | 286 | 334 | 94 | 13,5 | 10 | 123 | 17 | 12 | | | | | | | | |
| M30 | 164 | 215 | 131 | 185 | 253 | — | 350 | 408 | 108 | 16 | 12 | 140 | 19 | 14 | | | | | | | | |
| M33 | 203 | 265 | 161 | 229 | 312 | — | 432 | 505 | 122 | 18 | 14 | 160 | 21,5 | 15,5 | | | | | | | | |
| M36 | 234 | 306 | 190 | 269 | 368 | — | 509 | 594 | 136 | 21 | 16 | 180 | 24 | 17,5 | | | | | | | | |
| M39 | 285 | 373 | 227 | 322 | 440 | — | 608 | 710 | 150 | 23 | 18 | 200 | 26,5 | 19,5 | | | | | | | | |

NOTES

1 The clamping forces for property class 5 nuts are equal to 75 % of the proof loads of property class 5.8 bolts for nominal diameters $d = 3$ mm to 24 mm inclusive, and 75 % of the proof loads of property class 4.8 bolts for nominal diameters $d \geq 24$ mm. The clamping forces for property class 6, 8, 9, 10 and 12 nuts are equal to 75 % of the proof loads of property class 6.8, 8.8, 9.8, 10.9 and 12.9 bolts, respectively. Proof loads of bolts are given in ISO 898-1.

2 The evaluation of results from the prevailing torque test by statistical process control (SPC) methods has no statistical relevance.

1) The prevailing torques for the first assembly apply for all-metal nuts only. For nuts with non-metallic insert the maximum torques for the first assembly shall be 50 % of these values.