

INTERNATIONAL
STANDARD

ISO
19935-2

First edition
2020-09

Plastics — Temperature modulated DSC —

Part 2: Measurement of specific heat capacity c_p

iTech Standards
Plastiques — DSC à température modulée —
Partie 2: Mesurage précis de la chaleur spécifique c_p
(<https://standards.iteh.ai>)
Document Preview

[ISO 19935-2:2020](#)
<https://standards.iteh.ai/catalog/standards/iso/7b61f0c8-b29c-42e6-9c1c-26d814b8ba68/iso-19935-2-2020>



Reference number
ISO 19935-2:2020(E)

© ISO 2020

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

[ISO 19935-2:2020](#)

<https://standards.iteh.ai/catalog/standards/iso/7b61f0c8-b29c-42e6-9c1c-26d814b8ba68/iso-19935-2-2020>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2020

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Symbols and abbreviated terms	1
4.1 Temperature modulation, $T(t)$	1
4.2 Scanning rate	1
4.3 Heat flow rate, $\Phi(t)$	1
5 Principles of determination of specific heat capacity with temperature modulated DSC	2
5.1 General	2
5.2 Specific heat capacity with no processes	2
5.3 Reversing and non-reversing specific heat capacity	2
5.4 Step scan method	2
5.5 Multiple frequencies	2
6 Apparatus and materials	2
6.1 General	2
6.2 Temperature control of the modulated differential scanning calorimeter	2
7 Calibration	3
7.1 General	3
7.2 Calibration of modulation amplitude	3
7.3 Calibration of phase	3
8 Procedure	3
8.1 General	3
8.2 Calculation of the specific heat capacity	4
8.3 Examples of the results	4
8.3.1 Modulated heat flow rate and scanning rate of modulation	4
8.3.2 Determination of specific heat capacity	5
9 Precision and bias	6
10 Test report	7
Annex A (informative) Example of the c_p values of polystyrene (PS)	8
Annex B (informative) Example of the calibration constant $K(\omega)$ determined with the literature values of $\alpha\text{-Al}_2\text{O}_3$ [3]	10
Annex C (informative) Example of a reversing heat flow rate curve based on a modulated heat flow rate curve and a comparison with the specific heat capacity	11
Annex D (informative) Example of determination of specific heat capacity based on a multifrequency modulated heat flow rate curve	12
Bibliography	14

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 5, *Physical-chemical properties*.

A list of all parts in the ISO 19935 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

This document describes the realization of standardized thermoanalytical test methods which can be used for the determination of specific heat capacity data needed for data sheets or databases as well as for research purposes. It can also be applied to quality assurance or to routine checks of raw materials and finished products, if desired. The procedures mentioned in this document apply as long as special product standards or standards describing special atmospheres for conditioning of samples do not require alternate regulations.

For scientific investigations or resolution of special analytical problems, all technical capabilities of the instruments beyond the regulations of this document may be used.

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

[ISO 19935-2:2020](#)

<https://standards.iteh.ai/catalog/standards/iso/7b61f0c8-b29c-42e6-9c1c-26d814b8ba68/iso-19935-2-2020>

Plastics — Temperature modulated DSC —

Part 2: Measurement of specific heat capacity c_p

1 Scope

This document establishes a method for measurement of specific heat capacity, c_p , using temperature modulated differential scanning calorimetry.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 472, *Plastics — Vocabulary*

ISO 11357-1, *Plastics — Differential scanning calorimetry (DSC) — Part 1: General principles*

ISO 19935-1, *Plastics — Temperature modulated DSC — Part 1: General principles*

ISO 80000-5, *Quantities and units — Part 5: Thermodynamics*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 472, ISO 11357-1, ISO 19935-1 and ISO 80000-5 apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

4 Symbols and abbreviated terms

4.1 Temperature modulation, $T(t)$

According to ISO 19935-1.

4.2 Scanning rate

According to ISO 19935-1.

4.3 Heat flow rate, $\Phi(t)$

According to ISO 19935-1.

5 Principles of determination of specific heat capacity with temperature modulated DSC

5.1 General

The use of temperature modulated DSC is advantageous for the measurement of specific heat capacity not only outside the region of a transition, because it does not require a stable baseline to achieve high accuracy. The measurement of specific heat capacity is only based on the amplitude of the modulated heat flow rate signal.

5.2 Specific heat capacity with no processes

According to ISO 19935-1.

5.3 Reversing and non-reversing specific heat capacity

According to ISO 19935-1.

5.4 Step scan method

In the step scan method, the isothermal line is called iso-kinetic (iso-K) base line. Specific heat capacity, c_p , can be determined by integrating the heat flow rate $\Phi(t)$ in one cycle as [Formula \(1\)](#):

$$c_p = \frac{1}{m\Delta T} \int_{t_0}^{t_e} \Phi(t) dt \quad (1)$$

where

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

m is the mass of the sample;

ΔT is a temperature step; [ISO 19935-2:2020](#)

<https://standards.iteh.ai/catalog/standards/iso/7b61f0c8-b29c-42e6-9c1c-26d814b8ba68/iso-19935-2-2020>
 t_e, t_0 is a time interval in one period.

5.5 Multiple frequencies

Assuming the linear response theory, the input of multiple frequencies or random pulses as a modulated heat source are analysed with the procedures in the ISO 19935-1. An example is shown in [Annex D](#).

6 Apparatus and materials

6.1 General

Use the apparatus according to ISO 19935-1.

6.2 Temperature control of the modulated differential scanning calorimeter

Specifications of temperature control required for temperature modulated DSC are added as follows.

- a) Capability to vary temperature periodically, or stepwise, or by an input of a pulse sequence with an amplitude, typically in the range of ($\pm 0,1$ to $2,0$) K, and a frequency, typically down to 10 mHz, superimposed on the underlying rate, typically less than 3 K/min.

- b) Depending on the relation of the underlying scanning rate β_0 to the amplitude of sample temperature profile $T_A\omega$ (where ω the angular frequency) four cases of scanning rates are distinguished.
 - 1) Quasi-isothermal mode, $\beta_0 = 0$. If $\beta_0 = 0$, heat capacity can be measured as function of time, e.g. during chemical reactions like curing or during crystallization. All other calorimetric methods measure heat capacity as function of temperature only.
 - 2) For other modes, such as $T_A\omega > \beta_0$, $T_A\omega < \beta_0$, and $T_A\omega = \beta_0$, refer to ISO 19935-1.
- c) Any mode of temperature modulation specified in ISO 19935-1 can be used.

7 Calibration

7.1 General

According to ISO 19935-1.

7.2 Calibration of modulation amplitude

According to ISO 19935-1.

7.3 Calibration of phase

According to ISO 19935-1.

iTeh Standards

8 Procedure (<https://standards.iteh.ai>)

8.1 General

Document Preview

The procedures of temperature modulated DSC (setting up the apparatus, loading the specimen into the crucibles, insertion of crucibles into the instrument, performing measurements, and removal of crucibles) shall be in accordance with ISO 11357-1.<https://standards.iteh.ai>

The experimental conditions specified for temperature modulated DSC (for example, amplitude of the modulated heat flow rate, amplitude of modulated temperature, and the frequency of the modulation superimposed on the underlying rate) to be used depend on the magnitude of the specific heat capacity to be determined.

8.2 Calculation of the specific heat capacity

Specific heat capacity is calculated as [Formula \(2\)](#):

$$c_p = \frac{\Phi_A}{m \cdot T_A \cdot \omega} \cdot K(\omega) \quad (2)$$

where

- c_p is the specific heat capacity of the specimen, in $\text{Jg}^{-1}\text{K}^{-1}$;
- T_A is the amplitude of sample temperature profile, in K;
- Φ_A is the amplitude of the periodic part of the modulated heat flow rate, in mW;
- m is the mass of the specimen, in mg;
- ω is the angular frequency of the modulated temperature, in rad/s; $\omega = 2\pi f$, where f is the frequency in Hz;
- $K(\omega)$ is the calibration constant calculated according to the definition in ISO 19953-1. For precise measurements, ω shall be low (typically $\omega < 60$ mrad/s), so that $K(\omega)$ becomes independent on ω .

For the case of step scan mode, [Formula \(1\)](#) shall be used to calculate c_p .

8.3 Examples of the results

8.3.1 Modulated heat flow rate and scanning rate of modulation

[Figure 1](#) shows a typical example of modulated temperature and scanning rate (of modulation) derived by a derivative of modulated temperature of a sinusoidal waveform for the heat flux DSC plotted vs time. The scanning rate of modulation is measured as a sinusoidal wave.