
Praškasti premazi - 3. del: Določanje gostote s piknometrom z izpodrivom tekočine (ISO/DIS 8130-3:2020)

Coating powders - Part 3: Determination of density by liquid displacement pyknometer (ISO/DIS 8130-3:2020)

Pulverlacke - Teil 3: Bestimmung der Dichte mit einem Pyknometer durch Flüssigkeitsverdrängung (ISO/DIS 8130-3:2020)

Poudres pour revêtement - Partie 3: Détermination de la masse volumique à l'aide d'un pycnomètre à déplacement de liquide (ISO/DIS 8130-3:2020)

<https://standards.iteh.ai/catalog/standards/sist/a5eb238b-ce1d-44ef-af8b-b35786e74b7a/osist-pr-en-iso-8130-3-2020>

Ta slovenski standard je istoveten z: prEN ISO 8130-3

ICS:

87.040

Barve in laki

Paints and varnishes

oSIST prEN ISO 8130-3:2020**en,fr,de**

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[oSIST prEN ISO 8130-3:2020](https://standards.iteh.ai/catalog/standards/sist/a5eb238b-ce1d-44ef-af8b-b35786c7fb7a/osist-pren-iso-8130-3-2020)

<https://standards.iteh.ai/catalog/standards/sist/a5eb238b-ce1d-44ef-af8b-b35786c7fb7a/osist-pren-iso-8130-3-2020>

DRAFT INTERNATIONAL STANDARD

ISO/DIS 8130-3

ISO/TC 35/SC 9

Secretariat: BSI

Voting begins on:
2020-09-22Voting terminates on:
2020-12-15

Coating powders —

Part 3: Determination of density by liquid displacement pycnometer

*Poudres pour revêtement —**Partie 3: Détermination de la masse volumique à l'aide d'un pycnomètre à déplacement de liquide*

ICS: 87.040

iTeh STANDARD PREVIEW (standards.iteh.ai)

[oSIST prEN ISO 8130-3:2020](https://standards.iteh.ai/catalog/standards/sist/a5eb238b-ce1d-44ef-af8b-b35786c7fb7a/osist-pren-iso-8130-3-2020)<https://standards.iteh.ai/catalog/standards/sist/a5eb238b-ce1d-44ef-af8b-b35786c7fb7a/osist-pren-iso-8130-3-2020>

THIS DOCUMENT IS A DRAFT CIRCULATED FOR COMMENT AND APPROVAL. IT IS THEREFORE SUBJECT TO CHANGE AND MAY NOT BE REFERRED TO AS AN INTERNATIONAL STANDARD UNTIL PUBLISHED AS SUCH.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

This document is circulated as received from the committee secretariat.



Reference number
ISO/DIS 8130-3:2020(E)

© ISO 2020

iTeh STANDARD PREVIEW (standards.iteh.ai)

[oSIST prEN ISO 8130-3:2020
https://standards.iteh.ai/catalog/standards/sist/a5eb238b-ce1d-44ef-af8b-
b35786c7fb7a/osist-pren-iso-8130-3-2020](https://standards.iteh.ai/catalog/standards/sist/a5eb238b-ce1d-44ef-af8b-b35786c7fb7a/osist-pren-iso-8130-3-2020)



COPYRIGHT PROTECTED DOCUMENT

© ISO 2020

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword.....	iv
1 Scope.....	1
2 Normative references.....	1
3 Terms and definitions.....	1
4 Principle.....	1
5 Materials.....	1
6 Apparatus.....	2
7 Sampling.....	2
8 Procedure.....	2
8.1 Number of determinations.....	2
8.2 Determination of the density of the displacement liquid.....	2
8.3 Determination of the density of the coating powder.....	2
9 Expression of results.....	3
10 Precision.....	3
11 Test report.....	3
Bibliography.....	4

iTeh STANDARD PREVIEW
(standards.iteh.ai)

<https://standards.iteh.ai/catalog/standards/sist/a5eb238b-cc1d-44ef-af8b-b35786c7fb7a/osist-pren-iso-8130-3-2020>

ISO/DIS 8130-3:2020(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 35, *Paints and varnishes*, Subcommittee SC 9, *General test methods for paints and varnishes*.

This second edition cancels and replaces the first edition (ISO 8130-3:1992), which has been technically revised. The main changes compared to the previous edition are as follows:

- a) the scope has been revised editorially;
- b) a terms and definitions clause has been added;
- c) the reference for the pycnometer has been changed from ISO 787-10 ^[1] to ISO 2811-1;
- d) the use of acetone for cleaning the pycnometer has been deleted;
- e) the order of filling the pycnometer has been changed;
- f) the text has been editorially revised and the normative references have been updated.

A list of all parts in the ISO 8130, *Coating powders*, series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Coating powders —

Part 3: Determination of density by liquid displacement pycnometer

1 Scope

This document specifies a liquid displacement pycnometer method for the determination of the density of coating powders. The method is based on a determination of the mass and the volume of a test portion.

Coating powders with density $< 1 \text{ g/cm}^3$, may be measured in accordance with ISO 1183-1 and the appropriate method, by agreement.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1183-1, *Plastics — Methods for determining the density of non-cellular plastics — Part 1: Immersion method, liquid pycnometer method and titration method* 3:2020

ISO 2811-1, *Paints and varnishes — Determination of density — Part 1: Pycnometer method*

ISO 3696, *Water for analytical laboratory use — Specification and test methods*

ISO 8130-14, *Coating powders — Part 14: Vocabulary*

ISO 15528, *Paints, varnishes and raw materials for paints and varnishes — Sampling*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 8130-14 apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <https://www.iso.org/obp>

4 Principle

The density of the coating powder is determined in a liquid displacement pycnometer, using a liquid that completely wets the product under test without swelling or dissolving it.

5 Materials

5.1 Water, of at least grade 3 purity as defined in ISO 3696, freshly boiled and cooled.

ISO/DIS 8130-3:2020(E)

5.2 Displacement liquid: a suitable aliphatic hydrocarbon or mixture of aliphatic hydrocarbons, free from aromatic compounds, with a boiling point within the range 80 °C to 140 °C.

Ensure there is no interaction with the product or its components under test; otherwise a suitable alternative liquid may be used. For coating powders of density < 1 g/cm³, water may be used as the displacement liquid, in accordance with ISO 1183-1.

6 Apparatus

Ordinary laboratory apparatus, together with the following:

- 6.1 **Pycnometer**, complying with ISO 2811-1.
- 6.2 **Vacuum pump**, with rubber pressure tube attachment.
- 6.3 **Balance**, capacity 200 g, capable of weighing to 1 mg.

7 Sampling

Take a representative sample of the product to be tested as described in ISO 15528.

8 Procedure

iTeh STANDARD PREVIEW

8.1 Number of determinations (standards.iteh.ai)

Carry out the determination in duplicate at (23 ± 1) °C and at a relative humidity of (50 ± 5) %.

8.2 Determination of the density of the displacement liquid

Weigh the empty clean pycnometer (6.1) (m_0), fill it to the mark with the displacement liquid (5.2) and reweigh (m_1). Empty the pycnometer, clean and dry it. Refill the pycnometer with water at (23 ± 1) °C (5.1) and reweigh (m_2).

Calculate the density ρ_1 , in grams per cubic centimetre, of the displacement liquid at (23 ± 1) °C, using [Formula \(1\)](#):

$$\rho_1 = \frac{m_1 - m_0}{m_2 - m_0} \times \rho_0 \quad (1)$$

where

m_0 is the mass, in grams, of the empty pycnometer;

m_1 is the mass, in grams, of the pycnometer containing the displacement liquid;

m_2 is the mass, in grams, of the pycnometer containing water;

ρ_0 is the density, in grams per cubic centimetre, of the water. For the purposes of this document, take the density of water at 23 °C as 0,998 g/cm³.

8.3 Determination of the density of the coating powder

Empty the pycnometer, clean and dry it. Fill the pycnometer to the half with the displacement liquid. Slowly introduce a test portion of the sample appropriate to the type and volume of the pycnometer

(m_3), in a manner that the powder is wetted by the displacement liquid. Air bubbles, when evident, can be removed by using the vacuum pump (6.2).

Then fill the pycnometer to the mark with the displacement liquid, taking care not to disturb the sedimented powder. Reweigh the filled pycnometer (m_4).

Take care also on filling in order to avoid powder remaining in the neck of the pycnometer.

9 Expression of results

Calculate the density ρ_p , in grams per cubic centimetre, of the coating powder at (23 ± 1) °C, following [Formula \(2\)](#):

$$\rho_p = \frac{m_3}{(m_1 - m_0) - (m_4 - m_3 - m_0)} \times \rho_1 \quad (2)$$

where

m_0 is the mass, in grams, of the empty pycnometer;

m_1 is the mass, in grams, of the pycnometer containing the displacement liquid;

m_3 is the mass, in grams, of the test portion;

m_4 is the mass, in grams, of the pycnometer containing the test portion and the displacement liquid;

ρ_1 is the density, in grams per cubic centimetre, of the displacement liquid at (23 ± 1) °C.

If the two results differ by more than 2 %, repeat the procedure described in [Clause 8](#).

Calculate the mean of two valid determinations and report the result to the nearest 0,01 g/cm³.

10 Precision

No precision data are currently available.

11 Test report

The test report shall contain at least the following information:

- a) all details necessary to identify the product tested;
- b) a reference to this document, i.e. ISO 8130-3:—;
- c) the type and volume of pycnometer used;
- d) the type and grade of displacement liquid used;
- e) the mass of the test sample;
- f) the result of the test (individual values and mean value);
- g) any deviation from the test method specified;
- h) any unusual features (anomalies) observed during the test.
- i) the date of the test.

Bibliography

- [1] ISO 787-10, *General methods of test for pigments and extenders — Part 10: Determination of density — Pyknometer method*

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[oSIST prEN ISO 8130-3:2020](https://standards.iteh.ai/catalog/standards/sist/a5eb238b-ce1d-44ef-af8b-b35786c7fb7a/osist-pren-iso-8130-3-2020)
<https://standards.iteh.ai/catalog/standards/sist/a5eb238b-ce1d-44ef-af8b-b35786c7fb7a/osist-pren-iso-8130-3-2020>