



Designation: ~~C 425-04~~ Designation: C425 - 04 (Reapproved 2009)

Standard Specification for Compression Joints for Vitrified Clay Pipe and Fittings¹

This standard is issued under the fixed designation C425; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope

1.1 This specification covers materials and test requirements for compression joints for vitrified clay pipe and fittings. See Specification ~~C 700~~C700 for pipe specifications. The test requirements are applicable to pipe joint assemblies prior to field installation of pipe.

~~1.2 The values stated in inch-pound units are to be regarded as the standard. The values given in parentheses are for information only.~~

NOTE 1—Install pipe in accordance with Practice ~~C 12~~C12.

1.2 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.3 The following precautionary caveat pertains only to the Test Requirements portion, Section 7, of this standard. *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:²

A167 Specification for Stainless and Heat-Resisting Chromium-Nickel Steel Plate, Sheet, and Strip

A240/A240M Specification for Heat-Resisting Chromium and Chromium-Nickel Stainless Steel Plate, Sheet, and Strip for Pressure Vessels and for General Applications

C12 Practice for Installing Vitrified Clay Pipe Lines

C700 Specification for Vitrified Clay Pipe, Extra Strength, Standard Strength, and Perforated

C896 Terminology Relating to Clay Products

D395 Test Methods for Rubber Property—Compression Set

D412 Test Methods for Vulcanized Rubber and Thermoplastic Elastomers—Tension

D471 Test Method for Rubber Property—Effect of Liquids

D518 Test Method for Rubber Deterioration—Surface Cracking

D543 Practices for Evaluating the Resistance of Plastics to Chemical Reagents

D573 Test Method for Rubber—Deterioration in an Air Oven

D883 Terminology Relating to Plastics—583 Methods of Test for Water Resistance of Textile Fabrics³

~~D1149 Test Method for Rubber Deterioration—Surface Ozone Cracking in a Chamber~~ Test Methods for Rubber Deterioration Cracking in an Ozone Controlled Environment

D1566 Terminology Relating to Rubber

D2240 Test Method for Rubber Property—Durometer Hardness

3. Terminology

3.1 *Definitions*—Terms relating to plastics and rubber shall be as defined in Terminologies ~~D 883 and D 1566~~D 883D583 and D1566, respectively.

3.2 Terminology ~~C 896~~C 896

¹ This specification is under the jurisdiction of ASTM Committee C04 on Vitrified Clay Pipe and is the direct responsibility of Subcommittee C04.20 on Methods of Test and Specifications.

Current edition approved April 1, 2004. Published May 2004. Originally approved in 1958. Last previous edition approved in 2002 as C 425-02.

Current edition approved Oct. 1, 2009. Published October 2009. Originally approved in 1958. Last previous edition approved in 2004 as C425-04. DOI: 10.1520/C0425-04R09.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

3.2 Terminology C896 can be used for clarification of terminology in this specification.

4. Principles of Joint Design

- 4.1 Sealing elements shall be compressed between bearing surfaces to assure watertight integrity as required in Section 7.
 4.2 Sealing elements shall either be bonded to bearing surfaces or be independent elements.

5. Materials and Manufacture

- 5.1 Rubber ring-sealing elements shall conform to the requirements of Table 1.
 5.2 Rubber for other than ring-sealing elements shall conform to the requirements of Table 2.
 5.3 Plastic components shall conform to the requirements of Table 3.

5.4 Metallic components shall be of corrosion-resistant metal conforming to Specifications A 167 and A 240/A 240MA167 and A240/A240M.

5.5 If any of the test specimens fail to meet the chemical resistance requirements, the manufacturer will be allowed a retest of two additional specimens, representative of the original material tested, for each one that failed. The jointing material will be acceptable if all retest specimens meet the test requirements.

5.6 Joints complying with this standard are suitable for most domestic and commercial applications. However, attention is called to the fact that industrial effluents vary in content, concentration, duration of discharge and temperature; and specific evaluations of joint performance in such environments are necessary. In those instances, consult the manufacturer.

6. Joint Specimen Preparation

- 6.1 When required, assembled joints representative of the pipe and joints to be used, shall be selected from the supplier's stock by the purchaser or his representative.
 6.2 Specimens selected for the test shall be up to 0.25 % of the number of joints to be furnished. No fewer than two assembled joints shall be tested for each diameter of pipe furnished.
 6.3 Test specimens shall not be taken from damaged joints or pipe.

7. Test Requirements for Joints

7.1 Joints shall meet the requirements of 7.1.1 and 7.1.2 or 7.1.1 and 7.1.3, when subjected to an internal 10-ft (3.1-m) head of water pressure (4.3 psi (30 kPa)), for a total test period of 1 h. The recommended temperature of the water, pipe, and atmosphere is 60 to 75°F (16 to 24°C).

7.1.1 Joints shall not leak when tested in the straight position and when deflected to amounts shown in Table 4. The ends of the test line shall only be restrained the amount that is necessary to prevent longitudinal movement. The deflection shall be determined by measuring the distance the free end of one pipe moves away from the center line in any direction while the other pipe remains fixed.

TABLE 1 Tests for Rubber—Ring-Sealing Elements

NOTE—Except for the water absorption test (Test Method D 471 D471), the tests shall be run on specimens cut from rubber test slabs representative of the finished product.

Test	Test Requirement	ASTM Standard
Chemical resistance:		D 543D 543 [48 h at 23 ± 2°C]
Chemical resistance:		D543 [48 h at 23 ± 2°C]
1N sulfuric acid	no weight loss	
1N hydrochloric acid	no weight loss	
Tensile strength	1500 psi (10.4 MPa) min; 500 % min elongation at break	D 412D 412
Tensile strength	1500 psi (10.4 MPa) min; 500 % min elongation at break	D412
Hardness	Shore A durometer 35 min to 50 max	D 2240D 2240
Hardness	Shore A durometer 35 min to 50 max	D2240
Compression set	16 % max of original deflection	D 395D 395, Method B [22 h at 70 ± 2°C]
Compression set	16 % max of original deflection	D395, Method B [22 h at 70 ± 2°C]
Water absorption	5 % max	D 471—Immerse a 2-in. (51-mm) long section cut from a rubber-sealing element in distilled water for 7 days at 70 ± 2°C
Water absorption	5 % max	D471—Immerse a 2-in. (51-mm) long section cut from a rubber-sealing element in distilled water for 7 days at 70 ± 2°C
Ozone resistance	no visible cracking under 2× specimen magnification using D 518 D 518, Procedure B, stretched 20 % and exposed to ozone concentrations of 0.5 ppm for 24 h at 40 ± 1°C	D 1149D 1149
Ozone resistance	no visible cracking under 2× specimen magnification using D518, Procedure B, stretched 20 % and exposed to ozone concentrations of 0.5 ppm for 24 h at 40 ± 1°C	D1149
Accelerated oven aging	80 % min of original tensile strength	D 573 D 573 [7 days at 70 ± 2°C]
Accelerated oven aging	80 % min of original tensile strength	D573 [7 days at 70 ± 2°C]
	75 % min of original elongation	