

Designation: B 546 – 04 (Reapproved 2009)

Standard Specification for Electric Fusion-Welded Ni-Cr-Co-Mo Alloy (UNS N06617), Ni-Fe-Cr-Si Alloys (UNS N08330 and UNS N08332), Ni-Cr-Fe-Al Alloy (UNS N06603), Ni-Cr-Fe Alloy (UNS N06025), and Ni-Cr-Fe-Si Alloy (UNS N06045) Pipe¹

This standard is issued under the fixed designation B 546; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope

- 1.1 This specification covers electric fusion-welded nickel-chromium-cobalt-molybdenum alloy UNS N06617, nickel-iron-chromium-silicon alloys UNS N08330 and UNS N08332, Ni-Cr-Fe-Al Alloy (UNS N06603), Ni-Cr-Fe Alloy UNS N06025, and Ni-Cr-Fe-Si Alloy UNS N06045 pipe intended for heat resisting applications and general corrosive service.
- 1.2 This specification covers pipe in sizes 3 in. (76.2 mm) nominal diameter and larger and possessing a minimum wall thickness of 0.083 in. (2.11 mm).
- 1.3The values stated in inch-pound units are to be regarded as the standard. The values given in parentheses are for information only.
- 1.3 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.
- 1.4 This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to become familiar with all hazards including those identified in the appropriate Material Safety Data Sheet (MSDS) for this product/material as provided by the manufactureer, to establish appropriate safety and health practices, and determine the applicability of regulatory limitations prior to use.

2. Referenced Documents

Document Preview

- 2.1 ASTM Standards:²
- B 168 Specification for Nickel-Chromium-Iron Alloys (UNS N06600, N06601, N06603, N06690, N06693, N06025, N06045, and N06690) N06690) and Nickel-Chromium-Cobalt-Molybdenum Alloy (UNS N06617) Plate, Sheet, and Strip
- B 536 Specification for Nickel-Iron-Chromium-Silicon Alloys (UNS N08330 and N08332) Plate, Sheet, and Strip
- B 775 Specification for General Requirements for Nickel and Nickel Alloy Welded Pipe² Specification for General Requirements for Nickel and Nickel Alloy Welded Pipe
- B 899 Terminology Relating to Non-ferrous Metals and Alloys
- E 10 Test Method for Brinell Hardness of Metallic Materials
- E140Hardness Conversion Tables for Metals (Relationship Between Brinell Hardness, Vickers Hardness, Rockwell Hardness, Rockwell Hardness, and Knoop Hardness)³. Test Method for Brinell Hardness of Metallic Materials
- E 140 Hardness Conversion Tables for Metals Relationship Among Brinell Hardness, Vickers Hardness, Rockwell Hardness, Superficial Hardness, Knoop Hardness, and Scleroscope Hardness
- E 1473 Test Methods for Chemical Analysis of Nickel, Cobalt, and High-Temperature Alloys
- 2.2 ASME Standards:

Boiler and Pressure Vessel Code, Section VIII, Paragraph UW-51

Boiler and Pressure Vessel Code, Section IX⁶

Boiler and Pressure Vessel Code, Section VIII Paragraph UW-51

Boiler and Pressure Vessel Code, Section IX

¹ This specification is under the jurisdiction of ASTM Committee B-2 B02 on Nonferrous Metals and Alloys and is the direct responsibility of Subcommittee B02.07 on Refined Nickel and Cobalt and Their Alloys.

Current edition approved Dec. 10, 1998. Published January 1999. Originally published as B546-71. Last previous edition B546-97.

Current edition approved Oct. 1, 2009. Published October 2009. Originally approved in 1971. Last previous edition approved in 2004 as B 546 - 04.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For Annual Book of ASTM Standards, Vol 02.04.volume information, refer to the standard's Document Summary page on the ASTM website.

Annual Book of ASTM Standards, Vol 03.01.

3. Terminology

3.1 Definitions:

3.1.1 Definitions for terms defined in Terminology B 899 shall apply unless otherwise defined by the requirements of this document.

4. General Requirement

34.1 Material furnished in accordance with this specification shall conform to the applicable requirements of the current edition of Specification B 775 unless otherwise provided herein.

4.

5. Classification

4 1

5.1 Two classes of pipe are covered as follows:

4.1.1

<u>5.1.1</u> Class 1—All welded joints to be 100 % inspected by radiography.

4.1.2

5.1.2 Class 2—No radiographic examination is required.

5.

6. Ordering Information

5.Ht6.1 It is the responsibility of the purchaser to specify all requirements that are necessary for the safe and satisfactory performance of material ordered under this specification. Examples of such requirements include, but are not limited to, the following:

56.1.1 Alloy (Table 1),

5.1.2ASTM designation and year of issue,

5.1.3Class (See 4.1

6.1.2 ASTM designation and year of issue,

6.1.3 Class (See 5.1),

56.1.4 Dimensions (standard pipe size and schedule),

56.1.5 Length (specific or random),

56.1.6 Quantity (feet or number of pieces),

56.1.7 Certification—State if certification is required, M B546-04(2009)

5.1.86.1.8 Whether type of filler metal and deposited composition is required (see 7.38.3), 3cc4d8a/astm-b546-042009

TABLE 1 Chemical Requirements

Element	Composition Limits, %					
	N08330	N08332	N06603	N06617	N06025	N06045
Carbon	0.08 max	0.05-0.10	0.20-0.40	0.05-0.15	0.15-0.25	0.05-0.12
Manganese	2.00 max	2.00 max	0.15 max	1.0 max	0.15 max	1.0 max
Phosphorus	0.03 max	0.03 max	0.20 max		0.02 max	0.02 max
Sulfur	0.03 max	0.03 max	0.10 max	0.015 max	0.010 max	0.010 max
Silicon	0.75 to 1.50	0.75 to 1.50	0.50 max	1.0 max	0.5 max	2.5-3.0
Chromium	17.0 to 20.0	17.0 to 20.0	0.24-0.26	20.0-24.0	24.0-26.0	26.0-29.0
Nickel	34.0 to 37.0	34.0 to 37.0	Bal	remainder	Bal	45.0 min
Copper	1.00 max	1.00 max	0.50 max	0.5 max	0.1 max	0.3 max
Lead	0.005 max	0.005 max				
Tin	0.025 max	0.025 max				
Iron	remainder ^A	remainder	8.0-11.0	3.0 max	8.0-11.0	21.0-25.0
Aluminum			2.4-3.0	0.8-1.5	1.8-2.4	
Cobalt				10.0-15.0		
Molybdenum				8.0-10.0		
Zirconium			0.01-0.10		0.01-0.10	
Yttrium			0.01-0.15		0.05-0.12	
Cerium						0.3-0.09
Titanium			0.010-0.025			

^A Element shall be determined arithmetically by difference.

³ Available from American Society of Mechanical Engineers (ASME), ASME International Headquarters, Three Park Ave., New York, NY 10016-5990, http://www.asme.org.