
Petrokemična industrija ter industrija za predelavo nafte in zemeljskega plina - Zunanja protikorozijska zaščita dvižnih cevi s prevlekami in oblogami - 2. del: Vzdrževanje in popravilo proizvodnih cevi na kraju samem (ISO 18797-2:2021)

Petroleum, petrochemical and natural gas industries - External corrosion protection of risers by coatings and linings - Part 2: Maintenance and field repair coatings for riser pipes (ISO 18797-2:2021)

Erdöl-, petrochemische und Erdgasindustrie - Äußerer Korrosionsschutz von Steigleitungen durch Beschichtungen und Auskleidungen - Teil 2: Wartungs- und Reparaturbeschichtungen für Steigleitungen (ISO 18797-2:2021)

Industries du pétrole, de la pétrochimie et du gaz naturel - Protection de la corrosion externe des tubes de production par revêtements et doublures - Partie 2: Entretien et réparation in situ des tubes de production (ISO 18797-2:2021)

Ta slovenski standard je istoveten z: EN ISO 18797-2:2021

ICS:

25.220.01	Površinska obdelava in prevleke na splošno	Surface treatment and coating in general
75.180.10	Oprema za raziskovanje, vrtanje in odkopavanje	Exploratory, drilling and extraction equipment

SIST EN ISO 18797-2:2021**en,fr,de**

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN ISO 18797-2:2021

<https://standards.iteh.ai/catalog/standards/sist/c9bca136-d317-4a91-bd96-15c2f338f377/sist-en-iso-18797-2-2021>

EUROPEAN STANDARD

EN ISO 18797-2

NORME EUROPÉENNE

EUROPÄISCHE NORM

September 2021

ICS 75.180.10

English Version

Petroleum, petrochemical and natural gas industries -
External corrosion protection of risers by coatings and
linings - Part 2: Maintenance and field repair coatings for
riser pipes (ISO 18797-2:2021)

Industries du pétrole, de la pétrochimie et du gaz
naturel - Protection de la corrosion externe des tubes
de production par revêtements et doublures - Partie 2:
Entretien et réparation in situ des tubes de production
(ISO 18797-2:2021)

Erdöl-, petrochemische und Erdgasindustrie - Äußerer
Korrosionsschutz von Steigleitungen durch
Beschichtungen und Auskleidungen - Teil 2: Wartungs-
und Reparaturbeschichtungen für Steigleitungen (ISO
18797-2:2021)

This European Standard was approved by CEN on 28 August 2021.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

Contents	Page
European foreword.....	3

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 18797-2:2021](https://standards.iteh.ai/catalog/standards/sist/c9bca136-d317-4a91-bd96-15c2f338f377/sist-en-iso-18797-2-2021)
<https://standards.iteh.ai/catalog/standards/sist/c9bca136-d317-4a91-bd96-15c2f338f377/sist-en-iso-18797-2-2021>

European foreword

This document (EN ISO 18797-2:2021) has been prepared by Technical Committee ISO/TC 67 "Materials, equipment and offshore structures for petroleum, petrochemical and natural gas industries" in collaboration with Technical Committee CEN/TC 12 "Materials, equipment and offshore structures for petroleum, petrochemical and natural gas industries" the secretariat of which is held by NEN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by March 2022, and conflicting national standards shall be withdrawn at the latest by March 2022.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

Any feedback and questions on this document should be directed to the users' national standards body/national committee. A complete listing of these bodies can be found on the CEN website.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

(standards.iteh.ai)

Endorsement notice

[SIST EN ISO 18797-2:2021](https://standards.iteh.ai/catalog/standards/sist/c9bca136-d317-4a91-bd96-15c2b381377/sist-en-iso-18797-2-2021)

The text of ISO 18797-2:2021 has been approved by CEN as EN ISO 18797-2:2021 without any modification.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN ISO 18797-2:2021

<https://standards.iteh.ai/catalog/standards/sist/c9bca136-d317-4a91-bd96-15c2f338f377/sist-en-iso-18797-2-2021>

INTERNATIONAL
STANDARD

ISO
18797-2

First edition
2021-09

**Petroleum, petrochemical and natural
gas industries — External corrosion
protection of risers by coatings and
linings —**

Part 2:

**Maintenance and field repair coatings
for riser pipes**
(standards.iteh.ai)

*Industries du pétrole, de la pétrochimie et du gaz naturel —
Protection de la corrosion externe des tubes de production par
revêtements et doublures —
Partie 2: Entretien et réparation in situ des tubes de production*

<https://standards.iteh.ai/catalog/standards/sist/06ca956-d317-4a91-bd96-15c2938f77/sist-en-iso-18797-2-2021>



Reference number
ISO 18797-2:2021(E)

© ISO 2021

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN ISO 18797-2:2021

<https://standards.iteh.ai/catalog/standards/sist/c9bca136-d317-4a91-bd96-15c2f338f377/sist-en-iso-18797-2-2021>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2021

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

Page

Foreword	vi
Introduction	vii
1 Scope	1
2 Normative references	1
3 Terms and definitions	4
4 Symbols and abbreviated terms	7
4.1 Symbols.....	7
4.2 Abbreviated terms.....	7
5 Coating types	7
6 General requirements	8
6.1 Client's requirements.....	8
6.1.1 Approval of repair coating and repair method.....	8
6.1.2 Specification of purchase order mandatory information.....	8
6.1.3 Specification of purchase order additional information.....	9
6.2 Contractor's requirements.....	9
6.2.1 Documented information.....	9
6.2.2 Marking of coating materials.....	10
6.3 Rounding.....	10
6.4 Conformity to requirements.....	10
6.5 Criteria for the condition assessment of an existing coating.....	10
6.5.1 General – Evaluation of coating condition.....	10
6.5.2 Applicable inspection techniques.....	11
7 Qualification processes and application procedures	11
7.1 General.....	11
7.2 APS and ITP.....	12
7.2.1 General.....	12
7.2.2 APS.....	12
7.2.3 ITP.....	13
7.3 Technical assessment of coating conformity.....	13
7.4 Procedure qualification trial.....	13
7.5 Pre-production trial.....	14
7.6 Production, testing and inspection.....	15
7.6.1 General.....	15
7.6.2 Inspection documents and traceability.....	15
8 Selection criteria for repair coatings	15
8.1 General.....	15
8.2 Application constraints.....	16
8.2.1 Wet substrates.....	16
8.2.2 Contamination by soluble salts.....	17
8.2.3 Dust contamination.....	17
8.2.4 Contamination by oil, grease and other petroleum-like products.....	17
8.2.5 Compatibility with existing coating.....	17
8.2.6 Feasibility of surface cleaning.....	18
8.2.7 Space and riser access constraints.....	18
8.2.8 Time constraints.....	18
8.2.9 Temperatures and relative humidity.....	18
8.2.10 Coating continuity.....	18
8.3 Operational conditions.....	19
8.3.1 Resistance to ageing, weathering and water.....	19
8.3.2 Resistance to mechanical loads.....	19
8.3.3 Interaction with cathodic protection.....	19

ISO 18797-2:2021(E)

9	Test programs	19
9.1	Substrate conditions used for tests	19
9.2	Inspections, tests and frequencies	19
9.3	Thickness testing	20
9.4	Retest	20
10	Non-crystalline low-viscosity polyolefin-based coatings	21
10.1	Coating identification	21
10.2	Description of the coatings	21
10.3	Surface preparation	22
10.4	Application of coatings	22
10.4.1	General	22
10.4.2	Overlap	22
10.5	Testing of coatings	22
10.5.1	General	22
10.5.2	Thickness	22
10.5.3	Glass transition temperature and crystallization temperature	23
10.5.4	Holiday detection	23
10.5.5	Drip resistance	23
10.5.6	Adhesion to pipe surface and existing coating	23
10.5.7	Lap shear resistance	24
10.5.8	Specific electrical insulation resistance	24
10.5.9	Impact resistance	24
10.5.10	Indentation resistance	24
10.5.11	Cathodic disbondment resistance	25
10.5.12	Resistance to ageing and weathering	25
10.5.13	Peel strength between layers of outer wrap	25
10.5.14	Thermal ageing resistance	26
10.5.15	Hot-water immersion test	26
11	Petrolatum and wax-based tape wrap systems	31
11.1	Coating identification	31
11.2	Description of the tape wrap systems	32
11.2.1	Petrolatum tape wrap systems (type 11A)	32
11.2.2	Wax-based tape wrap systems (type 11B)	32
11.3	Surface preparation	32
11.4	Application of coating systems	32
11.4.1	General	32
11.4.2	Overlap	32
11.5	Testing of the coating systems	33
11.5.1	General	33
11.5.2	Density	33
11.5.3	Dielectric strength	33
11.5.4	Thickness	33
11.5.5	Holiday detection	34
11.5.6	Impact resistance	34
11.5.7	Specific electrical insulation resistance	34
11.5.8	Cathodic disbondment resistance	34
11.5.9	Adhesion to pipe surface and existing coating	34
11.5.10	Drip resistance	35
11.5.11	Hot water immersion test	35
11.5.12	Resistance to ageing and weathering	35
12	Polychloroprene-based elastomeric coatings	41
12.1	Coating identification	41
12.2	Description of the coatings	41
12.3	Surface preparation	41
12.4	Application of the coating	41
12.4.1	General	41
12.4.2	Overlap	42

12.5	Testing of the coatings	42
12.5.1	General	42
12.5.2	Visual appearance	42
12.5.3	Thickness	42
12.5.4	Holiday detection	42
12.5.5	Hardness	42
12.5.6	Adhesion to pipe surface and existing coating	42
12.5.7	Cathodic disbondment resistance	43
12.5.8	Density	43
12.5.9	Rheometer curve	43
12.5.10	Tensile strength	43
12.5.11	Elongation at break	43
12.5.12	Tear strength	43
12.5.13	Electrical volume resistivity	43
12.5.14	Ozone resistance	43
12.5.15	Resistance to seawater	44
12.5.16	Hot-water immersion test	44
12.5.17	Thermal ageing resistance	44
12.5.18	Resistance to ageing and weathering	44
13	Liquid-applied epoxy coatings	46
13.1	Coating identification	46
13.2	Description of the liquid-applied epoxy coating	47
13.3	Surface preparation	47
13.4	Application of the coatings	47
13.4.1	General	47
13.4.2	Overlap	47
13.5	Testing of the coatings	47
13.5.1	General	47
13.5.2	Dry-film thickness	48
13.5.3	Holiday detection	48
13.5.4	Hardness	48
13.5.5	Impact resistance	48
13.5.6	Indentation resistance	48
13.5.7	Specific electrical insulation resistance	48
13.5.8	Cathodic disbondment resistance	49
13.5.9	Adhesion to pipe surface and existing coating	49
13.5.10	Thermal ageing resistance	49
13.5.11	Hot-water immersion test	49
13.5.12	Resistance to ageing and weathering	49
	Annex A (informative) Likelihood of exposure in splash zone area	54
	Annex B (informative) Tests for coatings applied on wet substrates	56
	Bibliography	65

ISO 18797-2:2021(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 67, *Materials, equipment and offshore structures for petroleum, petrochemical and natural gas industries*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 12, *Materials, equipment and offshore structures for petroleum, petrochemical and natural gas industries*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

A list of all parts in the ISO 18797 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

This document has been developed in response to worldwide demand for minimum specifications for field applied maintenance and repair coatings for riser pipes. ISO 18797-1 specifies the shop applied coatings for risers. Coated offshore risers are intermittently exposed to varying conditions. These include – but are not limited to – sunlight, rain, snow, hail, water spray, salt spray, high humidity, fluctuating ambient temperatures (varying from sub-zero to high temperature), water currents, and impacts from waves, drifting debris and marine growth. Exposure to such conditions can cause severe coating deterioration in time, resulting in ineffective corrosion prevention of the steel riser pipe.

Users of this document are advised that further or differing requirements can be utilized for individual applications. This document can also be used for the maintenance and repair of coatings on other types of structures in the offshore splash zone, such as jetty piles and platform legs. This document does not limit the contractor or the manufacturer from proposing, or from accepting, alternative engineering solutions for the individual application. This can be particularly applicable where there is innovative or developing technology. Where an alternative is proposed, the specification issuer is expected to identify any deviations from this document and provide details.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST EN ISO 18797-2:2021](https://standards.iteh.ai/catalog/standards/sist/c9bca136-d317-4a91-bd96-15c2f338f377/sist-en-iso-18797-2-2021)

<https://standards.iteh.ai/catalog/standards/sist/c9bca136-d317-4a91-bd96-15c2f338f377/sist-en-iso-18797-2-2021>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN ISO 18797-2:2021

<https://standards.iteh.ai/catalog/standards/sist/c9bca136-d317-4a91-bd96-15c2f338f377/sist-en-iso-18797-2-2021>

Petroleum, petrochemical and natural gas industries — External corrosion protection of risers by coatings and linings —

Part 2: Maintenance and field repair coatings for riser pipes

1 Scope

This document specifies the selection criteria and minimum requirements for protective coating systems for maintenance and field repair of risers exposed to conditions in the splash zone. It is applicable for maintenance requirements and field repairs of riser coatings.

This document does not apply to the selection of techniques and materials used to restore integrity of the risers to be coated, nor does it apply to the selection of additional mechanical protective materials that are not part of the coating systems described in this document.

New construction shop applied riser coatings are covered in ISO 18797-1. Compatible maintenance and repair coating systems specified in ISO 18797-1 are covered in this document.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 34-1, *Rubber, vulcanized or thermoplastic — Determination of tear strength — Part 1: Trouser, angle and crescent test pieces*

ISO 37, *Rubber, vulcanized or thermoplastic — Determination of tensile stress-strain properties*

ISO 48-2, *Rubber, vulcanized or thermoplastic — Determination of hardness — Part 2: Hardness between 10 IRHD and 100 IRHD*

ISO 527-1, *Plastics — Determination of tensile properties — Part 1: General principles*

ISO 527-2, *Plastics — Determination of tensile properties — Part 2: Test conditions for moulding and extrusion plastics*

ISO 527-3, *Plastics — Determination of tensile properties — Part 3: Test conditions for films and sheets*

ISO 868, *Plastics and ebonite — Determination of indentation hardness by means of a durometer (Shore hardness)*

ISO 1183-1, *Plastics — Methods for determining the density of non-cellular plastics — Part 1: Immersion method, liquid pycnometer method and titration method*

ISO 1431-1, *Rubber, vulcanized or thermoplastic — Resistance to ozone cracking — Part 1: Static and dynamic strain testing*

ISO 1523, *Determination of flash point — Closed cup equilibrium method*

ISO 1817, *Rubber, vulcanized or thermoplastic — Determination of the effect of liquids*