



SLOVENSKI STANDARD
oSIST prEN ISO 18796-1:2020
01-september-2020

**Petrokemična industrija ter industrija za predelavo nafte in zemeljskega plina -
Notranji premazi in obloge posod za proizvodnjo ogljikovega jekla - 1. del:
Tehnične zahteve (ISO 18796-1:2018)**

Petroleum, petrochemicals and natural gas industries - Internal coating and lining of carbon steel process vessels - Part 1: Technical requirements (ISO 18796-1:2018)

Erdöl-, petrochemische und Erdgasindustrie - Innere Schutzbeschichtungen und Auskleidungen für Prozessbehälter aus unlegiertem Stahl - Teil 1: Allgemeine Anforderungen (ISO 18796-1:2018)

Industries du pétrole, de la pétrochimie et du gaz naturel - Revêtement de protection interne et doublure des récipients de production en acier au carbone - Partie 1: Exigences techniques (ISO 18796-1:2018)

Ta slovenski standard je istoveten z: prEN ISO 18796-1

ICS:

75.180.20 Predelovalna oprema Processing equipment

oSIST prEN ISO 18796-1:2020 **en,fr,de**

INTERNATIONAL
STANDARD

ISO
18796-1

First edition
2018-10

**Petroleum, petrochemicals and
natural gas industries — Internal
coating and lining of carbon steel
process vessels —**

**Part 1:
Technical requirements**

*Industries du pétrole, de la pétrochimie et du gaz naturel —
Revêtement de protection interne et doublure des récipients de
production en acier au carbone —*

Partie 1: Exigences techniques

<https://standards.iteh.ai/catalog/standards/sist/734baf23-4478-4537-9ef4-690d88285b43/sist-en-iso-18796-1-2020>



Reference number
ISO 18796-1:2018(E)

© ISO 2018

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN ISO 18796-1:2020

<https://standards.iteh.ai/catalog/standards/sist/734baf23-4478-4537-9ef4-690d88285b43/sist-en-iso-18796-1-2020>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2018

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword	v
Introduction	vi
1 Scope	1
2 Normative references	1
3 Terms, definitions and abbreviated terms	3
3.1 Terms and definitions.....	3
3.2 Abbreviated terms.....	4
4 Conformance	5
4.1 Rounding.....	5
4.2 Conformance to this document.....	5
5 Pre-work requirements	6
5.1 General.....	6
5.2 Safety precautions in flammable atmosphere.....	6
5.3 Safety precautions in confined space.....	6
5.4 Safety precautions for blasting and coating works.....	6
5.5 Isolation and ventilation.....	7
5.6 Qualification of coating/lining application and inspection personnel.....	7
6 Coating/lining materials	7
6.1 General.....	7
6.2 Approvals.....	7
6.3 Procedure qualification trial (PQT).....	8
6.4 Pre-production trial (PPT).....	8
6.5 Thickness classifications of coatings.....	9
6.6 Holding (blast) primer.....	9
6.7 Coating and lining systems.....	9
6.8 Material approvals — Coating and lining systems.....	10
7 Surface preparation	11
7.1 General.....	11
7.2 Preparations.....	11
7.3 Patching, grinding, degreasing and washing (for new and rehabilitation works).....	12
7.4 Dry abrasive blasting cleaning.....	12
7.5 Humidity control.....	13
7.6 After blast cleaning.....	14
8 Coating/lining application	14
8.1 General requirements.....	14
8.2 Application of environmental conditions.....	15
8.3 Primer application.....	15
8.4 Coating/lining thickness.....	15
9 Coating/lining application	16
10 Inspection and testing	16
10.1 General requirements.....	16
10.2 Environmental conditions testing.....	17
10.3 Materials and equipment inspection.....	17
10.4 Compressed air and abrasive.....	17
10.5 Surface preparation inspection.....	17
10.6 Coating/lining inspection and testing.....	18
10.6.1 General.....	18
10.6.2 Lining film thickness.....	18
10.6.3 Holiday detection test.....	18
10.6.4 Curing test.....	18

ISO 18796-1:2018(E)

10.7	Adhesion test.....	19
11	Quality requirements	19
12	Documentation.....	19
12.1	General.....	19
12.2	Work proposal.....	20
12.3	Work records/reports.....	20
12.4	Inspection and testing reporting.....	20
12.5	Final report.....	20
Annex A	(informative) Example of coating/lining work record/data sheet.....	21
Annex B	(informative) Example of coating/lining inspection and testing data sheet.....	22
Bibliography	23

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN ISO 18796-1:2020

<https://standards.iteh.ai/catalog/standards/sist/734baf23-4478-4537-9ef4-690d88285b43/sist-en-iso-18796-1-2020>

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see www.iso.org/iso/foreword.html.

This document was prepared by ISO/TC 67, *Materials, equipment and offshore structures for petroleum, petrochemical and natural gas industries*.

A list of all parts in the ISO 18796 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

ISO 18796-1:2018(E)**Introduction**

The objective of this document is to define the minimum technical requirements for the corrosion protection by coating/lining of internal surfaces of carbon steel process vessels used in the oil and gas industry and subject to marked pressure/temperature changes and/or acidic or other aggressive chemicals. In addition, this document provides technical guidance for developing project specifications and helps to ensure compliance in coating/lining material selection and performance with contract requirements.

Further or differing requirements can be specified for individual applications. This document does not limit the contractor and/or manufacturer from proposing, or the company from accepting, alternative engineering solutions for the individual application. This can particularly be applicable where there is an innovative or emerging technology. Where an alternative is proposed, the specification issuer will need to identify any deviation from this document and provide details.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 18796-1:2020](https://standards.iteh.ai/catalog/standards/sist/734baf23-4478-4537-9ef4-690d88285b43/sist-en-iso-18796-1-2020)

<https://standards.iteh.ai/catalog/standards/sist/734baf23-4478-4537-9ef4-690d88285b43/sist-en-iso-18796-1-2020>

Petroleum, petrochemicals and natural gas industries — Internal coating and lining of carbon steel process vessels —

Part 1: Technical requirements

1 Scope

This document specifies the minimum technical requirements for surface preparation, materials, application, inspection and testing of internal coating and lining systems that are intended to be applied on internal surfaces of process vessels that are subject to marked pressure/temperature changes and/or potentially corrosive conditions or processes and aggressive chemicals, used in the oil and gas industry.

This document covers both new construction and maintenance works of process vessels as well as the repair of defective and deteriorated coating and lining systems.

This document also provides the minimum requirements for the coated and lined samples and the criteria for their approval.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 2812 (all parts), *Paints and varnishes — Determination of resistance to liquids*

ISO 3233 (all parts), *Paints and varnishes — Determination of the percentage volume of non-volatile matter*

ISO 4624¹⁾, *Paints and varnishes — Pull-off test for adhesion*

ISO 7027, *Water quality — Determination of turbidity*

ISO 7619-1, *Rubber, vulcanized or thermoplastic — Determination of indentation hardness — Part 1: Durometer method (Shore hardness)*

ISO 8501-1²⁾, *Preparation of steel substrates before application of paints and related products — Visual assessment of surface cleanliness — Part 1: Rust grades and preparation grades of uncoated steel substrates and of steel substrates after overall removal of previous coatings*

ISO 8501-3, *Preparation of steel substrates before application of paints and related products — Visual assessment of surface cleanliness — Part 3: Preparation grades of welds, edges and other areas with surface imperfections*

ISO 8502-3, *Preparation of steel substrates before application of paints and related products — Tests for the assessment of surface cleanliness — Part 3: Assessment of dust on steel surfaces prepared for painting (pressure-sensitive tape method)*

1) ASTM D4541 is equivalent to this document.

2) SSPC-SP5/NACE No. 1 is equivalent to this document.

ISO 18796-1:2018(E)

ISO 8502-6³⁾, *Preparation of steel substrates before application of paints and related products — Tests for the assessment of surface cleanliness — Part 6: Extraction of soluble contaminants for analysis — The Bresle method*

ISO 8502-9⁴⁾, *Preparation of steel substrates before application of paints and related products — Tests for the assessment of surface cleanliness — Part 9: Field method for the conductometric determination of water-soluble salts*

ISO 10474⁵⁾, *Steel and steel products — Inspection documents*

ISO 11124 (all parts), *Preparation of steel substrates before application of paints and related products — Specifications for metallic blast-cleaning abrasives*

ISO 11125 (all parts), *Preparation of steel substrates before application of paints and related products — Test methods for metallic blast-cleaning abrasives*

ISO 11126 (all parts), *Preparation of steel substrates before application of paints and related products — Specifications for non-metallic blast-cleaning abrasives*

ISO 11127-6, *Preparation of steel substrates before application of paints and related products — Test methods for non-metallic blast-cleaning abrasives — Part 6: Determination of water-soluble contaminants by conductivity measurement*

ISO 16276 (all parts)⁶⁾, *Corrosion protection of steel structures by protective paint systems — Assessment of, and acceptance criteria for, the adhesion/cohesion (fracture strength) of a coating*

ISO 19840⁷⁾, *Paints and varnishes — Corrosion protection of steel structures by protective paint systems — Measurement of, and acceptance criteria for, the thickness of dry films on rough surfaces*

ISO 21809-3:2016⁸⁾, *Petroleum and natural gas industries — External coatings for buried or submerged pipelines used in pipeline transportation systems — Part 3: Field joint coatings*

ISO 29601⁹⁾, *Paints and varnishes — Corrosion protection by protective paint systems — Assessment of porosity in a dry film*

ISO 80000-1:2009, *Quantities and units — Part 1: General*

ASTM D522, *Standard Test Methods for Mandrel Bend Test of Attached Organic Coatings*

ASTM D610, *Standard Practice for Evaluating Degree of Rusting on Painted Steel Surfaces*

ASTM D714, *Standard Test Method for Evaluating Degree of Blistering of Paints*

ASTM D2583, *Standard Test Method for Indentation Hardness of Rigid Plastics by Means of a Barcol Impressor*

ASTM D4060, *Standard Test Method for Abrasion Resistance of Organic Coatings by the Taber Abraser*

ASTM D4285, *Standard Test Method for Indicating Oil or Water in Compressed Air*

ASTM D4414, *Standard Practice for Measurement of Wet Film Thickness by Notch Gages*

3) SSPC-Guide 15 is equivalent to this document (together with ISO 8502-9).

4) SSPC-Guide 15 is equivalent to this document (together with ISO 8502-6).

5) EN 10204 is equivalent to this document.

6) ASTM D4541 is equivalent to this document.

7) SSPC-PA2 is equivalent to this document.

8) ASMT G42 is equivalent to this document.

9) NACE SP0188 is equivalent to this document.

ASTM F21, *Standard Test Method for Hydrophobic Surface Films by the Atomizer Test*

NACE/TM 0174, *Standard Test Method — Laboratory Methods for the Evaluation of Protective Coatings and Lining Materials on Metallic Substrates in Immersion Service*

SSPC-SP1, *Steel Structure Painting Council Surface Preparation Specifications — Solvent Cleaning*

3 Terms, definitions and abbreviated terms

3.1 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

3.1.1

abrasive blast cleaning

surface preparation method that uses an abrasive propelled by air pressure, centrifugal force, or water pressure to clean and usually to profile a surface

3.1.2

application procedure specification

document describing procedures, methods, equipment and tools used for coating application

3.1.3

applicator

contractor or subcontractor having the technical capability, knowledge, equipment, qualified personnel that is approved by the client for the coating processes as required by this document

3.1.4

coat

one layer of protective coating or paint applied to the surface in a single application to form an evenly distributed film when dry

3.1.5

contractor

vendor or company that agrees to furnish materials and/or perform specific project/services to the client

3.1.6

curing

chemical process of developing the intended properties of a coating/polymerized product in the lining system, generally due to a reaction between two or more chemicals (e.g. resin and curative)

3.1.7

client

entity for which professional services are rendered or person that receives a product

3.1.8

dew-point

temperature of a given air/water vapour mixture at which condensation starts, because its maximum water content saturation is reached at that temperature

3.1.9

dry film thickness

thickness of a coat of paint, layer of tape or coating system in its fully cured condition

ISO 18796-1:2018(E)**3.1.10****epoxy**

resin containing functional epoxy groups that allow for curing by polymerization with a variety of curatives

3.1.11**grit abrasive**

angular or irregularly shaped particles of abrasives

3.1.12**holiday**

discontinuity in a lining or contamination in the coating film that significantly lowers the performance of a coating

Note 1 to entry: Examples of discontinuity in a lining are pinhole, void, crack, thin spot, and inclusion of foreign material.

3.1.13**lining**

internal coating

Note 1 to entry: The term 'coating' is also used for the purposes of this document.

Note 2 to entry: Internal coating can be applied to the internal surfaces of a tank vessel to serve as a barrier to corrosion and/or product contamination, for example.

3.1.14**novolac**

phenol-formaldehyde resin with formaldehyde to phenol molar ratio of less than 1

3.1.15**phenolic**

resin of the phenol-formaldehyde type

3.1.16**pinhole**

small film defect characterized by small pore like flaws in the lining that would permit corrosion of the substrate under the conditions for which the lining is designed

Note 1 to entry: A pinhole can extend entirely through the film and lead to a holiday.

3.1.17**surface profile**

micro-roughness of a surface, generally expressed as the average height of the major peaks relative to the major valleys

3.2 Abbreviated terms

APS	application procedure specification
ASTM	American Society for Testing and Materials
BGAS	British Gas
BS	British Standard
CV	curriculum vitae
DFT	dry film thickness
GRUP	glass reinforced unsaturated polyester