



Designation: D6910/D6910M – 09

# Standard Test Method for Marsh Funnel Viscosity of Clay Construction Slurries<sup>1</sup>

This standard is issued under the fixed designation D6910/D6910M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1 This test method provides an indirect measurement of the viscosity of clay slurries using a funnel (Marsh Funnel) and a graduated cup of specific dimensions. This test method provides a practical indicator of the viscosity on a routine basis. This test method has been modified from the API Recommended Practice 13B-2.

1.2 The result determined using the method is referred to as the Marsh Funnel Viscosity.

1.3 This test can be performed in the laboratory, or used in the field to assess the apparent viscosity of a clay slurry for quality control purposes. The most commonly used slurry is a bentonite clay slurry.

1.4 The values stated in either SI units or inch-pound units [given in brackets] are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

1.6 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

## 2. Referenced Documents

### 2.1 ASTM Standards:<sup>2</sup>

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee D18 on Soil and Rock and is the direct responsibility of Subcommittee D18.16 on Grouting.

Current edition approved Oct. 1, 2009. Published October 2009. Originally approved in 2004. Last previous edition approved in 2004 as D6910 – 04. DOI: 10.1520/D6910\_D6910M-09.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

D653 Terminology Relating to Soil, Rock, and Contained Fluids

D3740 Practice for Minimum Requirements for Agencies Engaged in Testing and/or Inspection of Soil and Rock as Used in Engineering Design and Construction

2.2 API Document:

API Recommended Practice, Standard Procedure for Testing Drilling Fluids, Sixth Edition<sup>3</sup>

## 3. Terminology

3.1 *Definitions:* For common definitions of technical terms in this standard, refer to Terminology D653.

3.2 *Definitions of Terms Specific to This Standard:*

3.2.1 *marsh funnel viscosity (MFV)*—also known as *funnel viscosity*. The time required (in seconds) for 946 mL [1 qt] of a slurry to flow into a graduated cup from a funnel (known as a Marsh Funnel) with specific dimensions. The Marsh Funnel Viscosity is not a true viscosity, it is only an apparent value and good in a relative sense. High MFV values are obtained for slurries with high viscosity and low MFV values are obtained for slurries with low viscosity.

## 4. Summary of Test Method

4.1 In this method, a slurry is poured into a funnel with specific dimensions (Marsh Funnel). The slurry is then allowed to flow into a graduated cup. The time for the slurry to fill a volume of 946 mL [1 qt] is measured and reported as the Marsh Funnel Viscosity. The test temperature is also reported for comparison purposes.

## 5. Significance and Use

5.1 This test method allows for the assessment of an apparent viscosity of clay slurries in the laboratory and in the field. Viscosity is a fundamental characteristic for slurries in construction applications. The Marsh Funnel Viscosity test can be used for field quality control of slurries. Relative changes in slurry viscosity can be identified using Marsh Funnel measurements and modifications can be made to mixing and handling procedures.

<sup>3</sup> Available from American Petroleum Institute (API), 1220 L. St., NW, Washington, DC 20005-4070, http://www.api.org.