

SLOVENSKI STANDARD

oSIST prEN ISO 11403-1:2020

01-september-2020

Polimerni materiali - Pridobitev in predstavitev primerljivih podatkov, dobljenih pri različnih pogojih - 1. del: Mehanske lastnosti (ISO/DIS 11403-1:2020)

Plastics - Acquisition and presentation of comparable multipoint data - Part 1: Mechanical properties (ISO/DIS 11403-1:2020)

Kunststoffe - Ermittlung und Darstellung von vergleichbaren Vielpunkt-Kennwerten - Teil 1: Mechanische Eigenschaften (ISO/DIS 11403-1:2020)

Plastiques - Acquisition et présentation de données multiples comparables - Partie 1: Propriétés mécaniques (ISO/DIS 11403-1:2020)

[kSIST prEN ISO 11403-1:2021](https://standards.iteh.ai/catalog/standards/sist/51f1779b-86cc-4d5d-bfc7-4198-b32238/ksist-pr-en-iso-11403-1-2020)

[https://standards.iteh.ai/catalog/standards/sist/51f1779b-86cc-4d5d-bfc7-](https://standards.iteh.ai/catalog/standards/sist/51f1779b-86cc-4d5d-bfc7-4198-b32238/ksist-pr-en-iso-11403-1-2020)

Ta slovenski standard je istoveten z: prEN ISO 11403-1

ICS:

83.080.01	Polimerni materiali na splošno	Plastics in general
-----------	--------------------------------	---------------------

oSIST prEN ISO 11403-1:2020

en,fr,de

iTeh STANDARD PREVIEW (standards.iteh.ai)

[kSIST FprEN ISO 11403-1:2021](https://standards.iteh.ai/catalog/standards/sist/51f1779b-86cc-4d5d-bfc7-418fbbf32238/ksist-fpren-iso-11403-1-2021)

<https://standards.iteh.ai/catalog/standards/sist/51f1779b-86cc-4d5d-bfc7-418fbbf32238/ksist-fpren-iso-11403-1-2021>

DRAFT INTERNATIONAL STANDARD

ISO/DIS 11403-1

ISO/TC 61/SC 2

Secretariat: KATS

Voting begins on:
2020-07-06Voting terminates on:
2020-09-28

Plastics — Acquisition and presentation of comparable multipoint data —

Part 1: Mechanical properties

Plastiques — Acquisition et présentation de données multiples comparables —

Partie 1: Propriétés mécaniques

ICS: 83.080.01

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ksIST FprEN ISO 11403-1:2021](https://standards.iteh.ai/catalog/standards/sist/51f1779b-86cc-4d5d-bfc7-418fbbf32238/ksist-fpren-iso-11403-1-2021)

<https://standards.iteh.ai/catalog/standards/sist/51f1779b-86cc-4d5d-bfc7-418fbbf32238/ksist-fpren-iso-11403-1-2021>

THIS DOCUMENT IS A DRAFT CIRCULATED FOR COMMENT AND APPROVAL. IT IS THEREFORE SUBJECT TO CHANGE AND MAY NOT BE REFERRED TO AS AN INTERNATIONAL STANDARD UNTIL PUBLISHED AS SUCH.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

This document is circulated as received from the committee secretariat.

ISO/CEN PARALLEL PROCESSING



Reference number
ISO/DIS 11403-1:2020(E)

© ISO 2020

iTeh STANDARD PREVIEW (standards.iteh.ai)

[kSIST FprEN ISO 11403-1:2021](https://standards.iteh.ai/catalog/standards/sist/51f1779b-86cc-4d5d-bfc7-418fbbf32238/ksist-fpren-iso-11403-1-2021)

<https://standards.iteh.ai/catalog/standards/sist/51f1779b-86cc-4d5d-bfc7-418fbbf32238/ksist-fpren-iso-11403-1-2021>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2020

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	2
4 Specimen preparation	2
5 Conditioning	3
6 Test requirements	4
6.1 General.....	4
6.2 Dynamic modulus: ISO 6721-2 or ISO 6721-4.....	4
6.3 Tensile properties at constant test speed: ISO 527-1 and ISO 527-2.....	4
6.3.1 General.....	4
6.3.2 Ultimate stress and strain.....	4
6.3.3 Tensile stress-strain curves.....	5
6.4 Tensile creep: ISO 899-1.....	5
6.5 Charpy impact strength: ISO 179-1 or ISO 179-2.....	5
6.6 Puncture impact behaviour: ISO 6603-2.....	6
7 Presentation of data	6
8 Precision	7
Bibliography	12

ITEH STANDARD PREVIEW
(standards.iteh.ai)

[ksIST FprEN ISO 11403-1:2021](https://standards.iteh.ai/catalog/standards/sist/51f1779b-86cc-4d5d-bfc7-418fbbf32238/ksist-fpren-iso-11403-1-2021)

<https://standards.iteh.ai/catalog/standards/sist/51f1779b-86cc-4d5d-bfc7-418fbbf32238/ksist-fpren-iso-11403-1-2021>

ISO/DIS 11403-1:2020(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 2, *Mechanical behaviour*.

This fourth edition cancels and replaces the third edition (ISO 11403-1:2014), which has been technically revised. The main changes compared to the previous edition are as follows:

— ISO 13586, ISO 15850 and ISO 17281 are deleted in Bibliography.

A list of all parts in the ISO 11403 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

This International Standard has been prepared because users of plastics find sometimes that available data cannot be used readily to compare the properties of similar materials, especially when the data have been supplied by different sources. Even when the same standard tests have been used, they often allow the adoption of a wide range of alternative test conditions, and the data obtained are not necessarily comparable. The purpose of this International Standard is to identify specific methods and conditions of test to be used for the acquisition and presentation of data in order that valid comparisons between materials can be made.

ISO 10350 is concerned with single-point data. Such data represent the most basic method for characterizing materials and are useful for the initial stages of material selection. The present International Standard identifies test conditions and procedures for the measurement and presentation of a more substantial quantity of data. Each property here is characterized by multipoint data which demonstrate how that property depends upon important variables such as time, temperature and environmental effects. Additional properties are also considered in this standard. These data therefore enable more discriminating decisions to be made regarding a material's suitability for a particular application. Some data are also considered adequate for undertaking predictions of performance in service and of optimum processing conditions for moulding a component, although it should be recognized that, for purposes of design, additional data will often be needed. One reason for this is that some properties are strongly dependent upon the physical structure of the material. The test procedures referred to in this standard employ, where possible, the multipurpose tensile bar, and the polymer structure in this test specimen may be significantly different from that in specific regions of a moulded component. Under these circumstances, therefore, the data will not be suitable for accurate design calculations for product performance. The material supplier should be consulted for specific information on the applicability of data.

ISO 10350 and the various parts of this International Standard together define the means for acquiring and presenting a core set of comparable data for use in material selection. Use of these standards should result in a rationalization of effort and a reduction of cost associated with provision of these data. Furthermore, reference to these standards will simplify the development of data models for the computerized storage and exchange of data concerning material properties.

Where appropriate, values for test variables have been specified by this standard. For some tests however, owing to the wide range of conditions over which different plastics perform, the standard gives guidance in the selection of certain test conditions so that they cover the operating range for that polymer. Because, in general, the properties and performance specifications for different polymers differ widely, there is no obligation to generate data under all the test conditions specified in this standard.

Data on a wide range of properties are needed to enable plastics to be selected and used in the large variety of applications to which they are suited. ISO standards describe experimental procedures which are suitable for the acquisition of relevant information on many of these properties. The standard has therefore been divided into parts so that each part can be developed independently. In this way, additional properties can be included as new or revised standards become available.

iTeh STANDARD PREVIEW **(standards.iteh.ai)**

[kSIST FprEN ISO 11403-1:2021](https://standards.iteh.ai/catalog/standards/sist/51f1779b-86cc-4d5d-bfc7-418fbbf32238/ksist-fpren-iso-11403-1-2021)

<https://standards.iteh.ai/catalog/standards/sist/51f1779b-86cc-4d5d-bfc7-418fbbf32238/ksist-fpren-iso-11403-1-2021>

Plastics — Acquisition and presentation of comparable multipoint data —

Part 1: Mechanical properties

1 Scope

This document specifies test procedures for the acquisition and presentation of multipoint data on the following mechanical properties of plastics:

- dynamic modulus;
- tensile properties at constant test speed;
- ultimate stress and strain;
- tensile stress-strain curves;
- tensile creep;
- Charpy impact strength;
- puncture impact behaviour.

The test methods and test conditions apply predominantly to those plastics that can be injection- or compression-moulded or prepared as sheets of specified thickness from which specimens of the appropriate size can be machined.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 179-1, *Plastics — Determination of Charpy impact properties — Part 1: Non-instrumented impact test*

ISO 179-2, *Plastics — Determination of Charpy impact properties — Part 2: Instrumented impact test*

ISO 293, *Plastics — Compression moulding of test specimens of thermoplastic materials*

ISO 294-1, *Plastics — Injection moulding of test specimens of thermoplastic materials — Part 1: General principles, and moulding of multipurpose and bar test specimens*

ISO 294-3, *Plastics — Injection moulding of test specimens of thermoplastic materials — Part 3: Small plates*

ISO 295, *Plastics — Compression moulding of test specimens of thermosetting materials*

ISO 527-1, *Plastics — Determination of tensile properties — Part 1: General principles*

ISO 527-2, *Plastics — Determination of tensile properties — Part 2: Test conditions for moulding and extrusion plastics*

ISO 899-1, *Plastics — Determination of creep behaviour — Part 1: Tensile creep*

ISO 2818, *Plastics — Preparation of test specimens by machining*

ISO/DIS 11403-1:2020(E)

ISO 6603-2, *Plastics — Determination of puncture impact behaviour of rigid plastics — Part 2: Instrumented impact testing*

ISO 6721-2, *Plastics — Determination of dynamic mechanical properties — Part 2: Torsion-pendulum method*

ISO 6721-4, *Plastics — Determination of dynamic mechanical properties — Part 4: Tensile vibration — Non-resonance method*

ISO 10724-1, *Plastics — Injection moulding of test specimens of thermosetting powder moulding compounds (PMCs) — Part 1: General principles and moulding of multipurpose test specimens*

ISO 10724-2, *Plastics — Injection moulding of test specimens of thermosetting powder moulding compounds (PMCs) — Part 2: Small plates*

ISO 20753, *Plastics — Test specimens*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

— ISO Online browsing platform: available at <https://www.iso.org/obp>

— IEC Electropedia: available at <http://www.electropedia.org/>

3.1 multipoint data
data characterizing the behaviour of a plastics material by means of a number of test results for a property measured over a range of test conditions

4 Specimen preparation

In the preparation of specimens by injection or compression moulding, the procedures described in ISO 293, ISO 294-1 and 294-3, ISO 295 or ISO 10724-1 and 10724-2 shall be used. The method of moulding and the conditions will depend upon the material being moulded. If these conditions are specified in the International Standard appropriate to the material, then they shall be adopted, where possible, for the preparation of every specimen on which data are obtained using this document. For those plastics for which moulding conditions have not yet been standardized, the conditions employed shall be within the range recommended by the polymer manufacturer and shall, for each of the processing methods, be the same for every specimen. Where moulding conditions are not stipulated in any International Standard, the values used for the parameters in [Table 1](#) shall be recorded with the data for that material.

Where specimens are prepared by machining from sheet, the machining shall be performed in accordance with ISO 2818.

Table 1 — Moulding parameters

Type of moulding material and moulding method	Standard (where applicable)	Moulding parameters
Thermoplastic Injection	ISO 294-1 and 294-3	Melt temperature Mould temperature Injection velocity ^a
^a Values specified in materials standards refer to the preparation of the multipurpose test specimen only (see ISO 294-1). For the preparation of small plate specimens (see ISO 294-3), values for the injection velocity shall be chosen to give an injection time comparable to that achieved with the multipurpose test specimen.		

Table 1 (continued)

Type of moulding material and moulding method	Standard (where applicable)	Moulding parameters
Thermoplastic Compression	ISO 293	Mould temperature Moulding time Cooling rate Demoulding temperature
Thermosetting Injection	ISO 10724-1 and 10724-2	Injection temperature Mould temperature Injection velocity Cure time
Thermosetting Compression	ISO 295	Mould temperature Moulding pressure Cure time

^a Values specified in materials standards refer to the preparation of the multipurpose test specimen only (see ISO 294-1). For the preparation of small plate specimens (see ISO 294-3), values for the injection velocity shall be chosen to give an injection time comparable to that achieved with the multipurpose test specimen.

5 Conditioning

After moulding, specimens shall be conditioned for $28 \text{ d} \pm 2 \text{ d}$ at $23 \text{ °C} \pm 2 \text{ °C}$ and $(50 \pm 10) \%$ relative humidity prior to testing (see note) unless special conditioning is required by the relevant material standards. For those materials whose properties are known to be insensitive to moisture, the control of relative humidity is not necessary. Where it can be demonstrated that the use of a shorter conditioning period has no significant influence on the measured properties, then this shorter period may be used and shall be recorded with the property data in the tables in [Clause 7](#).

NOTE Changes in the molecular structure of a test specimen occur following cooling from the moulding temperature. At elevated temperatures, changes in the size and structure of crystalline regions will take place. In amorphous regions, molecular rearrangements will also occur (physical ageing) and, whereas changes in crystallinity are inhibited at temperatures below the glass transition temperature, physical ageing continues in many polymers at ambient temperatures. These structural changes have a significant influence on certain properties and therefore give rise to a dependence of properties on thermal history. By prescribing an isothermal conditioning period for specimens prior to testing, a reproducible and traceable structural state is established for subsequent measurements carried out in the short-term around, or slightly above, ambient temperatures. However, when measurements are made over a wider and increasing temperature range, or at a constant elevated temperature, further structural changes can take place during the test. Subsequent cooling will establish different structural states and, if the test is non-destructive, repeat measurements will not reproduce previous values.

If special conditioning procedures are specified in material standards which involve heating, to prepare specimens in their dry state or with a more stable structure, then, after conditioning, specimens shall be heated to the glass transition temperature of the polymer and held at that temperature for a period of 20 min and subsequently cooled in still air at 23 °C prior to conditioning for $28 \text{ d} \pm 2 \text{ d}$ at $23 \text{ °C} \pm 2 \text{ °C}$. Where data on materials whose properties are sensitive to water content are to be presented for the polymer in its dry state, conditioning shall be carried out at 0 % relative humidity.

Where specimens have been subject to a thermal history under conditions other than 23 °C and 50 % relative humidity, details of this history shall be recorded with the associated property data in the tables in [Clause 7](#).

Subsequent thermal conditioning is required for certain tests and is specified with test requirements in [Clause 6](#).