



SLOVENSKI STANDARD SIST EN ISO 11403-3:2021

01-september-2021

Nadomešča:

SIST EN ISO 11403-3:2014

Polimerni materiali - Pridobitev in predstavitev primerljivih podatkov, dobljenih pri različnih pogojih - 3. del: Vplivi okolja na lastnosti (ISO 11403-3:2021)

Plastics - Acquisition and presentation of comparable multipoint data - Part 3: Environmental influences on properties (ISO 11403-3:2021)

Kunststoffe - Ermittlung und Darstellung von vergleichbaren Vielpunkt-Kennwerten - Teil 3: Umgebungseinflüsse auf Eigenschaften (ISO 11403-3:2021)

Plastiques - Acquisition et présentation de données multiples comparables - Partie 3: Effets induits par l'environnement sur les propriétés (ISO 11403-3:2021)

Ta slovenski standard je istoveten z: EN ISO 11403-3:2021

ICS:

83.080.01	Polimerni materiali na splošno	Plastics in general
-----------	--------------------------------	---------------------

SIST EN ISO 11403-3:2021

en,fr,de

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 11403-3:2021](#)

<https://standards.iteh.ai/catalog/standards/sist/751e31d9-4ae1-43c0-840a-54767ebf0285/sist-en-iso-11403-3-2021>

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN ISO 11403-3

June 2021

ICS 83.080.01

Supersedes EN ISO 11403-3:2014

English Version

**Plastics - Acquisition and presentation of comparable
multipoint data - Part 3: Environmental influences on
properties (ISO 11403-3:2021)**

Plastiques - Acquisition et présentation de données
multiples comparables - Partie 3: Effets induits par
l'environnement sur les propriétés (ISO 11403-
3:2021)

Kunststoffe - Ermittlung und Darstellung von
vergleichbaren Vielpunkt-Kennwerten - Teil 3:
Umgebungseinflüsse auf Eigenschaften (ISO 11403-
3:2021)

This European Standard was approved by CEN on 6 June 2021.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

Contents	Page
European foreword.....	3

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 11403-3:2021](https://standards.iteh.ai/catalog/standards/sist/751e31d9-4ae1-43c0-840a-54767ebf0285/sist-en-iso-11403-3-2021)
<https://standards.iteh.ai/catalog/standards/sist/751e31d9-4ae1-43c0-840a-54767ebf0285/sist-en-iso-11403-3-2021>

European foreword

This document (EN ISO 11403-3:2021) has been prepared by Technical Committee ISO/TC 61 "Plastics" in collaboration with Technical Committee CEN/TC 249 "Plastics" the secretariat of which is held by NBN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by December 2021, and conflicting national standards shall be withdrawn at the latest by December 2021.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 11403-3:2014.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

iTeh STANDARD PREVIEW
Endorsement notice
(standards.iteh.ai)

The text of ISO 11403-3:2021 has been approved by CEN as EN ISO 11403-3:2021 without any modification.

<https://standards.iteh.ai/catalog/standards/sist/751e31d9-4ae1-43c0-840a-54767ebf0285/sist-en-iso-11403-3-2021>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 11403-3:2021](#)

<https://standards.iteh.ai/catalog/standards/sist/751e31d9-4ae1-43c0-840a-54767ebf0285/sist-en-iso-11403-3-2021>

INTERNATIONAL STANDARD

ISO 11403-3

Third edition
2021-06

Plastics — Acquisition and presentation of comparable multipoint data —

Part 3: Environmental influences on properties

iTeh STANDARD PREVIEW

(standards.iteh.ai)
*Plastiques — Acquisition et présentation de données multiples
comparables —*

Partie 3: Effets induits par l'environnement sur les propriétés

<https://standards.iteh.ai/catalog/standards/sist/751e31d9-4ae1-43c0-840a-54767ebf0285/sist-en-iso-11403-3-2021>



Reference number
ISO 11403-3:2021(E)

© ISO 2021

iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST EN ISO 11403-3:2021](https://standards.iteh.ai/catalog/standards/sist/751e31d9-4ae1-43c0-840a-54767ebf0285/sist-en-iso-11403-3-2021)

<https://standards.iteh.ai/catalog/standards/sist/751e31d9-4ae1-43c0-840a-54767ebf0285/sist-en-iso-11403-3-2021>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2021

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	2
4 Specimen preparation	2
5 Conditioning	3
6 Test requirements	3
6.1 General.....	3
6.2 Indicative properties and indicative data.....	4
6.3 Test specimens.....	4
6.4 Test speed.....	4
6.5 Prolonged exposure to heat: ISO 2578.....	4
6.6 Liquid chemicals.....	6
6.7 Environmental stress cracking under constant tensile stress: ISO 22088 ^[10]	6
6.8 Artificial weathering: ISO 4892-2.....	8
6.9 Set of exposure conditions 1: Open air.....	8
6.10 Set of exposure conditions 2: Behind glass, low temperature.....	8
6.11 Set of exposure conditions 3: Behind glass, high temperature.....	9
7 Presentation of data	9
8 Precision	11
Annex A (informative) Information relating to certain test requirements	12
Annex B (normative) Chemicals for chemical resistance and environmental stress cracking resistance tests	14
Bibliography	15

ISO 11403-3:2021(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 2, *Mechanical behaviour*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 249, *Plastics*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This third edition cancels and replaces the second edition (ISO 11403-3:2014), of which it constitutes a minor revision.

The changes compared to the previous edition are as follows:

- unified the indication methods of the unit;
- unified the quotation of the specimen shape in ISO 20753;
- performed the editorial corrections.

A list of all parts in the ISO 11403 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

This document has been prepared because users of plastics find sometimes that available data cannot be used readily to compare the properties of similar materials, especially when the data have been supplied by different sources. Even when the same standard tests have been used, they often allow the adoption of a wide range of alternative test conditions, and the data obtained are not necessarily comparable. The purpose of this document is to identify specific methods and conditions of test to be used for the acquisition and presentation of data in order that valid comparisons between materials can be made. These data are not necessarily suitable for design.

The ISO 10350 series^{[Z][8]} is concerned with single-point data. Such data represent the most basic method for characterizing materials and are useful for the initial stages of material selection. This document identifies test conditions and procedures for the measurement and presentation of a more substantial quantity of data. Each property here is characterized by multipoint data which demonstrate how that property depends upon important variables such as time, temperature and environmental effects. Additional properties are also considered in this document. These data therefore enable more discriminating decisions to be made regarding the material's suitability for a particular application. Some data are also considered adequate for undertaking predictions of performance in service and of optimum processing conditions for moulding a component, although it should be recognized that, for purposes of design, additional data are often needed. One reason for this is that some properties are strongly dependent upon the physical structure of the material. The test procedures referred to in this document employ standard test specimens, and the polymer structure in these specimens may be significantly different from that in specific regions of a moulded component. Under these circumstances, therefore, the data are not suitable for accurate design calculations for product performance. The material supplier should be consulted for specific information on the applicability of data.

The ISO 10350 series together with the ISO 11403 series define the means for acquiring and presenting a core set of comparable data for use in material selection. Use of these International Standards should result in a rationalization of effort and a reduction of cost associated with provision of these data. Furthermore, reference to these International Standards simplifies the development of data models for the computerized storage and exchange of data concerning material properties.

Where appropriate, values for test variables have been specified by this document. For some tests however, owing to the wide range of conditions over which different plastics perform, the standard gives guidance in the selection of certain test conditions so that they cover the operating range for that polymer. Because, in general, the properties and performance specifications for different polymers differ widely, there is no obligation to generate data under all the test conditions specified in this document.

Data on a wide range of properties are needed to enable plastics to be selected and used in the large variety of applications to which they are suited. ISO standards describe experimental procedures which are suitable for the acquisition of relevant information on many of these properties. For other properties, however, ISO standards either do not exist or exhibit shortcomings that complicate their use at present for the generation of comparable data (see [Annex A](#)). The ISO 11403 series has therefore been divided into parts so that each part can be developed independently. In this way, additional properties can be included as new or revised standards become available.