



SLOVENSKI STANDARD
SIST-TP CEN ISO/TR 19402:2020

01-december-2020

Barve in laki - Oprijemljivost premazov (ISO/TR 19402:2018)

Paints and varnishes - Adhesion of coatings (ISO/TR 19402:2018)

Beschichtungsstoffe - Haftfestigkeit von Beschichtungen (ISO/TR 19402:2018)

Peintures et vernis - Adhérence des revêtements (ISO/TR 19402:2018)

Ta slovenski standard je istoveten z: CEN ISO/TR 19402:2020

[SIST-TP CEN ISO/TR 19402:2020](https://standards.iteh.ai/catalog/standards/sist/e36a46a5-7a01-4ffb-aea6-dab94d39af9c/sist-tp-cen-iso-tr-19402-2020)

<https://standards.iteh.ai/catalog/standards/sist/e36a46a5-7a01-4ffb-aea6-dab94d39af9c/sist-tp-cen-iso-tr-19402-2020>

ICS:

87.040 Barve in laki Paints and varnishes

SIST-TP CEN ISO/TR 19402:2020 **en,fr,de**

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST-TP CEN ISO/TR 19402:2020](https://standards.iteh.ai/catalog/standards/sist/e36a46a5-7a01-4ffb-aea6-dab94d39af9c/sist-tp-cen-iso-tr-19402-2020)

<https://standards.iteh.ai/catalog/standards/sist/e36a46a5-7a01-4ffb-aea6-dab94d39af9c/sist-tp-cen-iso-tr-19402-2020>

TECHNICAL REPORT

CEN ISO/TR 19402

RAPPORT TECHNIQUE

TECHNISCHER BERICHT

October 2020

ICS 87.040

English Version

Paints and varnishes - Adhesion of coatings (ISO/TR 19402:2018)

Peintures et vernis - Adhérence des revêtements
(ISO/TR 19402:2018)

Beschichtungsstoffe - Haftfestigkeit von
Beschichtungen (ISO/TR 19402:2018)

This Technical Report was approved by CEN on 4 October 2020. It has been drawn up by the Technical Committee CEN/TC 139.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST-TP CEN ISO/TR 19402:2020](https://standards.iteh.ai/catalog/standards/sist/e36a46a5-7a01-4ffb-aea6-dab94d39af9c/sist-tp-cen-iso-tr-19402-2020)

<https://standards.iteh.ai/catalog/standards/sist/e36a46a5-7a01-4ffb-aea6-dab94d39af9c/sist-tp-cen-iso-tr-19402-2020>



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

Contents	Page
European foreword.....	3

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST-TP CEN ISO/TR 19402:2020](https://standards.iteh.ai/catalog/standards/sist/e36a46a5-7a01-4ffb-aea6-dab94d39af9c/sist-tp-cen-iso-tr-19402-2020)
<https://standards.iteh.ai/catalog/standards/sist/e36a46a5-7a01-4ffb-aea6-dab94d39af9c/sist-tp-cen-iso-tr-19402-2020>

European foreword

The text of ISO/TR 19402:2018 has been prepared by Technical Committee ISO/TC 35 "Paints and varnishes" of the International Organization for Standardization (ISO) and has been taken over as CEN ISO/TR 19402:2020 by Technical Committee CEN/TC 139 "Paints and varnishes" the secretariat of which is held by DIN.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

Endorsement notice

The text of ISO/TR 19402:2018 has been approved by CEN as CEN ISO/TR 19402:2020 without any modification.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST-TP CEN ISO/TR 19402:2020](https://standards.iteh.ai/catalog/standards/sist/e36a46a5-7a01-4ffb-aea6-dab94d39af9c/sist-tp-cen-iso-tr-19402-2020)

<https://standards.iteh.ai/catalog/standards/sist/e36a46a5-7a01-4ffb-aea6-dab94d39af9c/sist-tp-cen-iso-tr-19402-2020>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST-TP CEN ISO/TR 19402:2020](https://standards.iteh.ai/catalog/standards/sist/e36a46a5-7a01-4ffb-aea6-dab94d39af9c/sist-tp-cen-iso-tr-19402-2020)

<https://standards.iteh.ai/catalog/standards/sist/e36a46a5-7a01-4ffb-aea6-dab94d39af9c/sist-tp-cen-iso-tr-19402-2020>

TECHNICAL REPORT

ISO/TR 19402

First edition
2018-08

Paints and varnishes — Adhesion of coatings

Peintures et vernis — Adhérence des revêtements

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST-TP CEN ISO/TR 19402:2020](https://standards.iteh.ai/catalog/standards/sist/e36a46a5-7a01-4ffb-aea6-dab94d39af9c/sist-tp-cen-iso-tr-19402-2020)

<https://standards.iteh.ai/catalog/standards/sist/e36a46a5-7a01-4ffb-aea6-dab94d39af9c/sist-tp-cen-iso-tr-19402-2020>



Reference number
ISO/TR 19402:2018(E)

© ISO 2018

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST-TP CEN ISO/TR 19402:2020

<https://standards.iteh.ai/catalog/standards/sist/e36a46a5-7a01-4ffb-aea6-dab94d39af9c/sist-tp-cen-iso-tr-19402-2020>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2018

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword	v
Introduction	vi
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Adhesive strength tests without scratch/cut	3
4.1 Tests with mechanical stress application on the coating.....	3
4.1.1 Pull-off test.....	3
4.1.2 Twist-off test.....	5
4.1.3 Peel-off test 1.....	6
4.1.4 Peel-off test 2.....	8
4.2 Tests with continuous deformation of test specimens.....	9
4.2.1 Bend test with a wedge-shaped conical mandrel.....	9
4.2.2 Bend test with a conical mandrel.....	11
4.2.3 Bend test with a cylindrical mandrel 1.....	12
4.2.4 Bend test with a cylindrical mandrel 2.....	14
4.2.5 Three point bending method.....	15
4.2.6 T-bend test 1.....	17
4.2.7 T-bend test 2.....	19
4.2.8 Cupping test 1.....	20
4.3 Test with impact stress application.....	22
4.3.1 Single-impact test 1.....	22
4.3.2 Single-impact test 2.....	25
4.3.3 Single-impact test 3.....	27
4.3.4 Single-impact test 4.....	28
4.3.5 Falling-weight test 1.....	30
4.3.6 Falling-weight test 2.....	33
4.3.7 Falling-weight test 3.....	35
4.3.8 Multi-impact test 1.....	36
4.3.9 Multi-impact test 2.....	38
4.3.10 Multi-impact test 3.....	41
4.3.11 Multi-impact test 4.....	43
4.3.12 Impact-bend test.....	44
5 Adhesive strength tests with scratch/cut	45
5.1 Tests with single scratch.....	45
5.1.1 Scratch test 1.....	45
5.1.2 Scratch test 2.....	46
5.1.3 Scratch test 3 (Scrape-adhesion test).....	47
5.2 Test with multiple scratch (without deformation of test specimens).....	49
5.2.1 Pressure-water jetting test.....	49
5.2.2 Cross-cut test 1.....	53
5.2.3 Cross-cut test 2.....	56
5.2.4 Cross-cut test 3.....	57
5.2.5 X-cut test 1.....	58
5.2.6 X-cut test 2.....	58
5.2.7 X-cut test 3.....	59
5.2.8 X-cut test 4.....	59
5.2.9 Scribe test with a square-diagonal grid.....	60
5.2.10 Scribe test with a rhombus grid.....	61
5.3 Test with multiple scratch (with deformation of test specimens).....	62
5.3.1 Cupping test 2.....	62
6 Evaluation methods for adhesive strength	63

ISO/TR 19402:2018(E)

6.1	Auxiliary methods.....	63
6.1.1	Contrasting 1.....	63
6.1.2	Contrasting 2.....	64
6.2	Visual methods.....	64
6.2.1	Failure pattern analysis.....	64
6.2.2	Comparison of areas.....	65
6.2.3	General assessment.....	66
6.3	Instrumental methods.....	67
6.3.1	Digital image evaluation 1.....	67
6.3.2	Digital image evaluation 2.....	67
Annex A Synoptical tables for the methods.....		69
Bibliography.....		76

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST-TP CEN ISO/TR 19402:2020

<https://standards.iteh.ai/catalog/standards/sist/e36a46a5-7a01-4ffb-aea6-dab94d39af9c/sist-tp-cen-iso-tr-19402-2020>

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 35, *Paints and varnishes*, Subcommittee SC 9, *General test methods for paints and varnishes*.

SIST-TP CEN ISO/TR 19402:2020
<https://standards.iteh.ai/catalog/standards/sist/e36a46a5-7a01-4ffb-aea6-dab94d39af9c/sist-tp-cen-iso-tr-19402-2020>

ISO/TR 19402:2018(E)**Introduction**

The determination of the adhesive strength is one of the most important preconditions for evaluating the protective function of coatings.

This document offers a helpful overview for the selection of the test method most suitable for each individual case in regard to the evaluation of the adhesive strength.

**iTeh STANDARD PREVIEW
(standards.iteh.ai)**

[SIST-TP CEN ISO/TR 19402:2020](https://standards.iteh.ai/catalog/standards/sist/e36a46a5-7a01-4ffb-aea6-dab94d39af9c/sist-tp-cen-iso-tr-19402-2020)

<https://standards.iteh.ai/catalog/standards/sist/e36a46a5-7a01-4ffb-aea6-dab94d39af9c/sist-tp-cen-iso-tr-19402-2020>

Paints and varnishes — Adhesion of coatings

1 Scope

This document summarises the common methods for evaluating the adhesive strength of coatings on a substrate, which can be another coating beneath or the substrate itself. The test methods and evaluation methods are described in [Clauses 4, 5, and 6](#). In the case of standardized test methods the respective standard is referenced in regard to procedure and evaluation. [Annex A](#) compares the methods in the synoptic [Tables A.1, A.2, and A.3](#).

Often the adhesive strength cannot be sufficiently evaluated by means of a single method.

The purely physical methods for measuring the adhesive strength are such in which mechanical quantities (e.g. force or torsion moment) are measured directly.

All other methods are based on the evaluation of behaviour under mechanic stress according to practical conditions. For these methods the viscoelastic properties have a wide influence on the evaluation of the adhesive strength, so that it can only be tested comparatively within one method.

Each method has its specific application. An unsuitable method can lead to false information. All of the test methods for the evaluation of the adhesive strength require a certain routine of the test person, especially in regard to identifying the separation line. For most of the test methods the test results, among other things, depend on the film thickness of the coating to be tested. In addition, for several methods differences between tests on a test sheet and in practice can occur, due to different roughness of the substrate.

Effects of delamination caused by weathering or corrosion influences are not subject of this document.

In case cohesion failures predominantly occur during an adhesive strength test, this is no measure for the adhesive strength. However, information can be given on the protective effect of the coating against corrosion.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 4618, *Paints and varnishes — Terms and definitions*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 4618 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

3.1

adhesion

phenomenon of attachment at the interface between a solid surface and another material caused by molecular forces

Note 1 to entry: Adhesion should not be confused with cohesion.

ISO/TR 19402:2018(E)

[SOURCE: ISO 4618:2014, 2.7]

3.2

cohesion

forces that bind a film or coat into an integral entity

Note 1 to entry: Cohesion should not be confused with adhesion.

[SOURCE: ISO 4618:2014, 2.55]

3.3

adhesion failure

detachment of a coating from the substrate caused by external forces

Note 1 to entry: The substrate can be another coating beneath or the working material.

3.4

cohesion failure

loss of coherence within a coating caused by external forces

3.5

adhesive strength

force required to detach a coating from a substrate or another coating

[SOURCE: ISO 4618:2014, 2.8]

3.6

wet adhesive strength

adhesive strength (3.5) immediately after previous exposure to moisture

iTeh STANDARD PREVIEW
(standards.iteh.ai)

3.7

separation line

interface in which *adhesion failure* (3.3) occurs

SIST-TP CEN ISO/TR 19402:2020

<https://standards.iteh.ai/catalog/standards/sist/e36a46a5-7a01-4ffb-aca6-dab94d39af9c/sist-tp-cen-iso-tr-19402-2020>

3.8

failure pattern

entirety of the visual coating defects, which are caused by an *adhesive strength* (3.5) test

3.9

failure pattern assessment

classification of a *failure pattern* (3.8) by means of criteria or reference patterns

3.10

failure pattern analysis

quantitative evaluation of a *failure pattern* (3.8) with specification of the relative percentages of area for *adhesion failure* (3.3) and *cohesion failure* (3.4) as well as the separation line(s)

3.11

main separation line

separation line with the largest area

3.12

repeatability conditions

conditions where independent test results are obtained with the same method on identical test items in the same laboratory by the same operator using the same equipment within short intervals of time

[SOURCE: ISO 5725-1:1994, 3.14]

3.13 repeatability limit

r

the value less than or equal to which the absolute difference between two test results obtained under *repeatability conditions* (3.12) may be expected to be with a probability of 95 %

[SOURCE: ISO 5725-1:1994, 3.16]

3.14 reproducibility conditions

conditions where independent test results are obtained with the same method on identical test items in different laboratories with different operators using different equipment

[SOURCE: ISO 5725-1:1994, 3.18]

3.15 reproducibility limit

R

the value less than or equal to which the absolute difference between two test results obtained under *reproducibility conditions* (3.14) may be expected to be with a probability of 95 %

[SOURCE: ISO 5725-1:1994, 3.20]

4 Adhesive strength tests without scratch/cut

4.1 Tests with mechanical stress application on the coating (standards.iteh.ai)

4.1.1 Pull-off test

- Principle <https://standards.iteh.ai/catalog/standards/sist/e36a46a5-7a01-4ffb-aea6-dab94d39af9c/sist-tp-cen-iso-tr-19402-2020>

A uniformly increasing tensile force is applied to a test cylinder (metal cylinder of diameter 20 mm), which is adhered to the coating, until the test cylinder is pulled off. The pull-off strength is determined by calculating the tensile force to pull off the test cylinder and the area of the test cylinder.

The principle of the pull-off test is illustrated schematically in [Figure 1](#).