

Designation: B327-09 Designation: B327 - 09a

Standard Specification for Master Alloys Used in Making Zinc Die Casting Alloys¹

This standard is issued under the fixed designation B327; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

- 1.1 This specification covers aluminum—base and <u>zinc—base zinc—base</u> master alloys used to make zinc die-casting alloys. Alloy compositions specified for aluminum—base master alloys (hardeners) are designated as shown in Table 1. Alloy compositions specified for the zinc-base master alloys are designated as shown in Table 2.
- 1.2 Aluminum alloy hardeners are added to Special High Grade zinc (per Specification B6) in the proper alloying ratios, as shown in Table 1, to produce zinc alloys for die casting.
- 1.3 Zinc-base master alloy is added to Special High Grade zinc (per Specification B6) in the proper alloying ratio, as shown in Table 3, to produce zinc alloy for die casting.
 - 1.4 Master alloys may be supplied in the form of shot, bar, ingot or jumbo ingot as specified by the purchaser.
- 1.5 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.
- 1.6 This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to become familiar with all hazards including those identified in the appropriate Material Safety Data Sheet (MSDS) for this product/material as provided by the manufacturer, to establish appropriate safety and health practices, and determine the applicability of regulatory limitations prior to use.

2. Referenced Documents

- 2.1 The following documents of the issue in effect on date of order acceptance form a part of this specification to the extent referenced herein:
 - 2.2 ASTM Standards:²
 - **B6** Specification for Zinc
 - B899 Terminology Relating to Non-ferrous Metals and Alloys
 - B908 Practice for the Use of Color Codes for Zinc Casting Alloy Ingot
 - E29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications
 - E34 Test Methods for Chemical Analysis of Aluminum and Aluminum-Base Alloys
 - E88 Practice for Sampling Nonferrous Metals and Alloys in Cast Form for Determination of Chemical Composition
 - E101 Test Method for Spectrographic Analysis of Aluminum and Aluminum Alloys by the Point-to-Plane Technique³
 - E227 Test Method for Optical Emission Spectrometric Analysis of Aluminum and Aluminum Alloys by the Point-to-Plane Technique
 - E527 Practice for Numbering Metals and Alloys in the Unified Numbering System (UNS)
 - E536 Test Methods for Chemical Analysis of Zinc and Zinc Alloys
 - 2.3 ISO Standards:⁴
 - ISO 3815-1 Zinc and zinc alloys Part 1: Analysis of solid samples by optical emission spectrometry
 - ISO 3815-2 Zinc and zinc alloys Part 2: Analysis by inductively coupled plasma optical emission spectrometry

3. Terminology

- 3.1 Terms shall be defined in accordance with Terminology B899.
- 3.2 Definitions of Terms Specific to This Standard:

¹ This specification is under the jurisdiction of ASTM Committee B02 on Nonferrous Metals and Alloys and is the direct responsibility of Subcommittee B02.04 on Zinc and Cadmium.

Current edition approved April 15, Oct. 1, 2009. Published June November 2009. Originally approved in 1958. Last previous edition approved in 2008 2009 as B327 – 089. DOI: 10.1520/B0327-09A.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Withdrawn

⁴ Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, http://www.ansi.org.

TABLE 1 Chemical Requirements for Aluminum-Base Master Alloys

Note 1—The following applies to all specified limits in this table: For purposes of determining conformance with this specification, the observed value or calculated value obtained from analysis shall be rounded off "to the nearest unit" in the last right hand place of figures used in expressing the specified limit, in accordance with the rounding method of Practice E29.

ASTM	Composition, percent										_		
Alloy (UNS) ^A	Alu- minum, min	Copper	Iron, max	Silicon, max	Manga- nese, max	Magnesium ^B	Zinc	Chro- mium, max	Nickel, max	Tin, max	Lead, max ^B	Cad- mium, max ^B	Usage
ZG71A (A07131)ht	87.0 tp://myastr	1.7 max n.astm.org/§	0.8 SUPPOR	0.7 T_DOCS/B(0.50 9 20000010 9	0.65–1.05 015.pdf	6.5-7.5	0.20	0.20	0.02	0.020	0.010	1 part by weight of ZG71A, 21 parts by weight of Special High Grade zinc ^C to make ASTM zinc Alloy Z33520 (AG40A)
ZG71A (A07131)	87.0	1.7 max	0.8	0.7	0.50	0.65–1.05	6.5-7.5	0.20	0.20	0.02	0.020	0.010	1 part by weight of ZG71A, 21 parts by weight of Special High Grade zinc ^C to make ASTM zinc Alloy Z33520 (AG40A)

^A UNS designations were established in accordance with Recommended Practice E527.

TABLE 2 Chemical and Color Code Requirements for Zinc-Base Master Alloys A,B,C

Common (UNS)	Color Code ^D	Composition, percent							
Alum- inum Alum-	Mag- nesium Aluminum	Magnesium Magnesium	Iron, max Iron	Copper, max Copper	Lead, max Lead	Cadmium, max Cadmium	Tin, max Tin	Zinc Zinc	
inum V12 (Z33730)	Pink	11.7 12.6	max. 0.075 0.12	max. 0.070	max. 0.25	max. 0.005	max. 0.004	0.003	remain-der
<u>V12-3</u> (Z33730)	<u>Pink</u>	11.7–12.6	0.090-0.16	0.070	0.025 max	0.005	0.004	0.003	Remainder
V12–5 (Z)	Pink/Black	11.7–12.6	0.090-0.16	0.070	2.1–3.3	0.005	0.004	0.003	<u>Remain</u> der

A Zinc-base master alloys V12-3 (Z33730) and V12-5 (Z----) used for producing die casting alloys may contain nickel, chromium, silicon, and manganese up to 0.02, 0.035 and 0.05 %, respectively. No harmful effects have ever been noted due to the presence of these elements in up to these concentrations in die casting alloys and, therefore, analyses are not required for these elements, except that nickel analysis is required when producing die casting alloy Z33522 or Z35530.

nttps://standards.iteh.ai/catalog/standards/sist/88128ffd-14d0-4a14-8f86-11f68408777f/astm-b327-09

TABLE 3 Weight Requirements for Zinc-Base Master Alloy Jumbo Ingots

Note 1—These requirements are based on the use of nominal 2400 lb or 1200 lb jumbo ingots of V12 (Z33730).

Nominal		Weight R	ange, Ib ^A	Usage					
_	Weight, lb	Minimum	Maximum	Osage					
	2400	2325	2475	1 part by weight of V12 (one 2400 lb jumbo ingot), 2 parts by weight (two 2400 lb jumbo ingots) of Special High Grade zinc to make ASTM zinc alloyZ 33520 (AG40A).					
	2400	<u>2325</u>	<u>2475</u>	1 part by weight of V12-3 (one 2400 lb jumbo ingot), 2 parts by weight (two 2400 lb jumbo ingots) of Special High Grade zinc to make zinc alloy 3 (Zamak 3, UNS Z33520, AG40A) or 1 part by weight of V12-5 (one 2400 lb jumbo ingot), 2 parts by weight (two 2400 lb jumbo ingots) of Special High					
	1200	1150	1250	Grade zinc to make zinc alloy 5 (Zamak 5, UNS Z35531, AC41A) 1 part by weight of V12-3 (one 1200 lb jumbo ingot), 2 parts by weight (one 2400 lb jumbo ingot) of Special High Grade zinc to make zinc alloy 3 (Zamak 3, UNS Z33520, AG40A) or 1 part by weight of V12 (one 1200 lb jumbo ingot), 2 parts by weight (one 2400 lb jumbo ingot) of Special High Grade					
-				zine to make ASTM zine alleyZ33520 (AG40A). 1 part by weight of V12-5 (one 1200 lb jumbo ingot), 2 parts by weight (one 2400 lb jumbo ingot) of Special High Grade					
				zinc to make zinc alloy 5 (Zamak 5, UNS Z35531, AC41A)					

^A Jumbo ingots outside the above weight limits may be acceptable depending upon the chemistry, if mutually agreed upon between the producer and purchaser.

3.2.1 *hardener*, *n*—an aluminum-base master alloy added to Special High Grade Zinc (SHG) to produce a zinc alloy for die casting.

4. Ordering Information

- 4.1 Orders for master alloys under this specification shall include the following information:
- 4.1.1 Quantity,

^B Carried to one additional decimal place to ensure proper control in the final alloy.

^C ASTM Specification B6, for Zinc.

^B The UNS assignations were established in accordance with Practice E527.

^C For purposes of determining conformance with this specification, the observed value or calculated value obtained from analysis shall be rounded off "to the nearest unit" in the last right hand place of figures used in expressing the specified limit, in accordance with the rounding method of Practice E29.

^D Refer to Practice B908. (Note: Color Codes indicated are for North American applications.)