
Dodajni materiali za varjenje - Žične in tračne elektrode, žice in palice za talilno varjenje niklja in nikljevih zlitin - Razvrstitev (ISO/DIS 18274:2021)

Welding consumables - Solid wire electrodes, solid strip electrodes, solid wires and solid rods for fusion welding of nickel and nickel alloys - Classification (ISO/DIS 18274:2021)

Schweißzusätze - Draht- und Bandelektroden, Massivdrähte und -stäbe zum Schmelzschweißen von Nickel und Nickellegierungen - Einteilung (ISO/DIS 18274:2021)

Produits consommables pour le soudage - Fils-électrodes pleins, feuilards pleins, fils pleins et baguettes pleines pour le soudage par fusion du nickel et des alliages de nickel (ISO/DIS 18274:2021)

<https://standards.iteh.ai/catalog/standards/sist/399d798a-3f58-4b1b-8eb7-e6732ae63397/osist-pren-iso-18274-2021>

Ta slovenski standard je istoveten z: prEN ISO 18274

ICS:

25.160.20	Potrošni material pri varjenju	Welding consumables
77.120.40	Nikelj, krom in njune zlitine	Nickel, chromium and their alloys

oSIST prEN ISO 18274:2021**en,fr,de**

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[oSIST prEN ISO 18274:2021](#)

<https://standards.iteh.ai/catalog/standards/sist/399d798a-3f58-4b1b-8eb7-e6732ae63397/osist-pren-iso-18274-2021>

DRAFT INTERNATIONAL STANDARD

ISO/DIS 18274

ISO/TC 44/SC 3

Secretariat: ANSI

Voting begins on:
2021-08-23Voting terminates on:
2021-11-15

Welding consumables — Solid wire electrodes, solid strip electrodes, solid wires and solid rods for fusion welding of nickel and nickel alloys — Classification

Produits consommables pour le soudage — Fils-électrodes pleins, feuilards pleins, fils pleins et baguettes pleines pour le soudage par fusion du nickel et des alliages de nickel — Classification

ICS: 25.160.20

iTeh STANDARD PREVIEW (standards.iteh.ai)

[oSIST prEN ISO 18274:2021](https://standards.iteh.ai/catalog/standards/sist/399d798a-3f58-4b1b-8eb7-e6732ae63397/osist-pren-iso-18274-2021)<https://standards.iteh.ai/catalog/standards/sist/399d798a-3f58-4b1b-8eb7-e6732ae63397/osist-pren-iso-18274-2021>

THIS DOCUMENT IS A DRAFT CIRCULATED FOR COMMENT AND APPROVAL. IT IS THEREFORE SUBJECT TO CHANGE AND MAY NOT BE REFERRED TO AS AN INTERNATIONAL STANDARD UNTIL PUBLISHED AS SUCH.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

This document is circulated as received from the committee secretariat.

ISO/CEN PARALLEL PROCESSING



Reference number
ISO/DIS 18274:2021(E)

© ISO 2021

iTeh STANDARD PREVIEW (standards.iteh.ai)

<https://standards.iteh.ai/catalog/standards/sist/399d798a-3f58-4b1b-8eb7-e6732ae63397/osist-pren-iso-18274-2021>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2021

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword.....	iv
Introduction.....	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Classification	1
5 Symbols and requirements	1
5.1 Symbols for the product form.....	1
5.2 Symbol for the chemical composition.....	2
6 Mechanical properties of the weld metal	9
7 Chemical analysis	9
8 Rounding procedure	9
9 Retests	9
10 Technical delivery conditions	9
11 Designation	9
Annex A (informative) Description and uses of welding consumable alloys	11
Annex B (informative) System for designation of welding consumables	19
Annex C (informative) Corresponding national classifications and typical weld metal tensile strengths	20
Bibliography	23

ISO/DIS 18274:2021(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 44, *Welding and allied processes*, Subcommittee SC 3, *Welding Consumables*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 121, *Welding and allied processes*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This third edition cancels and replaces the second edition (ISO 18274:2010), which has been technically revised.

Any feedback, question or request for official interpretation related to any aspect of this document should be directed to the Secretariat of ISO/TC 44/SC 3 via your national standards body. A complete listing of these bodies can be found at www.iso.org/members.html. Official interpretations, where they exist, are available from this page: <https://committee.iso.org/sites/tc44/home/interpretation.html>.

The main changes compared to the previous edition are as follows:

- A number of new restricted alloy symbols, commonly used in the USA, were added to [Table 1](#) and [Table C.1](#);
- A number of alloy symbols were updated in [Table 1](#) and [Table C.1](#);
- A new example 4 was added to [Clause 11](#) for a Z classification.

Introduction

For nickel welding consumables, there is no unique relationship between the product form (solid wire electrode, solid strip electrode, solid wire, solid rod) and the welding process used (e.g. gas shielded metal arc welding, gas tungsten arc welding, plasma arc welding, submerged arc welding, strip overlay welding, laser welding or other welding processes). For this reason, the solid wire electrode, solid strip electrode, solid wire, solid rod may be classified on the basis of any of the above product forms and can be used as appropriate, for more than one of the above processes (see also [Annex B](#)).

iTeh STANDARD PREVIEW (standards.iteh.ai)

<https://standards.iteh.ai/catalog/standards/sist/399d798a-3f58-4b1b-8eb7-e6732ae63397/osist-pren-iso-18274-2021>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[oSIST prEN ISO 18274:2021](https://standards.iteh.ai/catalog/standards/sist/399d798a-3f58-4b1b-8eb7-e6732ae63397/osist-pren-iso-18274-2021)

<https://standards.iteh.ai/catalog/standards/sist/399d798a-3f58-4b1b-8eb7-e6732ae63397/osist-pren-iso-18274-2021>

Welding consumables — Solid wire electrodes, solid strip electrodes, solid wires and solid rods for fusion welding of nickel and nickel alloys — Classification

1 Scope

This document specifies requirements for classification of solid wire electrodes, solid strip electrodes, solid wires, solid rods for fusion welding of nickel and nickel alloys. The classification of the solid wire electrodes, solid strip electrodes, solid wires, and solid rods is based on their chemical composition.

The principles of this standard can be applied to metal powders for cladding, hard facing and additive manufacturing.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 544, *Welding consumables — Technical delivery conditions for filler materials and fluxes — Type of product, dimensions, tolerances and markings*

ISO 14344, *Welding consumables — Procurement of filler materials and fluxes*

ISO 80000-1:2009, *Quantities and units — Part 1: General*
oSIST prEN ISO 18274:2021
<https://standards.iteh.ai/catalog/standards/sist/599d798a-3f58-4b1b-8eb7-e6732ae63397/osist-pren-iso-18274-2021>

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

4 Classification

The classification is divided into two parts:

- a) the first part indicates the product form, being solid wire electrode, solid strip electrode, solid wire, solid rod, see [5.1](#);
- b) the second part gives a numerical symbol indicating the chemical composition of the solid wire electrode, solid strip electrode, solid wire, solid rod, see [Table 1](#).

5 Symbols and requirements

5.1 Symbols for the product form

The symbol for the solid wire electrode, solid wire or solid rod shall be “S”.

ISO/DIS 18274:2021(E)

The symbol for the solid strip electrode shall be “B”.

NOTE One product form can be used for more than one welding process.

5.2 Symbol for the chemical composition

The initial symbol “Ni” in [Table 1](#) identifies the welding consumable as a nickel base alloy. The following four digits indicate the chemical composition of the solid wire electrode, solid strip electrode, solid wire or solid rod, determined under conditions given in [Clause 7](#). The first digit is an indicator of the alloy group as follows:

- 1, significant molybdenum addition without significant chromium addition (nickel-molybdenum alloys);
- 2, no significant alloy addition;
- 4, significant copper addition (nickel-copper alloys);
- 5, significant copper additions with aluminium and titanium for precipitation hardening;
- 6, significant chromium addition, with iron less than 25 % (by mass) (nickel-chromium-iron and nickel-chromium-molybdenum alloys);
- 7, same as 6, but with aluminium and titanium for precipitation hardening;
- 8, significant chromium addition, with iron more than 25 % (by mass) (nickel-iron-chromium alloys).

The remaining digits indicate the alloy composition of the welding consumable. A description of common uses of each welding consumable alloy is given in [Annex A](#). The basis of the system of designation is described in [Annex B](#).

NOTE 1 In addition, the chemical symbol can be used.

NOTE 2 Corresponding national classifications are shown in [Annex C](#)

iTech STANDARD PREVIEW
(standards.iteh.ai)

oSIST prEN ISO 18274:2021

<https://standards.iteh.ai/catalog/standards/sist/399d798a-3f58-4b1b-8eb7-c6732ae63397/osist-pr-en-iso-18274-2021>

Table 1 — Symbols and chemical composition requirements for solid wire electrodes, solid strip electrodes, solid wires and solid rods

Alloy symbols		Chemical composition, % (by mass) ^a													
Numerical ^b	Chemical	C	Mn	Fe	Si	Cu	Ni ^c	Co	Al	Ti	Cr	Nb ^d	Mo	W	Other ^{e,f}
Nickel															
Ni 2061	NiTi3	0,15	1,0	1,0	0,7	0,25	≥ 92,0	—	1,5	2,0 to 3,5	—	—	—	—	P 0,03
Ni 2061R	(NiTi3)	0,15	1,0	1,0	0,7	0,25	≥ 93,0	—	1,5	2,0 to 3,5	—	—	—	—	P 0,03
Nickel-Copper															
Ni 4060	NiCu30Mn3Ti	0,15	4,0	2,5	1,2	28,0 to 32,0	62,0 to 69,0	—	1,2	1,5 to 3,0	—	0,3	—	—	—
Ni 4061	NiCu30Mn3Nb	0,15	4,0	2,5	1,25	28,0 to 32,0	≥ 60,0	—	1,0	1,0	—	3,0	—	—	—
Ni 5504	NiCu25Al3Ti	0,25	1,5	2,0	1,0	≥ 20,0	63,0 to 70,0	—	2,0 to 4,0	0,3 to 1,0	—	—	—	—	P 0,03
Nickel-Chromium															
Ni 6072	NiCr44Ti	0,01 to 0,10	0,20	0,50	0,20	0,50	≥ 52,0	—	—	0,3 to 1,0	42,0 to 46,0	—	—	—	—
Ni 6073	NiCr38AlNbTi	0,03	0,50	1,0	0,30	0,30	≥ 63,0	1,0	0,75 to 1,20	0,25 to 0,75	36,0 to 39,0	0,25 to 1,00	0,50	—	P 0,02 B 0,003 Zr 0,02
Ni 6076	NiCr20	0,08 to 0,15	1,0	2,00	0,30	0,50	≥ 75,0	—	0,4	0,15 to 0,50	19,0 to 21,0	—	—	—	P 0,03
Ni 6082	NiCr20Mn3Nb	0,10	2,5 to 3,5	3,0	0,5	0,5	≥ 67,0	—	—	0,7	18,0 to 22,0	2,0 to 3,0	—	—	P 0,03
Ni 6699 ^h	NiCr29Al	0,005 to 0,10	0,5	2,5	0,50	0,50	≥ 60	—	1,9 to 3,0	0,60	26,0 to 30,0	0,50	—	—	Zr 0,10 N 0,05 S 0,01 B 0,008
Nickel-Chromium-Iron															
Ni 6002	NiCr21Fe18Mo9	0,05 to 0,15	1,0	17,0 to 20,0	1,0	0,5	≥ 44,0	0,5 to 2,5	—	—	20,5 to 23,0	—	8,0 to 10,0	0,2 to 1,0	P 0,04 S 0,03
Ni 6025	NiCr25Fe10AlY	0,15 to 0,25	0,5	8,0 to 11,0	0,5	0,1	≥ 59,0	1,0	1,8 to 2,4	0,1 to 0,2	24,0 to 26,0	—	—	—	Y 0,05 to 0,12 Zr 0,01 to 0,10

Table 1 (continued)

Alloy symbols		Chemical composition, % (by mass) ^a													
Numerical ^b	Chemical	C	Mn	Fe	Si	Cu	Ni ^c	Co	Al	Ti	Cr	Nb ^d	Mo	W	Others ^{e,f}
Ni 6030	NiCr30Fe15Mo5W	0,03	1,5	13,0 to 17,0	0,8	1,0 to 2,4	≥ 36,0	5,0	—	—	28,0 to 31,5	0,3 to 1,5	4,0 to 6,0	1,5 to 4,0	P 0,04 S 0,02
Ni 6043	NiCr30Fe9Nb2	0,04	3,0	7,0 to 12,0	0,5	0,30	≥ 54,0	—	0,50	0,5	28,0 to 31,5	1,0 to 2,5	0,50	—	—
Ni 6045	NiCr28Fe23Si3	0,05 to 0,12	1,0	21,0 to 25,0	2,5 to 3,0	0,3	≥ 40,0	1,0	0,30	—	26,0 to 29,0	—	—	—	P 0,020 S 0,010
Ni 6052	NiCr30Fe9	0,04	1,0	7,0 to 11,0	0,5	0,3	≥ 54,0	—	1,1	1,0	28,0 to 31,5	0,10	0,5	—	Al + Ti < 1,5
Ni 6054	NiCr29Fe9	0,04	1,0	7,0 to 11,0	0,50	0,30	≥ 51,0	0,12	1,10	1,0	28,0 to 31,5	0,5 to 1,0	0,50	—	P 0,02
Ni 6054R	(NiCr29Fe9)	0,04	1,0	7,0 to 11,0	0,50	0,30	≥ 51,0	0,12	1,10	1,0	28,0 to 31,5	0,5 to 1,0	0,50	—	P 0,02 Al + Ti 1,5 B 0,005 Zr 0,02
Ni 6055	NiCr29Fe5Mo4Nb3	0,03	1,0	14,4	0,50	0,30	52,0 to 62,0	0,10	0,50	0,50	28,5 to 31,0	2,1 to 4,0	3,0 to 5,0	—	P 0,02 B 0,003 Zr 0,02
Ni 6056	NiCr27Fe2Nb2	0,020 to 0,055	2,5 to 3,5	1,0 to 3,0	0,50	0,3	≥ 61,0	0,10	0,60	0,10 to 0,40	26,0 to 28,0	2,0 to 2,8	—	—	P 0,02
Ni 6062	NiCr15Fe8Nb	0,08	1,0	6,0 to 10,0	0,3	0,5	≥ 70,0	—	—	—	14,0 to 17,0	1,5 to 3,0	—	—	P 0,03
Ni 6176	NiCr16Fe6	0,05	0,5	5,5 to 7,5	0,5	0,1	≥ 76,0	0,05	—	—	15,0 to 17,0	—	—	—	—
Ni 6601	NiCr23Fe15Al	0,10	1,0	20,0	0,5	1,0	58,0 to 63,0	—	1,0 to 1,7	—	21,0 to 25,0	—	—	—	P 0,03
Ni 6693	NiCr29Fe4Al3	0,15	1,0	2,5 to 6,0	0,5	0,5	≥ 53,0	—	2,5 to 4,0	1,0	27,0 to 31,0	0,5 to 2,5	—	—	P 0,03 S 0,01
Ni 6701	NiCr36Fe7Nb	0,35 to 0,50	0,5 to 2,0	7,0	0,5 to 2,0	—	42,0 to 48,0	—	—	—	33,0 to 39,0	0,8 to 1,8	—	—	—
Ni 6975	NiCr25Fe13Mo6	0,03	1,0	10,0 to 17,0	1,0	0,7 to 1,2	47,0 to 52,0	—	—	0,70 to 1,50	23,0 to 26,0	—	5,0 to 7,0	—	P 0,03 S 0,03
Ni 6985	NiCr22Fe20Mo7Cu2	0,01	1,0	18,0 to 21,0	1,0	1,5 to 2,5	≥ 40,0	5,0	—	—	21,0 to 23,5	0,50	6,0 to 8,0	1,5	P 0,04 S 0,03