



Designation: ~~B188-02~~ Designation: B188-09

## Standard Specification for Seamless Copper Bus Pipe and Tube<sup>1</sup>

This standard is issued under the fixed designation B188; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reappraisal.

*This standard has been approved for use by agencies of the Department of Defense.*

### 1. Scope\*

1.1 This specification establishes the requirements for seamless copper bus pipe and tube intended for use as electrical conductors.

1.1.1 The product shall be made from one of the following coppers, as denoted in the ordering information:<sup>2</sup>

Copper UNS No. <sup>2</sup>	Previously Used Designation	Type of Copper
C10100	OFE	Oxygen-free, electronic
C10200	OF	Oxygen-free without residual deoxidants
C10300	—	Oxygen-free, extra low phosphorus
C10400, C10500, C10700	OFS	Oxygen-free, silver bearing
C11000	ETP	Electrolytic tough pitch
C11300, C11400, C11600	STP	Silver-bearing tough pitch
C12000	DLP	Phosphorized, low residual phosphorus

~~1.2 Unless otherwise specified, any one of the above coppers may be furnished.~~

~~1.3 The values stated in inch-pound units are the standard. The SI values given in parentheses are for information only.~~

~~1.2 Unless otherwise specified, any one of the above coppers may be furnished.~~

1.3 *Units*—Values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units, which are provided for information only and are not considered standard.

### 2. Referenced Documents

2.1 *ASTM Standards*:<sup>3</sup>

B193 Test Method for Resistivity of Electrical Conductor Materials

B428 Test Method for Angle of Twist in Rectangular and Square Copper and Copper Alloy Tube

B577 Test Methods for Detection of Cuprous Oxide (Hydrogen Embrittlement Susceptibility) in Copper

B601 Classification for Temper Designations for Copper and Copper Alloys Wrought and Cast

B846 Terminology for Copper and Copper Alloys

E8 Test Methods for Tension Testing of Metallic Materials

E18 Test Methods for Rockwell Hardness of Metallic Materials

E29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications

E53 Test Method for Determination of Copper in Unalloyed Copper by Gravimetry

E62 Test Methods for Chemical Analysis of Copper and Copper Alloys (Photometric Methods)

E243 Practice for Electromagnetic (Eddy-Current) Examination of Copper and Copper-Alloy Tubes

E255 Practice for Sampling Copper and Copper Alloys for the Determination of Chemical Composition

E527 Practice for Numbering Metals and Alloys in the Unified Numbering System (UNS)

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee B05 on Copper and Copper Alloys and is the direct responsibility of Subcommittee B05.04 on Pipe and Tube.

Current edition approved April 10, 2002. Published June 2002. Originally published as B188-44T. Last previous edition B188-00. DOI: 10.1520/B0188-02.

Current edition approved Oct. 1, 2009. Published November 2009. Originally approved in 1944. Last previous edition approved in 2002 as B188-02. DOI: 10.1520/B0188-09.

<sup>2</sup> The UNS system for copper and copper alloys (see Practice E527) is a simple expansion of the former standard designation system accomplished by the addition of a prefix “C” and a suffix “00.” The suffix can be used to accommodate composition variations of the base alloy.

<sup>3</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* Vol 02.03, volume information, refer to the standard’s Document Summary page on the ASTM website.

\*A Summary of Changes section appears at the end of this standard.

### 3. Terminology

3.1 For definitions of terms related to copper and copper alloys, refer to Terminology B846.

#### 3.2 Definitions:

##### 3.2.1 Definitions of Terms Specific to This Standard:

3.2.1 *bus pipe or tube*—a high conductivity copper tubular product used as an electrical conductor.

### 4. Ordering Information

4.1 Include the following information when placing orders for product under this specification, as applicable:

4.1.1 ASTM designation and year of issue,

4.1.2 Copper UNS designation,

4.1.2 Copper UNS designation (1.1.1 and 1.2),

4.1.3 Temper (Section 7),

4.1.4 Dimensions and form (Section 4.1.2),

4.1.5 Length (Section 4.1.2),

4.1.6 Total quantity of each size (

4.1.6 Quantity—total weight or total length or number of pieces of each size (Table 1),

4.1.7 Quantity of each item,

4.2 The following options are available under this specification and should be specified in the contract or purchase order when required:

4.2.1 Bend test (Section

4.2 The following options are available and should be specified at the time of placing the order when required:

4.2.1 Bend test (Section 10),

4.2.2 Hydrogen embrittlement susceptibility test (Section 12

4.2.2 Hydrogen embrittlement susceptibility test (Section 10),

4.2.3 Microscopical examination (Section 10),

**TABLE 1 Dimensions and Weights of Copper Pipe, Nominal or Standard Pipe Sizes<sup>A</sup>**

Nominal or Standard Pipe Size, in.	Dimensions, in. (mm)			Cross-Sectional Area of Wall, in. <sup>2</sup> (mm <sup>2</sup> )	Theoretical Weight, lb/ft (kg/m)
	Outside Diameter	Inside Diameter	Wall Thickness		
	Regular				
¼	0.540(13.7)	0.376(9.55)	0.082(2.08)	0.118(0.761)	0.457(0.680)
⅜	0.675(17.1)	0.495(12.6)	0.090(2.29)	0.165(1.06)	0.641(0.954)
½	0.840(21.3)	0.626(15.9)	0.107(2.72)	0.246(1.59)	0.955(1.42)
¾	1.050(26.7)	0.822(20.9)	0.114(2.90)	0.335(2.16)	1.30(1.93)
1	1.315(33.4)	1.063(27.0)	0.126(3.20)	0.471(3.04)	1.82(2.71)
1¼	1.660(42.2)	1.368(34.7)	0.146(3.71)	0.694(4.48)	2.69(4.00)
1½	1.900(48.3)	1.600(40.6)	0.150(3.81)	0.825(5.32)	3.20(4.76)
2	2.375(60.3)	2.063(52.4)	0.156(3.96)	1.09(7.03)	4.22(6.28)
2½	2.875(73.0)	2.501(63.5)	0.187(4.75)	1.58(10.2)	6.12(9.11)
3	3.500(88.9)	3.062(77.8)	0.219(5.56)	2.26(14.6)	8.75(13.0)
3½	4.000 (102)	3.500(88.9)	0.250(6.35)	2.95(19.0)	11.4(17.0)
4	4.500 (114)	4.000 (102)	0.250(6.35)	3.34(21.5)	12.9(19.2)
5	5.562 (141)	5.062 (129)	0.250(6.35)	4.17(26.9)	16.2(24.1)
6	6.625 (168)	6.125 (156)	0.250(6.35)	5.01(32.3)	19.4(28.9)
8	8.625 (219)	8.001 (203)	0.312(7.92)	8.15(52.6)	31.6(47.0)
10	10.750 (273)	10.020 (255)	0.365(9.27)	11.9(76.8)	46.2(68.7)
12	12.750 (324)	12.000 (305)	0.375(9.52)	14.6(94.2)	56.5(84.1)
	Extra Strong				
¼	0.540(13.7)	0.294(7.47)	0.123(3.12)	0.161(1.04)	0.625(0.930)
⅜	0.675(17.1)	0.421(10.7)	0.127(3.23)	0.219(1.41)	0.847(1.26)
½	0.840(21.3)	0.542(13.8)	0.149(3.78)	0.323(2.08)	1.25(1.86)
¾	1.050(26.7)	0.736(18.7)	0.157(3.99)	0.440(2.84)	1.71(2.54)
1	1.315(33.4)	0.951(24.2)	0.182(4.62)	0.648(4.18)	2.51(3.73)
1¼	1.660(42.2)	1.272(32.3)	0.194(4.93)	0.893(5.76)	3.46(5.15)
1½	1.900(48.3)	1.494(37.9)	0.203(5.16)	1.08(6.97)	4.19(6.23)
2	2.375(60.3)	1.933(49.1)	0.221(5.61)	1.50(9.68)	5.80(8.63)
2½	2.875(73.0)	2.315(58.8)	0.280(7.11)	2.28(14.7)	8.85(13.2)
3	3.500(88.9)	2.892(73.6)	0.304(7.72)	3.05(19.7)	11.8(17.6)
3½	4.000 (102)	3.358(85.3)	0.321(8.15)	3.71(23.9)	14.4(21.4)
4	4.500 (114)	3.818(97.0)	0.341(8.66)	4.46(28.8)	17.3(25.7)
5	5.562 (141)	4.812 (122)	0.375(9.52)	6.11(39.4)	23.7(35.3)
6	6.625 (168)	5.751 (146)	0.437(11.1)	8.50(54.8)	32.9(49.0)
8	8.625 (219)	7.625 (194)	0.500(12.7)	12.8(82.6)	49.5(73.7)
10	10.750 (273)	9.750 (248)	0.500(12.7)	16.1(104)	62.4(92.9)

<sup>A</sup> 1 in.<sup>2</sup> = 1 270 000 cmil.

- 4.2.4 Tension testing (Section 9),
- 4.2.5 Eddy-current test (Section 1311),
- 4.2.6 Certification (Section 2321),
- 4.2.7 Mill test report (Section 2422), and
- 4.2.8 Special packaging, if required (Section 2523).

## 5. Materials and Manufacture

### 5.1 Material:

5.1.1 The material of manufacture shall be cast billet of one of the UNS copper alloy numbers included in the scope, and as so specified in the contract or purchase order, and shall be of such purity and soundness as to be suitable for processing into lengths of pipe or tube for the intended application.

### 5.2 Manufacture:

5.2.1 The ~~material product~~ shall be manufactured by such hot-working, cold-working, and annealing processing as to produce a uniform, wrought, seamless ~~wrought~~ structure in the finished product.

5.2.2 The method of manufacture shall be ~~such that hot or cold working~~ to the finished ~~material conforms size, and subsequent annealing when required to meet the specified temper properties specified~~ (see 7.1).

## 6. Chemical Composition

6.1 The material shall conform to the chemical composition requirements in Table 2 ~~for the copper UNS No. specified in the ordering information:~~

~~6.2 These composition limits do not preclude the presence of other elements. Limits for unnamed elements may be established and analysis required by agreement between the manufacturer or supplier and purchaser. for the copper UNS No. designation specified in the ordering information.~~

6.2 These composition limits do not preclude the presence of other elements. By agreement between the manufacturer or supplier and purchaser, limits may be established and analysis required for unnamed elements.

## 7. Temper

7.1 The material shall be furnished in either the O60 (soft anneal) or H80 (hard drawn) temper as defined in Classification B601. ~~The requirements are specified in~~ The standard tempers for products described in this specification are given in Table 3 as defined in Classification B601.

## ~~8. Electrical Resistivity Requirements~~ Electrical Resistivity Requirements

~~8.1 The material shall conform to the maximum electrical resistivity requirements prescribed in~~

### ~~7.1.1 Soft Anneal—O60.~~

### ~~7.1.2 Hard Drawn—H80.~~

## 8. Electrical Resistivity Requirements

8.1 The product furnished shall conform to the maximum electrical resistivity requirements prescribed in Table 3 when tested in accordance with Test Method B193.

## 9. Mechanical Property Requirements

~~9.1 The product shall conform to the mechanical property requirements prescribed in~~

**TABLE 2 Chemical Requirements**

NOTE 1—If the type of silver-bearing copper is not specified (that is, whether tough-pitch, phosphorized, or oxygen-free) any one of the three types may be supplied at the option of the manufacturer.

Element	Composition, %										
	Copper UNS No.										
	C10100 <sup>A</sup>	C10200	C10300	C10400 <sup>B</sup>	C10500 <sup>B</sup>	C10700 <sup>B</sup>	C11000	C11300 <sup>C</sup>	C11400 <sup>C</sup>	C11600 <sup>C</sup>	C12000
Copper (incl silver), min	99.99 <sup>D</sup>	99.95	99.95 <sup>E</sup>	99.95	99.95	99.95	99.90	99.90	99.90	99.90	99.90
Phosphorus	<sup>A</sup>	...	0.001– 0.005	...	...	...	...	...	...	...	0.004– 0.0012
Oxygen, max.	0.0005	0.0010	...	0.0010	0.0010	0.0010	...	...	...	...	...
Silver	<sup>A</sup>	...	...	8 <sup>F</sup>	10 <sup>F</sup>	25 <sup>F</sup>	...	8 <sup>F</sup>	10 <sup>F</sup>	25 <sup>F</sup>	...

<sup>A</sup> Impurity maximums in ppm of C10100 shall be: antimony 4, arsenic 5, bismuth 1.0, cadmium 1, iron 10, lead 5, manganese 0.5, nickel 10, phosphorus 3, selenium 3, silver 25, sulfur 15, tellurium 2, tin 2, and zinc 1.

<sup>B</sup> C10400, C01500, and C10700 are oxygen-free coppers with the addition of a specified amount of silver. The compositions of these alloys are equivalent to C10200 plus the intentional addition of silver.

<sup>C</sup> C11300, C11400, C11500, and C11600 are electrolytic tough-pitch copper with silver additions. The compositions of these alloys are equivalent to C11000 plus the intentional addition of silver.

<sup>D</sup> Copper shall be determined by difference between "impurity total" and 100 %.

<sup>E</sup> Copper (includes silver) + phosphorus, min.

<sup>F</sup> Values are minimum silver in troy ounces per avoirdupois ton (1 oz/ton is equivalent to 0.0034 %).

**TABLE 3 Mechanical and Electrical Properties<sup>A</sup>**

Temper Designation	Tensile Strength ksi (MPa) <sup>B</sup>		Electrical Resistivity <sup>B</sup> max at 20°C (68°F), Ω·g/m <sup>2</sup>					Rockwell Hardness (F Scale) 60-kg Load 1/16-in. Ball				
								Copper UNS No.				
								min	max	Elongation in 2 in. (51 mm), min, %	Bend Test Angle of Bend, °	C10100
O60	Soft	All types, all sizes	...	37 (255)	25	180	0.15176	0.15328	0.15614	0.17031	50 max	
O60	Soft Anneal	All types, all sizes	...	37 (255)	25	180	0.15176	0.15328	0.15614	0.17031	50 max	
H80	Hard	Rectangular or square:										
H80	Hard Drawn	Rectangular or square:										
		up to 6-in. (152-mm) major outside dimension, incl up to 3/16-in. (4.8-mm) wall thickness, incl	35 (240)	...	8	...	0.15585	0.15737	0.15940	0.17418	75 min	
		over 3/16-in. (4.8-mm) wall thickness	33 (230)	...	15	...	0.15521	0.15673	0.15940	0.17418	65 min	
		over 6-in. (152-mm) major outside dimension	32 (220)	...	20	...	0.15425	0.15577	0.15940	0.17418	65 min	
		Round (pipe and tube): up to 4-in. (102-mm) outside diameter, incl	40 (275)	...	3	90	0.15713	0.15865	0.15940	0.17418	80 min	
		over 4-in. (102-mm) outside diameter	38 (260)	...	6	...	0.15585	0.15737	0.15940	0.17418	75 min	

<sup>A</sup> See 6.1.

<sup>B</sup> See Appendix X2.

9.1 Product furnished under this specification shall conform to the tensile and hardness property requirements prescribed in Table 3.

9.1.1 Tension testing for tensile and elongation information need not be performed except when indicated by the purchaser at the time of placing the order (see 4.2.4).

9.1.2 The tension test shall be used to resolve cases of dispute.

9.2 All test specimens shall be tested in full size when practicable. When a machined specimen becomes necessary for any test required under this specification, enough metal shall be suitably removed from the sample to meet the limitations of the testing facilities.

### 10. Bend Test Requirements

10.1 The product shall conform to the bend testing requirements prescribed in

### 10. Performance Requirements

#### 10.1 Bend Test Requirements

10.1.1 The product shall conform to the bend testing requirements prescribed in Table 3.

10.1.2 Bend testing need not be performed except when indicated by the purchaser at the time of placing the order (see 4.2.4.2.1).

#### 10.2 Microscopical Examination

10.2.1 The test specimens of material designated as Copper UNS Nos. C10100, C10200, C10300, C10400, C10500, C10700, and C12000 shall be free of cuprous oxide as determined by Procedure A of Test Method B577. In case of a dispute, a referee method in accordance with Procedure C shall be used.

10.2.2 The test need not be performed except when indicated at the time of placing the order (see 4.2.3).

#### 10.3 Hydrogen Embrittlement Susceptibility Test

10.3.1 When tested, material designated as Copper UNS Nos. C10100, C10200, C10300, C10400, C10500, C10700, and C12000 shall pass the embrittlement test of Procedure B of Test Method B577. The actual performance of this test is not mandatory under the terms of this specification unless specified in the ordering information (see 4.2.2.2). In case of dispute, a referee method in accordance with Procedure C of Method B577 shall be employed.

### 13. Nondestructive Testing

13.1 When specified (see

## 11. Other Requirements

### 11.1 Nondestructive Testing

11.1.1 When specified (see 4.2.5), the product shall be tested in the final size but may be tested before the final anneal or heat treatment, when these thermal treatments are required, unless otherwise agreed upon by the manufacturer or supplier and purchaser.

#### 11.2

11.2.1 Eddy-Current Test—When specified, each piece of product from 1/8-in. (3.2-mm) up to and including 3/8-in. (79.4-mm) nominal outside diameter, or 2 1/2-in. (63.5-mm) distance between outside parallel surfaces, shall be subjected to an eddy-current test. Testing shall follow the procedures of Practice E243 except for determination of “end effect.” The product shall be passed through an eddy-current testing unit adjusted to provide information on the suitability of the product for the intended application.

11.2.2 Notch depth 11.1.3 Notch depth standards rounded to the nearest 0.001 in. (0.025 mm) shall be 22 % of the nominal wall thickness. The notch depth tolerance shall be  $\pm 0.0005$  in. (0.013 mm). Alternatively, when the test is performed using speed-insensitive equipment that can select a maximum imbalance signal, a maximum imbalance signal of 0.3 % shall be used.

11.4 Product 11.1.4 Product that does not actuate the signaling device of the eddy-current test shall be considered as conforming to the requirements of this test. Product with discontinuities indicated by the testing unit may be reexamined or retested, at the option of the manufacturer, to determine whether the discontinuity is cause for rejection. Signals that are found to have been caused by minor mechanical damage, soil, or moisture shall not be cause for rejection of the product provided the dimensions of the product are still within prescribed limits and the product is suitable for its intended application.

## 12. Dimensions, Weights, and Permissible Variations

### 12.1

12.1 General—For the purpose of determining conformance with the dimensional requirements given in this specification, any measured value outside the specified limiting values for any dimension may be cause for rejection.

### 12.2

12.2 Dimensions and Weights—The dimensions and weights for nominal or standard copper pipe of various outside diameters shall be as prescribed in Table 1.

### 12.3

12.3 Weight Tolerances—The weight of the nominal or standard pipe shall not vary from the theoretical weight per foot prescribed in Table 1 by more than the following:

Nominal or Standard Pipe Size, in.	Weight Tolerance, %
6 and under	5
Over 6 to 8, incl	7
Over 8	8

### 12.4

12.4 Thickness Tolerances—The wall thickness of nominal or standard pipe at any point shall not be less than that prescribed in Table 3<sup>1</sup> by more than the following:

Nominal or Standard Pipe Size, in.	Thickness Tolerance, % <sup>A</sup>
6 and under	5
Over 6 to 8, incl.	7
Over 8	8

<sup>A</sup> Expressed to the nearest 0.001 in. (0.025 mm).

### 12.5

#### 12.5 Copper Tube (Other than Pipe):

#### 12.5.1

12.5.1 Round Tube—Wall thickness tolerances shall be in accordance with Table 4. Diameter tolerances shall be in accordance with Table 5.

#### 12.5.2

12.5.2 Rectangular Including Square Tube—Wall thickness tolerances shall be in accordance with Table 6. The tolerances on distance between parallel surfaces for rectangular and square tube in straight lengths only shall be in accordance with Table 7 and Fig. 1.

#### 12.5.3

12.5.3 Length and Length Tolerances—Tube ordered to specific or stock lengths with or without ends shall conform to the tolerances prescribed in Table 8 and Table 9.

12.5.3.1 Pipe ordered to specific stock lengths with or without ends shall conform to tolerances prescribed in Table 10 and Table 11.

### 12.6

12.6 Roundness—For drawn unannealed tube or pipe in straight lengths, the roundness tolerances shall be as follows:

**TABLE 4 Wall Thickness Tolerances for Copper Tube (Not Applicable to Pipe)**

NOTE 1—*Maximum Deviation at Any Point:* The following tolerances are plus and minus; if tolerances all plus or all minus are desired, double the values given.

Wall Thickness, in. (mm)	Outside Diameter, in. (mm)					
	Over 1/8 (3.15) to 5/8 (15.9), incl	Over 5/8 (15.9) to 1 (25.4), incl	Over 1 (25.4) to 2 (50.8), incl	Over 2 (50.8) to 4 (102), incl	Over 4 (102) to 7 (178), incl	Over 7 (178) to 10 (254), incl
Up to 0.017 (0.432) incl	0.001 (0.025)	0.0015 (0.038)	0.002 (0.051)	...	...	...
Over 0.017 (0.432) to 0.024 (0.610) incl	0.002 (0.051)	0.002 (0.051)	0.0025 (0.064)	...	...	...
Over 0.024 (0.610) to 0.034 (0.864) incl	0.0025 (0.064)	0.0025 (0.064)	0.003 (0.076)	0.004 (0.10)	...	...
Over 0.034 (0.864) to 0.057 (1.45) incl	0.003 (0.076)	0.0035 (0.089)	0.0035 (0.089)	0.005 (0.13)	0.007 (0.18)	...
Over 0.057 (1.45) to 0.082 (2.08) incl	0.0035 (0.089)	0.004 (0.10)	0.004 (0.10)	0.006 (0.15)	0.008 (0.20)	0.010 (0.25)
Over 0.082 (2.08) to 0.119 (3.02) incl	0.004 (0.10)	0.005 (0.13)	0.005 (0.13)	0.007 (0.18)	0.009 (0.23)	0.011 (0.28)
Over 0.119 (3.02) to 0.164 (4.17) incl	0.005 (0.13)	0.006 (0.15)	0.006 (0.15)	0.008 (0.20)	0.010 (0.25)	0.012 (0.30)
Over 0.164 (4.17) to 0.219 (5.56) incl	0.007 (0.18)	0.0075 (0.19)	0.008 (0.20)	0.010 (0.25)	0.012 (0.30)	0.014 (0.36)
Over 0.219 (5.56) to 0.283 (7.19) incl	...	0.009 (0.23)	0.010 (0.25)	0.012 (0.30)	0.014 (0.36)	0.016 (0.41)
Over 0.283 (7.19) to 0.379 (9.63) incl	...	0.012 (0.30)	5 <sup>A</sup>	5 <sup>A</sup>	6 <sup>A</sup>	6 <sup>A</sup>
Over 0.379 (9.62)	...	...	5 <sup>A</sup>	5 <sup>A</sup>	6 <sup>A</sup>	6 <sup>A</sup>

<sup>A</sup> Percent of the specified wall expressed to nearest 0.001 in. (0.025 mm).

**TABLE 5 Average Diameter Tolerances for Copper and Copper-Alloy Tube**

Specified Diameter, in. (mm)	Diameter to Which Tolerance Applies <sup>A</sup>	Tolerance, plus and minus, in. (mm)
Up to 5/8 (15.9), incl	inside or outside	0.002 (0.051)
Over 5/8 (15.9) to 1 (25.4), incl	inside or outside	0.0025 (0.064)
Over 1 (25.4) to 2 (50.8), incl	inside or outside	0.003 (0.076)
Over 2 (50.8) to 3 (76.2), incl	inside or outside	0.004 (0.10)
Over 3 (76.2) to 4 (102), incl	inside or outside	0.005 (0.13)
Over 4 (102) to 5 (127), incl	inside or outside	0.006 (0.15)
Over 5 (127) to 6 (152), incl	inside or outside	0.007 (0.18)
Over 6 (152) to 8 (203), incl	inside or outside	0.008 (0.20)
Over 8 (203) to 10 (254), incl	inside or outside	0.010 (0.25)

<sup>A</sup> The average outside diameter of a tube is the average of the maximum and minimum outside diameters, as determined at any one cross-section of the tube.

**TABLE 6 Wall Thickness Tolerances for Copper Rectangular and Square Tube**

NOTE 1—*Maximum deviation at any point.* The following tolerances are plus and minus; if tolerances all plus or all minus are desired, double the values given.

Wall Thickness, in. (mm)	Distance Between Outside Parallel Surface, in. <sup>A</sup> (mm)						
	1/32 (0.794) to 1/8 (3.18), incl	Over 1/8 (3.18) to 5/8 (15.9), incl	Over 5/8 (15.9) to 1 (25.4), incl	Over 1 (25.4) to 2 (50.8), incl	Over 2 (50.8) to 4 (102), incl	Over 4 (102) to 7 (178), incl	Over 7 (178) to 10 (254), incl
Up to 0.017 (0.432) incl	0.002 (0.051)	0.002 (0.051)	0.0025 (0.064)	0.003 (0.076)	...	...	...
Over 0.017 (0.432) to 0.024 (0.610) incl	0.003 (0.076)	0.0025 (0.064)	0.003 (0.076)	0.0035 (0.089)	...	...	...
Over 0.024 (0.610) to 0.034 (0.864) incl	0.0035 (0.089)	0.0035 (0.089)	0.0035 (0.089)	0.004 (0.10)	0.006 (0.15)	...	...
Over 0.034 (0.864) to 0.057 (1.45) incl	0.004 (0.10)	0.004 (0.10)	0.0045 (0.11)	0.005 (0.12)	0.007 (0.18)	0.009 (0.23)	...
Over 0.057 (1.45) to 0.082 (2.08) incl	...	0.005 (0.13)	0.006 (0.15)	0.007 (0.18)	0.008 (0.20)	0.010 (0.25)	0.012 (0.30)
Over 0.082 (2.08) to 0.119 (3.02) incl	...	0.007 (0.18)	0.008 (0.20)	0.009 (0.23)	0.010 (0.25)	0.012 (0.30)	0.014 (0.36)
Over 0.119 (3.02) to 0.164 (4.17) incl	...	0.009 (0.23)	0.010 (0.25)	0.011 (0.28)	0.012 (0.30)	0.014 (0.36)	0.016 (0.41)
Over 0.164 (4.17) to 0.219 (5.56) incl	...	0.011 (0.28)	0.012 (0.30)	0.013 (0.33)	0.015 (0.38)	0.017 (0.43)	0.019 (0.48)
Over 0.219 (5.56) to 0.283 (7.19) incl	...	...	0.015 (0.38)	0.016 (0.41)	0.018 (0.46)	0.020 (0.51)	0.022 (0.56)

<sup>A</sup> In the case of rectangular tube, the major dimension determines the thickness tolerance applicable to all walls.

t/D (Ratio of Wall Thickness to Outside Diameter)

Roundness Tolerance, % of Outside Diameter (Expressed to the Nearest 0.001 in. (0.025 mm))

0.01 to 0.03 incl  
Over 0.03 to 0.05, incl  
Over 0.05 to 0.10, incl  
Over 0.10

1.5  
1.0  
0.8 or 0.002 in. (0.51 mm), whichever is greater  
0.7 or 0.002 in. (0.51 mm), whichever is greater

142.6.1 Compliance with the roundness tolerance shall be determined by taking measurements on the outside diameter only, irrespective of the manner in which the tube dimensions are specified.