

Designation: B452 – 09 Designation: B452 – 09

# **Standard Specification for** Copper-Clad Steel Wire for Electronic Application<sup>1</sup>

This standard is issued under the fixed designation B452; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon  $(\varepsilon)$  indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

### 1. Scope

- 1.1 This specification covers bare round copper-clad steel wire for electronic application.
- 1.2 Four classes of copper-clad steel wire are covered as follows:
- 1.2.1 Class 30HS—Nominal 30 % conductivity hard-drawn,
- 1.2.2 Class 30A—Nominal 30 % conductivity annealed,
- 1.2.3 Class 40HS-Nominal 40 % conductivity hard-drawn, and
- 1.2.4 Class 40A—Nominal 40 % conductivity annealed.
- 1.3 The values stated in inch-pound units are to be regarded as the standard. The values given in parentheses are in SI units.

#### 2. Referenced Documents

- 2.1 The following documents of the issue in effect on the date of material purchase form a part of this specification to the extent referenced herein:
  - 2.2 ASTM Standards: <sup>2</sup>
  - B193 Test Method for Resistivity of Electrical Conductor Materials <sup>2</sup>
  - B258 Specification for Nominal Diameters and Cross-Sectional Areas of AWG Sizes of Solid Round Wires Used as Electrical Conductors
  - 2.3 National Institute of Standards and Technology:

    Tables

    Tables
  - NBS Handbook 100—Copper Wire Tables<sup>3</sup>

#### 3. Ordering Information

- 3.1 Orders for material under this specification shall include the following information:
- 3.1.1 Quantity of each size and class,
- 3.1.2 Wire size, diameter in inches (see 5.3 and Table 1), B452-09
- 3.1.3 Class of wire (see 1.2 and Table 1),
- 3.1.4 Packaging and shipping (Section 10),
- 3.1.5 If inspection is required (see 6.3.3), and
- 3.1.6 Place of inspection (see 6.1).

#### 4. Material

4.1 The wire shall consist of a core of homogeneous open-hearth, electric-furnace, or basic-oxygen steel with a continuous outer cladding of copper thoroughly bonded to the core throughout and shall be of such quality as to meet the requirements of this specification (Note 1).

Note 1—The copper-clad steel wire provides a high-strength conductor for use in wire and cable where greater strength is required and a lower conductivity can be tolerated. At high frequencies the reduced conductivity is less pronounced due to concentration of the current in the outer periphery of the wire. Minimum thickness of 6 % and 10 % of the radius for 30 and 40 % conductivity material, respectively, has been established to facilitate the inspection of thickness on fine wires.

<sup>&</sup>lt;sup>1</sup> This specification is under the jurisdiction of ASTM Committee B01 on Electrical Conductors and is the direct responsibility of Subcommittee B01.06 on Composite Conductors.

Current edition approved April 10, 2002. Published April 2002. Originally published as B452-67. Last previous edition B452-93(1998)<sup>e1</sup>. DOI: 10.1520/B0452-02. Current edition approved Oct. 1, 2009. Published November 2009. Originally approved in 1967. Last previous edition approved in 2002 as B452 - 02. DOI: 10.1520/B0452-09.

For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For Annual Book of ASTM Standards Vol 02.03. volume information, refer to the standard's Document Summary page on the ASTM website.

<sup>&</sup>lt;sup>3</sup> Available from the National Institute of Standards and Technology (NIST), Gaithersburg, MD 20899.

Available from National Institute of Standards and Technology (NIST), 100 Bureau Dr., Stop 1070, Gaithersburg, MD 20899-1070, http://www.nist.gov.

**TABLE 1 Tensile and Elongation Requirements** 

Diameter		Cross-Sectional Area at 20°C			Tensile Strength, psi (kgf/mm²)						Elongation, min. % in 10 in. (250 mm)		
in.	mm	cmil	in. <sup>2</sup>	mm²	Class	30HS, min	Clas	ss 30A, min	Class	40HS, min	Class 40A, min	Class 30HS and 40HS	Class 30A and 40A
0.0720	1.83	5180	0.00407	2.63	127 (	00 (89.3)	50	000 (35.2)	110	000 (77.3)	45 000 (31.6)	1.5	15
0.0641	1.63	4110	0.00323	2.08	127 (	00 (89.3)	50	000 (35.2)	110	000 (77.3)	45 000 (31.6)	1.5	15
0.0571	1.45	3260	0.00256	1.65	127 (	00 (89.3)	50	000 (35.2)	110	000 (77.3)	45 000 (31.6)	1.5	15
0.0508	1.29	2580	0.00203	1.31	127 (	00 (89.3)	50	000 (35.2)	110	000 (77.3)	45 000 (31.6)	1.5	15
0.0453	1.15	2050	0.00161	1.04	127 (	00 (89.3)	50	000 (35.2)	110	000 (77.3)	45 000 (31.6)	1.5	15
0.0403	1.02	1620	0.00128	0.823		00 (89.3)		000 (35.2)		000 (77.3)	45 000 (31.6)	1.0	15
0.0359	0.912	1290	0.00101	0.653	127 (	00 (89.3)	50	000 (35.2)	110	000 (77.3)	45 000 (31.6)	1.0	15
0.0320	0.813	1020	0.000804	0.519	127 (	00 (89.3)	50	000 (35.2)	110	000 (77.3)	45 000 (31.6)	1.0	15
0.0285	0.724	812	0.000638	0.412		00 (89.3)	55	000 (38.7)	110	000 (77.3)	50 000 (35.2)	1.0	15
0.0253	0.643	640	0.000503	0.324	127 (	00 (89.3)	55	000 (38.7)	110	000 (77.3)	50 000 (35.2)	1.0	15
0.0226	0.574	511	0.000401	0.259	127 (	00 (89.3)	55	000 (38.7)	110	000 (77.3)	50 000 (35.2)	1.0	15
0.0201	0.511	404	0.00317	0.205	127 (	00 (89.3)	55	000 (38.7)	110	000 (77.3)	50 000 (35.2)	1.0	10
0.0179	0.455	320	0.000252	0.162		00 (89.3)		000 (38.7)		000 (77.3)	50 000 (35.2)	1.0	10
0.0159	0.404	253	0.000199	0.128		00 (89.3)		000 (38.7)		000 (77.3)	50 000 (35.2)	1.0	10
0.0142	0.361	202	0.000158	0.102		00 (89.3)		000 (38.7)		000 (77.3)	50 000 (35.2)	1.0	10
0.0126	0.320	159	0.000125	0.0804	127 (	00 (89.3)	55	000 (38.7)	110	000 (77.3)	50 000 (35.2)	1.0	10
0.0113	0.287	128	0.000100	0.0647	127 (	00 (89.3)	55	000 (38.7)	110	000 (77.3)	50 000 (35.2)	1.0	10
0.0100	0.254	100	0.0000785	0.0507	127 (	00 (89.3)	55	000 (38.7)	110	000 (77.3)	50 000 (35.2)	1.0	10
0.0089	0.226	79.2	0.0000622	0.0401	127 (	00 (89.3)	55	000 (38.7)	110	000 (77.3)	50 000 (35.2)	1.0	10
0.0080	0.203	64.0	0.0000503	0.0324	127 (	00 (89.3)	55	000 (38.7)	110	000 (77.3)	50 000 (35.2)	1.0	10
0.0071	0.180	50.4	0.0000396	0.0255	127 (	00 (89.3)	55	000 (38.7)	110	000 (77.3)	50 000 (35.2)	1.0	10
0.0063	0.160	39.7	0.0000312	0.0201	127,0	00 (89.3)	55	000 (38.7)	110	000 (77.3)	50 000 (35.2)	1.0	10
0.0056	0.142	31.4	0.0000246	0.0159	127 0	00 (89.3)	55	000 (38.7)	110	000 (77.3)	50 000 (35.2)	1.0	10
0.0050	0.127	25.0	0.0000196	0.0127	127 (	00 (89.3)	55	000 (38.7)	110	000 (77.3)	50 000 (35.2)	1.0	10
0.0045	0.114	20.2	0.0000159	0.0103	127 (	00 (89.3)	55	000 (38.7)	110	000 (77.3)	50 000 (35.2)	1.0	10
0.0040	0.102	16.0	0.0000126	0.00811		00 (89.3)		000 (38.7)		000 (77.3)	50 000 (35.2)	1.0	10
0.0035	0.089	12.2	0.00000962	0.00621	127 (	00 (89.3)	55	000 (38.7)	110	000 (77.3)	50 000 (35.2)	1.0	10
0.0031	0.079	9.61	0.00000755	0.00487	127 (	00 (89.3)	55	000 (38.7)	110	000 (77.3)	50 000 (35.2)	1.0	10

## 5. General Requirements

- 5.1 Tensile Strength and Elongation—The copper-clad steel wire shall conform to the tensile strength and elongation requirements of Table 1. For intermediate sizes not listed in Table 1, the elongation requirements of the next smaller size shall apply; in the case of tensile strength, the requirements of the next larger size shall apply.
- 5.2 Resistivity—The electrical resistivity at a temperature of 20°C shall not exceed the values prescribed in Table 2. See Note 2 for calculating electrical resistance.

Note 2—Relationships which may be useful in connection with the values of electrical resistivity prescribed in this specification are shown in Table 3. Resistivity units are based on the International Annealed Copper Standard (IACS) adopted by IEC in 1913, which is ½s Ω·mm²/m at 20°C for 100 % conductivity. The value of 0.017241 Ω·mm <sup>2</sup>/m and the value of 0.15328 Ω·g/m<sup>2</sup> at 20°C are respectively the international equivalent of volume and weight resistivity of annealed copper equal to 100 % conductivity. The latter term means that a copper wire 1 in. in length and weighing 1 g would have a resistance of 0.15328  $\Omega$ . This is equivalent to a resistivity value of 875.20 $\Omega$ · lb/mile<sup>2</sup>, which signifies the resistance of a copper wire 1 mile in length weighing 1 lb. It is also equivalent, for example, to 1.7241  $\mu\Omega$ /cm of length of a copper bar 1 cm<sup>2</sup> in cross section. A complete discussion of this subject is contained in NBS Handbook 100. The use of five significant figures in expressing resistivity does not imply the need for greater accuracy of measurement than that specified in Test Method B193. The use of five significant figures is required for complete reversible conversion from one set of resistivity units to another.

5.3 Dimensions and Permissible Variations—The wire sizes shall be expressed as the diameter of the wire in decimal fractions of an inch to the nearest 0.0001 in. (0.003 mm) (Note 3). For diameters under 0.0100 in. (0.254 mm), the wire shall not vary from the specified diameter by more than  $\pm 0.0001$  in. (0.003 mm) and for diameters of 0.0100 in. (0.254 mm) and over, the wire shall not vary from the specified diameter by more than  $\pm 1$  %, expressed to the nearest 0.0001 in. (0.003 mm).

TABLE 2 Resistivity, max, at 20°C

	••
Class of Wire	$\Omega \cdot mm^2 / m$
30HS and 30A	0.05862 (0.058616)
40HS and 40A	0.04397 (0.043970)