

SLOVENSKI STANDARD oSIST prEN ISO 2566-1:2021

01-oktober-2021

Jekla - Pretvarjanje vrednosti raztezkov - 1. del: Ogljikova in malolegirana jekla (ISO/FDIS 2566-1:2021)

Steel - Conversion of elongation values - Part 1: Carbon and low alloy steels (ISO/FDIS 2566-1:2021)

Stahl - Umrechnung von Bruchdehnungswerten - Teil 1: Unlegierte und niedrig legierte Stähle (ISO/FDIS 2566-1:2021) TANDARD PREVIEW

Acier - Conversion des valeurs d'allongement - Partie 1. Aciers au carbone et aciers faiblement alliés (ISO/FDIS 2566-1:2021)

https://standards.iteh.ai/catalog/standards/sist/7206a339-af80-4509-b36a-

Ta slovenski standard je istoveten 2:7/osist prEN ISO 2566-1

ICS:

77.040.10Mehansko preskušanje kovinMechanical testing of metals77.080.20JeklaSteels

oSIST prEN ISO 2566-1:2021 en,fr,de

oSIST prEN ISO 2566-1:2021

iTeh STANDARD PREVIEW (standards.iteh.ai)

oSIST prEN ISO 2566-1:2021 https://standards.iteh.ai/catalog/standards/sist/7206a339-af80-4509-b36a-875ef809cae7/osist-pren-iso-2566-1-2021 FINAL DRAFT

INTERNATIONAL STANDARD

ISO/FDIS 2566-1

ISO/TC 17/SC 20

Secretariat: SIS

Voting begins on: **2021-07-22**

Voting terminates on: **2021-10-14**

Steel — Conversion of elongation values —

Part 1: Carbon and low alloy steels

Acier — Conversion des valeurs d'allongement —

iTeh STPartie 1: Aciers au carbone et aciers faiblement alliés

(standards.iteh.ai)

oSIST prEN ISO 2566-1:2021 https://standards.iteh.ai/catalog/standards/sist/7206a339-af80-4509-b36a-875ef809cae7/osist-pren-iso-2566-1-2021

ISO/CEN PARALLEL PROCESSING

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNO-LOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STAN-DARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.



Reference number ISO/FDIS 2566-1:2021(E)

iTeh STANDARD PREVIEW (standards.iteh.ai)

oSIST prEN ISO 2566-1:2021 https://standards.iteh.ai/catalog/standards/sist/7206a339-af80-4509-b36a-875ef809cae7/osist-pren-iso-2566-1-2021



COPYRIGHT PROTECTED DOCUMENT

© ISO 2021

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office CP 401 • Ch. de Blandonnet 8 CH-1214 Vernier, Geneva Phone: +41 22 749 01 11 Email: copyright@iso.org Website: www.iso.org

Published in Switzerland

ISO/FDIS 2566-1:2021(E)

Contents

Forew	ord	iv
Introd	luction	v
1	Scope	1
2	Normative references	1
3	Terms, definitions and symbols3.1Terms and definitions3.2Symbols	1 1 2
4	Basic formula	2
5	Requirements on conversions	2
6	Conversion from one proportional gauge length to another proportional gauge length	3
7	Conversion from one non-proportional gauge length to another non-proportional gauge length for test pieces of equal cross-sectional area	3
8	Conversion from a non-proportional gauge length to another non-proportional gauge length for test pieces of different cross-sectional areas	4
9	Conversion from a proportional gauge length to a non-proportional gauge length 9.1 General	4 4
	9.2 Conversion factors from 5,65 $\sqrt{S_0}$ to non-proportional gauge length	5
	 9.3 Conversion factors from 4 (S₀ to non-proportional gauge length	
10	Use of Figures	.26
Biblio	graphy https://standards.iteh.ai/catalog/standards/sist/7206a339-af80-4509-b36a- 875ef809cae7/osist-pren-iso-2566-1-2021	.33

ISO/FDIS 2566-1:2021(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 17, *Steel*, Subcommittee SC 20, *General technical delivery conditions, sampling and mechanical testing methods*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 459/SC 1, *Test methods for steel (other than chemical analysis)*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This second edition cancels and replaces the first edition (ISO 2566-1:1984), of which it constitutes a minor revision. The changes compared to the previous edition are as follows:

- complete editorial revision;
- <u>Tables 2</u> to <u>5</u> have been renamed due to reordering in order to follow the logical flow of information of this document;
- <u>Clause 8</u> has been restructured into four sub-clauses in order to follow the logical flow of information of this document.

A list of all parts in the ISO 2566 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at <u>www.iso.org/members.html</u>.

Introduction

Several different gauge lengths are commonly in use for the determination of percentage elongation of steels in tensile testing. Fixed gauge lengths of 50 mm, 80 mm, 100 mm and 200 mm are used; proportional gauge lengths of $k\sqrt{S_0}$ are also used for flat and round test pieces, where *k* may be one of a number of values, i.e. 4; 5,65; 8,16 or 11,3.

The value $5{,}65\sqrt{S_0}$ is adopted as the internationally preferred proportional gauge length.

Arising from this choice and the existence of specifications stipulating minimum percentage elongations on different gauge lengths, a growing need has been evident for an International Standard that could be used to convert test results into values based on the different gauge lengths. Accordingly, this document includes tables of conversion factors, tables of actual conversions for some of the most commonly used gauge lengths and elongation values, and figures which may also be used for such conversions. When using these conversions, however, note should be taken of the limitations on their applicability, as stated in <u>Clause 1</u>.

iTeh STANDARD PREVIEW (standards.iteh.ai)

oSIST prEN ISO 2566-1:2021 https://standards.iteh.ai/catalog/standards/sist/7206a339-af80-4509-b36a-875ef809cae7/osist-pren-iso-2566-1-2021

iTeh STANDARD PREVIEW (standards.iteh.ai)

oSIST prEN ISO 2566-1:2021 https://standards.iteh.ai/catalog/standards/sist/7206a339-af80-4509-b36a-875ef809cae7/osist-pren-iso-2566-1-2021

Steel — Conversion of elongation values —

Part 1: Carbon and low alloy steels

1 Scope

This document specifies a method of converting room temperature percentage elongations after fracture obtained on various proportional and non-proportional gauge lengths to other gauge lengths.

Formula (1), on which conversions are based, is considered to be reliable when applied to carbon, carbon manganese, molybdenum and chromium molybdenum steels within the tensile strength range 300 to 700 N/mm² and in the hot-rolled, hot-rolled and normalized or annealed conditions, with or without tempering.

These conversions are not applicable to:

- a) cold reduced steels;
- b) quenched and tempered steels: ANDARD PREVIEW
- c) austenitic steels.

(standards.iteh.ai)

These conversions are not applicable when the gauge length exceeds $25\sqrt{S_0}$ or where the width to thickness ratio of the test piece exceeds 20 EN ISO 2566-1:2021

https://standards.iteh.ai/catalog/standards/sist/7206a339-af80-4509-b36a-875ef809cae7/osist-pren-iso-2566-1-2021

2 Normative references

There are no normative references in this document.

3 Terms, definitions and symbols

3.1 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <u>https://www.iso.org/obp</u>
- IEC Electropedia: available at <u>http://www.electropedia.org/</u>

3.1.1 gauge length

length of the parallel portion of the test piece used for measurement of strain

Note 1 to entry: The term is hereafter used in this document to denote the original gauge length, L_0 , marked on the test piece for the determination of percentage elongation after fracture, A.

3.1.2

proportional gauge length

gauge length (3.1.1) having a specified relation to the square root of the cross-sectional area, for example $5,65\sqrt{S_0}$

ISO/FDIS 2566-1:2021(E)

3.1.3

non-proportional gauge length

gauge length (3.1.1) not specifically related to the cross-sectional area of the test piece, usually expressed in a given dimension, for example 50 mm

3.2 Symbols

Α	Percentage elongation after fracture on a gauge length, obtained on test
A _r	Percentage elongation on a different gauge length, required by conversion
d	Diameter of test piece
L ₀	Original gauge length
S_0	Original cross-sectional area of test piece

Basic formula 4

The data contained in this document are based on the Oliver formula^[1], which is now widely used for such elongation conversions. The Oliver formula can, in a simplified form, be expressed as <u>Formula (1)</u>:

$$A_{\rm r} = 1,74A \left(\frac{\sqrt{S}_0}{L_0}\right)^{0,4}$$
 iTeh STANDARD PREVIEW (1)
ere **(standards.iteh.ai)**

where

- is the required elongation on gauge length 4050 2566-1:2021 A_r
- https://standards.iteh.ai/catalog/standards/sist/7206a339-af80-4509-b36a-is the elongation on gauge length of 4-20 osist-pren-iso-2566-1-2021 Α
- L_0 is the original gauge length;
- S_0 is the original cross-sectional area of test piece.

Formula (1) gives a direct conversion of elongation on $4\sqrt{S_0}$ to the equivalent for a test piece of crosssectional area S_0 , and a gauge length L_0 . Expressed in terms of $5{,}65\sqrt{S_0}$, which is now regarded as the internationally accepted standard gauge length, it becomes Formula (2):

$$A_{\rm r} = 2A \left(\frac{\sqrt{S}_0}{L_0}\right)^{0,4} \tag{2}$$

where *A* is the elongation on gauge length of $5{,}65\sqrt{S_0}$.

Tables 1 to 21 and Figures 1 to 5 are based on Formulae (1) and (2).

Care should be exercised in the case of strip under 4 mm thickness, as the index in Formulae (1) and (2) increases with decreasing thickness; the value to be used shall be the subject of agreement between the customer and the supplier.

Requirements on conversions 5

While, as indicated, the conversions are considered to be reliable within the stated limitations, because of the various factors influencing the determination of percentage elongations, they shall be used for acceptance purposes only by agreement between the customer and supplier.

In cases of dispute, the elongation shall be determined on the gauge length stated in the relevant specification.

6 Conversion from one proportional gauge length to another proportional gauge length

Simple multiplying factors based on the formula are used for such conversions, and the relationships between several of the more widely used proportional gauge lengths are given in Table 1. Detailed conversions of elongations obtained on $4\sqrt{S_0}$ to $5{,}65\sqrt{S_0}$ are given in <u>Table 2</u>.

Conversion	Factor for conversion to:						
from:	$4\sqrt{S_0}$	$5,65\sqrt{S_0}$	$8,16\sqrt{S_0}$	11,3 $\sqrt{S_0}$	4 <i>d</i>	5 <i>d</i>	8 <i>d</i>
$4\sqrt{S_0}$	1,000	0,870	0,759	0,661	0,953	0,870	0,721
$5,65\sqrt{S_0}$	1,149	1,000	0,863	0,759	1,093	1,000	0,828
$8,16\sqrt{S_0}$	1,330	1,158	1,000	0,879	1,268	1,158	1,960
11,3 $\sqrt{S_0}$	1,514	1,317	1,137	1,000	1,443	1,317	1,091
4 <i>d</i>	1,050	0,916	0,790	0,694	1,000	0,916	0,758
5 <i>d</i>	1,149	1,000	0,863	0,759	1,093	1,000	0,828
8 <i>d</i>	1,389	l en _{1,207} A	N 1,042 K	D 0,918	1,319	1,207	1,000

Table 1 — Conversion factors : Proportional gauge length

(standards.iteh.ai) Table 2 — Elongation values^a on 5,65 $\sqrt{S_0}$ corresponding to those obtained on $4\sqrt{S_0}$ gauge oSIST prEN IS ength 2021

Actual elonga-	https://sta	ndards.iteh 875e	.ai/catalog/ f809c &0/7 8	standards/s sespondi	ist/7206a3. ng_elong	39-af80-45 a tion (%)	09-b36a-) on 5,65	$\sqrt{S_0}$		
measured on $4\sqrt{S_0}$	0	1	2	3	4	5	6	7	8	9
10	9	10	10	11	12	13	14	15	16	17
20	17	18	19	20	21	22	23	23	24	25
30	26	27	28	29	30	30	31	32	33	34
40	35	36	37	37	38	39	40	41	42	43
50	43	44	45	46	47	48	49	50	50	51
^a Factor 0,87. Values rounded to nearest whole number.										

Conversion from one non-proportional gauge length to another non-7 proportional gauge length for test pieces of equal cross-sectional area

The conversion of elongation values of different fixed gauge lengths on test pieces of equal crosssectional area are also made by simple factors. Conversion factors for gauge lengths of 50 mm, 80 mm, 100 mm and 200 mm are given in Table 3.

Conversion from	Factor for conversion to:						
Conversion from:	50 mm	80 mm	100 mm	200 mm			
50 mm	1,000	0,829	0,758	0,754			
80 mm	1,207	1,000	0,915	0,693			
100 mm	1,320	1,093	1,000	0,758			
200 mm	1,741	1,443	1,320	1,000			
Provided cross-sectional areas are the same							

Table 3 — Conversion factors^a: Non-proportional gauge length

8 Conversion from a non-proportional gauge length to another non-proportional gauge length for test pieces of different cross-sectional areas

It is preferable for this calculation to be made in two stages with an initial conversion to $5{,}65\sqrt{S_0}$.

EXAMPLE

Elongation of 24 % on 200 mm for a 40 mm x 15 mm test piece in terms of equivalent on a 30 mm x 10 mm test piece with gauge lengths equal to 200 mm, 100 mm and 50 mm.

 $24 \times 1/0,863 = 27,8 \%$ on $-5,65\sqrt{S_0}$ (see Table 3). RD PREVIEW 27,8 x 0,752 = 20,9 % on 30 mm x 10 mm with 200 mm gauge length 27,8 x 0,992 = 27,6 % on 30 mm x 10 mm with 100 mm gauge length

27,8 x 1,309 = 36,4 % on 30 mm x 10 mm with 50 mm gauge length

Elongation on other proportional gauge lengths can be obtained by using the factors given in <u>Table 1</u>. 875ef809cae7/osist-pren-iso-2566-1-2021

9 Conversion from a proportional gauge length to a non-proportional gauge length

9.1 General

The conversion factors are variable according to the cross-sectional area of the non-proportional test piece. Table 4 gives the multiplying factors for conversion from elongation on $5,65\sqrt{S_0}$ to the equivalent on fixed gauge lengths of 50 mm, 80 mm, 100 mm and 200 mm for a range of cross-sectional areas. For conversions in the reverse direction, i.e. elongation on a fixed gauge length to the equivalent of $5,65\sqrt{S_0}$, the reciprocal of the factors is used.

EXAMPLE

- a) Elongation of 20 % on $5{,}65\sqrt{S_0}$ is equivalent to 20 x 1,139 = 22,78 % on a 25 mm wide test piece of 6 mm thickness with a 50 mm gauge length (see Table 4);
- b) Elongation of 25 % on a 40 mm x 10 mm test piece of 200 mm gauge length is equivalent to $25 \times 1/0.796 = 31.4$ % on $5.65\sqrt{S_0}$ (see Table 4).

From the examples shown, it will be seen that conversions involving other proportional gauge lengths can be obtained by prior or subsequent use of the factors shown in <u>Table 1</u>.

9.2 Conversion factors from $5{,}65\sqrt{S_0}$ to non-proportional gauge length

Factors shown under "non-proportional gauge lengths" give the value of

$$2\left(\frac{\sqrt{S}_{0}}{L}\right)^{0,4}$$

To convert from values on a gauge length of $5,65\sqrt{S_0}$ to a non-proportional gauge length, multiply by the appropriate factor.

To convert from values on a non-proportional gauge length to $5{,}65\sqrt{S_0}$, divide by the appropriate factor.

See also <u>Figures 1</u> and <u>2</u>.

Cross sectional area of test piece:	Factor for non-proportional gauge length of:					
mm ²	200 mm	100 mm	80 mm	50 mm		
5	0,331	0,437	0,478	0,577		
10	0,381	0,502	0,549	0,663		
15	iTeb4STA	NDAR545 PRE	V 10,59 6	0,719		
20	0,437	0,577	0,631	0,761		
25	0,457 Stal	10a1 0,603 en.al	0,660	0,796		
30	0,474	0,626	0,684	0,826		
35 h	ttps://standard8.fteh.ai/cata	alog/standar0.545/7206a339	-af80-45 0 9 795 6a-	0,852		
40	0,5 02 5ef809ca	ae7/osist-pr 0;663- 2566-1-20	0,725	0,875		
45	0,514	0,679	0,742	0,896		
50	0,525	0,693	0,758	0,915		
55	0,535	0,706	0,772	0,932		
60	0,545	0,719	0,786	0,949		
70	0,562	0,741	0,811	0,978		
80	0,577	0,761	0,833	1,005		
90	0,591	0,780	0,852	1,029		
100	0,603	0,796	0,871	1,051		
110	0,615	0,812	0,887	1,071		
120	0,626	0,826	0,903	1,090		
130	0,636	0,839	0,917	1,107		
140	0,645	0,852	0,931	1,124		
150	0,654	0,863	0,944	1,139		
160	0,663	0,875	0,956	1,154		
170	0,671	0,885	0,968	1,168		
180	0,679	0,896	0,979	1, 182		
190	0,686	0,905	0,990	1,195		
200	0,693	0,915	1,000	1,207		
210	0,700	0,924	1,010	1,219		
220	0,706	0,932	1,019	1,230		
230	0,713	0,941	1,028	1,241		

Table 4 — Conversion factors from 5,65 $\sqrt{S_0}$ to non-proportional gauge lengths