



SLOVENSKI STANDARD
oSIST prEN ISO 18256-2:2020
01-november-2020

Tehnologija jedrskih goriv - Raztapljanje materialov, ki vsebujejo plutonijev dioksid - 2. del: Raztapljanje peletov in praškov MOX (ISO 18256-2:2019)

Nuclear fuel technology - Dissolution of plutonium dioxide-containing materials - Part 2: Dissolution of MOX pellets and powders (ISO 18256-2:2019)

iTeh STANDARD PREVIEW
(standards.iteh.ai)

Technologie du combustible nucléaire - Dissolution des matériaux contenant du dioxyde de plutonium - Partie 2: Dissolution de pastilles et poudres de MOX (ou mélanges d'oxydes) (ISO 18256-2:2019)

<https://standards.iteh.ai/catalog/standards/sist/c088150c-28c0-4854-bc76-45c002c45675/sist-en-iso-18256-2-2021>

Ta slovenski standard je istoveten z: prEN ISO 18256-2

ICS:

27.120.30	Cepljivi materiali in jedrska gorivna tehnologija	Fissile materials and nuclear fuel technology
-----------	---	---

oSIST prEN ISO 18256-2:2020

en,fr,de

INTERNATIONAL
STANDARD

ISO
18256-2

First edition
2019-01

**Nuclear fuel technology — Dissolution
of plutonium dioxide-containing
materials —**

**Part 2:
Dissolution of MOX pellets and
powders**

*Technologie du combustible nucléaire — Dissolution des matériaux
contenant du dioxyde de plutonium —*

*Partie 2: Dissolution de pastilles et poudres de MOX (ou mélanges
d'oxydes)*

[ISO 18256-2:2021](https://standards.iteh.ai/catalog/standards/sist/c088150c-28c0-4854-bc76-45c002c45675/sist-en-iso-18256-2-2021)

<https://standards.iteh.ai/catalog/standards/sist/c088150c-28c0-4854-bc76-45c002c45675/sist-en-iso-18256-2-2021>



Reference number
ISO 18256-2:2019(E)

© ISO 2019

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN ISO 18256-2:2021

<https://standards.iteh.ai/catalog/standards/sist/c088150c-28c0-4854-bc76-45c002c45675/sist-en-iso-18256-2-2021>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2019

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents		Page
Foreword		iv
Introduction		v
1	Scope	1
2	Normative references	1
3	Terms and definitions	1
4	Summary of the method	1
5	Apparatus and reagents	2
	5.1 Apparatus.....	2
	5.2 Reagents.....	2
6	Sample dissolution	3
	6.1 Procedure for common plutonium containing materials.....	3
	6.2 Solution adjustment (optional).....	5
7	Quality control	6
Bibliography		7

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN ISO 18256-2:2021

<https://standards.iteh.ai/catalog/standards/sist/c088150c-28c0-4854-bc76-45c002c45675/sist-en-iso-18256-2-2021>

ISO 18256-2:2019(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 85, *Nuclear energy, nuclear technologies, and radiological protection*, Subcommittee SC 5, *Nuclear installations, processes and technologies*.

A list of all the parts in the ISO 18256 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

This document describes a method to dissolve samples consisting of MOX pellets or powders to provide suitable aliquots for subsequent analysis of elemental concentration and isotopic composition.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN ISO 18256-2:2021

<https://standards.iteh.ai/catalog/standards/sist/c088150c-28c0-4854-bc76-45c002c45675/sist-en-iso-18256-2-2021>

Nuclear fuel technology — Dissolution of plutonium dioxide-containing materials —

Part 2: Dissolution of MOX pellets and powders

1 Scope

This document specifies the dissolution of samples consisting of MOX pellets or powders to provide suitable aliquots for subsequent analysis of elemental concentration and isotopic composition.

2 Normative references

There are no normative references in this document.

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

— ISO Online browsing platform: available at <https://www.iso.org/obp>

— IEC Electropedia: available at <http://www.electropedia.org/>

4 Summary of the method

Among the factors affecting the formation of solid solution and hence, the ease of dissolution are:

- the method of fuel fabrication (i.e. mechanically blended oxides, co-precipitated oxides, microwave denitrated oxides or sol-gel oxides);
- the degree of sintering.

Therefore, different dissolution methods are applied depending on the type of MOX sample to be dissolved.

The radiological hazard of plutonium and the need to minimize the waste shall be taken into account when choosing the mass of the sample to be dissolved. A MOX mass of 0,1 g to 10 g should be sufficient for most of the analyses. Some analysis may however require more material.

For the highest possible assay accuracy only gravimetric dissolution methods are recommended. However for a less critical assay, volumetric dissolution may be appropriate.

ISO 18256-2:2019(E)

For grain-size powders, the sample is transferred in a pre-weighed flask or vial made of glass, high-density polyethylene (HDPE), polytetrafluoroethylene (PTFE), Nalgene^{TM1)} or other container types, but the choice of the container has consequences.

- When using a glass dissolution vessel, the added fluoride will attack the glass (resulting in a falsification of the pre-weighed tare) but with the benefit that the fluoride is ultimately removed from the solution via release of volatile SiF₄. The resulting reduction in fluoride content of the final solution guards against the formation of insoluble plutonium fluoride (especially below 8 M), which would negatively bias the plutonium element content up to 0,1 % [or more when large quantities of hydrofluoric acid (HF) are used]. The tare mass of the etched glass vessel may be re-established by careful cleaning, drying and re-weighing of the vessel.
- HDPE, PTFE or Nalgene^{TM1)} dissolution vessels are not reactive to HF, therefore tare mass remains unaffected. However, these materials have the disadvantage that fluoride ions in the dissolution liquor promote the precipitation of insoluble plutonium fluoride when the oxidation state of plutonium is reduced from IV to III (e.g. by later volume adjustments using a low molarity acid).

An aqueous dissolving mixture comprising nitric acid (about 8 mol/l to 14 mol/l) and an effective catalytic amount of fluoride ions from either hydrofluoric acid (about 0,05 mol/l to 0,1 mol/l) or ammonium bifluoride (about 2 g/l) is added and the pre-weighted dissolution vessel is closed with a reflux cap (or watch glass). The vessel is placed on a hotplate and heat is applied until the dissolution is completed. The solution is then ready for concentration determination of plutonium or uranium per gram of solution by suitable analytical methods. The solution can be used for other analyses, e.g. plutonium or uranium isotopic abundances or impurities determination.

5 Apparatus and reagents

WARNING — Because of the radiological hazard of plutonium, it shall be handled in glove boxes or hot cells and extreme care shall be taken to prevent direct contact, inhalation or ingestion.

5.1 Apparatus

Normal laboratory equipment for a plutonium laboratory and, in particular, the following.

5.1.1 Analytical balance, with a capacity up to 1 200 g and an accuracy of 0,001 g.

5.1.2 Dissolution vessels, dissolution flask or vial with a PTFE-lined screw cap.

The volume of the flask should be adapted to the volume of solution for the appropriate concentration required for subsequent analysis. PTFE-lined screw cap is recommended for the samples which will be stored for long term.

5.1.3 Glass or PTFE reflux cap, or watch glass.

5.1.4 Reflux condenser.

5.1.5 Shielded hotplate, equipped with a temperature control unit and a fume hood.

5.1.6 PTFE coated tweezers.

5.2 Reagents

Use only reagents of recognized analytical grade.

1) NalgeneTM is the trademark of a suitable product available commercially. This information is given for the convenience of users of this document and does not constitute an endorsement by ISO of the product named. Equivalent products may be used if they can be shown to lead to the same results.