



Designation: ~~B392-03~~ Designation: B392 - 09

Standard Specification for Niobium and Niobium Alloy Bar, Rod, and Wire¹

This standard is issued under the fixed designation B392; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers four grades of wrought niobium and niobium alloy bar, rod, and wire as follows: ~~Note 1—~~ Committee B10 has adopted “niobium” as the designation for Element No. 41, formerly named “columbium.”

1.1.1 *R04200-Type 1*—Reactor grade unalloyed niobium,

1.1.2 *R04210-Type 2*—Commercial grade unalloyed niobium,

1.1.3 *R04251-Type 3*—Reactor grade niobium alloy containing 1 % zirconium, and

1.1.4 *R04261-Type 4*—Commercial grade niobium alloy containing 1 % zirconium.

~~1.2 The values stated in inch-pound units are to be regarded as the standard. The values given in parentheses are for information only.~~

1.2 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.3 *The following precautionary caveat pertains only to the test methods portion of this specification. This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*²

B391 [Specification for Niobium and Niobium Alloy Ingots](#)

E8 [Test Methods for Tension Testing of Metallic Materials](#)

~~E29 [Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications](#)~~ [Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications](#)

E2626 [Guide for Spectrometric Analysis of Reactive and Refractory Metals](#)

3. Terminology

3.1 *Definitions of Terms Specific to This Standard:* Descriptions of Terms Specific to This Standard:

3.1.1 ~~lot~~ *lot, n*—a lot shall consist of all material produced from the same ingot at one time, with the same cross section, processed with the same nominal metallurgical parameters and heat treated at the same conditions.

3.1.2 ~~bar~~ *bar, n*—material less than 6 in. (152.4 mm) in width and 0.187 in. (4.75 mm) or greater in thickness, with a rectangular cross section, supplied in straight lengths.

3.1.3 ~~rod~~ *rod, n*—material 0.125 to 2.50 in. (3.18 to 63.50 mm) in diameter, in round, hexagonal, or octagonal cross section supplied in straight lengths.

3.1.4 ~~wire~~ *wire, n*—material 0.020 to 0.124 in. (0.51 to 3.15 mm) in diameter, furnished in coils or on spools or reels. Material less than 0.020 in. (0.51 mm) in diameter is not covered by this specification.

4. Ordering Information

4.1 Orders for materials under this specification shall include the following information as applicable:

4.1.1 Type and grade (Section 1),

4.1.2 ASTM designation and year of issue,

¹ This specification is under the jurisdiction of ASTM Committee B10 on Reactive and Refractory Metals and Alloys and is the direct responsibility of Subcommittee B10.03 on Niobium and Tantalum.

Current edition approved Sept. 10, 2003. Published September 2003. Originally approved in 1989. Last previous edition approved in 1999 as B392-99. DOI: 10.1520/B0392-03.

Current edition approved Oct. 1, 2009. Published December 2009. Originally approved in 1989. Last previous edition approved in 2003 as B392-03. DOI: 10.1520/B0392-09.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* Volume 02.04, volume information, refer to the standard's Document Summary page on the ASTM website.

- 4.1.3 Method of manufacture (Section 5),
- 4.1.4 Temper designation (Section 8),
- 4.1.5 Quantity in weight, number of pieces, and dimensions,
- 4.1.6 Chemistry (6.3),
- 4.1.7 Mechanical properties (Section 7),
- 4.1.8 Condition (8.2),
- 4.1.9 Permissible Variations (9.2),
- 4.1.10 Permissible overshipments (9.4),
- 4.1.11 Quality and finish (Section 10),
- 4.1.12 Sampling (Section 11),
- 4.1.13 Inspection (Section 15),
- 4.1.14 Required reports (Section 17), and
- 4.1.15 Additions to the specification and supplementary requirements, as required.

5. Materials and Manufacture

5.1 Material covered by this specification shall be made from ingots that conform to Specification B391 and that are produced by vacuum or plasma arc melting, vacuum electron-beam melting, or a combination of these three methods.

5.2 The various niobium mill products covered by this specification are formed with the conventional extrusion, forging, swaging, rolling, and drawing equipment normally available in metal working plants.

6. Chemical and Hardness Requirements

6.1 The niobium and niobium alloy ingots and billets for conversion to finished products covered by this specification shall conform to the requirements for chemical composition and hardness as prescribed in Table 1 and Table 2.

6.2 The manufacturer's ingot analysis shall be considered the chemical analysis for products supplied under this specification, except for interstitials as specified in 6.3. Alternately, an analysis of a representative sample of in process or final product from the same ingot may be substituted.

6.3 When requested by the purchaser at the time of purchase, the manufacturer shall furnish a report certifying the values of the interstitial elements (C, O, N, H) on end product, as prescribed in Table 3 for each lot of material supplied. ~~for each lot of material supplied.~~ End product interstitial samples must be taken after all thermal and chemical processing.

6.4 Guide E2626 is recommended as a guide, where applicable.

7. Mechanical Requirements

7.1 The annealed materials supplied under this specification shall conform to the requirements for mechanical properties as specified in ~~Table 4~~ Table 3.

TABLE 1 Chemical Requirements

Element	Type 1 (Reactor Grade Unalloyed Niobium) R04200	Type 2 (Commercial Grade Unalloyed Niobium) R04210	Type 3 (Reactor Grade Niobium-1 % Zirconium) R04251	Type 4 (Commercial Grade Niobium- 1 % Zirconium) R04261
	Max Weight % (Except Where Otherwise Specified)			
Each Ingot:				
Carbon	0.01	0.01	0.01	0.01
Nitrogen	0.01	0.01	0.01	0.01
Oxygen	0.015	0.025	0.015	0.025
Hydrogen	0.0015	0.0015	0.0015	0.0015
Zirconium	0.02	0.02	0.8 to 1.2 (range)	0.8 to 1.2 (range)
Tantalum	0.1	0.3	0.1	0.5
Iron	0.005	0.01	0.005	0.01
Silicon	0.005	0.005	0.005	0.005
Tungsten	0.03	0.05	0.03	0.05
Nickel	0.005	0.005	0.005	0.005
Molybdenum	0.010	0.020	0.010	0.050
Hafnium	0.02	0.02	0.02	0.02
Titanium	0.02	0.03	0.02	0.03
When Specified:				
Boron	2 ppm	...	2 ppm	...
Aluminum	0.002	0.005	0.002	0.005
Beryllium	0.005	...	0.005	...
Chromium	0.002	...	0.002	...
Cobalt	0.002	...	0.002	...