This document is not an ASTM standard and is intended only to provide the user of an ASTM standard an indication of what changes have been made to the previous version. Because it may not be technically possible to adequately depict all changes accurately, ASTM recommends that users consult prior editions as appropriate. In all cases only the current version of the standard as published by ASTM is to be considered the official document.

Designation: B393-05 Designation: B 393 - 09

Standard Specification for Niobium and Niobium Alloy Strip, Sheet, and Plate¹

This standard is issued under the fixed designation B 393; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers five grades of wrought niobium and niobium alloy strip, sheet, and plate as follows: Note1—Committee B10 has adopted "niobium" as the designation for Element No. 41, formerly named "columbium."

- 1.1.1 R04200-Type 1-Reactor grade unalloyed niobium,
- 1.1.2 R04210-Type 2-Commercial grade unalloyed niobium,
- 1.1.3 R04251-Type 3-Reactor grade niobium alloy containing 1 % zirconium, and
- 1.1.4 R04261-Type 4—Commercial grade niobium alloy containing 1 % zirconium.
- 1.1.5 R0xxxx-Type 5-RRR grade pure niobium.

NOTE2-This 1-This grade of niobium is used in superconducting applications that require the ultra high purity. Because of the high purity the product is conducive to very large grains that can adversely affect formability. It is not recommended for other applications.

1.2 Except for dimensional tolerances in Table 1, the values stated in inch-pound units are to be regarded as the standard. The values given in parentheses are for information only., the values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.3 The following precautionary caveat pertains only to the test methods portion of this specification. This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.

2. Referenced Documents

2.1 ASTM Standards:²

- B 391 Specification for Niobium and Niobium Alloy Ingots
- E 8 Test Methods for Tension Testing of Metallic Materials

E 29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications-Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications

E 2626 Guide for Spectrometric Analysis of Reactive and Refractory Metals 90012000/astm-b393-09

3. Terminology

3.1 Definitions of Terms Specific to This Standard:

3.1.1 lot, n—a lot shall consist of all material produced from the same ingot at one time, with the same cross section, processed with the same nominal metallurgical parameters and heat treated at the same conditions.

3.1.2 plate, n—a flat product 6 in. (152.4 mm) or more in width and greater than $\frac{3}{16}$ in. (4.76 mm) in thickness.

3.1.3 sheet, n—a flat product 6 in. (152.4 mm) or more in width and from 0.005 in. (0.13 mm) to $\frac{3}{16}$ in. (4.76 mm) in thickness. 3.1.4 strip, n—a flat product, which may be supplied in coil, less than 6 in. (152.4 mm) in width and from 0.005 in. (0.13 mm) to ³/₁₆ in. (4.76 mm) in thickness.

4. Ordering Information

4.1 Orders for materials under this specification shall include the following information as applicable:

- 4.1.1 Type and grade (Section 1),
- 4.1.2 ASTM designation and year of issue,

Copyright © ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States

¹ This specification is under the jurisdiction of ASTM Committee B10 on Reactive and Refractory Metals and Alloys and is the direct responsibility of Subcommittee B10.03 on Niobium and Tantalum.

Current edition approved MayOct. 1, 2005:2009. Published June 2005. October 2009. Originally approved in 1999. Last previous edition approved in 20032005 as B 393 - 035

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For Annual Book of ASTM Standards volume information, refer to the standard's Document Summary page on the ASTM website.



TABLE 1 Dimensional Tolerances for Niobium Flat-Rolled Products

Thickness of Material, in. (mm) in lower table	Tolerance on Thickness ^A plus or minus, in. (mm) in lower table		Tolerance on Width (slit) ^B plus or minus, in.(mm) in lower table		Tolerance on Sheared Lengths, in. (mm)			
	Width under 6 in. or 152.4 mm	Width 6 to 24 in. or 152.4 to 609.6 mm	Width under 6 in. or 152.4 mm	Width 6 to 24 in. or 152.4 to 609.6 mm	Length 12 in. or 304.8 mm and under		Length over 12 in. or 304.8 mm	
					Plus	Minus	Plus	Minus
	Inches							
0.005 to 0.010 excl	0.0005	0.001	0.012		1/16	0	3/32	0
0.010 to 0.015 excl	0.0007	0.001	0.015	0.015	1/16	0	3/32	0
0.015 to 0.020 excl	0.0008	0.0015	0.015	0.015	1/16	0	3/32	0
0.020 to 0.030 excl	0.0015	0.0025	0.020	0.025	1/16	0	3/32	0
0.030 to 0.060 excl	0.0025	0.0035	0.025	0.030	1/16	0	3/32	0
0.060 to 0.090 excl	0.004	0.005	0.025	0.035	1/16	0	3/32	0
0.090 to 0.125 excl	0.006	0.007			1/16	0	3/32	0
0.125 to 0.187 excl	0.010	0.010			1/16	0	3/32	0
0.187 to 0.250 excl	0.015	0.015			1/8	0	5/32	0
0.250 to 0.312 excl	0.020	0.020			1/8	0	5/32	0
0.312 to 0.375 excl	0.025	0.025			3⁄16	0	7/32	0
	Millimetres							
0.13 to 0.254 excl	0.013	0.025	0.30		1.59	0	2.38	0
0.254 to 0.381 excl	0.018	0.025	0.38	0.38	1.59	0	2.38	0
0.381 to 0.508 excl	0.020	0.038	0.38	0.38	1.59	0	2.38	0
0.508 to 0.762 excl	0.038	0.064	0.51	0.64	1.59	0	2.38	0
0.762 to 1.524 excl	0.064	0.089	0.64	0.76	1.59	0	2.38	0
1.524 to 2.286 excl	0.102	0.127	0.64	0.89	1.59	0	2.38	0
2.286 to 3.175 excl	0.15	0.18			1.59	0	2.38	0
3.175 to 4.75 excl	0.25	0.25			1.59	0	2.38	0
4.75 to 6.35 excl	0.38	0.38			3.18	0	3.97	0
6.35 to 7.925 excl	0.51	0.51			3.18	0	3.97	0
7.925 to 9.52 excl	0.64	0.64		tomdo	4.76	0	5.56	0

^A Tolerance on thickness of sheet over 24 in. (610 mm) wide shall be ±10 % of the thickness.

^B Tolerance on width of sheared sheet shall be ±1/16 in. (±1.6 mm) and on sheared plate shall be ±1/6 in. (±3.2 mm) up to material thickness of 0.375 in. (9.5 mm).

4.1.3 Quantity in weight, number of pieces, and dimensions,

4.1.4 Chemistry (6.3),

4.1.5 Temper designation (Section 8),

4.1.6 Permissible overshipment (9.3),

4.1.7 Quality and finish (10.3),

4.1.8 Sampling (11.2),

ASTM B393-09

4.1.9 Inspection (Section 15), dards/astm/cbc7dce2-797c-497b-bc74-e7369c012e0d/astm-b393-09

4.1.10 Required reports (Section 17),

4.1.11 Marking (Section 18), and

4.1.12 Additions to the specification and supplementary requirements, as required.

5. Materials and Manufacture

5.1 Material covered by this specification shall be made from ingots that conform to Specification B 391 and that are produced by vacuum or plasma arc melting, vacuum electron-beam melting, or a combination of these three methods.

5.2 The various niobium mill products covered by this specification are formed with the conventional extrusion, forging, swaging, rolling, and drawing equipment normally available in metal working plants.

6. Chemical and Hardness Requirements

6.1 The niobium and niobium alloy ingots and billets for conversion to finished products covered by this specification shall ■ conform to the requirements for chemical composition-and hardness as prescribed in Table 2and Table 3.

6.2 The manufacturer's ingot analysis shall be considered the chemical analysis for products supplied under this specification, except for <u>end product</u> interstitials as specified in 6.3.-. <u>Alternately, an analysis of a representative sample of in process or final</u> product from the same ingot may be specified.

6.3 When requested by the purchaser at the time of purchase, the manufacturer shall furnish a report certifying the values of the interstitial elements (C, O, N, H) <u>on end products</u> as prescribed in Table 43 for each lot of material supplied. End product interstitial samples must be taken after all thermal and chemical processing.

6.4 Guide E 2626 is recommended as a guide, where applicable.

7. Mechanical Requirements

7.1 The annealed materials supplied under this specification shall conform to the requirements for mechanical properties as specified in Table 5 Table 4.