



Designation: ~~C94/C94M-09~~ Designation: C94/C94M – 09a

Standard Specification for Ready-Mixed Concrete¹

This standard is issued under the fixed designation C94/C94M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope*

1.1 This specification covers ready-mixed concrete as defined in 3.2.2. Requirements for quality of concrete shall be either as hereinafter specified or as specified by the purchaser. In any case where the requirements of the purchaser differ from these in this specification, the purchaser's specification shall govern. This specification does not cover the placement, consolidation, curing, or protection of the concrete after delivery to the purchaser.

1.2 The values stated in either SI units, shown in brackets, or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

1.3 As used throughout this specification the manufacturer produces ready-mixed concrete. The purchaser buys ready-mixed concrete.

1.4 The text of this standard references notes and footnotes which provide explanatory material. These notes and footnotes (excluding those in tables and figures) shall not be considered as requirements of the standard.

1.5 *This standard does not purport to address all the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use. (Warning—Fresh hydraulic cementitious mixtures are caustic and may cause chemical burns to skin and tissue upon prolonged use.²)*

2. Referenced Documents

2.1 ASTM Standards:³

C31/C31M Practice for Making and Curing Concrete Test Specimens in the Field

C33 Specification for Concrete Aggregates

C39/C39M Test Method for Compressive Strength of Cylindrical Concrete Specimens

C125 Terminology Relating to Concrete and Concrete Aggregates

C138/C138M Test Method for Density (Unit Weight), Yield, and Air Content (Gravimetric) of Concrete

C143/C143M Test Method for Slump of Hydraulic-Cement Concrete

C150 Specification for Portland Cement

C172 Practice for Sampling Freshly Mixed Concrete

C173/C173M Test Method for Air Content of Freshly Mixed Concrete by the Volumetric Method

C231 Test Method for Air Content of Freshly Mixed Concrete by the Pressure Method

C260 Specification for Air-Entraining Admixtures for Concrete

C330 Specification for Lightweight Aggregates for Structural Concrete

C494/C494M Specification for Chemical Admixtures for Concrete

C567 Test Method for Determining Density of Structural Lightweight Concrete

C595 Specification for Blended Hydraulic Cements

C618 Specification for Coal Fly Ash and Raw or Calcined Natural Pozzolan for Use in Concrete

C637 Specification for Aggregates for Radiation-Shielding Concrete

C989 Specification for Slag Cement for Use in Concrete and Mortars

¹ This specification is under the jurisdiction of ASTM Committee C09 on Concrete and Concrete Aggregates and is the direct responsibility of Subcommittee C09.40 on Ready-Mixed Concrete.

Current edition approved Jan-Nov. 1, 2009. Published January-December 2009. Originally approved in 1933. Last previous edition approved in 2007/2009 as C94/C94M-07 ϵ . DOI: 10.1520/C0094_C0094M-09a.

² See Section on Safety Precautions, Manual of Aggregate and Concrete Testing, *Annual Book of ASTM Standards*, Vol. 04.02.

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

*A Summary of Changes section appears at the end of this standard.

C1017/C1017M [Specification for Chemical Admixtures for Use in Producing Flowing Concrete](#)
C1064/C1064M [Test Method for Temperature of Freshly Mixed Hydraulic-Cement Concrete](#)
C1077 [Practice for Laboratories Testing Concrete and Concrete Aggregates for Use in Construction and Criteria for Laboratory Evaluation](#)
C1157 [Performance Specification for Hydraulic Cement](#)
C1240 [Specification for Silica Fume Used in Cementitious Mixtures](#)
C1602/C1602M [Specification for Mixing Water Used in the Production of Hydraulic Cement Concrete](#) [Specification for Mixing Water Used in the Production of Hydraulic Cement Concrete](#)
C1611/C1611M [Test Method for Slump Flow of Self-Consolidating Concrete](#)

2.2 *ACI Documents:*⁴

CP-1 Technician Workbook for ACI Certification of Concrete Field Testing Technician–Grade I
211.1 Standard Practice for Selecting Proportions for Normal, Heavyweight, and Mass Concrete
211.2 Standard Practice for Selecting Proportions for Structural Lightweight Concrete
301 Standard Specifications for Structural Concrete
305R Hot Weather Concreting
306R Cold Weather Concreting
318 Building Code Requirements for Structural Concrete and Commentary

2.3 *Other Documents:*

Bureau of Reclamation Concrete Manual ⁵

3. Terminology

3.1 *Definitions:*

The terms used in this specification are defined in Terminology C125.

3.2 Definitions of Terms Specific to This Standard:

3.2.1 *concrete, central-mixed, n*—concrete mixed completely in a stationary mixer.

3.2.2 *concrete, ready-mixed, n*—concrete manufactured and delivered to a purchaser in a fresh state.

3.2.3 *concrete, shrink-mixed, n*—concrete partially mixed in a stationary mixer with mixing completed in a truck mixer.

3.2.4 *concrete, truck-mixed, n*—concrete completely mixed in a truck mixer.

4. Basis of Purchase

4.1 The basis of purchase shall be a cubic yard or cubic metre of fresh concrete as discharged from the transportation unit.

4.2 The volume of fresh concrete in a given batch shall be determined from the total mass of the batch divided by the density of the concrete. The total mass of the batch shall be determined as the net mass of the concrete in the batch as delivered, including the total mixing water as defined in 9.3. The density shall be determined in accordance with Test Method C138/C138M. The yield shall be determined as the average of at least three measurements, one from each of three different transportation units sampled in accordance with Practice C172.

NOTE 1—It should be understood that the volume of hardened concrete may be, or appear to be, less than expected due to waste and spillage, over-excavation, spreading forms, some loss of entrained air, or settlement of wet mixtures, none of which are the responsibility of the producer.

5. Materials

5.1 In the absence of designated applicable materials specifications, the following materials specifications shall be used:

5.2 *Cementitious Materials*

5.2.1 *Hydraulic Cement*—Hydraulic cement shall conform to Specification C150, Specification C595, or Specification C1157.

5.2.2 *Supplementary Cementitious Materials*—Coal fly ash or natural pozzolans shall conform to Specification C618. Ground granulated blast furnace slag shall conform to Specification C989. Silica fume shall conform to Specification C1240.

5.2.3 *Cementitious concrete mixtures*—Cementitious concrete mixtures shall contain the kind(s) and class(es) of hydraulic cement(s) and the kind(s) and class(es) of supplementary cementitious material(s) as specified by the purchaser. If hydraulic cement specification or type is not provided then the requirements of portland cement Type I or Type II conforming to Specification C150 shall apply or other cementitious materials that have a demonstrated ability to satisfy the intended use.

5.3 *Aggregates*—Normal weight aggregates shall conform to Specification C33. Lightweight aggregates shall conform to Specification C330 and heavyweight aggregates shall conform to Specification C637.

5.4 *Water*—Water shall conform to Specification C1602/C1602M.

5.5 *Air-Entraining Admixtures*—Air-entraining admixtures shall conform to Specification C260 (Note 2).

5.6 *Chemical Admixtures*—Chemical admixtures shall conform to either Specification C494/C494M or C1017/C1017M as applicable (Note 2).

⁴ Available from American Concrete Institute (ACI), P.O. Box 9094, Farmington Hills, MI 48333-9094, <http://www.concrete.org>.

⁵ Available from Superintendent of Documents, U. S. Government Printing Office, Washington, DC 20402.



NOTE 2—In any given instance, the required dosage of air-entraining, accelerating, and retarding admixtures may vary. Therefore, a range of dosages should be allowed which will permit obtaining the desired effect.

NOTE 3—Interchanging kinds, characteristics, types, classes, or grades of the materials permitted in ready-mixed concrete may produce concrete of different properties.

6. Ordering Information

6.1 In the absence of designated applicable general specifications, the purchaser shall specify the following:

6.1.1 Designated size, or sizes, of coarse aggregate,

6.1.2 Slump, or slumps, desired at the point of delivery (see Section 7 for acceptable tolerances),

~~6.1.3 When air-entrained concrete is specified, the air content of the samples taken at the point of discharge from the transportation unit (see Section~~

6.1.3 Slump flow, or flows, desired at the point of delivery (see Section 7 for acceptable tolerances),

6.1.4 When air-entrained concrete is specified, the air content of the samples taken at the point of discharge from the transportation unit (see Section 8 and Table 1 for the total air content and tolerances) (Note 4),

~~6.1.45~~ Which of Options A, B, or C shall be used as a basis for determining the proportions of the concrete to produce the required quality,

~~6.1.56~~ When structural lightweight concrete is specified, the mass per unit volume as wet mass, air-dry mass, or oven-dry mass (Note 5), and

~~6.1.6~~6.1.7 If desired, any of the optional requirements of Table 2 in Specification C1602/C1602M.

NOTE 4—In selecting the specified air content, the purchaser should consider the exposure conditions to which the concrete will be subjected. Air contents less than shown in Table 1 may not give the required resistance to freezing and thawing, which is the primary purpose of air-entrained concrete. Air contents higher than the levels shown may reduce strength without contributing any further improvement of durability.

NOTE 5—The mass per unit volume of fresh concrete, which is the only unit mass determinable at the time of delivery, is always higher than the air-dry or oven-dry mass. Definitions of, and methods for determining or calculating air-dry and oven-dry masses, are covered by Test Method C567.

6.2 Option A:

6.2.1 When the purchaser requires the manufacturer to assume full responsibility for the selection of the proportions for the concrete mixture (Note 6), the purchaser shall also specify the following:

6.2.1.1 Requirements for compressive strength as determined on samples taken from the transportation unit at the point of discharge evaluated in accordance with Section 18. The purchaser shall specify the requirements in terms of the compressive strength of standard specimens cured under standard laboratory conditions for moist curing (see Section 18). Unless otherwise specified the age at test shall be 28 days.

NOTE 6—The purchaser, in selecting requirements for which he assumes responsibility should give consideration to requirements for workability, placeability, durability, surface texture, and density, in addition to those for structural design. The purchaser is referred to Standard Practice ACI 211.1 and Standard Practice ACI 211.2 for the selection of proportions that will result in concrete suitable for various types of structures and conditions of exposure. The water-cement ratio of most structural lightweight concretes cannot be determined with sufficient accuracy for use as a specification basis.

6.2.2 At the request of the purchaser, the manufacturer shall, prior to the actual delivery of the concrete, furnish a statement to the purchaser, giving the dry masses of cement and saturated surface-dry-masses of fine and coarse aggregate and quantities, type, and name of admixtures (if any) and of water per cubic yard or cubic metre of concrete that will be used in the manufacture of each class of concrete ordered by the purchaser. He shall also furnish evidence satisfactory to the purchaser that the materials to be used and proportions selected will produce concrete of the quality specified.

6.3 Option B:

6.3.1 When the purchaser assumes responsibility for the proportioning of the concrete mixture, he shall also specify the following:

6.3.1.1 Cement content in bags or pounds per cubic yard [kilograms per cubic metre] of concrete,

6.3.1.2 Maximum allowable water content in gallons per cubic yard [litres per cubic metre] of concrete, including surface moisture on the aggregates, but excluding water of absorption (Note 6), and

6.3.1.3 If admixtures are required, the type, name, and dosage to be used. The cement content shall not be reduced when admixtures are used under this option without the written approval of the purchaser.

TABLE 1 Recommended Total Air Content for Air-Entrained Concrete^{A,B}

Exposure Condition ^C	Total Air Content, %						
	Nominal Maximum Sizes of Aggregate, in. [mm]						
	% [9.5]	½ [12.5]	¾ [19.0]	1 [25.0]	1½ [37.5]	2 [50.0]	3 [75.0]
Mild	4.5	4.0	3.5	3.0	2.5	2.0	1.5
Moderate	6.0	5.5	5.0	4.5	4.5	4.0	3.5
Severe	7.5	7.0	6.0	6.0	5.5	5.0	4.5

^A For air-entrained concrete, when specified.

^B Unless exposure conditions dictate otherwise, it is permissible to reduce air contents recommended above by up to 1 % for concretes with specified compressive strength, f_c , of 5000 psi [35 MPa] or above.

^C For description of exposure conditions, refer to Standard Practice ACI 211.1, Section 6.3.3, with attention to accompanying footnotes.

6.3.2 At the request of the purchaser, the manufacturer shall, prior to the actual delivery of the concrete, furnish a statement to the purchaser giving the sources, densities, and sieve analyses of the aggregates and the dry masses of cement and saturated-surface-dry masses of fine and coarse aggregate and quantities, type and name of admixture (if any) and of water per cubic yard or cubic metre of concrete that will be used in the manufacture of each class of concrete ordered by the purchaser.

6.4 *Option C:*

6.4.1 When the purchaser requires the manufacturer to assume responsibility for the selection of the proportions for the concrete mixture with the minimum allowable cement content specified (Note 7), the purchaser shall also specify the following:

6.4.1.1 Required compressive strength as determined on samples taken from the transportation unit at the point of discharge evaluated in accordance with Section 18. The purchaser shall specify the requirements for strength in terms of tests of standard specimens cured under standard laboratory conditions for moist curing (see Section 18). Unless otherwise specified the age at test shall be 28 days.

6.4.1.2 Minimum cement content in bags or pounds per cubic yard [kilograms per cubic metre] of concrete.

6.4.1.3 If admixtures are required, the type, name, and dosage to be used. The cement content shall not be reduced when admixtures are used.

NOTE 7—Option C can be distinctive and useful only if the designated minimum cement content is at about the same level that would ordinarily be required for the strength, aggregate size, and slump or slump flow specified. At the same time, it must be an amount that will be sufficient to ensure durability under expected service conditions, as well as satisfactory surface texture and density, in the event specified strength is attained with it. For additional information refer to Standard Practice ACI 211.1 and Standard Practice 211.2 referred to in Note 6.

6.4.2 At the request of the purchaser, the manufacturer shall, prior to the actual delivery of the concrete, furnish a statement to the purchaser, giving the dry masses of cement and saturated surface-dry masses of fine and coarse aggregate and quantities, type, and name of admixture (if any) and of water per cubic yard or cubic metre of concrete that will be used in the manufacture of each class of concrete ordered by the purchaser. He shall also furnish evidence satisfactory to the purchaser that the materials to be used and proportions selected will produce concrete of the quality specified. Whatever strengths are attained the quantity of cement used shall not be less than the minimum specified.

6.5 The proportions arrived at by Options A, B, or C for each class of concrete and approved for use in a project shall be assigned a designation to facilitate identification of each concrete mixture delivered to the project. This is the designation required in 14.1.7 and supplies information on concrete proportions when they are not given separately on each delivery ticket as outlined in 14.2. A certified copy of all proportions as established in Options A, B, or C shall be on file at the batch plant.

6.6 The purchaser shall ensure that the manufacturer is provided copies of all reports of tests performed on concrete samples taken to determine compliance with specification requirements. Reports shall be provided on a timely basis.

7. Tolerances in Slump—Tolerances in Slump or Slump Flow

7.1 Unless other tolerances are included in the project specifications, the following shall apply.

7.1.1 When the project specifications for slump are written as a “maximum” or “not to exceed” requirement:

	Specified slump:	
	If 3 in. [75 mm] or less	If more than 3 in. [75 mm]
Plus tolerance:	0	0
Minus tolerance:	1½ in. [40 mm]	2½ in. [65 mm]

This option is to be used only if one addition of water is permitted on the job provided such addition does not increase the water-cement ratio above the maximum permitted by the specifications.

7.1.2 When the project specifications for slump are *not* written as a “maximum” or “not to exceed” requirement:

Tolerances for Nominal Slumps

For Specified Slump of:	Tolerance
2 in. [50 mm] and less	± ½ in. [15 mm]
More than 2 through 4 in. [50 to 100 mm]	± 1 in. [25 mm]
More than 4 in. [100 mm]	± 1½ in. [40 mm]

~~7.2 Concrete shall be available within the permissible range of slump for a period of 30 min starting either on arrival at the job site or after the initial slump adjustment permitted in~~

7.1.3 When the project specifications indicate a slump flow requirement for self-consolidating concrete:

Tolerances for Slump Flow

For Specified Slump Flow	Tolerance
Less than or equal to 22 in. [550 mm]	± 1 ½ in. [40 mm]
More than 22 in [550 mm]	± 2 ½ in. [65 mm]

7.2 Concrete shall be available within the permissible range of slump or slump flow for a period of 30 min starting either on arrival at the job site or after the initial slump adjustment permitted in 12.7, whichever is later. The first and last ¼ yd³ or ¼ m³ discharged are exempt from this requirement. If the user is unprepared for discharge of the concrete from the vehicle, the producer

shall not be responsible for the limitation of minimum slump or slump flow after 30 min have elapsed starting either on arrival of the vehicle at the prescribed destination or at the requested delivery time, whichever is later.

8. Air-Entrained Concrete

8.1 When air-entrained concrete is desired the purchaser shall specify the total air content of the concrete. See Table 1 for recommended total air contents (Note 2).

8.2 The air content of air-entrained concrete when sampled from the transportation unit at the point of discharge shall be within a tolerance of ± 1.5 of the specified value.

8.3 When a preliminary sample taken within the time limits of 12.7 and prior to discharge for placement shows an air content below the specified level by more than the allowable tolerance in accordance with 8.2, the manufacturer may use additional air entraining admixture to achieve the desired air content level, followed by a minimum of 30 revolutions at mixing speed, so long as the revolution limit of 12.7 is not exceeded (see Note 8).

NOTE 8—Acceptance sampling and testing in accordance with Practice C172 is not obviated by this provision.

9. Measuring Materials

9.1 Except as otherwise specifically permitted, cementitious materials shall be measured by mass. When supplementary cementitious materials are used in the concrete mixtures, the cumulative mass is permitted to be measured with hydraulic cement, but in a batch hopper and on a scale which is separate and distinct from those used for other materials. The mass of the hydraulic cement shall be measured before supplementary cementitious materials. When the quantity of cementitious material exceeds 30 % of the full capacity of the scale, the measured quantity of the hydraulic cement shall be within ± 1 % of the required mass, and the cumulative measured quantity of hydraulic cement plus supplementary cementitious materials shall also be within ± 1 % of the required cumulative mass at each intermediate weighing. For smaller batches to a minimum of 1 yd³ [1 m³], the measured quantity of the hydraulic cement and the measured cumulative quantity of hydraulic cement plus supplementary cementitious materials used shall be not less than the required amount nor more than 4 % in excess. Under special circumstances approved by the purchaser, hydraulic cement is permitted to be measured in bags of standard mass (Note 9). No fraction of a bag of hydraulic cement shall be used unless its mass has been determined.

NOTE 9—In the United States the standard mass of a bag of portland cement is 94 lb [42.6 kg] ± 3 %.

9.2 Aggregate shall be measured by mass. Batch mass measurements shall be based on dry materials and shall be the required masses of dry materials plus the total mass of moisture (both absorbed and surface) contained in the aggregate. The quantity of aggregate used in any batch of concrete as indicated by the scale shall be within ± 2 % of the required mass when the mass is measured in individual aggregate weigh batchers. In a cumulative aggregate weigh batcher, the cumulative weight after each successive weighing shall be within ± 1 % of the required cumulative amount up to that point when the scale is used in excess of 30 % of its capacity. For cumulative weights for less than 30 % of scale capacity, the tolerance shall be ± 0.3 % of scale capacity or ± 3 % of the required cumulative weight, whichever is less.

9.3 Mixing water shall consist of water added to the batch, ice added to the batch, water occurring as surface moisture on the aggregates, and water introduced in the form of admixtures. The added water shall be measured by weight or volume to an accuracy of 1 % of the required total mixing water. Added ice shall be measured by weight. In the case of truck mixers, any wash water retained in the drum for use in the next batch of concrete shall be accurately measured; if this proves impractical or impossible the wash water shall be discharged prior to loading the next batch of concrete. Total water (including any wash water) shall be measured or weighed to an accuracy of ± 3 % of the specified total amount.

9.4 Chemical admixtures in powdered form shall be measured by mass. Liquid chemical admixtures shall be batched by mass or volume. Admixtures measured by either mass or volume, shall be batched with an accuracy of ± 3 % of the total amount required or plus or minus the amount or dosage required for 100 lb [50 kg] of hydraulic cement, whichever is greater.

NOTE 10—Admixture dispensers of the mechanical type capable of adjustment for variation of dosage, and of simple calibration, are recommended.

10. Batching Plant

10.1 Bins with adequate separate compartments shall be provided in the batching plant for fine and for each required size of coarse aggregate. Each bin compartment shall be designed and operated so as to discharge efficiently and freely, with minimum segregation, into the weighing hopper. Means of control shall be provided so that, as the quantity desired in the weighing hopper is approached, the material shall be shut off with precision. Weighing hoppers shall be constructed so as to eliminate accumulations of tare materials and to discharge fully.

10.2 Indicating devices shall be in full view and near enough to be read accurately by the operator while charging the hopper. The operator shall have convenient access to all controls.

10.3 Scales shall be considered accurate when at least one static load test within each quarter of the scale capacity can be shown to be within ± 0.15 % of the total capacity of the scale or 0.4 % of the net applied load, whichever is greater.

10.4 Adequate standard test weights shall be available for checking accuracy. All exposed fulcrums, clevises, and similar working parts of scales shall be kept clean. Beam scales shall be equipped with a balance indicator sensitive enough to show movement when a weight equal to 0.1 % of the nominal capacity of the scale is placed in the batch hopper. Pointer travel shall

be a minimum of 5 % of the net-rated capacity of the largest weigh beam for underweight and 4 % for overweight.

10.5 The device for the measurement of the added water shall be capable of delivering to the batch the quantity required within the accuracy required in 9.3. The device shall be so arranged that the measurements will not be affected by variable pressures in the water supply line. Measuring tanks shall be equipped with outside taps and valves to provide for checking their calibration unless other means are provided for readily and accurately determining the amount of water in the tank.

NOTE 11—The scale accuracy limitations of the National Ready Mixed Concrete Association Plant Certification meet the requirements of this specification.

11. Mixers and Agitators

11.1 Mixers will be stationary mixers or truck mixers. Agitators will be truck mixers or truck agitators.

11.1.1 Stationary mixers shall be equipped with a metal plate or plates on which are plainly marked the mixing speed of the drum or paddles, and the maximum capacity in terms of the volume of mixed concrete. When used for the complete mixing of concrete, stationary mixers shall be equipped with an acceptable timing device that will not permit the batch to be discharged until the specified mixing time has elapsed.

11.1.2 Each truck mixer or agitator shall have attached thereto in a prominent place a metal plate or plates on which are plainly marked the gross volume of the drum, the capacity of the drum or container in terms of the volume of mixed concrete, and the minimum and maximum mixing speeds of rotation of the drum, blades, or paddles. When the concrete is truck mixed as described in 12.5, or shrink mixed as described in 12.4, the volume of mixed concrete shall not exceed 63 % of the total volume of the drum or container. When the concrete is central mixed as described in 12.3, the volume of concrete in the truck mixer or agitator shall not exceed 80 % of the total volume of the drum or container. Truck mixers and agitators shall be equipped with means to readily verify the number of revolutions of the drum, blades, or paddles.

11.2 All stationary and truck mixers shall be capable of combining the ingredients of the concrete within the specified time or the number of revolutions specified in 11.5, into a thoroughly mixed and uniform mass and of discharging the concrete so that not less than five of the six requirements shown in Table A1.1 shall have been met.

NOTE 12—The sequence or method of charging the mixer will have an important effect on the uniformity of the concrete.

11.3 The agitator shall be capable of maintaining the mixed concrete in a thoroughly mixed and uniform mass and of discharging the concrete with a satisfactory degree of uniformity as defined by Annex A1.

11.4 Slump tests of individual samples taken after discharge of approximately 15 % and 85 % of the load will provide a quick check of the probable degree of uniformity (Note 13). These two samples shall be obtained within an elapsed time of not more than 15 min. If these slumps differ more than that specified in Annex A1, the mixer or agitator shall not be used unless the condition is corrected, except as provided in 11.5.

NOTE 13—No samples should be taken before 10 % or after 90 % of the batch has been discharged. Due to the difficulty of determining the actual quantity of concrete discharged, the intent is to provide samples that are representative of widely separated portions, but not the beginning and end of the load.

11.5 Use of the equipment is permitted when operation with a longer mixing time, a smaller load, or a more efficient charging sequence will permit the requirements of Annex A1 to be met.

11.6 Mixers and agitators shall be examined or their mass determined as frequently as necessary to detect changes in condition due to accumulations of hardened concrete or mortar and examined to detect wear of blades. When such changes are extensive enough to affect the mixer performance, the proof-tests described in Annex A1 shall be performed to show whether the correction of deficiencies is required.

12. Mixing and Delivery

12.1 Ready-mixed concrete shall be mixed and delivered to the point designated by the purchaser by means of one of the following combinations of operations:

12.1.1 *Central-Mixed Concrete.*

12.1.2 *Shrink-Mixed Concrete.*

12.1.3 *Truck-Mixed Concrete.*

12.2 Mixers and agitators shall be operated within the limits of capacity and speed of rotation designated by the manufacturer of the equipment.

12.3 *Central-Mixed Concrete*—Concrete that is mixed completely in a stationary mixer and transported to the point of delivery either in a truck agitator, or a truck mixer operating at agitating speed, or in nonagitating equipment approved by the purchaser and meeting the requirements of Section 13, shall conform to the following: The mixing time shall be counted from the time all the solid materials are in the drum. The batch shall be so charged into the mixer that some water will enter in advance of the cement and aggregate, and all water shall be in the drum by the end of the first one fourth of the specified mixing time.

12.3.1 Where no mixer performance tests are made, the acceptable mixing time for mixers having capacities of 1 yd³ [0.76 m³] or less shall be not less than 1 min. For mixers of greater capacity, this minimum shall be increased 15 s for each cubic yard [cubic metre] or fraction thereof of additional capacity (See Note 14).

NOTE 14—Stationary mixers of similar design bearing a Performance Rated plate of the Concrete Plant Manufacturers Bureau have been tested to