



Designation: ~~E1730-04~~ Designation: E1730 – 09

## Standard Specification for Rigid Foam for Use in Structural Sandwich Panel Cores<sup>1</sup>

This standard is issued under the fixed designation E1730; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the Department of Defense.*

### 1. Scope

1.1 This specification covers rigid, closed cell, polyurethane and polyisocyanurate thermal insulation for sandwich panels used in shelter construction for exposure to ambient temperatures of  $-25^{\circ}$  to  $160^{\circ}\text{F}$  ( $-32^{\circ}$  to  $71^{\circ}\text{C}$ ). Painted surfaces of shelters in actual field use reach temperatures of  $200^{\circ}\text{F}$  ( $93^{\circ}\text{C}$ ). The materials in this specification must be capable of withstanding processing, (laminating) temperatures of  $110^{\circ}\text{C}$  ( $230^{\circ}\text{F}$ ).

1.2 The values stated in either inch-pound or SI units are to be regarded separately as the standard. The values given in parentheses are for information only.

1.3 The following precautionary caveat pertains only to the test method portion, Section 12, of this specification: *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

### 2. Referenced Documents

#### 2.1 ASTM Standards:<sup>2</sup>

C165 Test Method for Measuring Compressive Properties of Thermal Insulations

C168 Terminology Relating to Thermal Insulation

C177 Test Method for Steady-State Heat Flux Measurements and Thermal Transmission Properties by Means of the Guarded-Hot-Plate Apparatus

C273 Test Method for Shear Properties of Sandwich Core Materials

~~C366/C366M~~

C366/C366M Test Methods for Measurement of Thickness of Sandwich Cores

C390 Practice for Sampling and Acceptance of Thermal Insulation Lots

C518 Test Method for Steady-State Thermal Transmission Properties by Means of the Heat Flow Meter Apparatus

C550 Test Method for Measuring Trueness and Squareness of Rigid Block and Board Thermal Insulation

D883 Terminology Relating to Plastics

D1621 Test Method for Compressive Properties Of Rigid Cellular Plastics

D1622 Test Method for Apparent Density of Rigid Cellular Plastics

D1623 Test Method for Tensile and Tensile Adhesion Properties of Rigid Cellular Plastics

D2126 Test Method for Response of Rigid Cellular Plastics to Thermal and Humid Aging

D2856 Test Method for Open-Cell Content of Rigid Cellular Plastics by the Air Pycnometer

#### 2.2 Code of Federal Regulations Aeronautics and Space:

14 CFR 25.853 (Federal Air Regulation 25.853) Compartment Interior (Amend. 25-72)<sup>3</sup>

#### 2.3 Federal Standard:

~~QQ-A-25011 Aluminum Alloy 6061-T6 Plate and Sheet~~

~~QQ-A-260/11 Aluminum Alloy 6081, Plate and Sheet<sup>4</sup>~~

QQ-A-250/11 Aluminum Alloy 6061-T6 Plate and Sheet<sup>4</sup>

#### 2.4 Military Standards:

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee E06 on Performance of Buildings and is under the direct responsibility of Subcommittee E06.53 on Materials and Processes for Durable Rigidwall Relocatable Structures.

Current edition approved Nov. 1, 2004-2009. Published November 2004-December 2009. Originally approved in 1995. Last previous edition approved in 2002-2004 as E1730 – 024. DOI: 10.1520/E1730-049.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

<sup>3</sup> Available from U.S. Government Printing Office Superintendent of Documents, 732 N. Capitol St., NW, Mail Stop: SDE, Washington, DC 20401, <http://www.access.gpo.gov>.

<sup>4</sup> Available from Standardization Documents Order Desk, DODSSP, Bldg. 4, Section D, 700 Robbins Ave., Philadelphia, PA 19111-5098, <http://dodssp.daps.dla.mil>.

MIL STD 105 Sampling Procedures and Tables for Inspection by Attributes<sup>4</sup>

2.5 *Other Documents:*<sup>5</sup>

Aircraft Materials Fire Test Handbook, Handbook DOT/FAA/AR-00/12  
Federal Aviation Regulation (FAR) 25.853

### 3. Terminology

3.1 *Definitions*—The terms used in this specification are defined in Terminologies C168 and D883.

### 4. Classification

4.1 The unfaced foam thermal insulation boards covered by this specification are classified as follows:

4.1.1 *Type 1*—Nominal density: 32 kg/m<sup>3</sup> (2.0 lb/ft<sup>3</sup>).

4.1.2 *Type 2*—Nominal density: 48 kg/m<sup>3</sup> (3.0 lb/ft<sup>3</sup>).

4.1.3 *Type 3*—Nominal density: 64 kg/m<sup>3</sup> (4.0 lb/ft<sup>3</sup>).

4.1.4 *Type 4*—Nominal density: 192 kg/m<sup>3</sup> (12.0 lb/ft<sup>3</sup>).

### 5. Ordering Information

5.1 Orders for materials purchased under this specification shall include the following:

5.1.1 Designation of this specification,

5.1.2 Product name and type, or both,

5.1.3 Dimensions and tolerances,

5.1.4 Impact resistance test specimen preparation,

5.1.5 Material marking requirements, and

5.1.6 Packaging requirements.

### 6. Foam

6.1 The morphology of the insulation shall consist of a multitude of individual cells of uniform size and dimension, essentially closed off from each other, homogeneous throughout, free of voids, accumulations of unexpanded material, foreign inclusions, or seams (see Table 1).

### 7. Dimensions and Tolerances

7.1 The dimensions, squareness, and tolerances shall be specified by the purchaser.

### 8. Qualification

8.1 When required by the purchaser, materials supplied under this specification must be tested for and meet the properties listed in Table 2. Having a qualified product does not obviate the supplier from continued, ongoing product compliance with all requirements to this specification.

8.2 In addition to meeting the requirements of the tests stipulated in Table 2 as manufactured, the compressive, tensile, and shear properties must also meet these requirements after having been preconditioned for 4 h at 110°C (230°F), and allowed to equilibrate in accordance with 11.2.

8.3 Unless otherwise specified by the purchaser, qualified materials remain qualified as long as there are no changes in product formulation, critical raw materials, that is, isocyanates and polyols, basic methods of manufacture, or plant location.

<sup>5</sup> Available from National Institute of Standards and Technology (NIST), 100 Bureau Dr., Stop 3460, Gaithersburg, MD 20899-3460, <http://www.nist.gov>.

**TABLE 1 Classification of Characteristics**

Characteristic	Major	Minor	Method of Inspection
Length, width, and thickness	X	...	9.4.3
Edge squareness	X	...	9.4.3
Holes through board exceeding 40 mm <sup>2</sup> for each 92900 mm <sup>2</sup> (0.0625 in. <sup>2</sup> for each square foot) of area	X	...	9.4.2
Crushed foam	X	...	9.4.2
Void larger than 40 mm (0.0625 in. <sup>2</sup> )	X	...	9.4.2
Unexpanded material	...	X	9.4.2
Foreign inclusions	...	X	9.4.2
Contaminants	...	X	9.4.2
Seams	X	...	9.4.5