

---

---

**Paper and board — Testing of cores —  
Part 8:  
Determination of natural frequency  
and flexural modulus by experimental  
modal analysis**

iTeh Standards  
Papier et carton — Essais des mandrins —  
Partie 8: Détermination de la fréquence propre et du module de  
flexion par analyse modale expérimentale  
**Document Preview**

[ISO 11093-8:2017](#)

<https://standards.iteh.ai/catalog/standards/iso/4a73fc72-0b59-4a55-88ac-eefc99a97e88/iso-11093-8-2017>



Reference number  
ISO 11093-8:2017(E)

© ISO 2017

# iTeh Standards

## (<https://standards.iteh.ai>)

### Document Preview

[ISO 11093-8:2017](#)

<https://standards.iteh.ai/catalog/standards/iso/4a73fc72-0b59-4a55-88ac-eefc99a97e88/iso-11093-8-2017>



#### COPYRIGHT PROTECTED DOCUMENT

© ISO 2017, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Ch. de Blandonnet 8 • CP 401  
CH-1214 Vernier, Geneva, Switzerland  
Tel. +41 22 749 01 11  
Fax +41 22 749 09 47  
copyright@iso.org  
www.iso.org

## Contents

	Page
<b>Foreword</b>	<b>iv</b>
<b>1 Scope</b>	<b>1</b>
<b>2 Normative references</b>	<b>1</b>
<b>3 Terms and definitions</b>	<b>1</b>
<b>4 Principle</b>	<b>2</b>
<b>5 Apparatus</b>	<b>2</b>
<b>6 Test piece</b>	<b>2</b>
6.1 Sampling	2
6.2 Test-piece size	3
6.3 Conditioning	3
<b>7 Procedure</b>	<b>5</b>
<b>8 Calculation</b>	<b>5</b>
8.1 Calculation of the flexural modulus	5
8.2 Calculation of the rotational speed factor	6
<b>9 Test report</b>	<b>6</b>
<b>Bibliography</b>	<b>8</b>

**iTeh Standards**  
**(<https://standards.iteh.ai>)**  
**Document Preview**

[ISO 11093-8:2017](#)

<https://standards.iteh.ai/catalog/standards/iso/4a73fc72-0b59-4a55-88ac-eefc99a97e88/iso-11093-8-2017>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html)

This document was prepared by Technical Committee ISO/TC 6, *Paper, board and pulps*.

This third edition cancels and replaces the second edition (ISO 11093-8:2012), of which it constitutes a minor revision with the following changes:

- correction to [8.1, Formula \(1\)](#); <https://standards.iec.ch/catalog/standards/iso/4a73fc72-0b59-4a55-88ac-eefc99a97e88/iso-11093-8-2017>
- editorial updates.

It also incorporates the Technical Corrigendum ISO 11093-8:2012/Cor 1:2013, which included updates to [Figure 1](#) and [Figure 2](#).

A list of all parts in the ISO 11093 series can be found on the ISO website.

# Paper and board — Testing of cores —

## Part 8: Determination of natural frequency and flexural modulus by experimental modal analysis

### 1 Scope

This document specifies a method for the determination of the flexural modulus by using experimentally measured natural frequencies in the free-free mode of transverse vibration of cylindrical paper and board cores, which meet the following criteria:

- internal diameter: 50 mm to 350 mm;
- minimum wall thickness:  $0,02 \times$  internal diameter or not less than 2,0 mm;
- minimum length of core:  $8 \times$  internal diameter.

NOTE For the determination of the flexural modulus by the three-point method, see ISO 11093-7.

### 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 11093-1, *Paper and board — Testing of cores — Part 1: Sampling*

<https://standards.iteh.ai/catalog/standards/iso/4a/3fc72-0b59-4a55-88ac-eefc99a97e88/iso-11093-8-2017>

ISO 11093-2, *Paper and board — Testing of cores — Part 2: Conditioning of test samples*

ISO 11093-3, *Paper and board — Testing of cores — Part 3: Determination of moisture content using the oven drying method*

### 3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <http://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

#### 3.1

##### natural frequency

$f_1$

first frequency which is the lowest frequency a structure vibrates in, depending on its material, shape and supporting system, when an impulse is applied to it

### 3.2 flexural modulus

$E$

material property which, together with core dimensions, describes the resistance of the core to bending deflection

### 3.3 rotational speed factor

$S_f$   
core  $E$ -modulus divided by its density ( $E/\rho$ ) which can be used to estimate vibration performance of cores

Note 1 to entry: Cores with equal dimensions, eccentricity and speed factor deliver at identical chucking conditions an equal resonance frequency.

Note 2 to entry: The higher the speed factor, the higher the resonance frequency.

## 4 Principle

In the experimental modal analysis, the test piece is considered as a “beam” and Timoshenko’s beam theory for isotropic materials is applied in evaluating transverse vibration. In this theory, the influence of rotary inertia and shear deformations on transverse vibrations are included. During the test, the test piece is suspended so that it is free to vibrate in the transverse direction. The flexural modulus is calculated as described in [8.1](#).

## 5 Apparatus

### 5.1 Test-piece suspension.

The basic idea is to measure the first natural frequency in the free-free mode of transverse vibration. To ensure free-free boundary conditions in the lateral direction, the test piece is supported by a wire and hanging with its axis in the vertical direction (see [Figure 1](#)). The minimum length of the support wire (1) is about 300 mm. The supporting system consists of two clamps and the wire. An example of attaching the clamps is shown in [Figure 2](#). The mass of the clamps should be less than  $0,01 \times$  mass of the test piece. The angle,  $\alpha$ , (see [Figure 2](#)) should be more than  $45^\circ$ . The distance of the fixing screw from the edge of the core should be 5 mm to 10 mm.

### 5.2 Experimental modal analysis system.

The first natural frequency is measured with a signal analyser. The test piece is impacted by a hammer in the direction (Z-direction) perpendicular to the plane of the support wires (XY-plane) (see [Figure 1](#)). The impulse response is measured by a piezoelectric accelerometer at one end of the test piece mounted with its axis in the Z-direction (see [Figure 1](#)). The sensitivity of the accelerometer shall be 8 mV/g to 100 mV/g; the frequency range limit of the accelerometer shall be 0,1 Hz to 10 000 Hz. The measured signal is analysed using a signal analyser and the frequency of the lowest mode of bending vibrations is determined from the frequency response function.

## 6 Test piece

### 6.1 Sampling

Samples shall be taken in accordance with ISO 11093-1, but it has to be ensured that the core is not damaged.