



# SLOVENSKI STANDARD SIST EN ISO 18096:2022

01-november-2022

Nadomešča:  
SIST EN 14707:2013

---

**Toplotnoizolacijski proizvodi za opremo stavb in industrijske inštalacije - Ugotavljanje najvišje temperature uporabe predoblikovanih cevni izolacij (ISO 18096:2022)**

Thermal insulating products for building equipment and industrial installations - Determination of maximum service temperature for preformed pipe insulation (ISO 18096:2022)

(standards.iteh.ai)

Wärmedämmstoffe für die Haustechnik und für betriebstechnische Anlagen - Bestimmung der oberen Anwendungsgrenztemperatur von vorgeformten Rohrdämmstoffen (ISO 18096:2022)

Produits isolants thermiques pour l'équipement du bâtiment et les installations industrielles - Détermination de la température maximale de service des coquilles isolantes préformées (ISO 18096:2022)

**Ta slovenski standard je istoveten z: EN ISO 18096:2022**

---

**ICS:**

91.100.60	Materiali za toplotno in zvočno izolacijo	Thermal and sound insulating materials
-----------	---	--

**SIST EN ISO 18096:2022**

**en,fr,de**



EUROPEAN STANDARD

EN ISO 18096

NORME EUROPÉENNE

EUROPÄISCHE NORM

September 2022

ICS 91.100.60

Supersedes EN 14707:2012

English Version

# Thermal insulating products for building equipment and industrial installations - Determination of maximum service temperature for preformed pipe insulation (ISO 18096:2022)

Produits isolants thermiques pour l'équipement du bâtiment et les installations industrielles - Détermination de la température maximale de service des coquilles isolantes préformées (ISO 18096:2022)

Wärmedämmstoffe für die Haustechnik und für betriebstechnische Anlagen - Bestimmung der oberen Anwendungsgrenztemperatur von vorgeformten Rohrdämmstoffen (ISO 18096:2022)

This European Standard was approved by CEN on 6 August 2022.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

Contents	Page
European foreword.....	3

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[SIST EN ISO 18096:2022](https://standards.iteh.ai/catalog/standards/sist/231e6941-0acc-402a-b407-dc11d9a2bd17/sist-en-iso-18096-2022)  
<https://standards.iteh.ai/catalog/standards/sist/231e6941-0acc-402a-b407-dc11d9a2bd17/sist-en-iso-18096-2022>

## European foreword

This document (EN ISO 18096:2022) has been prepared by Technical Committee ISO/TC 163 "Thermal performance and energy use in the built environment" in collaboration with Technical Committee CEN/TC 88 "Thermal insulating materials and products" the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by March 2023, and conflicting national standards shall be withdrawn at the latest by September 2025.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 14707:2012.

Any feedback and questions on this document should be directed to the users' national standards body/national committee. A complete listing of these bodies can be found on the CEN website.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and the United Kingdom.

(standards.iteh.ai)

## Endorsement notice

SIST EN ISO 18096:2022

The text of ISO 18096:2022 has been approved by CEN as EN ISO 18096:2022 without any modification.



INTERNATIONAL  
STANDARD

ISO  
18096

Second edition  
2022-08

---

---

**Thermal insulating products for  
building equipment and industrial  
installations — Determination of  
maximum service temperature for  
preformed pipe insulation**

*Produits isolants thermiques pour l'équipement du bâtiment et  
les installations industrielles — Détermination de la température  
maximale de service des coquilles isolantes préformées*

iTeh STANDARDS  
(standards.iteh.ai)

SIST EN ISO 18096:2022

<https://standards.iteh.ai/catalog/standards/sist/231e6941-0acc-402a-b407-dc11d9a2bd17/sist-en-iso-18096-2022>



Reference number  
ISO 18096:2022(E)

© ISO 2022

# iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN ISO 18096:2022

<https://standards.iteh.ai/catalog/standards/sist/231e6941-0acc-402a-b407-dc11d9a2bd17/sist-en-iso-18096-2022>



## **COPYRIGHT PROTECTED DOCUMENT**

© ISO 2022

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
CP 401 • Ch. de Blandonnet 8  
CH-1214 Vernier, Geneva  
Phone: +41 22 749 01 11  
Email: [copyright@iso.org](mailto:copyright@iso.org)  
Website: [www.iso.org](http://www.iso.org)

Published in Switzerland



# Contents

Page

Foreword.....	iv
<b>1 Scope.....</b>	<b>1</b>
<b>2 Normative references.....</b>	<b>1</b>
<b>3 Terms and definitions.....</b>	<b>1</b>
<b>4 Principle.....</b>	<b>1</b>
<b>5 Apparatus.....</b>	<b>2</b>
<b>6 Test specimens.....</b>	<b>4</b>
6.1 Dimensions of test specimens.....	4
6.2 Number of test specimens.....	4
6.3 Conditioning of test specimens.....	5
<b>7 Procedure.....</b>	<b>5</b>
7.1 Test conditions.....	5
7.2 Test procedure.....	5
<b>8 Calculation and expression of results.....</b>	<b>6</b>
8.1 Thickness deformation versus time.....	6
8.2 Additional tests and/or observations.....	8
8.3 Internal self-heating.....	8
<b>9 Accuracy of measurement.....</b>	<b>8</b>
<b>10 Test report.....</b>	<b>9</b>
<b>Annex A (normative) Modifications of and additions to the general test method for mineral wool products.....</b>	<b>10</b>
<b>Annex B (normative) Modifications of and additions to the general test method for polyethylene foam (PEF) and flexible elastomeric foam (FEF) products.....</b>	<b>12</b>
<b>Annex C (normative) Modifications of and additions to the general test method for phenolic foam products.....</b>	<b>15</b>
<b>Bibliography.....</b>	<b>17</b>

## ISO 18096:2022(E)

### Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

This document was prepared by Technical Committee ISO/TC 163, *Thermal performance and energy use in the built environment*, Subcommittee SC 1, *Test and measurement methods*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 88, *Thermal insulating materials and products*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This second edition cancels and replaces the first edition (ISO 18096:2013), which has been technically revised.

The main changes are as follows:

- EN 14707:2012 and ISO 18096:2013 have been merged into one document;
- editorial revisions.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at [www.iso.org/members.html](http://www.iso.org/members.html).

# Thermal insulating products for building equipment and industrial installations — Determination of maximum service temperature for preformed pipe insulation

## 1 Scope

This document specifies the equipment and procedures for determining the maximum service temperature for preformed pipe insulation. It is applicable to thermal insulating products.

## 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 5725-2:2019, *Accuracy (trueness and precision) of measurement methods and results — Part 2: Basic method for the determination of repeatability and reproducibility of a standard measurement method*

ISO 12628, *Thermal insulating products for building equipment and industrial installations — Determination of dimensions, squareness and linearity of preformed pipe insulation*

ISO 16544, *Thermal insulating products for building applications — Conditioning to moisture equilibrium under specified temperature and humidity conditions*

## 3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

### 3.1

#### **maximum service temperature**

highest temperature at which the thermal insulation product, when installed at the recommended thickness in a given application, continues to function within specified limits of performance

Note 1 to entry: The required performance may be in the areas of dimensional stability, thermal properties, and mechanical properties, as well as changes in appearance and resistance against creation of hazards such as internal self-heating (see annexes and requirements in the relevant product standard).

Note 2 to entry: The test procedure in this document, which is used as a reference, the test specimen is exposed to a temperature difference going from ambient to the maximum service temperature. This may not reflect the actual application conditions when products are exposed to different temperatures on the two main faces, e.g. in multi-layer systems or for faced products where the facing may limit the maximum service temperature.

[SOURCE: ISO 9229:2020, 3.6.9.1, modified — Notes 1 and 2 to entry have been added.]

## 4 Principle

The thickness and length shall be measured after one sided heat treatment for a specified time period, at the maximum service temperature, achieved using a specified rate of temperature increase. The