INTERNATIONAL STANDARD

ISO 12570

First edition 2000-03-15 **AMENDMENT 2** 2018-03

Hygrothermal performance of building materials and products — Determination of moisture content by drying at elevated temperature

AMENDMENT 2

iTeh STPerformance hygrothermique des matériaux et produits pour le bâtiment — Détermination du taux d'humidité par séchage à chaud (standards iteh.ai)

<u>ISO 12570:2000/Amd 2:2018</u> https://standards.iteh.ai/catalog/standards/sist/1179b03e-a51a-4bea-b964e45e77056f61/iso-12570-2000-amd-2-2018



Reference number ISO 12570:2000/Amd.2:2018(E)

iTeh STANDARD PREVIEW (standards.iteh.ai)

<u>ISO 12570:2000/Amd 2:2018</u> https://standards.iteh.ai/catalog/standards/sist/1179b03e-a51a-4bea-b964e45e77056f61/iso-12570-2000-amd-2-2018



COPYRIGHT PROTECTED DOCUMENT

© ISO 2018

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office CP 401 • Ch. de Blandonnet 8 CH-1214 Vernier, Geneva Phone: +41 22 749 01 11 Fax: +41 22 749 09 47 Email: copyright@iso.org Website: www.iso.org

Published in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 163, *Thermal performance and energy use in the built environment*, Subcommittee SC 1, *Test and measurement methods*. https://standards.iteh.ai/catalog/standards/sist/1179b03e-a51a-4bea-b964-

e45e77056f61/iso-12570-2000-amd-2-2018

iTeh STANDARD PREVIEW (standards.iteh.ai)

<u>ISO 12570:2000/Amd 2:2018</u> https://standards.iteh.ai/catalog/standards/sist/1179b03e-a51a-4bea-b964e45e77056f61/iso-12570-2000-amd-2-2018

Hygrothermal performance of building materials and products — Determination of moisture content by drying at elevated temperature

AMENDMENT 2

8.3

Replace the existing NOTE with the following:

NOTE The density of water at other temperatures (θ °C) can be determined from the empirical equation:

 $\rho_w = 999,90 + 0,05201\theta - 0,00759\theta^2 + 0,3871 \times 10^{-4}\theta^3$

iTeh STANDARD PREVIEW (standards.iteh.ai)

<u>ISO 12570:2000/Amd 2:2018</u> https://standards.iteh.ai/catalog/standards/sist/1179b03e-a51a-4bea-b964e45e77056f61/iso-12570-2000-amd-2-2018

iTeh STANDARD PREVIEW (standards.iteh.ai)

<u>ISO 12570:2000/Amd 2:2018</u> https://standards.iteh.ai/catalog/standards/sist/1179b03e-a51a-4bea-b964e45e77056f61/iso-12570-2000-amd-2-2018

ICS 91.100.01 Price based on 1 page