



SLOVENSKI STANDARD

oSIST prEN 851:2021

01-marec-2021

Aluminij in aluminijeve zlitine - Rondele in polizdelki za izdelavo jedilnih pripomočkov in posode - Specifikacije

Aluminium and aluminium alloys - Circle and circle stock for the production of culinary utensils - Specifications

Aluminium und Aluminiumlegierungen - Ronden und Rondenvormaterial zur Herstellung von Küchengeschirr - Spezifikationen

Aluminium et alliages d'aluminium - Disques et ébauches pour disques pour applications culinaires - Spécifications

<https://standards.iteh.ai/catalog/standards/sist/cbd1a7eb-95e5-4af8-b68b-8a01ff2c0a81/osist-pr-en-851-2021>

Ta slovenski standard je istoveten z: prEN 851

ICS:

77.150.10	Aluminijski izdelki	Aluminium products
97.040.60	Kuhinjska posoda, jedilni servisi in jedilni pribor	Cookware, cutlery and flatware

oSIST prEN 851:2021

en,fr,de

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[oSIST prEN 851:2021](#)

<https://standards.iteh.ai/catalog/standards/sist/cbd1a7eb-95e5-4af8-b68b-fla0dfbc0a81/osist-pren-851-2021>

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

DRAFT
prEN 851

January 2021

ICS 77.150.10

Will supersede EN 851:2014

English Version

Aluminium and aluminium alloys - Circle and circle stock for the production of culinary utensils - Specifications

Aluminium et alliages d'aluminium - Disques et
ébauches pour disques pour applications culinaires -
Spécifications

Aluminium und Aluminiumlegierungen - Ronden und
Rondenvormaterial zur Herstellung von
Küchengeschirr - Spezifikationen

This draft European Standard is submitted to CEN members for enquiry. It has been drawn up by the Technical Committee CEN/TC 132.

If this draft becomes a European Standard, CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

This draft European Standard was established by CEN in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.

Recipients of this draft are invited to submit, with their comments, notification of any relevant patent rights of which they are aware and to provide supporting documentation.

Warning : This document is not a European Standard. It is distributed for review and comments. It is subject to change without notice and shall not be referred to as a European Standard.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

Contents	Page
European foreword.....	3
1 Scope	4
2 Normative references	4
3 Terms and definitions	5
4 Technical conditions for inspection and delivery	5
4.1 General	5
4.2 Orders or tenders	5
5 Mechanical properties	6
5.1 General	6
5.2 Earing	6
6 Tolerances on dimensions and form	7
6.1 General	7
6.2 Diameter	7
6.3 Thickness	7
6.4 Tolerances on flatness for circle	7
6.5 Edge burr tolerances for circle	7
7 Other requirements	7
Bibliography	12

[oSIST prEN 851:2021](https://standards.iteh.ai/catalog/standards/sist/cbd1a7eb-95e5-4af8-b68b-fla0dfbc0a81/osist-pren-851-2021)

<https://standards.iteh.ai/catalog/standards/sist/cbd1a7eb-95e5-4af8-b68b-fla0dfbc0a81/osist-pren-851-2021>

European foreword

This document (prEN 851:2021) has been prepared by Technical Committee CEN/TC 132 “Aluminium and aluminium alloys”, the secretariat of which is held by AFNOR.

This document is currently submitted to the CEN Enquiry.

This document will supersede EN 851:2014.

Compared to the previous edition, 6.4 was modified.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[oSIST prEN 851:2021](https://standards.iteh.ai/catalog/standards/sist/cbd1a7eb-95e5-4af8-b68b-fla0dfbc0a81/osist-pren-851-2021)

<https://standards.iteh.ai/catalog/standards/sist/cbd1a7eb-95e5-4af8-b68b-fla0dfbc0a81/osist-pren-851-2021>

prEN 851:2021 (E)

1 Scope

This document specifies the particular requirements for wrought aluminium and aluminium alloys in the form of circle or circle stock for culinary utensils applications.

This standard is applicable to:

- Circles made out of hot or cold rolled circles stock, with a thickness from 0,2 mm up to and including 12 mm and with a diameter from 100 mm up to and including 1 600 mm.

NOTE Circles with a diameter up to 1 000 mm can be produced by blanking.

- Hot or cold-rolled circle stock with a thickness from 0,2 mm up to and including 12 mm and with a width up to 1 600 mm.

This document is not applicable to slugs for impact extrusions which are dealt with in other European Standards.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 485-1:2016, *Aluminium and aluminium alloys - Sheet, strip and plate - Part 1: Technical conditions for inspection and delivery*

EN 485-2, *Aluminium and aluminium alloys - Sheet, strip and plate - Part 2: Mechanical properties*

EN 485-3, *Aluminium and aluminium alloys - Sheet, strip and plate - Part 3: Tolerances on dimensions and form for hot-rolled products*

EN 485-4, *Aluminium and aluminium alloys - Sheet, strip and plate - Part 4: Tolerances on shape and dimensions for cold-rolled products*

EN 515, *Aluminium and aluminium alloys - Wrought products - Temper designations*

EN 602, *Aluminium and aluminium alloys - Wrought products - Chemical composition of semi-finished products used for the fabrication of articles for use in contact with foodstuff*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

3.1 circle

circular flat product obtained by circular sawing or shearing, or by blanking of a flat rolled product with a uniform thickness over 0,20 mm

3.2 circle stock

flat rolled product of rectangular cross-section with uniform thickness over 0,20 mm, supplied in coils, sheets, or plates, usually with sheared or sawn edges, and intended to be sawn, sheared or blanked into flat shapes to be subsequently formed, drawn, etc.

Note 1 to entry: The thickness does not exceed one tenth of the width.

3.3 hot rolled circle and circle stock

circle or circle stock whose final thickness is obtained by hot rolling

3.4 cold rolled circle and circle stock

circle or circle stock whose final thickness is obtained by cold rolling

4 Technical conditions for inspection and delivery

4.1 General

All the provisions of EN 485-1 shall apply, except EN 485-1:2016, Clause 4 (Orders and tenders) which is modified as follows:

4.2 Orders or tenders

The order or tender shall define the product required and shall contain the following information:

- a) the form and the type of product:
 - 1) the form of the product (circle and circle stock);
 - 2) the designation of the aluminium or aluminium alloy;
 - 3) when subsequent decorative anodising, anti-adhesive coating, enamelling, etc. by the customer is intended, this shall be expressly stated on the order. In all other cases, indication of the customer application is recommended;
- b) the metallurgical temper of the material for delivery according to EN 515 (degree of hardness or heat treatment condition) and, if different, the metallurgical temper for use;

prEN 851:2021 (E)

- c) the reference of this document or of the relevant Technical Specification, or where none exists, the properties agreed between purchaser and supplier;
- d) the dimensions and shape of the product as applicable:
 - 1) thickness;
 - 2) diameter of the circle;
 - 3) width of the strip, sheet, or plate;
 - 4) length of the sheet or plate;
 - 5) internal and external diameters of the coil;
- e) whether hot rolled or cold rolled tolerances apply;
- f) quantity:
 - 1) mass or number of pieces;
 - 2) tolerances on quantity if required;
- g) any requirements for inspection documents;
- h) any special requirements agreed between purchaser and supplier:
 - 1) marking of products;
 - 2) references to drawings, etc.;
 - 3) any special test required (earring, etc.) and the corresponding acceptance limits;
- i) for products intended to be surface treated by the purchaser the order shall also contain the following information:
 - 1) the intended particular surface treatment (according to the relevant European Standard);
 - 2) the number of sides for which a good visual appearance is required and, if only one side, its position with respect to the strip (inside or outside of the coil) or the sheet, plate or circle (upside or downside).

ITEH STANDARD PREVIEW
 (standards.iteh.ai)

oSIST prEN 851:2021

<https://standards.iteh.ai/catalog/standards/sist/cbd1a7eb-95e5-4af8-b68b-fla0dfbc0a81/osist-pren-851-2021>

5 Mechanical properties**5.1 General**

The mechanical properties shall conform to the requirements specified in EN 485-2.

5.2 Earing

When applications, such as deep drawing and spinning require a limited level of earing, the maximum acceptable level shall be agreed between purchaser and supplier, recognizing that test results may be dependent on testing procedures.

6 Tolerances on dimensions and form

6.1 General

Tolerances on dimensions and form shall conform to EN 485-3 and EN 485-4, with the amendments and additions given in 6.2 to 6.5.

6.2 Diameter

Tolerances on diameters for circle shall conform to Table 1. These tolerances include the tolerances on roundness.

For circle obtained by blanking, the recommended standard diameters are:

- From 100 mm up to 500 mm nominal diameter: every multiple of 5;
- Over 500 mm up to 1 000 mm nominal diameter: every multiple of 10.

6.3 Thickness

Tolerances on thickness for hot rolled circle and circle stock shall conform to Table 2.

Tolerances on thickness for cold rolled circle and circle stock shall conform to Table 3. The partition into group I and group II of most common materials which may be used for the present application, in conformance with EN 602, shall be as shown in Table 4.

6.4 Tolerances on flatness for circle

Tolerances on flatness for circles, expressed as a percentage of the diameter D and/or the measured chord length L , shall conform to Table 5.

Deviation from flatness d , resulting from arching or buckling, shall be measured as shown in Figures 1 and 2, using a lightweight straightedge and a feeler gauge, dial gauge or scale, at least the same length as the circle, while the circle is resting on a horizontal base plate, concave side upwards.

Two measurements shall be carried out with the straight edge respectively parallel and perpendicular to the rolling direction.

6.5 Edge burr tolerances for circle

The edge burr shall not be detachable under slight pressure with the thumb, in order not to induce mechanical defects on the surface during the subsequent forming operations (deep drawing, spinning, etc.).

It is recommended that the height of the total burr as measured from the flat surface of the circle (see Figure 3) should not exceed:

- 0,2 mm for thicknesses up to 2 mm;
- 10 % of the nominal thickness for thickness above 2 mm.

7 Other requirements

Particular surface roughness requirements may be agreed between supplier and customer. In that case, the maximum acceptable roughness shall be specified as well as the method of measurement, according to an appropriate standard or specification, and the location and number of measuring points.

Table 1 — Tolerances on diameter

Dimensions in millimetres

Specified thickness		Method of production	Diameter tolerances for specified diameter ^a		
over	up to		up to 600	over 600 up to 1 000	over 1 000 up to 1 600
0,2	4,0	Blanking	±0,3	±0,3	-
		circular sawing or shearing	+ 3 0	+ 4 0	+ 7 0
4,0	6,0	Blanking	±0,5	±0,5	-
		circular sawing or shearing	+ 4 0	+ 5 0	+ 8 0
6,0	12,0	Blanking	±0,7	±0,7	-
		circular sawing or shearing	+ 4 0	+ 5 0	+ 8 0

^a These tolerances include the tolerances on roundness.

oSIST prEN 851:2021

Table 2 — Thickness tolerances for hot rolled circle and circle stock

Dimensions in millimetres

Specified thickness		Thickness tolerance for specified diameter or width	
over	up to	up to 1 250	over 1 250 up to 1 600
2,5	4,0	±0,28	±0,28
4,0	5,0	±0,30	±0,30
5,0	6,0	±0,32	±0,32
6,0	8,0	±0,35	±0,35
8,0	10,0	±0,40	±0,45
10,0	12,0	±0,45	±0,55