



Standard Test Method for Corrosion Resistance of Ferrous Metal Fastener Assemblies Used in Roofing and Waterproofing¹

This standard is issued under the fixed designation D6294/D6294M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

^{ε1} NOTE—Editorially corrected the units of measure in December 2009.

1. Scope

1.1 This test method covers components of ferrous metal fastener assemblies, excluding those of stainless steel, such as fasteners, stress plates, and batten bars used in low slope roofing and waterproofing, to a sulfurous acid environment. This test method evaluates relative corrosion resistance of the components by determination of percentage of rust or white rust.

1.2 The components may or may not have a surface treatment applied.

1.3 A limiting factor is the subjectiveness when determining actual percentage of rust or white rust corrosion.

1.4 Other performance characteristics of ferrous metal components such as abrasion resistance of barrier coatings are not evaluated in this method.

1.5 This test method was developed based on Practice G87.

~~1.6 The values stated in SI units are to be regarded as the standard. The inch-pound values given in parentheses may be approximate, and are presented for information purposes.~~

1.6 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

1.7 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*²

D16 Terminology for Paint, Related Coatings, Materials, and Applications

D1079 Terminology Relating to Roofing and Waterproofing

G15 Terminology Relating to Corrosion and Corrosion Testing

G87 Practice for Conducting Moist SO₂ Tests

3. Terminology

3.1 *Definitions:*

3.1.1 For definitions of terms used in this test method, see Terminology D1079, G15, and D16.

3.2 *Definitions of Terms Specific to This Standard:*

3.2.1 *barrier*—any material limiting passage through itself of solids, liquids, semi-solids, gases, vapors, or forms of energy such as ultraviolet light.

3.2.2 *surface treatment*—a process by which the surface of the ferrous metal component is treated with a barrier coating to inhibit corrosion. Examples of barrier coatings for ferrous metal components include galvanization, zinc plating with or without yellow or clear chromate sealer, cadmium, mechanical zinc plating and organic or inorganic polymers.

¹ This test method is under the jurisdiction of ASTM Committee D08 on Roofing and Waterproofing and is the direct responsibility of Subcommittee D08.20 on Roofing Membrane Systems.

Current edition approved July 10, 2003; Dec. 1, 2009. Published July 2003; December 2009. Originally approved in 1998. Last previous edition approved in 1998 as D6294-98. DOI: 10.1520/D6294_D6294M-98R039E01.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

4. Summary of Test Method

4.1 This test method exposes ferrous metal specimens to 15 or 30 (24) h cycles consisting of the following:

4.1.1 Eight (8) h exposure to the sulfur dioxide atmosphere in a closed chamber.

4.1.2 An intermediate step of rinsing with distilled water, and

4.1.3 Sixteen (16) h of drying under vented conditions at controlled temperature and humidity.

4.2 After drying, the test specimens are visually examined to evaluate the percentage of rust or white rust that formed on the surface.

4.3 The total surface area of the components exposed in the chamber is $0.5 \pm 0.1 \text{ m}^2$ (~~775~~[775 \pm 155 in.²]-].

5. Significance and Use

5.1 It is important to evaluate the corrosion resistance of ferrous metal components used in low-slope roofing and waterproofing because they provide integrity and securement of other system components, such as insulation and membranes. Corrosion of ferrous metal components may result in their early deterioration and may lead to roofing or waterproofing system failure.

5.2 Results from testing ferrous metal components in an acidic atmosphere serve as an indication of the relative corrosion resistance of such components, coated or uncoated, to the environment of the test chamber. The results are not to be construed as a general guideline to the corrosion resistance of such components in other environments or in usage that may be conducive to corrosion.

5.3 Moist air containing sulfur dioxide quickly produces easily visible corrosion on many ferrous metals. It is therefore a test medium suited to detect pores or other sources of weakness in protective barrier coatings.

5.4 This test method applies primarily to evaluating the effectiveness of barrier coatings to provide general corrosion protection under test conditions. It is not intended to evaluate the resistance of the components to specific corrosion mechanisms such as crevice, galvanic, or stress corrosion.

5.5 This test method does not address abrasion resistance of barrier coatings when the fasteners are driven through above roof deck components, such as an existing built-up roof or insulations, or both.

5.6 Only the above deck portion of fasteners subjected to this test method is evaluated.

6. Apparatus

6.1 The apparatus required for evaluating the corrosion resistance of the components consists of a test chamber³ having an internal capacity of 300 L (~~10.6~~[10.6 ft³]-], a supply of sulfur dioxide with metering device, specimen supports, provisions for heating the chamber, and necessary means of control. The size and detailed construction of the apparatus shall be in accordance with Section 4 of Practice G87.

7. Reagents

7.1 The reagents, (that is, sulfur dioxide and water), their purity, and the means for introducing the sulfur dioxide into the test chamber shall be in accordance with Section 7 of Practice G87.

8. Test Specimen

8.1 Select the number of test specimens such that the total combined exposed surface area of the specimens at any one time shall be $0.5 \pm 0.1 \text{ m}^2$ (~~755~~[755 \pm 155 in.²]-].

8.2 It is allowable to mix the type of ferrous metal components (that is, fasteners, stress plates, an batten bars) in the test chamber, provided that the different components do not have vastly different resistance to corrosion under test conditions. The different types of components that may be evaluated in the chamber simultaneously are to be agreed upon between the laboratory and client requesting the test.

NOTE 1—The laboratory may have to conduct preliminary cycling tests to estimate the relative resistance of each component.

NOTE 2—Specimens may be produced by the laboratory showing 10, 15, 20, and 30 % rust or white rust surface corrosion to be used as controls to aid in the test result evaluation in accordance with 10.1.3 and 11.1.6.

8.3 To obtain quantitative corrosion-rate data, only ferrous metal components with similar reactivities should be included in a test run.

8.4 Roof Fastener Test Specimens:

8.4.1 Fasteners of any length may be tested according to this method. The length is to be agreed upon between the laboratory and client.

8.4.2 Roof fasteners are evaluated in this method in relation to deck materials into which they are expected to be installed in service. For purposes of this test method, these deck materials are structural concrete, lightweight insulating concrete, cementitious wood fiber, gypsum, metal, and wood. Prepare the fastener test specimens as follows:

³Annual Book of ASTM Standards, Vol 04.04.

³The sole source of supply of the apparatus known to the committee at this time is Most Associates, 114 Waters Edge Drive, Jupiter, FL 33477, and Atotech USA, 20026 Progress Drive, Strongsville, OH 44136. If you are aware of alternative suppliers, please provide this information to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend.