

# DRAFT INTERNATIONAL STANDARD

## ISO/DIS 8784-3

ISO/TC 6/SC 2

Secretariat: SIS

Voting begins on:  
2019-04-08

Voting terminates on:  
2019-07-01

---

---

### **Pulp, paper and board — Microbiological examination — Part 3: Enumeration of yeast and mould based on disintegration**

ICS: 07.100.99; 85.040; 85.060

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[ISO/DIS 8784-3](https://standards.iteh.ai/catalog/standards/sist/8030a940-4c6c-4d09-988c-8f0542bdc63a/iso-dis-8784-3)

<https://standards.iteh.ai/catalog/standards/sist/8030a940-4c6c-4d09-988c-8f0542bdc63a/iso-dis-8784-3>

THIS DOCUMENT IS A DRAFT CIRCULATED FOR COMMENT AND APPROVAL. IT IS THEREFORE SUBJECT TO CHANGE AND MAY NOT BE REFERRED TO AS AN INTERNATIONAL STANDARD UNTIL PUBLISHED AS SUCH.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

This document is circulated as received from the committee secretariat.



Reference number  
ISO/DIS 8784-3:2019(E)

© ISO 2019

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

ISO/DIS 8784-3

<https://standards.iteh.ai/catalog/standards/sist/8030a940-4c6c-4d09-988c-8f0542bdc63a/iso-dis-8784-3>



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2019

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
CP 401 • Ch. de Blandonnet 8  
CH-1214 Vernier, Geneva  
Phone: +41 22 749 01 11  
Fax: +41 22 749 09 47  
Email: [copyright@iso.org](mailto:copyright@iso.org)  
Website: [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

Page

Foreword .....	iv
<b>1 Scope .....</b>	<b>1</b>
<b>2 Normative references .....</b>	<b>1</b>
<b>3 Terms and definitions .....</b>	<b>1</b>
<b>4 Principle .....</b>	<b>2</b>
<b>5 Culture media and diluents .....</b>	<b>2</b>
5.1 General .....	2
5.2 Water .....	2
5.3 Culture media for total yeast and mould count .....	2
5.4 Diluents .....	3
5.5 Non-ionic surfactant .....	3
<b>6 Apparatus and equipment .....</b>	<b>3</b>
<b>7 Sampling .....</b>	<b>4</b>
<b>8 Preparation of the test material .....</b>	<b>4</b>
8.1 General .....	4
8.2 Weighing .....	5
8.3 Disintegration .....	5
<b>9 Determination of yeast and mould count .....</b>	<b>5</b>
9.1 General .....	5
9.2 Plating for yeast and mould count .....	5
9.3 Incubation .....	6
<b>10 Enumeration of the colonies .....</b>	<b>6</b>
<b>11 Calculation and report .....</b>	<b>7</b>
11.1 Calculation .....	7
11.2 Interpretation .....	7
11.3 Report .....	8
<b>12 Test report .....</b>	<b>8</b>
<b>Bibliography .....</b>	<b>9</b>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

This document was prepared by Technical Committee ISO/TC 6, *Paper, board and pulps*, Subcommittee SC 2, *Test methods and quality specifications for paper and board*.

A list of all parts in the ISO 8784 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at [www.iso.org/members.html](http://www.iso.org/members.html).

# Pulp, paper and board — Microbiological examination —

## Part 3:

# Enumeration of yeast and mould based on disintegration

## 1 Scope

This part of ISO 8784 specifies a method for determining the total number of colony-forming units of yeast and mould in dry market pulp, paper and paperboard after disintegration. The enumeration relates to specific media.

## 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 186, *Paper and board — Sampling to determine average quality*

ISO 638, *Paper, board and pulps — Determination of dry matter content — Oven-drying method*

ISO 6887-1, *Microbiology of the food chain — Preparation of test samples, initial suspension and decimal dilutions for microbiological examination — Part 1: General rules for the preparation of the initial suspension and decimal dilutions*

ISO/DIS 8784-3

<https://standards.iteh.ai/catalog/standards/sist/8030a940-4c6c-4d09-988c-80542bdc63a/iso-dis-8784-3>

ISO 7213, *Pulps — Sampling for testing*

ISO 7218, *Microbiology of food and animal feeding stuffs — General requirements and guidance for microbiological examinations*

ISO 11133, *Microbiology of food, animal feed and water — Preparation, production, storage and performance testing of culture media*

## 3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

### 3.1

#### yeast

mesophilic aerobic microorganism which, at 25 °C using mycological agar medium under the conditions described in this part of ISO 8784, develops matt or shiny round colonies on the surface of the medium, usually having a regular outline and a more or less convex surface

Note 1 to entry: Yeasts within, rather than on, a medium develop round, lenticular, colonies.

**3.2  
mould**

mesophilic aerobic filamentous microorganism which, on the surface of mycological agar medium under the conditions described in this part of ISO 8784, usually develops flat or fluffy spreading propagules/germs or colonies often with coloured fruiting or sporing structures

Note 1 to entry: Moulds within, rather than on, a medium can develop round, lenticular, colonies.

**3.3  
yeast and mould count**

number of colony-forming units (CFU) of yeast and mould formed after incubation in a standard culture medium, under the test conditions specified in this part of ISO 8784

**4 Principle**

This pour plate method involves enumeration of colonies in a standard culture medium. A fibre suspension, prepared from paper, paperboard, or pulp samples, is plated in agar.

The plates are incubated at  $25\text{ °C} \pm 1\text{ °C}$  for 3 to 5 days. The total numbers of yeast and mould are enumerated by counting the colonies formed in the agar. The results are expressed as the number of CFU per gram of sample.

**5 Culture media and diluents**

iTeh STANDARD PREVIEW  
(standards.iteh.ai)

**5.1 General**

All substrates and diluents shall be appropriately sterilized. When preparing the culture medium, make sure that the ingredients are completely dissolved by mixing while heating prior to dispensing into suitable containers for sterilization. See ISO 11133 for quality assurance and guidelines on preparation and production of culture media.

**5.2 Water**

When water is mentioned in a formula, use distilled water or purified water, see ISO 11133.

**5.3 Culture media for total yeast and mould count**

Culture medium shall be prepared as follows, or from commercially available dehydrated culture media according to the manufacturer's instructions. Ready-to-use medium may be used when its composition is comparable to that given in this part of ISO 8784. To test the performance of the medium, see ISO 11133.

Potato dextrose agar (PDA) composition per litre:

- Potato extracts 200, 0 g;
- Dextrose 20, 0 g;
- Agar 15, 0 g;
- Water 1 000 ml;
- Final pH  $5,6 \pm 0,2$ .

In order to decrease the pH to  $3,5 \pm 0,1$  add approx. 14 ml of a sterile 10 % tartaric acid solution/litre at a temperature of  $45\text{ °C}$ , thereby inhibiting bacterial growth.

The plates are clear and yellowish-brown.

After the tartaric acid is added, do not reliquary.

#### 5.4 Diluents

Ringer's solution ¼ strength

Composition per litre:

- Sodium chloride (NaCl) 2,250 g;
- Potassium chloride (KCl) 0,105 g;
- Calcium chloride (CaCl<sub>2</sub>) 6 H<sub>2</sub>O 0,120 g;
- Sodium hydrogen carbonate (NaHCO<sub>3</sub>) 0,050 g;
- Water 1 000 ml.

NOTE 1 Ringer's solution is preferred, although other isotonic solutions may be used. See ISO 6887-1.

NOTE 2 Ringer's tablets are commercially available.

#### 5.5 Non-ionic surfactant

Poly (oxyethylene)-sorbitan monooleate (Tween 80).

To facilitate the release of cells from the fibres, it is recommended to add 20 µl of Tween 80 per litre to the Ringer's solution prior to sterilization by autoclaving.

iTech STANDARD PREVIEW  
(standards.iteh.ai)

### 6 Apparatus and equipment

ISO/DIS 8784-3

<https://standards.iteh.ai/catalog/standards/sist/8030a940-4c6c-4d09-988c-8f0542bdc63a/iso-dis-8784-3>

#### 6.1 General

Disposable apparatus is an acceptable alternative to re-usable glassware and plastic if it has suitable specifications.

All laboratory equipment and parts of the equipment in direct contact with the sample and the diluents or the culture medium shall be sterilized.

NOTE For advice on standard microbiological equipment, see ISO 7218.

Usual microbiological laboratory equipment and in particular the following.

#### 6.2 Apparatus for sterilisation (moist and dry heat)

- a) for moist heat sterilisation, an autoclave capable of being maintained at 121<sub>0</sub><sup>+3</sup> °C for a minimum holding time of 15 min;
- b) for dry heat sterilisation, a hot air oven capable of being maintained at 180<sub>0</sub><sup>+5</sup> °C for a minimum holding time of 30 min, at 170<sub>0</sub><sup>+5</sup> °C for a minimum holding time of 1 h or at 160<sub>0</sub><sup>+5</sup> °C for a minimum holding time of 2 h.

#### 6.3 Biological safety cabinet, class II.

**6.4 Suitable wrapping material**, e.g. aluminium foil (non-coated and inert), ready-to-use envelopes of different sizes or self-closing plastic bags, all of which are commercially available.

**6.5 Disintegrator**, high speed electrical blender with metal (preferably stainless steel) or glass cup that can be sterilized.

NOTE Other homogenizing system with equivalent efficiency may be used.

**6.6 Incubator**, capable of maintaining a constant temperature of  $25\text{ °C} \pm 1\text{ °C}$ .

**6.7 Petri dishes**, having a diameter of 90 mm (standard) or 140 mm to 150 mm (alternative).

**6.8 Pipette**, of wide-mouth type and suitable volume.

The width of the mouth must be large enough so that a 1 % fibre suspension can easily be drawn into the pipette tip.

NOTE A suitable volume is 10 ml or 50 ml.

**6.9 Colony-counting equipment or magnifying device**, with a magnification between  $1,5\times$  and  $2,5\times$ .

**6.10 Balance**, with an accuracy of 0,01 g.

**6.11 Cutting devices**, such as scissors, scalpels, and/or knives.

## 7 Sampling

iTeh STANDARD PREVIEW  
(standards.iteh.ai)

Make sure that the sampling procedure is performed using aseptic techniques.

If the sample is to represent a lot of paper or paperboard, the sampling shall be in accordance with ISO 186. From each unit of paper or paperboard to be sampled, cut several top layers and discard them to eliminate surface contamination. Use a sterile knife to cut through several layers of the paper or board sample, producing a stack of sheets. Discard the top sheet.

If the sample is to represent a lot of pulp, the sampling shall be in accordance with ISO 7213. From each unit of dry market pulp to be sampled, discard several top sheets from each bale to eliminate surface contamination.

In other cases, sample a sufficient number of units so that the test material is representative of the paper, the paperboard, or the dry market pulp to be tested. In all sampling and examination procedures, make sure that the test material taken is representative of the sample received.

Ideally, a sample should contain at least four sheets, each of them having a minimum size of 200 mm  $\times$  250 mm of dry market pulp, paper, or paperboard (at least 2 sheets for testing and 2 protective sheets).

NOTE For paperboard or thicker material, it might be sufficient to use only 1 sheet for determination. For thinner paper, more than 2 sheets can be used for determination.

After sampling, wrap the unexposed test material in suitable wrapping material (6.3).

## 8 Preparation of the test material

### 8.1 General

Preferably, conduct the procedure under aseptic conditions. A laminar flow hood is recommended for cutting/plating. Unwrap the test material under aseptic conditions. Remove the protective sheets on the top and bottom of the sample stack without touching the test sheets in the centre of the sample stack.



If the result is to be reported on a dry-mass basis, determine the dry-matter content of the test material,  $X$ , in accordance with ISO 638.

If the result is to be reported on an “as received”-mass basis (not on a dry-mass basis), omit the determination of dry-matter content and report accordingly. [see 11.1 and Clause 12].

## 8.2 Weighing

Place a closed Petri dish (6.7) on the pan of the balance and determine its tare mass.

With sterile tweezers, hold the sheet or sheets along one edge in one hand, trim and discard the remaining edges with sterile scissors. Cut the sample material into small pieces. Weigh a sufficient amount of the test material (mass approximately 2 g to 3 g),  $m$ , into the Petri dish, to be able to prepare a fibre suspension having a concentration of 1 %.

NOTE In order to get a short disintegration time it might be useful to cut pieces that are smaller than 5 mm.

Transfer the test material aseptically to the disintegrator jar (6.5). Ensure the sterility of the disintegration jar (6.5) for each test material.

## 8.3 Disintegration

Use cooled diluent solution adjusted to room temperature (5.4). Avoid overheating (increase of the suspension temperature above 45 °C) during disintegration due to its effects on number of microorganism. Ensure the sterility of the disintegration jar (6.5) for each test material.

Disintegrate the test material (8.2) in diluent solution (5.4) to obtain a 1 % fibre suspension (for 2,0 g of test material, the volume of diluent should be 200 ml, and for 3,0 g it should be 300 ml). Disintegrate the suspension until it would be free from fibre clumps.

If it is difficult to obtain a fibre suspension free from fibre clumps using a disintegrator, other suitable equipment with equivalent efficiency may be used, and shall be stated in the test report.

## 9 Determination of yeast and mould count

### 9.1 General

The procedure shall be carried out in aseptic conditions. The work area shall be cleaned with a suitable disinfectant. If available, a laminar flow hood is recommended for plating.

After disintegration of the sample, add the fibre suspension to Petri dishes. When using the wide-mouth pipette tip, ensure that no fibre clumps remained in the pipette tip.

NOTE Yeast and mould might be attached to fibres, and if an inhomogeneous fibre suspension is added to the Petri dishes, the colony counts can be incorrect.

### 9.2 Plating for yeast and mould count

**9.2.1** Immediately after disintegration, with a sterile wide mouth pipette (6.8), distribute 10 ml,  $v$ , of the 1 % fibre suspension evenly among 5 sterile standard Petri dishes (6.7), i.e. approximately 2 ml per each plate (90 mm). This will represent 0,1 g of the test material.

**9.2.2** Within less than 5 min, pour into each plate 15 ml to 20 ml of the selected culture medium (5.3) cooled to approximately 45 °C. Immediately after the addition, rotate the plate with agitation to obtain a uniform distribution of fibre throughout the culture medium. Avoid a swirling motion since the colonies